SGS

PRODUCT CATALOG





www.sgstool.com

Overview	
Tool Wizard	3
Common Legend	4
Coatings	6
Milling	8
High Performance End Mills	14
General Purpose End Mills	98
Hole Making	158
High Performance Drills	163
General Purpose Drills	197
Countersinks	221
Reamers	235
Routing	242
High Performance Routers	246
General Purpose Routers	249
Technical Information	
EDP Index	257
SGS Reference Information	273
Decimal Equivalent Chart	274
Hardness Conversion Chart	275



Tool Wizard

CALCULATE APPLICATION PARAMETERS

The SGS Tool Wizard is designed to assist in the selection and application of products manufactured by SGS Tool Company and is now available to download on the App Store for Apple and Android Devices.

Use the Tool Wizard to calculate application parameters and select the right tool for the job.

- High Performance End Mills and Drills
- General Purpose Tooling
- Search by Application or EDP number
- Calculate Speeds and Feeds

To the best of our knowledge, the information contained in the Tool Wizard database is accurate. Due to differences in machining conditions (coolant, rigidity, spindle condition, etc.), and the subsequent effects, these recommendations must be considered a starting point, with possible variations to achieve the desired result. Refer to the SGS Tool Wizard for complete technical information.

Available for Android and Apple devices on the App store or visit www.sgstool.com to sign up.

www.sgstool.com

Common Legend
Leyenda habitual
Légende commune

TO ORDER: Please specify quantity and EDP number.
PARA SU PEDIDO: Por favor especifique cantidad y número de EDP.
POUR COMMANDER: Veuillez préciser la quantité et le code article EDP.

RETURN POLICY: An RMA number must accompany all product returns. Contact your Customer Service Representative for an RMA number.
DEVOLUCIONES: Todo material devuelto debe ir acompañado de un número de RMA correspondiente. Para solicitarlo, póngase en contacto con su Representante de Servicio.
POLITIQUE DE RETOUR: Tous les produits retournés doivent être accompagnés d'un numéro RMA. Contacter votre interlocuteur commercial pour obtenir un numéro RMA.

REGULATION SAFETY GLASSES SHOULD ALWAYS BE WORN WHEN USING HIGH-SPEED CUTTING EQUIPMENT

DEBEN USARSE GAFAS PROTECTORAS CUANDO SE UTILIZA UN EQUIPO DE ALTA VELOCIDAD

DES LUNNETTES DE SÉCURITE DOIVENT ÊTRE IMPÉRATIVEMENT PORTÉES LORS D'UTILISATION D'OUTILS À GRANDE VITESSE



Z1PLB
FRACTIONAL SERIES
TECH INFO 57

Refers to exact page where Speed and Feed Information can be found.
Hace referencia a la página exacta en la que puede encontrarse la información de velocidades y avances.
Indique la page exacte des informations de vitesse et avance.

INDUSTRY
INDUSTRIAS
INDUSTRIES

These icons indicate for which industry applications SGS High Performance Products are best suited.

Estos íconos indican las aplicaciones industriales más adecuadas para los productos SGS de alto rendimiento.

Ces icônes indiquent les applications industrielles pour lesquelles les produits haute performance SGS sont les mieux adaptés.

Aerospace | Aeroespacial | Aérospatiale
Medical | Médica | Médical
Power Generation | Energética | Production d'énergie
Automotive | Automotriz | Automobile
Mold & Die | Moldes y matrices | Moules et coquilles
Castings & Foundaries | Fundición | Moulages et fonderies
General Engineering | Ingeniería | Ingénierie générale

Common Legend
Leyenda habitual
Légende commune

MATERIALS
MATERIALES
MATÉRIAUX

- Steels | Aceros | Aciers
- Stainless Steels | Aceros Inoxidables | Inox
- Cast Iron | Hierro Fundido | Fonte
- High Temp Alloys | Aleaciones a Altas Temperaturas | Alliages Haute Temp
- Titanium | Titanio | Titane
- Non-Ferrous | No Férrico | Non Ferreux
- Plastics/Composites | Plásticos/Resinas | Plastiques/Composites
- Hardened Steels | Aceros Endurecidos | Aciers Trempés


TOOL LENGTH
LONGITUD FRESA
LONGUEUR DE L'OUTIL


Stub | Corta | Court


Medium | Media | Moyen


Long | Larga | Long


Long Reach Neck | Larga con cuello | Gorge de dégagement longue portée


Extra Long | Extra-larga | Extra-long

FLUTES
FILOS
GOUJURES


Flutes - 2 | 2 filos | Goujures - 2


Flutes - 3 | 3 filos | Goujures - 3


Flutes - 4 | 4 filos | Goujures - 4


Flutes - 5 | 5 filos | Goujures - 5


Flutes - 6 | 6 filos | Goujures - 6


Multi-Flute | Filo múltiple | Multi-goujure

COATINGS

	 Ti-NAMITE	 Ti-NAMITE-A	 Ti-NAMITE-B
Coating	Titanium (TiN)	Aluminum Titanium Nitride (AlTiN)	Titanium DiBoride (TiB2)
Identifying Color	gold	violet-grey	light grey-silver
Layer Structure	monolayer	nano structure	monolayer
Thickness	1–4 microns	1–4 microns	1–2 microns
Hardness (HV)	2200	3300	4000
Coefficient of Friction (Fetting)	0.4–0.65	0.45	0.45
Thermal Stability	600°C / 1112°F	800°C / 1472°F	850°C / 1562°F
General Information	A general purpose coating with good adhesion and abrasion resistant properties. Suitable for a wide variety of materials.	Excellent thermal and chemical resistance allows for dry cutting and improvements in performance of carbide. The coating has a high hardness giving great protection against abrasive wear and erosion.	This coating offers a very smooth surface and a low affinity to cold welding or built up edge, which makes it optimal for Titanium, Aluminum (>10%) and copper applications. It has high toughness and high hardness.

		
Titanium Carbonitride (TiCN)	Proprietary (TX)	Crystalline Diamond (Diamond)
pink-red	violet-grey	light grey-silver
gradient	nano structure	monolayer
1–4 microns	1–4 microns	6–20 microns
3000	3000	>8000
0.3–0.45	0.50	0.15–0.2
400°C / 752°F	900°C / 1562°F	800°C / 1470°F
A very wear resistant coating with high toughness and shock resistance. Good in interrupted cuts found in applications like milling.	Applied utilizing a patented process, this coating offers unsurpassed adhesion aiding in long tool life. The coating deposition is consistent and dense giving strength advantages to the coating.	This is the hardest coating available with the best abrasion resistance. It is carbon based so it is limited in application capabilities. It is also the most expensive with the longest processing time.

SGS

ENDMILLS



Milling

HIGH PERFORMANCE END MILLS	SERIES	PAGE
Z-Carb-AP Variable Rake End Mills	Z1PCR, Z1MPCR, Z1PLC, Z1MPLC, Z1PLB	14
Z-Carb End Mills	Z1, Z1M, Z1B, Z1MB, Z16CR	19
Z-Carb-HTA End Mills	ZH1CR, ZH1MCR	24
Z-Carb-MD End Mills	ZD1CR, ZD1MCR	25
Series 7 End Mills	7, 7M, 7B, 7MB	26
V-Carb Finishing & Semi-Finishing End Mills	55, 55M, 55CR	30
T-Carb End Mills	51, 51M, 51L, 51ML, 51CR, 51MCR, 51LC, 51MLC	34
Multi-Carb Finishing End Mills	66, 66M, 66CR, 66MCR	38
Turbo-Carb End Mills	56B, 56MB	40
Power-Carb End Mills	57, 57M	41
Series 33 End Mills	33CR, 33MCR	42
Ski-Carb End Mills	45, 44, 44M	43
S-Carb 3 Flute End Mills	43CR, 43MCR, 43LC, 43, 43M, 43L	46
S-Carb Roughing End Mills	43CB, 43MCB	53
S-Carb 2 Flute End Mills	47, 47M, 47B, 47MB, 47ES, 47MES, 47EB, 47MEB	54
CFRP Slow Helix End Mills	27, 27M	58
TECHNICAL INFORMATION		
Speed & Feed Recommendations		60

(continued)

GENERAL PURPOSE END MILLS	SERIES	PAGE
4 Flute Square End Stub	16, 16M	98
4 Flute Square End	1, 1L, 1EL, 1M, 1XLM	99
4 Flute Double End Mills	14, 14M	102
4 Flute Ball End	1B, 1LB, 1ELB, 1MB, 1XLMB	104
4 Flute Double End Ball End	14B, 14MB	107
4 Flute Corner Radius	1CR, 1MCR	109
4 Flute High Shear End Mills	54, 54M	112
2 Flute Square End Stub	17, 17M	113
2 Flute Square End	3, 3L, 3EL, 3M, 3XLM	114
2 Flute Square End Long Reach	59, 59M	117
2 Flute Double End Mills	15, 15M	118
2 Flute Ball End	3B, 3LB, 3ELB, 3MB, 3XLMB	120
2 Flute Ball End Long Reach	59B, 59MB	123
2 Flute Double End Ball End	15B, 15MB	124
2 Flute Corner Radius	3CR	126
2 Flute High Shear End Mills	52, 52M	127
3 Flute Square End	5, 5M, 5XLM	128
3 Flute Ball End	5B, 5MB, 5XLMB	130
Single End Roughers	61, 61M, 62, 62M	132
Micro End Mills	MK2, MK2M	134
Tapered Square End	23	136
Tapered Radius End	24	137
End Mills Sets		138
TECHNICAL INFORMATION		
Speed & Feed Recommendations		139
Application Tips		154

Fresado

FRESAS DE ALTO RENDIMIENTO	SERIE	PÁGINA
Fresas de inclinación variable Z-Carb-AP	Z1PCR, Z1MPCR, Z1PLC, Z1MPLC, Z1PLB	14
Fresas Z-Carb	Z1, Z1M, Z1B, Z1MB, Z16CR	19
Fresas Z-Carb-HTA	ZH1CR, ZH1MCR	24
Fresas Z-Carb-MD	ZD1CR, ZD1MCR	25
Fresas Serie 7	7, 7M, 7B, 7MB	26
Fresas de acabado y semiacabado V-Carb	55, 55M, 55CR	30
Fresas T-Carb	51, 51M, 51L, 51ML, 51CR, 51MCR, 51LC, 51MLC	34
Fresas de acabado Multi-Carb	66, 66M, 66CR, 66MCR	38
Fresas Turbo-Carb	56B, 56MB	40
Fresas Power-Carb	57, 57M	41
Fresas Serie 33	33CR, 33MCR	42
Fresas Ski-Carb	45, 44, 44M	43
Fresas de 3 filos S-Carb	43CR, 43MCR, 43LC, 43, 43M, 43L	46
Fresas desbastadoras S-Carb	43CB, 43MCB	53
Fresas de 2 filos S-Carb	47, 47M, 47B, 47MB, 47ES, 47MES, 47EB, 47MEB	54
Fresas helicoidales de avance lento CFRP	27, 27M	58
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		60

FRESAS DE USO GENERAL	SERIE	PÁGINA
4 filos, pieza de punta cuadrada	16, 16M	98
4 filos, punta cuadrada	1, 1L, 1EL, 1M, 1XLM	99
4 filos, fresas dobles	14, 14M	102
4 filos, punta esférica	1B, 1LB, 1ELB, 1MB, 1XLMB	104
4 filos, punta doble, punta esférica	14B, 14MB	107
4 filos, radio angulado	1CR, 1MCR	109
4 filos, fresas de corte de alto rendimiento	54, 54M	112
2 filos, pieza de punta cuadrada	17, 17M	113
2 filos, punta cuadrada	3, 3L, 3EL, 3M, 3XLM	114
2 filos, punta cuadrada, largo alcance	59, 59M	117
2 filos, fresas dobles	15, 15M	118
2 filos, punta esférica	3B, 3LB, 3ELB, 3MB, 3XLMB	120
2 filos, punta esférica, largo alcance	59B, 59MB	123
2 filos, punta doble, punta esférica	15B, 15MB	124
2 filos, radio angulado	3CR	126
2 filos, fresas de corte de alto rendimiento	52, 52M	127
3 filos, punta cuadrada	5, 5M, 5XLM	128
3 filos, punta esférica	5B, 5MB, 5XLMB	130
Desbastadores sencillos Microfresas	61, 61M, 62, 62M	132
Microfresas	MK2, MK2M	134
Punta cuadrada cónica	23	136
Punta redonda cónica	24	137
Juegos de fresas		138
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		139
Puntas para aplicaciones		154

Fraisage

FRAISES A DETOURER UNIVERSELLES	SERIES	PAGE
Fraises Z-Carb-AP à vague de coupe variable	Z1PCR, Z1MPCR, Z1PLC, Z1MPLC, Z1PLB	14
Fraises en bout Z-Carb	Z1, Z1M, Z1B, Z1MB, Z16CR	19
Fraises en bout Z-Carb HTA	ZH1CR, ZH1MCR	24
Fraises en bout Z-Carb MD	ZD1CR, ZD1MCR	25
Fraises en bout série 7	7, 7M, 7B, 7MB	26
Fraises en bout de finition et semi-finition V-Carb	55, 55M, 55CR	30
Fraises en bout T-Carb	51, 51M, 51L, 51ML, 51CR, 51MCR, 51LC, 51MLC	34
Fraises en bout de finition Multi-Carb	66, 66M, 66CR, 66MCR	38
Fraises en bout Turbo-Carb	56B, 56MB	40
Fraises en bout Power-Carb	57, 57M	41
Fraises en bout série 33	33CR, 33MCR	42
Fraises en bout Ski-Carb	45, 44, 44M	43
Fraise 3 dents S-Carb	43CR, 43MCR, 43LC, 43, 43M, 43L	46
Fraise d'ébauche S-Carb	43CB, 43MCB	53
Fraise 2 dents S-Carb	47, 47M, 47B, 47MB, 47ES, 47MES, 47EB, 47MEB	54
Fraises hélice lente CFRP	27, 27M	58
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		60

FRAISES A USAGE GENERAL	SERIES	PAGE
Moignon 4 dents bout plat.	16, 16M	98
4 dents bout plat	1, 1L, 1EL, 1M, 1XLM	99
Fraises 4 dents double bouts	14, 14M	102
Fraise 4 dents en bout hémisphérique	1B, 1LB, 1ELB, 1MB, 1XLMB	104
Fraise 4 dents en bout double bouts hémisphérique	14B, 14MB	107
4 dents, rayon en coin	1CR, 1MCR	109
Fraises 4 dents en bout cisaillement élevé	54, 54M	112
Moignon 2 dents bout plat	17, 17M	113
2 dents en bout plat	3, 3L, 3EL, 3M, 3XLM	114
2 dents en bout plat longue portée	59, 59M	117
Fraises 2 dents en double bouts	15, 15M	118
2 dents en bout hémisphérique	3B, 3LB, 3ELB, 3MB, 3XLMB	120
2 dents en bout hémisphérique longue portée	59B, 59MB	123
2 dents en double bouts hémisphériques	15B, 15MB	124
2 dents, rayon en coin	3CR	126
Fraises 2 dents en bout cisaillement élevé	52, 52M	127
3 dents en bout plat	5, 5M, 5XLM	128
3 dents bout en hémisphérique	5B, 5MB, 5XLMB	130
Fraises en bout d'ébauche à bout unique	61, 61M, 62, 62M	132
Micro fraises	MK2, MK2M	134
Bout plat conique	23	136
Bout arrondi conique	24	137
Jeux de fraises		138
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		139
Conseils d'utilisation		154

End Mill Icon Legend
Leyenda del icono de las fresas
Légende d'icone de fraise

END CONFIGURATIONS
CONFIGURACIONES DE LA PUNTA
CONFIGURATIONS TERMINALES



Ball
Esférica
Boule



Corner
Plana con borde romo
Coin



Square
Plana
Carrée

SHANK TYPE
TIPO DE VÁSTAGO
TYPE DE TIGE



Weldon Flat
Weldon plano
Méplat Weldon



Common
Normal
Commune



Straight
Recto
Droite

HELIX ANGLES
ÁNGULOS HELICOIDALES
ANGLES DE L'HÉLICE



Right Spiral
Espiral sentido derecho
Spirale droite



Left Spiral
Espiral sentido izquierdo
Spirale gauche



Variable Right Spiral
Espiral sentido derecha con ángulo variable
Spirale droite variable

RAKE ANGLE
ÁNGULO DE ATAQUE
ANGLE DE PENTE



Positive
Positivo
Positif



Neutral
Neutro
Neutre



Negative
Negativo
Négatif



Variable
Variable
Variable

COOLANT OPTIONS
OPCIONES DE REFRIGERACIÓN
OPTIONS DE REFROIDISSEMENT



JetStream Coolant Slots

Ranuras del refrigerante JetStream
Fentes de refroidissement JetStream



Internal Coolant

Refrigerante interno
Refroidissement interne



External Coolant Recommended
Refrigerante externo recomendado
Agent de refroidissement recommandé

ADDITIONAL GEOMETRY
CARACTERÍSTICAS GEOMÉTRICAS ADICIONALES
GÉOMÉTRIE SUPPLÉMENTAIRE



Left Cut Direction
Fresado sentido izquierda
Coupe vers la gauche



Right Cut Direction
Fresado sentido derecha
Coupe vers la droite



Flute Spacing Unequal
Espaciado filos desigual
Espacement inégal entre les goujoures



Chip Breaker
Rompevirutas
Brise-copeaux



High Speed Machining
Mecanizado de alta velocidad
Usinage à grande vitesse

COATINGS
REVESTIMIENTOS
REVÊTEMENTS



Uncoated



Ti-NAMITE
(TiN)



Ti-NAMITE-A
(AlTiN)



Ti-NAMITE-B
(TiB2)



Ti-NAMITE-C
(TiCN)




Ti-NAMITE-X
(TX)



Di-NAMITE
(Diamond)







Z1PCR

FRACTIONAL SERIES

TECH INFO 60

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch					EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-X	Ti-NAMITE-X W/FLAT	JetStream*
1/16	3/16	1-1/2	1/8	.005	36872	–	–
3/32	9/32	1-1/2	1/8	.010	36873	–	–
1/8	3/8	1-1/2	1/8	.010	36370	–	–
1/8	3/8	1-1/2	1/8	.015	36851	–	–
3/16	7/16	2	3/16	.010	36371	–	–
3/16	7/16	2	3/16	.015	36852	–	–
3/16	7/16	2	3/16	.030	36722	–	–
1/4	1/2	2-1/2	1/4	.010	36372	–	–
1/4	1/2	2-1/2	1/4	.015	36723	–	–
1/4	1/2	2-1/2	1/4	.020	36853	–	–
1/4	1/2	2-1/2	1/4	.030	36373	–	–
1/4	3/4	2-1/2	1/4	.010	36599	–	–
1/4	3/4	2-1/2	1/4	.015	36600	–	–
1/4	3/4	2-1/2	1/4	.020	36854	–	–
1/4	3/4	2-1/2	1/4	.030	36601	–	–
5/16	13/16	2-1/2	5/16	.015	36724	–	–
5/16	13/16	2-1/2	5/16	.020	36855	–	–
5/16	13/16	2-1/2	5/16	.030	36374	–	–
3/8	7/8	2-1/2	3/8	.010	36375	36701	–
3/8	7/8	2-1/2	3/8	.015	36725	36736	–
3/8	7/8	2-1/2	3/8	.020	36856	36864	–
3/8	7/8	2-1/2	3/8	.030	36376	36702	–
3/8	7/8	2-1/2	3/8	.060	36727	36738	–
7/16	1	2-3/4	7/16	.020	36857	36865	–

continued on next page

*JetStream Patented Coolant Technology

TOLERANCES (inch)

<1/8 DIAMETER
D_1 = +0.0005/–0.0005
D_2 = h_6
R = +0.000/–0.0010

1/8–1/4 DIAMETER
D_1 = +0.000/–0.0012
D_2 = h_6
R = +0.000/–0.0020

>1/4–3/8 DIAMETER
D_1 = +0.000/–0.0016
D_2 = h_6
R = +0.000/–0.0020

>3/8–1 DIAMETER
D_1 = +0.000/–0.0020
D_2 = h_6
R = +0.000/–0.0020

U.S. Patents 7,306,408 and 7,789,597



Z1PCR
FRACTIONAL SERIES

CONTINUED


inch					EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-X	Ti-NAMITE-X W/FLAT	JetStream*
1/2	1	3	1/2	.010	36378	36704	36804
1/2	1	3	1/2	.015	36729	36740	36810
1/2	1	3	1/2	.030	36858	36866	36805
1/2	1	3	1/2	.060	36380	36706	36811
1/2	1	3	1/2	.090	36381	36707	36812
1/2	1	3	1/2	.125	36731	36742	36813
1/2	1-1/4	3-1/4	1/2	.010	36602	36603	–
1/2	1-1/4	3-1/4	1/2	.015	36604	36605	–
1/2	1-1/4	3-1/4	1/2	.030	36859	36867	–
1/2	1-1/4	3-1/4	1/2	.060	36610	36611	–
1/2	1-1/4	3-1/4	1/2	.090	36612	36613	–
1/2	1-1/4	3-1/4	1/2	.125	36614	36615	–
9/16	1-1/8	3-1/2	9/16	.030	36860	36868	36806
5/8	1-1/4	3-1/2	5/8	.030	36383	36709	36814
5/8	1-1/4	3-1/2	5/8	.040	36861	36869	36807
5/8	1-1/4	3-1/2	5/8	.060	36384	36710	36815
5/8	1-1/4	3-1/2	5/8	.090	36385	36711	36816
5/8	1-1/4	3-1/2	5/8	.125	36733	36744	36817
3/4	1-1/2	4	3/4	.030	36386	36712	36818
3/4	1-1/2	4	3/4	.040	36862	36870	36808
3/4	1-1/2	4	3/4	.060	36387	36713	36819
3/4	1-1/2	4	3/4	.090	36388	36714	36820
3/4	1-1/2	4	3/4	.125	36389	36715	36821
1	1-1/2	4	1	.030	36390	36716	36822
1	1-1/2	4	1	.040	36863	36871	36809
1	1-1/2	4	1	.060	36391	36717	36823
1	1-1/2	4	1	.090	36392	36718	36824
1	1-1/2	4	1	.125	36393	36719	36825

*JetStream Patented Coolant Technology

U.S. Patents 7,306,408 and 7,789,597







Z1MPCR

METRIC SERIES

TECH INFO 62

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

mm					EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-X	Ti-NAMITE-X W/FLAT	JetStream*
1,5	4,5	57,0	6,0	0,1	46849	–	–
2,0	6,0	57,0	6,0	0,2	46850	–	–
3,0	8,0	57,0	6,0	0,3	46851	–	–
3,0	8,0	57,0	6,0	0,5	46880	–	–
4,0	11,0	57,0	6,0	0,3	46852	–	–
4,0	11,0	57,0	6,0	0,5	46881	–	–
5,0	13,0	57,0	6,0	0,3	46853	–	–
6,0	13,0	57,0	6,0	0,25	46882	–	–
6,0	13,0	57,0	6,0	0,5	46854	–	–
6,0	13,0	57,0	6,0	1,0	46855	–	–
6,0	13,0	57,0	6,0	1,5	46884	–	–
8,0	19,0	63,0	8,0	0,5	46856	–	–
8,0	19,0	63,0	8,0	1,0	46857	–	–
8,0	19,0	63,0	8,0	1,5	46886	–	–
8,0	19,0	63,0	8,0	2,0	46887	–	–
10,0	22,0	72,0	10,0	0,5	46858	–	–
10,0	22,0	72,0	10,0	1,0	46859	–	–
10,0	22,0	72,0	10,0	1,5	46889	–	–
10,0	22,0	72,0	10,0	2,0	46890	–	–
10,0	22,0	72,0	10,0	2,5	46891	–	–
12,0	26,0	83,0	12,0	0,5	46860	46909	–
12,0	26,0	83,0	12,0	0,75	46861	46910	–
12,0	26,0	83,0	12,0	1,0	46893	46911	–
12,0	26,0	83,0	12,0	1,5	46894	46912	–
12,0	26,0	83,0	12,0	2,0	46895	46913	–
12,0	26,0	83,0	12,0	2,5	46896	46914	–
12,0	26,0	83,0	12,0	3,0	42718	46915	–
14,0	26,0	83,0	14,0	1,0	46862	46916	46494
16,0	32,0	92,0	16,0	1,0	46863	46917	46495
16,0	32,0	92,0	16,0	1,5	46898	46918	–
16,0	32,0	92,0	16,0	2,0	46899	46919	–
16,0	32,0	92,0	16,0	2,5	46900	46920	–
16,0	32,0	92,0	16,0	3,0	46864	46921	–
20,0	38,0	104,0	20,0	1,0	46865	46922	46497
20,0	38,0	104,0	20,0	1,5	46903	46923	–
20,0	38,0	104,0	20,0	2,0	46904	46924	–
20,0	38,0	104,0	20,0	2,5	46905	46925	–
20,0	38,0	104,0	20,0	3,0	42722	46926	–
25,0	38,0	104,0	25,0	1,0	46866	46927	46498

U.S. Patents 7,306,408 and 7,789,597
*JetStream Patented Coolant Technology

TOLERANCES (mm)

<3 DIAMETER
D_1 = +0,012/–0,012
D_2 = h_6
R = +0,000/–0,025


3–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6
R = +0,000/–0,050

>10–25 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050







TOLERANCES (inch)

1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6
R = +0.0000/–0.0020

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6
R = +0.0000/–0.0020

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6
R = +0.0000/–0.0020

Z1PLC
FRACTIONAL SERIES

TECH INFO 60

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-X
1/4	1/2	4	1/4	1-1/4	.020	36450
5/16	13/16	4	5/16	1-5/8	.020	36452
3/8	7/8	5	3/8	1-7/8	.020	36456
7/16	1	6	7/16	2	.020	36460
1/2	1	6	1/2	2-1/4	.030	36462
9/16	1-1/8	6	9/16	2-1/2	.030	36466
5/8	1-1/4	6	5/8	3	.040	36470
3/4	1-1/2	6	3/4	3-1/2	.040	36472
1	1-1/2	6	1	4	.040	36474

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM

TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6
R = +0,000/–0,050

>10–25 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050

Z1MPLC
METRIC SERIES


TECH INFO 62

mm						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-X
6,0	8,0	75,0	6,0	24,0	0,5	46821
8,0	10,0	75,0	8,0	32,0	1,0	46822
8,0	10,0	75,0	8,0	32,0	2,0	46823
10,0	12,0	100,0	10,0	40,0	1,0	46824
10,0	12,0	100,0	10,0	40,0	2,0	46825
12,0	15,0	100,0	12,0	48,0	1,0	46826
12,0	15,0	100,0	12,0	48,0	1,5	46827
12,0	15,0	100,0	12,0	48,0	2,0	46828
12,0	15,0	100,0	12,0	48,0	3,0	46829
16,0	20,0	115,0	16,0	65,0	1,0	46830
16,0	20,0	115,0	16,0	65,0	1,5	46831
16,0	20,0	115,0	16,0	65,0	2,0	46832
16,0	20,0	115,0	16,0	65,0	3,0	46833
16,0	20,0	115,0	16,0	65,0	4,0	46834
16,0	20,0	115,0	16,0	65,0	5,0	46835
20,0	24,0	140,0	20,0	80,0	1,0	46836
20,0	24,0	140,0	20,0	80,0	1,5	46737
20,0	24,0	140,0	20,0	80,0	2,0	46838
20,0	24,0	140,0	20,0	80,0	3,0	46839
20,0	24,0	140,0	20,0	80,0	4,0	46840
20,0	24,0	140,0	20,0	80,0	5,0	46841

U.S. Patents 7,306,408 and 7,789,597







Z1PLB

FRACTIONAL SERIES

TECH INFO 60

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	Ti-NAMITE-X
1/4	1/2	4	1/4	1-1/4	36480
5/16	13/16	4	5/16	1-5/8	36482
3/8	7/8	5	3/8	1-7/8	36486
7/16	1	6	7/16	2	38490
1/2	1	6	1/2	2-1/4	38492
9/16	1-1/8	6	9/16	2-1/2	38496
5/8	1-1/4	6	5/8	3	36500
3/4	1-1/2	6	3/4	3-1/2	36502
1	1-1/2	6	1	4	36504

TOLERANCES (inch)

1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6


>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

U.S. Patents 7,306,408 and 7,789,597







TOLERANCES (inch)

1/8–1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

Z1
FRACTIONAL SERIES

TECH INFO 64


inch				EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	JetStream*
1/8	3/8	1-1/2	1/8	36404	–	–
5/32	7/16	2	3/16	36406	–	–
3/16	7/16	2	3/16	36408	–	–
7/32	7/16	2-1/2	1/4	36410	–	–
1/4	1/2	2-1/2	1/4	36416	–	–
1/4	3/4	2-1/2	1/4	36596	–	–
9/32	5/8	2-1/2	5/16	36418	–	–
5/16	13/16	2-1/2	5/16	36420	–	–
11/32	13/16	2-1/2	3/8	36422	–	–
3/8	7/8	2-1/2	3/8	36424	36530	–
13/32	15/16	2-3/4	7/16	36426	36531	–
7/16	1	2-3/4	7/16	36428	36532	–
1/2	1	3	1/2	36430	36533	–
1/2	1	3	1/2	36432	36534	36826
1/2	1-1/4	3-1/4	1/2	36597	36598	–
9/16	1-1/8	3-1/2	9/16	36436	36535	36827
5/8	1-1/4	3-1/2	5/8	36440	36536	36828
3/4	1-1/2	4	3/4	36442	36537	36829
1	1-1/2	4	1	36444	36538	36830

*JetStream Patented Coolant Technology

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM







Z1M
METRIC SERIES

TECH INFO 66

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	JetStream*
3,0	8,0	57,0	6,0	46357	–
4,0	11,0	57,0	6,0	46358	–
5,0	13,0	57,0	6,0	46359	–
6,0	13,0	57,0	6,0	46360	–
8,0	19,0	63,0	8,0	46362	–
10,0	22,0	72,0	10,0	46364	–
12,0	26,0	83,0	12,0	46366	–
14,0	26,0	83,0	14,0	46368	46506
16,0	32,0	92,0	16,0	46370	46507
18,0	32,0	92,0	18,0	46372	46508
20,0	38,0	104,0	20,0	46374	46509
25,0	38,0	104,0	25,0	46376	46510

*JetStream Patented Coolant Technology

TOLERANCES (mm)


3–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6

>10–25 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6







TOLERANCES (inch)

1/8–1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

Z1B
FRACTIONAL SERIES

TECH INFO 64


inch				EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	JetStream*
1/8	3/8	1-1/2	1/8	36358	–	–
5/32	7/16	2	3/16	36357	–	–
3/16	7/16	2	3/16	36359	–	–
7/32	7/16	2-1/2	1/4	36361	–	–
1/4	1/2	2-1/2	1/4	36344	–	–
1/4	3/4	2-1/2	1/4	36590	–	–
9/32	5/8	2-1/2	5/16	36353	–	–
5/16	13/16	2-1/2	5/16	36345	–	–
11/32	13/16	2-1/2	3/8	36354	–	–
3/8	7/8	2-1/2	3/8	36346	36539	–
13/32	15/16	2-3/4	7/16	36355	36540	–
7/16	1	2-3/4	7/16	36347	36541	–
15/32	1	3	1/2	36356	36542	–
1/2	1	3	1/2	36348	36543	36846
1/2	1-1/4	3-1/4	1/2	36591	36592	–
9/16	1-1/8	3-1/2	9/16	36349	36544	36847
5/8	1-1/4	3-1/2	5/8	36350	36545	36848
3/4	1-1/2	4	3/4	36351	36546	36849
1	1-1/2	4	1	36352	36547	36850

*JetStream Patented Coolant Technology

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM







Z1MB
METRIC SERIES

TECH INFO 66

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	JetStream*
3,0	8,0	57,0	6,0	46354	–
4,0	11,0	57,0	6,0	46355	–
5,0	13,0	57,0	6,0	46356	–
6,0	13,0	57,0	6,0	46343	–
8,0	19,0	63,0	8,0	46344	–
10,0	22,0	72,0	10,0	46345	–
12,0	26,0	83,0	12,0	46346	–
14,0	26,0	83,0	14,0	46347	46518
16,0	32,0	92,0	16,0	46348	46519
18,0	32,0	92,0	18,0	46349	46520
20,0	38,0	104,0	20,0	46350	46521
25,0	38,0	104,0	25,0	46351	46522

*JetStream Patented Coolant Technology

TOLERANCES (mm)


3–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6

>10–25 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6







TOLERANCES (inch)

1/8–1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6


Z16CR
FRACTIONAL SERIES


TECH INFO 64

inch					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)
1/8	1/4	1-1/2	1/8	.010–.015	36505
5/32	5/16	2	3/16	.010–.015	36506
3/16	3/8	2	3/16	.010–.015	36507
7/32	3/8	2	1/4	.015–.020	36508
1/4	7/16	2	1/4	.015–.020	36509
5/16	1/2	2	5/16	.015–.020	36511
3/8	5/8	2	3/8	.015–.020	36513
7/16	5/8	2-1/2	7/16	.015–.020	36515
1/2	5/8	2-1/2	1/2	.025–.030	36517
5/8	3/4	3	5/8	.035–.040	36519
3/4	1	3	3/4	.035–.040	36520

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM







ZH1CR
FRACTIONAL SERIES

TECH INFO 68

HIGH TEMP ALLOYS

TITANIUM

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
1/4	1/2	2-1/2	1/4	.015–.020	36570	–
1/4	3/4	2-1/2	1/4	.015–.020	36616	–
5/16	13/16	2-1/2	5/16	.015–.020	36571	–
3/8	7/8	2-1/2	3/8	.015–.020	36572	36555
7/16	1	2-3/4	7/16	.015–.020	36573	36556
1/2	1	3	1/2	.025–.030	36574	36557
1/2	1-1/4	3-1/4	1/2	.025–.030	36618	36617
9/16	1-1/8	3-1/2	9/16	.025–.030	36575	36558
5/8	1-1/4	3-1/2	5/8	.035–.040	36576	36559
3/4	1-1/2	4	3/4	.035–.040	36577	36560
1	1-1/2	4	1	.035–.040	36578	36561

TOLERANCES (inch)

1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–1 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

ZH1MCR
METRIC SERIES

TECH INFO 68

mm					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
6,0	13,0	57,0	6,0	0,5	46450	–
6,0	13,0	57,0	6,0	1,0	46451	–
6,0	13,0	57,0	6,0	1,5	46452	–
8,0	19,0	63,0	8,0	0,5	46453	–
8,0	19,0	63,0	8,0	1,0	46454	–
8,0	19,0	63,0	8,0	1,5	46455	–
10,0	22,0	72,0	10,0	0,5	46456	–
10,0	22,0	72,0	10,0	1,0	46457	–
10,0	22,0	72,0	10,0	1,5	46458	–
10,0	22,0	72,0	10,0	2,0	46459	–
12,0	26,0	83,0	12,0	0,5	46460	46471
12,0	26,0	83,0	12,0	1,0	46461	46472
12,0	26,0	83,0	12,0	1,5	46462	46473
12,0	26,0	83,0	12,0	2,0	46463	46474
12,0	26,0	83,0	12,0	3,0	46464	46475
16,0	32,0	92,0	16,0	1,5	46465	46476
16,0	32,0	92,0	16,0	2,0	46466	46477
16,0	32,0	92,0	16,0	3,0	46467	46478
20,0	38,0	104,0	20,0	3,0	46468	46479
20,0	38,0	104,0	20,0	4,0	46469	46480
20,0	38,0	104,0	20,0	5,0	46470	46481


TOLERANCES (mm)


6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6
R = +0,000/–0,050

>10–20 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050







TOLERANCES (inch)

1/8–1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6
R = +0.0000/–0.0020

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6
R = +0.0000/–0.0020

>3/8–1 DIAMETER
D_1 = +0.0000/–0.002
D_2 = h_6
R = +0.0000/–0.0020

ZD1CR
FRACTIONAL SERIES

TECH INFO 69

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)
1/8	5/32	2-1/2	1/4	1/2	.010	36780
3/16	7/32	2-1/2	1/4	3/4	.020	36781
1/4	9/32	2-1/2	1/4	3/4	.020	36782
5/16	13/32	2-1/2	5/16	1	.040	36783
3/8	15/32	2-1/2	3/8	1	.040	36784
7/16	9/16	2-3/4	7/16	1	.040	36785
1/2	5/8	3	1/2	1-1/4	.040	36786
1/2	5/8	4-1/2	1/2	2-1/4	.040	36787
5/8	3/4	3-1/2	5/8	1-1/2	.040	36788
5/8	3/4	4-1/2	5/8	2-1/4	.040	36789
5/8	3/4	5-1/2	5/8	3-1/4	.040	36790
3/4	15/16	4	3/4	1-3/4	.060	36791
3/4	15/16	4-1/2	3/4	2-1/4	.060	36792
3/4	15/16	5-1/2	3/4	3-1/4	.060	36793

STEELS

HARDENED STEELS

TOLERANCES (mm)

3–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6
R = +0,000/–0,050

>10–20 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050


ZD1MCR
METRIC SERIES

TECH INFO 69

mm						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)
3,0	4,0	57,0	6,0	15,0	0,2	46560
4,0	5,0	57,0	6,0	15,0	0,3	46561
5,0	6,0	57,0	6,0	15,0	0,5	46562
6,0	7,0	57,0	6,0	15,0	1,0	46563
8,0	10,0	63,0	8,0	25,0	1,0	46564
10,0	12,0	72,0	10,0	30,0	1,0	46565
12,0	15,0	83,0	12,0	35,0	1,0	46566
16,0	20,0	92,0	16,0	45,0	1,5	46567
20,0	24,0	104,0	20,0	55,0	2,0	46568







7
FRACTIONAL SERIES

TECH INFO 70

TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
1/8	3/4	2-1/4	1/8	70470
1/8	1	3	1/8	70471
3/16	3/4	2-1/2	3/16	70472
3/16	1-1/8	3	3/16	70473
1/4	1-1/8	3	1/4	70474
1/4	1-1/2	4	1/4	70475
5/16	1-1/8	3	5/16	70476
5/16	1-5/8	4	5/16	70477
3/8	1-1/8	3	3/8	70478
3/8	1-3/4	4	3/8	70479
7/16	2	4-1/2	7/16	70480
7/16	3	6	7/16	70481
1/2	2	4-1/2	1/2	70482
1/2	3	6	1/2	70483
5/8	2-1/4	5	5/8	70484
5/8	3	6	5/8	70485
3/4	2-1/4	5	3/4	70486
3/4	3	6	3/4	70487
1	2-1/4	5	1	70488
1	3	6	1	70489






TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6



7M
METRIC SERIES


TECH INFO 71

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
3,0	25,0	75,0	3,0	70551
4,0	25,0	75,0	4,0	70552
5,0	25,0	75,0	5,0	70553
6,0	25,0	75,0	6,0	70554
8,0	25,0	75,0	8,0	70555
10,0	38,0	100,0	10,0	70556
12,0	50,0	100,0	12,0	70557
12,0	75,0	150,0	12,0	70558
14,0	75,0	150,0	14,0	70559
16,0	75,0	150,0	16,0	70560
18,0	75,0	150,0	18,0	70561
20,0	75,0	150,0	20,0	70562
25,0	75,0	150,0	25,0	70563

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM







7B
FRACTIONAL SERIES

TECH INFO 70

TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
1/8	3/4	2-1/4	1/8	70441
1/8	1	3	1/8	70442
3/16	3/4	2-1/2	3/16	70444
3/16	1-1/8	3	3/16	70445
1/4	1-1/8	3	1/4	70447
1/4	1-1/2	4	1/4	70448
5/16	1-1/8	3	5/16	70450
5/16	1-5/8	4	5/16	70451
3/8	1-1/8	3	3/8	70453
3/8	1-3/4	4	3/8	70454
7/16	2	4-1/2	7/16	70456
7/16	3	6	7/16	70457
1/2	2	4-1/2	1/2	70459
1/2	3	6	1/2	70460
5/8	2-1/4	5	5/8	70462
5/8	3	6	5/8	70463
3/4	2-1/4	5	3/4	70465
3/4	3	6	3/4	70466
1	2-1/4	5	1	70468
1	3	6	1	70469






TOLERANCES (mm)

D_1 = +0,000/+0,050

D_2 = h_6



7MB
METRIC SERIES


TECH INFO 71

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
3,0	25,0	75,0	3,0	70527
4,0	25,0	75,0	4,0	70529
5,0	25,0	75,0	5,0	70531
6,0	25,0	75,0	6,0	70533
8,0	25,0	75,0	8,0	70535
10,0	38,0	100,0	10,0	70537
12,0	50,0	100,0	12,0	70539
12,0	75,0	150,0	12,0	70540
14,0	75,0	150,0	14,0	70542
16,0	75,0	150,0	16,0	70544
18,0	75,0	150,0	18,0	70546
20,0	75,0	150,0	20,0	70548
25,0	75,0	150,0	25,0	70550

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM







55
FRACTIONAL SERIES

TECH INFO 72

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
1/8	1/4	1-1/2	1/8	32672	–
1/8	1/2	1-1/2	1/8	32655	–
5/32	9/16	2	3/8	32656	–
3/16	5/16	2	3/8	32673	–
3/16	5/8	2	3/8	32657	–
7/32	3/4	2-1/2	1/4	32658	–
1/4	3/8	2	1/4	32674	–
1/4	3/4	2-1/2	1/4	32659	–
5/16	7/16	2	5/16	32675	–
5/16	13/16	2-1/2	5/16	32660	–
3/8	1/2	2	3/8	32676	32677
3/8	1	2-1/2	3/8	32661	32662
7/16	1	2-3/4	7/16	32663	–
1/2	5/8	2-1/2	1/2	32678	32679
1/2	1-1/4	3	1/2	32664	32665
5/8	3/4	3	5/8	32680	32681
5/8	1-5/8	3-1/2	5/8	32666	32667
3/4	1	3	3/4	32682	32683
3/4	1-5/8	4	3/4	32668	32669
1	1-1/2	4	1	32670	32671


TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6







TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6

55M
METRIC SERIES


TECH INFO 74

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
6,0	12,0	50,0	6,0	42606	–
6,0	19,0	63,0	6,0	42607	–
6,0	25,0	75,0	6,0	42608	–
8,0	12,0	50,0	8,0	42609	–
8,0	20,0	63,0	8,0	42610	–
8,0	25,0	75,0	8,0	42611	–
10,0	16,0	50,0	10,0	42612	–
10,0	22,0	75,0	10,0	42622	42613
10,0	38,0	100,0	10,0	42614	–
12,0	19,0	63,0	12,0	42615	–
12,0	25,0	75,0	12,0	42616	42623
12,0	50,0	100,0	12,0	42617	–
16,0	32,0	89,0	16,0	42618	42624
16,0	75,0	150,0	16,0	42619	–
20,0	38,0	100,0	20,0	42620	42625
20,0	75,0	150,0	20,0	42621	–

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM







55CR
FRACTIONAL SERIES

TECH INFO 72

TOLERANCES (inch)

D_1 = +0.0000/–0.0020
D_2 = h_6
R = +0.0000/–0.0020

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
1/8	1/4	1-1/2	1/8	.010	32606	–
1/8	1/2	1-1/2	1/8	.010	32607	–
5/32	5/16	2	3/16	.010	32608	–
5/32	9/16	2	3/16	.010	32609	–
3/16	5/16	2	3/16	.010	32610	–
3/16	5/8	2	3/16	.010	32611	–
7/32	3/8	2	1/4	.015	32612	–
7/32	3/4	2-1/2	1/4	.015	32613	–
1/4	3/8	2	1/4	.015	32614	–
1/4	3/4	2-1/2	1/4	.015	32615	–
1/4	1-1/4	4	1/4	.015	32616	–
5/16	7/16	2	5/16	.015	32619	–
5/16	13/16	2-1/2	5/16	.015	32620	–
5/16	1-1/4	4	5/16	.015	32621	–
3/8	1/2	2	3/8	.015	32625	32591
3/8	1/2	2	3/8	.030	32592	32593
3/8	1	2-1/2	3/8	.015	32626	32628
3/8	1	2-1/2	3/8	.030	32573	32574
3/8	1-1/2	4	3/8	.015	32627	–
3/8	1-1/2	4	3/8	.030	32569	–

continued on next page




55CR
FRACTIONAL SERIES

CONTINUED

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT
7/16	1	2-3/4	7/16	.015	32632	–
7/16	2	4	7/16	.015	32633	–
1/2	5/8	2-1/2	1/2	.030	32594	32595
1/2	5/8	2-1/2	1/2	.060	32596	32597
1/2	1-1/4	3	1/2	.030	32575	32576
1/2	1-1/4	3	1/2	.060	32577	32578
1/2	2	4	1/2	.030	32685	–
1/2	2	4	1/2	.060	32686	–
5/8	3/4	3	5/8	.030	32598	32599
5/8	3/4	3	5/8	.060	32600	32601
5/8	1-5/8	3-1/2	5/8	.030	32579	32580
5/8	1-5/8	3-1/2	5/8	.060	32581	32582
5/8	2-1/2	5	5/8	.030	32570	–
5/8	2-1/2	5	5/8	.060	32687	–
3/4	1	3	3/4	.030	32602	32603
3/4	1	3	3/4	.060	32604	32605
3/4	1-5/8	4	3/4	.030	32583	32584
3/4	1-5/8	4	3/4	.060	32585	32586
3/4	3-1/4	6	3/4	.030	32571	–
3/4	3-1/4	6	3/4	.060	32688	–
1	1-1/2	4	1	.030	32587	32588
1	1-1/2	4	1	.060	32589	32590
1	2-5/8	6	1	.030	32572	–
1	2-5/8	6	1	.060	32689	–





51
FRACTIONAL SERIES

TECH INFO 76

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-X
1/4	3/4	2-1/2	1/4	35100
3/8	1	2-1/2	3/8	35101
1/2	1-1/4	3	1/2	35102
5/8	1-5/8	3-1/2	5/8	35103
3/4	1-5/8	4	3/4	35104
1	2-5/8	6	1	35105

TOLERANCES (inch)
D1 = +0.0000/–0.0020
D2 = h6

- STEELS
- STAINLESS STEELS
- HIGH TEMP ALLOYS
- TITANIUM

51M
METRIC SERIES


TECH INFO 78

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-X
6,0	19,0	63,0	6,0	45100
8,0	20,0	63,0	8,0	45101
10,0	22,0	75,0	10,0	45102
12,0	26,0	83,0	12,0	45103
16,0	32,0	92,0	16,0	45104
20,0	38,0	104,0	20,0	45105

TOLERANCES (mm)
D1 = +0,000/–0,050
D2 = h6







TOLERANCES (inch)

D1 = +0.0000/–0.0020
D2 = h6

51L
FRACTIONAL SERIES

TECH INFO 76

inch					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_2	Ti-NAMITE-X
1/4	3/8	4	1/4	1-1/8	35106
3/8	1/2	4	3/8	2-1/8	35107
1/2	5/8	4	1/2	2-1/4	35108
5/8	3/4	5	5/8	2-1/2	35109
3/4	1	6	3/4	3-3/8	35110
1	1-1/4	6	1	3-3/8	35111

STEELS
STAINLESS STEELS
HIGH TEMP ALLOYS
TITANIUM

TOLERANCES (mm)

D1 = +0,000/–0,050
D2 = h6


51ML
METRIC SERIES

TECH INFO 78

mm					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_2	Ti-NAMITE-X
6,0	8,0	75,0	6,0	32,0	45106
8,0	10,0	75,0	8,0	32,0	45107
10,0	12,0	100,0	10,0	40,0	45108
12,0	15,0	100,0	12,0	48,0	45109
16,0	20,0	115,0	16,0	65,0	45110
20,0	24,0	150,0	20,0	80,0	45111







51CR
FRACTIONAL SERIES

TECH INFO 76

inch					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-X
1/4	3/4	2-1/2	1/4	.015	35112
3/8	1	2-1/2	3/8	.015	35113
3/8	1	2-1/2	3/8	.030	35114
1/2	1-1/4	3	1/2	.030	35115
1/2	1-1/4	3	1/2	.090	35116
1/2	1-1/4	3	1/2	.120	35117
5/8	1-5/8	3-1/2	5/8	.030	35118
5/8	1-5/8	3-1/2	5/8	.090	35119
5/8	1-5/8	3-1/2	5/8	.120	35120
3/4	1-5/8	4	3/4	.030	35121
3/4	1-5/8	4	3/4	.090	35122
3/4	1-5/8	4	3/4	.120	35123
1	2-5/8	6	1	.030	35124
1	2-5/8	6	1	.090	35125
1	2-5/8	6	1	.120	35126

TOLERANCES (inch)
D1 = +0.0000/–0.0020
D2 = h6
R = +0.000/–0.002

STEELS
STAINLESS STEELS
HIGH TEMP ALLOYS
TITANIUM

51MCR
METRIC SERIES


TECH INFO 78

mm					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	Ti-NAMITE-X
6,0	19,0	63,0	6,0	0,5	45112
8,0	20,0	63,0	8,0	0,5	45113
8,0	20,0	63,0	8,0	1,0	45114
10,0	22,0	75,0	10,0	1,0	45115
10,0	22,0	75,0	10,0	1,5	45116
10,0	22,0	75,0	10,0	2,0	45117
12,0	26,0	83,0	12,0	1,0	45118
12,0	26,0	83,0	12,0	1,5	45119
12,0	26,0	83,0	12,0	2,0	45120
16,0	32,0	92,0	16,0	1,0	45121
16,0	32,0	92,0	16,0	1,5	45122
16,0	32,0	92,0	16,0	2,0	45123
20,0	38,0	104,0	20,0	1,0	45124
20,0	38,0	104,0	20,0	1,5	45125
20,0	38,0	104,0	20,0	2,0	45126

TOLERANCES (mm)
D1 = +0,000/–0,050
D2 = h6
R = +0,000/–0,050







TOLERANCES (inch)

D1 = +0.0000/–0.0020
D2 = h6
R = +0.000/–0.002

51LC
FRACTIONAL SERIES

TECH INFO 76

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-X
1/4	3/8	4	1/4	1-1/8	.015	35127
3/8	1/2	4	3/8	2-1/8	.015	35128
3/8	1/2	4	3/8	2-1/8	.030	35129
1/2	5/8	4	1/2	2-1/4	.030	35130
1/2	5/8	4	1/2	2-1/4	.090	35131
1/2	5/8	4	1/2	2-1/4	.120	35132
5/8	3/4	5	5/8	2-1/2	.030	35133
5/8	3/4	5	5/8	2-1/2	.090	35134
5/8	3/4	5	5/8	2-1/2	.120	35135
3/4	1	6	3/4	3-3/8	.030	35136
3/4	1	6	3/4	3-3/8	.090	35137
3/4	1	6	3/4	3-3/8	.120	35138
1	1-1/4	6	1	3-3/8	.030	35139
1	1-1/4	6	1	3-3/8	.090	35140
1	1-1/4	6	1	3-3/8	.120	35141

STEELS
STAINLESS STEELS
HIGH TEMP ALLOYS
TITANIUM

TOLERANCES (mm)

D1 = +0,000/–0,050
D2 = h6
R = +0,000/–0,050

51MLC
METRIC SERIES


TECH INFO 78

mm						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	Ti-NAMITE-X
6,0	8,0	75,0	6,0	32,0	0,5	45127
8,0	10,0	75,0	8,0	32,0	0,5	45128
8,0	10,0	75,0	8,0	32,0	1,0	45129
10,0	12,0	100,0	10,0	40,0	1,0	45130
10,0	12,0	100,0	10,0	40,0	1,5	45131
10,0	12,0	100,0	10,0	40,0	2,0	45132
12,0	15,0	100,0	12,0	48,0	1,0	45133
12,0	15,0	100,0	12,0	48,0	1,5	45134
12,0	15,0	100,0	12,0	48,0	2,0	45135
16,0	20,0	115,0	16,0	65,0	1,0	45136
16,0	20,0	115,0	16,0	65,0	1,5	45137
16,0	20,0	115,0	16,0	65,0	2,0	45138
20,0	24,0	150,0	20,0	80,0	1,0	45139
20,0	24,0	150,0	20,0	80,0	1,5	45140
20,0	24,0	150,0	20,0	80,0	2,0	45141

MULTI Carb
HIGH PERFORMANCE FINISHING END MILLS







66
FRACTIONAL SERIES

TECH INFO 80

inch					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	Ti-NAMITE-A (AlTiN)
3/16	5/8	2	3/16	7	36620
1/4	3/4	2-1/2	1/4	7	36621
3/8	1	3	3/8	7	36622
1/2	1-1/4	3	1/2	9	36623
5/8	1-5/8	3-1/2	5/8	9	36624
3/4	1-5/8	4	3/4	11	36625
1	2	6	1	11	36626

Neck Option Available

STEELS
STAINLESS STEELS
HIGH TEMP ALLOYS
TITANIUM

TOLERANCES (inch)
D_1 = +0.0000/–0.0020
D_2 = h_6

66M
METRIC SERIES

TECH INFO 82


mm					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	Ti-NAMITE-A (AlTiN)
6,0	19,0	63,0	6,0	7	46620
8,0	20,0	63,0	8,0	7	46621
10,0	22,0	75,0	10,0	7	46622
12,0	26,0	83,0	12,0	9	46623
16,0	32,0	92,0	16,0	9	46624
20,0	38,0	104,0	20,0	11	46625
25,0	38,0	104,0	25,0	11	46626

Neck Option Available

TOLERANCES (mm)
D_1 = +0,000/–0,050
D_2 = h_6







TOLERANCES (inch)

D_1 = +0.0000/–0.0020
D_2 = h_6
R = +0.0000/–0.0020

66CR
FRACTIONAL SERIES

TECH INFO 82

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	NO. OF FLUTES	Ti-NAMITE-A (AlTiN)
3/16	5/8	2	3/16	.010	7	36627
1/4	3/4	2-1/2	1/4	.015	7	36628
3/8	1	3	3/8	.015	7	36629
1/2	1-1/4	3	1/2	.030	9	36630
1/2	1-1/4	3	1/2	.090	9	36631
1/2	1-1/4	3	1/2	.120	9	36632
5/8	1-5/8	3-1/2	5/8	.030	9	36633
5/8	1-5/8	3-1/2	5/8	.090	9	36634
5/8	1-5/8	3-1/2	5/8	.120	9	36635
3/4	1-5/8	4	3/4	.030	11	36636
3/4	1-5/8	4	3/4	.090	11	36637
3/4	1-5/8	4	3/4	.120	11	36638
1	2	6	1	.030	11	36639
1	2	6	1	.090	11	36640
1	2	6	1	.120	11	36641

Neck Option Available

STEELS
STAINLESS STEELS
HIGH TEMP ALLOYS
TITANIUM

TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050

66MCR
METRIC SERIES


TECH INFO 82

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	NO. OF FLUTES	Ti-NAMITE-A (AlTiN)
6,0	19,0	63,0	6,0	0,5	7	46627
8,0	20,0	63,0	8,0	0,5	7	46629
10,0	22,0	75,0	10,0	0,5	7	46632
12,0	26,0	83,0	12,0	1,0	9	46636
12,0	26,0	83,0	12,0	2,0	9	46638
12,0	26,0	83,0	12,0	3,0	9	46640
16,0	32,0	92,0	16,0	1,0	9	46641
16,0	32,0	92,0	16,0	2,0	9	46643
16,0	32,0	92,0	16,0	3,0	9	46645
20,0	38,0	104,0	20,0	1,0	11	46647
20,0	38,0	104,0	20,0	2,0	11	46649
20,0	38,0	104,0	20,0	3,0	11	46651
25,0	38,0	104,0	25,0	1,0	11	46654
25,0	38,0	104,0	25,0	2,0	11	46656
25,0	38,0	104,0	25,0	3,0	11	46658

Neck Option Available







56B
FRACTIONAL SERIES

TECH INFO 84

STEELS

HARDENED STEELS

inch						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	α	REACH L_3	Ti-NAMITE-A (AlTiN)
1/32	1/32	3	1/4	8°20'	1/16	93272
1/16	1/16	3	1/4	7°40'	1/8	93273
3/32	3/32	3	1/4	6°50'	3/16	93274
1/8	1/8	3	1/4	6°	1/4	93275
3/16	3/16	3	1/4	3°35'	3/8	93276
1/4	1/4	3-1/2	1/4	–	1/2	93277
5/16	5/16	4	5/16	–	5/8	93278
3/8	3/8	4	3/8	–	3/4	93279
1/2	1/2	4-1/2	1/2	–	1	93280
5/8	5/8	5-1/2	5/8	–	1-1/4	93281
3/4	3/4	6-1/2	3/4	–	1-1/2	93282

Neck Option Available

TOLERANCES (inch)

1/32–3/32 DIAMETER
D_1 = +0.0000/–0.0010
D_2 = h_6

>3/32–1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

>1/4–3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

>3/8–3/4 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

56MB
METRIC SERIES

TECH INFO 85

mm						EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	α	REACH L_3	Ti-NAMITE-A (AlTiN)
1,0	1,0	76,0	6,0	8°10'	2,0	91349
1,5	1,5	76,0	6,0	7°45'	3,0	91350
2,0	2,0	76,0	6,0	7°10'	4,0	91351
2,5	2,5	76,0	6,0	6°35'	5,0	91352
3,0	3,0	76,0	6,0	6°	6,0	91353
4,0	4,0	76,0	6,0	4°30'	8,0	91354
5,0	5,0	89,0	6,0	2°30'	10,0	91355
6,0	6,0	89,0	6,0	–	12,0	91356
8,0	8,0	102,0	8,0	–	16,0	91357
10,0	10,0	102,0	10,0	–	20,0	91358
12,0	12,0	114,0	12,0	–	24,0	91359
16,0	16,0	140,0	16,0	–	32,0	91360
20,0	20,0	165,0	20,0	–	40,0	91361

TOLERANCES (mm)

1–2,5 DIAMETER
D_1 = +0,000/–0,025
D_2 = h_6


>2,5–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6

>10–20 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6







TOLERANCES (inch)

1/4 DIAMETER
D_1 = +0.0000/–0.0012
D_2 = h_6

5/16 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

3/8 DIAMETER
D_1 = +0.0000/–0.0016
D_2 = h_6

1/2 DIAMETER
D_1 = +0.0000/–0.0020
D_2 = h_6

57
FRACTIONAL SERIES

TECH INFO 86

HARDENED STEELS

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
1/4	17/32	3-1/2	1/4	36140
5/16	11/16	4	5/16	36141
3/8	13/16	4	3/8	36142
1/2	1-3/32	4-1/2	1/2	36143

Neck Option Available
Ideal for Trochodial Milling

TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6

8 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6

10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6

12 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6

57M
METRIC SERIES


TECH INFO 87

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
6,0	13,0	89,0	6,0	46140
8,0	18,0	102,0	8,0	46141
10,0	22,0	102,0	10,0	46142
12,0	26,0	114,0	12,0	46143

Neck Option Available
Ideal for Trochodial Milling







33CR
FRACTIONAL SERIES

TECH INFO 88

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM

inch					
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	TI-NAMITE-A (AlTiN) EDP NO.
1/8	3/8	2-1/2	1/4	.015	33345
3/16	9/16	2-1/2	1/4	.015	33346
1/4	3/4	2-1/2	1/4	.020	33347
5/16	13/16	2-1/2	5/16	.020	33348
3/8	1	2-1/2	3/8	.020	33349
7/16	1-1/8	2-3/4	7/16	.020	33350
1/2	1-1/4	3-1/4	1/2	.030	33351
5/8	1-1/2	3-1/2	5/8	.040	33352
3/4	1-3/4	4	3/4	.040	33353
1	2-1/4	5	1	.040	33354

TOLERANCES (inch)

1/8–1/4 DIAMETER
D1 = +0.0000/–0.0012
D2 = h6
R = +0.0000/–0.0020

>1/4–3/8 DIAMETER
D1 = +0.0000/–0.0016
D2 = h6
R = +0.0000/–0.0020

>3/8–1 DIAMETER
D1 = +0.0000/–0.0020
D2 = h6
R = +0.0000/–0.0020

33MCR
METRIC SERIES

TECH INFO 90

mm					
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	TI-NAMITE-A (AlTiN) EDP NO.
3,0	9,0	57,0	6,0	0,3	43445
4,0	12,0	57,0	6,0	0,3	43446
5,0	15,0	57,0	6,0	0,3	43447
6,0	18,0	57,0	6,0	0,5	43448
8,0	20,0	63,0	8,0	0,5	43449
10,0	27,0	72,0	10,0	0,5	43450
12,0	30,0	83,0	12,0	0,5	43451
16,0	38,0	92,0	16,0	1,0	43452
20,0	46,0	104,0	20,0	1,0	43453

TOLERANCES (mm)


3–6 DIAMETER
D_1 = +0,000/–0,030
D_2 = h_6
R = +0,00/–0,05

>6–10 DIAMETER
D_1 = +0,000/–0,040
D_2 = h_6
R = +0,00/–0,05

>10–25 DIAMETER
D_1 = +0,000/–0,050
D_2 = h_6
R = +0,00/–0,05







TOLERANCES (inch)

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6
R = +0.0000/–0.0020

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6
R = +0.0000/–0.002

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6
R = +0.0000/–0.0020

45
FRACTIONAL SERIES

TECH INFO 92

inch						EDP NO.			
CUTTING DIA. D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	REACH* L_3	CORNER RADIUS R	UNCOATED W/FLAT	UNCOATED W/O FLAT	Ti-NAMITE-B (TiB_2) W/FLAT	Ti-NAMITE-B (TiB_2) W/O FLAT
1/4	3/8	2-1/2	3/8	1	.010	91257	91250	91235	91242
5/16	7/16	2-1/2	3/8	1-1/8	.012	91258	91251	91236	91243
3/8	9/16	2-1/2	3/8	1-1/8	.015	91259	91252	91237	91244
1/2	3/4	3	1/2	1-1/2	.020	91260	91253	91238	91245
5/8	7/8	3-1/2	5/8	1-3/4	.025	91261	91254	91239	91246
3/4	1	4	3/4	2	.030	91262	91255	91240	91247
1	1-1/4	4	1	2-1/8	.040	91263	91256	91241	91248


*Reach (Optional)

NON-FERROUS

PLASTICS/COMPOSITES







44
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch					EDP NO.			
CUTTING DIA. D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	CORNER RADIUS* R	UNCOATED W/FLAT	UNCOATED W/O FLAT	Ti-NAMITE-B (TiB_2) W/FLAT	Ti-NAMITE-B (TiB_2) W/O FLAT
1/4	3/4	2-7/16	3/8	.015–.060	34501	32033	34502	32053
1/4	1-1/4	3-1/16	3/8	.015–.060	34503	32034	34504	32054
1/4	1-3/4	3-9/16	3/8	.015–.060	34505	32035	34506	32055
5/16	1-3/8	3-1/8	3/8	.015–.060	34507	32036	34508	32056
3/8	3/4	2-1/2	3/8	.015–.060	34509	32037	34510	32057
3/8	1-1/2	3-1/4	3/8	.015–.060	34511	32038	34512	32058
3/8	2-1/2	4-1/4	3/8	.015–.060	34513	32039	34514	32059
1/2	1-1/4	3-1/4	1/2	.015–.125	34515	32040	34516	32060
1/2	2	4	1/2	.015–.125	34517	32041	34518	32061
1/2	3	5	1/2	.015–.125	34519	32042	34520	32062
5/8	1-5/8	3-3/4	5/8	.015–.125	34521	32043	34522	32063
5/8	2-1/2	4-5/8	5/8	.015–.125	34523	32044	34524	32064
3/4	1-5/8	3-7/8	3/4	.015–.125	34525	32045	34526	32065
3/4	3	5-1/4	3/4	.015–.125	34527	32046	34528	32066
3/4	4	6-1/4	3/4	.015–.125	34529	32047	34530	32067
1	2	4-1/2	1	.015–.125	34531	32048	34532	32068
1	4	6-1/2	1	.015–.125	34533	32049	34534	32069

*Contact your SGS Sales Representative for more information on Corner Radius options.

TOLERANCES (inch)


1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6
R = +0.0000/–0.0020

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6
R = +0.0000/–0.0020

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6
R = +0.0000/–0.0020







TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,000/–0,006
D_2 = h_6
R = +0,000/–0,050

>3–6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6
R = +0,000/–0,050

>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6
R = +0,000/–0,050

>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6
R = +0,000/–0,050

44M
METRIC SERIES

TECH INFO 94


mm					EDP NO.			
CUTTING DIA. D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	CORNER RADIUS* R	UNCOATED W/FLAT	UNCOATED W/O FLAT	Ti-NAMITE-B (TiB_2) W/FLAT	Ti-NAMITE-B (TiB_2) W/O FLAT
3,0	8,0	52,0	6,0	0,36–0,76	44505	49663	44506	49674
4,0	11,0	55,0	6,0	0,36–0,76	44509	49664	44510	49675
5,0	13,0	57,0	6,0	0,36–0,76	44513	49665	44514	49676
6,0	13,0	57,0	6,0	0,36–0,76	44517	49666	44518	49677
8,0	19,0	69,0	10,0	0,38–1,52	44521	49667	44522	49678
10,0	22,0	72,0	10,0	0,38–1,52	44525	49668	44526	49679
12,0	26,0	83,0	12,0	0,38–3,17	44529	49669	44530	49680
14,0	26,0	83,0	14,0	0,38–3,17	44533	49670	44534	49681
16,0	32,0	92,0	16,0	0,38–3,17	44537	49671	44538	49682
18,0	32,0	92,0	18,0	0,38–3,17	44541	49672	44542	49683
20,0	38,0	104,0	20,0	0,38–3,17	44545	49673	44546	49684

*Contact your SGS Sales Representative for more information on Corner Radius options.

NON-FERROUS
PLASTICS/COMPOSITES







43CR
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	3/8	1-1/2	1/8	.010	34771	34793
3/16	9/16	2	3/16	.010	34772	34794
1/4	3/4	2-1/2	1/4	.010	34773	34795
1/4	3/4	2-1/2	1/4	.030	34774	34796
5/16	5/8	2-1/2	5/16	.030	34775	34797
3/8	1	2-1/2	3/8	.010	34776	34798
3/8	1	2-1/2	3/8	.030	34777	34799
3/8	1	2-1/2	3/8	.060	32761	32825
1/2	1-1/4	3-1/4	1/2	.010	34778	34800
1/2	1-1/4	3-1/4	1/2	.030	34779	34801
1/2	1-1/4	3-1/4	1/2	.060	34780	34802
1/2	1-1/4	3-1/4	1/2	.090	34781	34803
1/2	1-1/4	3-1/4	1/2	.120	32766	32830
5/8	1-5/8	3-3/4	5/8	.030	34782	34804
5/8	1-5/8	3-3/4	5/8	.060	34783	34805
5/8	1-5/8	3-3/4	5/8	.090	34784	34806
3/4	1-5/8	4	3/4	.030	34785	34807
3/4	1-5/8	4	3/4	.060	34786	34808
3/4	1-5/8	4	3/4	.090	34787	34809
3/4	1-5/8	4	3/4	.120	34815	34817
1	2	4-1/2	1	.030	34789	34811
1	2	4-1/2	1	.060	34790	34812
1	2	4-1/2	1	.090	34791	34813
1	2	4-1/2	1	.120	34816	34818

TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6
R = +0.0000/–0.0020


1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6
R = +0.0000/–0.0020

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6
R = +0.0000/–0.0020

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6
R = +0.0000/–0.0020







43MCR
METRIC SERIES

TECH INFO 94

TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6
R = +0,000/–0,050

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6
R = +0,000/–0,050

>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6
R = +0,000/–0,050


>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6
R = +0,000/–0,050

mm						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
6,0	10,0	63,0	6,0	20,0	0,5	44769	44789
6,0	10,0	63,0	6,0	20,0	1,0	44770	44790
6,0	13,0	72,0	6,0	30,0	0,5	44771	44791
6,0	13,0	72,0	6,0	30,0	1,0	44772	44792
8,0	12,0	75,0	8,0	25,0	0,3	44773	44793
8,0	12,0	75,0	8,0	25,0	0,5	44774	44794
8,0	12,0	75,0	8,0	25,0	1,0	44775	44795
8,0	12,0	75,0	8,0	25,0	1,5	44776	44796
10,0	14,0	100,0	10,0	35,0	0,3	44777	44797
10,0	14,0	100,0	10,0	35,0	0,5	44778	44798
10,0	14,0	100,0	10,0	35,0	1,0	44779	44799
10,0	14,0	100,0	10,0	35,0	1,5	44780	44800
12,0	16,0	100,0	12,0	40,0	0,5	44781	44801
12,0	16,0	100,0	12,0	40,0	1,0	44782	44802
12,0	16,0	100,0	12,0	40,0	1,5	44783	44803
12,0	16,0	100,0	12,0	40,0	2,0	44784	44804
16,0	20,0	125,0	16,0	50,0	2,0	44785	44805
16,0	20,0	125,0	16,0	50,0	4,0	44786	44806
20,0	25,0	150,0	20,0	65,0	2,0	44787	44807
20,0	25,0	150,0	20,0	65,0	4,0	44788	44808

NON-FERROUS
PLASTICS/COMPOSITES







43LC
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	5/32	3	1/8	1/2	.010	32751	32815
3/16	7/32	3	3/16	1/2	.010	32752	32816
1/4	3/8	4	1/4	3/4	.010	32753	32817
1/4	3/8	4	1/4	3/4	.030	32754	32818
1/4	3/8	4	1/4	1-1/2	.010	32755	32819
1/4	3/8	4	1/4	1-1/2	.030	32756	32820
1/4	3/8	4	1/4	2-1/8	.010	32757	32821
1/4	3/8	4	1/4	2-1/8	.030	32758	32822
5/16	7/16	4	5/16	1-1/8	.030	32759	32823
5/16	7/16	4	5/16	2-1/8	.030	32760	32824
3/8	1/2	4	3/8	1-1/8	.030	32762	32826
3/8	1/2	4	3/8	1-1/8	.060	32763	32827
3/8	1/2	4	3/8	2-1/8	.030	32764	32828
3/8	1/2	4	3/8	2-1/8	.060	32765	32829
1/2	5/8	4	1/2	1-3/8	.030	32767	32831
1/2	5/8	4	1/2	1-3/8	.060	32768	32832
1/2	5/8	4	1/2	1-3/8	.090	32769	32833
1/2	5/8	4	1/2	1-3/8	.120	32770	32834
1/2	5/8	6	1/2	2-1/8	.030	32771	32835
1/2	5/8	6	1/2	2-1/8	.060	32772	32836
1/2	5/8	6	1/2	2-1/8	.090	32773	32837
1/2	5/8	6	1/2	2-1/8	.120	32774	32838
1/2	5/8	6	1/2	3-3/8	.030	32775	32839
1/2	5/8	6	1/2	3-3/8	.060	32776	32840
1/2	5/8	6	1/2	3-3/8	.090	32777	32841
1/2	5/8	6	1/2	3-3/8	.120	32778	32842

continued on next page

TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6
R = +0.0000/–0.0020

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6
R = +0.0000/–0.0020

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6
R = +0.0000/–0.0020

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6
R = +0.0000/–0.0020



43LC
FRACTIONAL SERIES

CONTINUED


inch						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
5/8	3/4	4	5/8	1-3/4	.030	32779	32843
5/8	3/4	4	5/8	1-3/4	.060	32780	32844
5/8	3/4	4	5/8	1-3/4	.090	32781	32845
5/8	3/4	4	5/8	1-3/4	.120	32782	32846
5/8	3/4	4	5/8	2-3/8	.030	32783	32847
5/8	3/4	4	5/8	2-3/8	.060	32784	32848
5/8	3/4	4	5/8	2-3/8	.090	32785	32849
5/8	3/4	4	5/8	2-3/8	.120	32786	32850
5/8	3/4	6	5/8	3-3/8	.030	32787	32851
5/8	3/4	6	5/8	3-3/8	.060	32788	32852
5/8	3/4	6	5/8	3-3/8	.090	32789	32853
5/8	3/4	6	5/8	3-3/8	.120	32790	32854
3/4	1	4	3/4	1-3/4	.030	32791	32855
3/4	1	4	3/4	1-3/4	.060	32792	32856
3/4	1	4	3/4	1-3/4	.090	32793	32857
3/4	1	4	3/4	1-3/4	.120	32794	32858
3/4	1	6	3/4	2-3/8	.030	32795	32859
3/4	1	6	3/4	2-3/8	.060	32796	32860
3/4	1	6	3/4	2-3/8	.090	32797	32861
3/4	1	6	3/4	2-3/8	.120	32798	32862
3/4	1	6	3/4	3-3/8	.030	32799	32863
3/4	1	6	3/4	3-3/8	.060	32800	32864
3/4	1	6	3/4	3-3/8	.090	32801	32865
3/4	1	6	3/4	3-3/8	.120	32802	32866
1	1-1/4	6	1	2-3/8	.030	32803	32867
1	1-1/4	6	1	2-3/8	.060	32804	32868
1	1-1/4	6	1	2-3/8	.090	32805	32869
1	1-1/4	6	1	2-3/8	.120	32806	32870
1	1-1/4	6	1	3-3/8	.030	32807	32871
1	1-1/4	6	1	3-3/8	.060	32808	32872
1	1-1/4	6	1	3-3/8	.090	32809	32873
1	1-1/4	6	1	3-3/8	.120	32810	32874

NON-FERROUS

PLASTICS/COMPOSITES







43
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	3/8	1-1/2	1/8	34701	34728
3/16	9/16	2	3/16	34702	34729
1/4	3/8	2	1/4	34703	34730
1/4	3/4	2-1/2	1/4	34704	34731
1/4	1-1/4	3-1/2	1/4	34705	34732
5/16	7/16	2	5/16	34706	34733
5/16	5/8	2-1/2	5/16	34707	34734
5/16	1-1/4	4	5/16	34708	34735
3/8	1/2	2	3/8	34709	34736
3/8	1	2-1/2	3/8	34710	34737
3/8	1-1/2	3-1/2	3/8	34711	34738
1/2	5/8	2-1/2	1/2	34712	34739
1/2	1-1/4	3-1/4	1/2	34713	34740
1/2	2	4	1/2	34714	34741
1/2	3-1/8	6	1/2	34715	34742
5/8	3/4	3	5/8	34716	34743
5/8	1-5/8	3-3/4	5/8	34717	34744
5/8	2-1/2	5	5/8	34718	34745
5/8	3-3/4	6	5/8	34719	34746
3/4	1	3	3/4	34720	34747
3/4	1-5/8	4	3/4	34721	34748
3/4	2-1/4	5	3/4	34722	34749
3/4	3-1/4	6	3/4	34723	34750
1	1-1/4	4	1	34724	34751
1	2	4-1/2	1	34725	34752
1	2-5/8	6	1	34726	34753
1	3-1/4	6	1	34727	34754

TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6


1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6







TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6

>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6

43M
METRIC SERIES


TECH INFO 94

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
6,0	13,0	57,0	6,0	44701	44715
6,0	13,0	72,0	6,0	44702	44716
8,0	19,0	63,0	8,0	44703	44717
10,0	22,0	72,0	10,0	44705	44719
12,0	26,0	83,0	12,0	44708	44722
16,0	32,0	92,0	16,0	44711	44725
20,0	38,0	104,0	20,0	44714	44728

NON-FERROUS
PLASTICS/COMPOSITES







43L
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	5/32	3	1/8	1/2	32700	32725
3/16	7/32	3	3/16	1/2	32701	32726
1/4	3/8	4	1/4	3/4	32702	32727
1/4	3/8	4	1/4	1-1/2	32703	32728
1/4	3/8	4	1/4	2-1/8	32704	32729
5/16	7/16	4	5/16	1-1/8	32705	32730
5/16	7/16	4	5/16	2-1/8	32706	32731
3/8	1/2	4	3/8	1-1/8	32707	32732
3/8	1/2	4	3/8	2-1/8	32708	32733
1/2	5/8	4	1/2	1-3/8	32709	32734
1/2	5/8	6	1/2	2-1/8	32710	32735
1/2	5/8	6	1/2	3-3/8	32711	32736
5/8	3/4	4	5/8	1-3/4	32712	32737
5/8	3/4	4	5/8	2-3/8	32713	32738
5/8	3/4	6	5/8	3-3/8	32714	32739
3/4	1	4	3/4	1-3/4	32715	32740
3/4	1	6	3/4	2-3/8	32716	32741
3/4	1	6	3/4	3-3/8	32717	32742
1	1-1/4	6	1	2-3/8	32718	32743
1	1-1/4	6	1	3-3/8	32719	32744
1	1-1/4	7	1	4-3/8	32720	32745

TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6


1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6







43CB
FRACTIONAL SERIES

TECH INFO 92

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
3/8	1	2-1/2	3/8	.020	34300	34305
1/2	1-1/4	3-1/4	1/2	.030	34301	34306
5/8	1-5/8	3-3/4	5/8	.030	34302	34307
3/4	1-5/8	4	3/4	.030	34303	34308
1	2	4-1/2	1	.030	34304	34309

TOLERANCES (inch)

3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6
R = +0.0000/–0.0020

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6
R = +0.0000/–0.0020

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6
R = +0.0000/–0.0020

NON-FERROUS

PLASTICS/COMPOSITES

43MCB
METRIC SERIES

TECH INFO 94

mm					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE-B (TiB_2)
8,0	19,0	63,0	8,0	0,3	44300	44305
10,0	22,0	72,0	10,0	0,3	44301	44306
12,0	26,0	83,0	12,0	1,0	44302	44307
16,0	32,0	92,0	16,0	1,0	44303	44308
20,0	38,0	104,0	20,0	1,0	44304	44309

TOLERANCES (mm)


8–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6
R = +0,000/–0,050

>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6
R = +0,000/–0,050

>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6
R = +0,000/–0,050







47
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	3/8	1-1/2	1/8	34620	34660
3/16	9/16	2	3/16	34621	34661
1/4	3/4	2-1/2	1/4	34622	34662
5/16	13/16	2-1/2	5/16	34623	34663
3/8	1	2-1/2	3/8	34624	34664
1/2	1-1/4	3-1/4	1/2	34625	34665
5/8	1-5/8	3-3/4	5/8	34626	34666
3/4	1-5/8	4	3/4	34627	34667
1	2	4-1/2	1	34628	34668

TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6

47M
METRIC SERIES

TECH INFO 94

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
3,0	8,0	38,0	3,0	44550	44587
4,0	11,0	50,0	4,0	44551	44588
5,0	13,0	50,0	5,0	44552	44589
6,0	13,0	57,0	6,0	44553	44590
8,0	19,0	63,0	8,0	44554	44591
10,0	22,0	72,0	10,0	44555	44592
12,0	26,0	83,0	12,0	44556	44593
14,0	26,0	83,0	14,0	44557	44594
16,0	32,0	92,0	16,0	44558	44595
20,0	38,0	104,0	20,0	44559	44596
25,0	44,0	104,0	25,0	44560	44597

TOLERANCES (mm)

3+ DIAMETER
D_1 = +0,000/–0,006
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6


>10–18 DIAMETER
D_1 = +0,000/–0,012
D_2 = h_6

>18–25 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6

CARB
Solid Carbide End Mills for Aluminum







TOLERANCES (inch)

1/8–3/16 DIAMETER
D_1 = +0.0000/–0.00032
D_2 = h_6

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6

47B
FRACTIONAL SERIES

TECH INFO 92

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
1/8	3/8	1-1/2	1/8	34630	34669
3/16	9/16	2	3/16	34631	34670
1/4	3/4	2-1/2	1/4	34632	34671
5/16	13/16	2-1/2	5/16	34633	34672
3/8	1	2-1/2	3/8	34634	34673
1/2	1-1/4	3-1/4	1/2	34635	34674
5/8	1-5/8	3-3/4	5/8	34636	34675
3/4	1-5/8	4	3/4	34637	34676
1	2	4-1/2	1	34638	34677

NON-FERROUS
PLASTICS/COMPOSITES

TOLERANCES (mm)

3+ DIAMETER
D_1 = +0,000/–0,006
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,000/–0,012
D_2 = h_6

>18–25 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6


47MB
METRIC SERIES

TECH INFO 94

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-B (TiB_2)
3,0	8,0	38,0	3,0	44570	44598
4,0	11,0	50,0	4,0	44571	44599
5,0	13,0	50,0	5,0	44572	44600
6,0	13,0	57,0	6,0	44573	44601
8,0	19,0	63,0	8,0	44574	44602
10,0	22,0	72,0	10,0	44575	44603
12,0	26,0	83,0	12,0	44576	44604
14,0	26,0	83,0	14,0	44577	44605
16,0	32,0	92,0	16,0	44578	44606
20,0	38,0	104,0	20,0	44579	44607
25,0	44,0	104,0	25,0	44580	44608







47ES
FRACTIONAL SERIES

TECH INFO 92

NON-FERROUS

PLASTICS/COMPOSITES

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	UNCOATED	Ti-NAMITE-B (TiB_2)
1/4	3/8	4	1/4	2-1/8	34640	34678
3/8	1/2	4	3/8	2-1/8	34641	34679
1/2	5/8	6	1/2	2-1/8	34642	34680
1/2	5/8	6	1/2	3-3/8	34643	34681
5/8	3/4	6	5/8	2-3/8	34644	34682
5/8	3/4	6	5/8	3-3/8	34645	34683
3/4	1	6	3/4	2-1/2	34646	34684
3/4	1	6	3/4	3-3/8	34647	34685

TOLERANCES (inch)

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6

47MES
METRIC SERIES

TECH INFO 94

mm					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	UNCOATED	Ti-NAMITE-B (TiB_2)
6,0	10,0	100,0	6,0	54,0	44561	44609
8,0	12,0	100,0	8,0	54,0	44562	44610
10,0	12,0	100,0	10,0	54,0	44563	44611
12,0	16,0	150,0	12,0	80,0	44564	44612
16,0	20,0	150,0	16,0	80,0	44565	44613
20,0	25,0	150,0	20,0	80,0	44566	44614

TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6


>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6

>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6

CARB
Solid Carbide End Mills for Aluminum







TOLERANCES (inch)

1/4–3/8 DIAMETER
D_1 = +0.0000/–0.00035
D_2 = h_6

1/2–5/8 DIAMETER
D_1 = +0.0000/–0.00043
D_2 = h_6

3/4–1 DIAMETER
D_1 = +0.0000/–0.00051
D_2 = h_6

47EB
FRACTIONAL SERIES

TECH INFO 92

inch					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	UNCOATED	Ti-NAMITE-B (TiB_2)
1/4	3/8	4	1/4	2-1/8	34650	34686
3/8	1/2	4	3/8	2-1/8	34651	34687
1/2	5/8	6	1/2	2-1/8	34652	34688
1/2	5/8	6	1/2	3-3/8	34653	34689
5/8	3/4	6	5/8	3-3/8	34654	34691
5/8	3/4	6	5/8	2-3/8	34655	34690
3/4	1	6	3/4	2-1/2	34656	34693
3/4	1	6	3/4	3-3/8	34657	34692

NON-FERROUS
PLASTICS/COMPOSITES

TOLERANCES (mm)

6 DIAMETER
D_1 = +0,000/–0,008
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,009
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,000/–0,011
D_2 = h_6

>18–20 DIAMETER
D_1 = +0,000/–0,013
D_2 = h_6


47MEB
METRIC SERIES

TECH INFO 94

mm					EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	REACH L_3	UNCOATED	Ti-NAMITE-B (TiB_2)
6,0	10,0	100,0	6,0	54,0	44581	44615
8,0	12,0	100,0	8,0	54,0	44582	44616
10,0	12,0	100,0	10,0	54,0	44583	44617
12,0	16,0	150,0	12,0	80,0	44584	44618
16,0	20,0	150,0	16,0	80,0	44585	44619
20,0	25,0	150,0	20,0	80,0	44586	44620







27
FRACTIONAL SERIES

TECH INFO 96

PLASTICS/COMPOSITES

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Di-NAMITE (Diamond)
1/4	1	2-1/2	1/4	72978	72979
3/8	1-1/8	2-1/2	3/8	72980	72981
1/2	1-1/2	3-1/2	1/2	72982	72983
3/4	1-3/8	4	3/4	72984	72985


TOLERANCES (inch)

D_1 = +0.0000/–0.0030

D_2 = h_6







TOLERANCES (mm)

D_1 = +0,000/–0,080

D_2 = h_6


27M
METRIC SERIES

TECH INFO 97

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Di-NAMITE (Diamond)
6,0	25,0	63,0	6,0	83056	83057
8,0	25,0	63,0	8,0	83058	83059
10,0	28,0	63,0	10,0	83060	83061
12,0	38,0	89,0	12,0	83062	83063
16,0	48,0	115,0	16,0	83064	83065


PLASTICS/COMPOSITES

CARB-AP
Patented Variable Rake End Mills

	Series Z1PCR, Z1PLC, Z1PLB Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Profile	≤ 0.5	≤ 1.5	555	RPM	16961	8480	5654	4240	3392	2827	2120
						(444-666)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	27.1	33.9	43.0	42.4	42.1	36.2	29.7
			Slot	1	≤ 1	440	RPM	13446	6723	4482	3362	2689	2241	1681
						(352-528)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	21.5	26.9	34.1	33.6	33.3	28.7	23.5
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Profile	≤ 0.5	≤ 1.5	315	RPM	9626	4813	3209	2407	1925	1604	1203
						(252-378)	Fz	0.0003	0.0008	0.0014	0.0019	0.0024	0.0025	0.0027
							Feed (IPM)	13.1	15.4	18.0	18.3	18.5	16.0	13.0
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0003	0.0008	0.0014	0.0019	0.0024	0.0025	0.0027
							Feed (IPM)	10.4	12.2	14.3	14.5	14.7	12.7	10.3
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.5	≤ 1.5	185	RPM	5654	2827	1885	1413	1131	942	707
						(148-222)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	4.5	5.7	7.5	7.3	7.2	6.4	5.1
			Slot	1	≤ 1	145	RPM	4431	2216	1477	1108	886	739	554
						(116-174)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	3.5	4.4	5.9	5.8	5.7	5.0	4.0
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Profile	≤ 0.5	≤ 1.5	355	RPM	10849	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0004	0.0010	0.0018	0.0024	0.0030	0.0031	0.0034
							Feed (IPM)	18.2	21.7	26.0	26.0	26.0	22.4	18.4
			Slot	1	≤ 1	445	RPM	13599	6800	4533	3400	2720	2267	1700
						(356-534)	Fz	0.0004	0.0010	0.0018	0.0024	0.0030	0.0031	0.0034
							Feed (IPM)	22.8	27.2	32.6	32.6	32.6	28.1	23.1
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	340	RPM	10390	5195	3463	2598	2078	1732	1299
						(272-408)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	12.5	14.5	19.4	18.7	19.1	16.6	13.0
			Slot	1	≤ 1	270	RPM	8251	4126	2750	2063	1650	1375	1031
						(216-324)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	9.9	11.6	15.4	14.9	15.2	13.2	10.3
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Profile	≤ 0.5	≤ 1.5	490	RPM	14974	7487	4991	3744	2995	2496	1872
						(392-588)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	18.0	21.0	28.0	27.0	27.6	24.0	18.7
			Slot	1	≤ 1	390	RPM	11918	5959	3973	2980	2384	1986	1490
						(312-468)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	14.3	16.7	22.2	21.5	21.9	19.1	14.9


continued on next page

CARB-AP
Patented Variable Rake End Mills

	Series Z1PCR, Z1PLC, Z1PLB Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	340	RPM	10390	5195	3463	2598	2078	1732	1299
						(272-408)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	8.3	12.5	15.2	14.5	15.0	13.2	10.4
			Slot	1	≤ 1	270	RPM	8251	4126	2750	2063	1650	1375	1031
						(216-324)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	6.6	9.9	12.1	11.6	11.9	10.5	8.3
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	310	RPM	9474	4737	3158	2368	1895	1579	1184
						(248-372)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	7.6	11.4	13.9	13.3	13.6	12.0	9.5
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	6.1	9.2	11.2	10.7	11.0	9.7	7.6
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	80	RPM	2445	1222	815	611	489	407	306
						(64-96)	Fz	0.0002	0.0004	0.0008	0.0010	0.0013	0.0014	0.0015
							Feed (IPM)	1.5	2.0	2.6	2.4	2.5	2.3	1.8
			Slot	1	≤ 1	65	RPM	1986	993	662	497	397	331	248
						(52-78)	Fz	0.0002	0.0004	0.0008	0.0010	0.0013	0.0014	0.0015
							Feed (IPM)	1.2	1.6	2.1	2.0	2.1	1.9	1.5
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	62	RPM	1895	947	632	474	379	316	237
						(50-74)	Fz	0.0001	0.0003	0.0005	0.0007	0.0009	0.0010	0.0011
							Feed (IPM)	0.8	1.1	1.3	1.3	1.4	1.3	1.0
			Slot	1	≤ 1	50	RPM	1528	764	509	382	306	255	191
						(40-60)	Fz	0.0001	0.0003	0.0005	0.0007	0.0009	0.0010	0.0011
							Feed (IPM)	0.6	0.9	1.0	1.1	1.1	1.0	0.8
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	215	RPM	6570	3285	2190	1643	1314	1095	821
						(172-258)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	5.3	6.6	8.8	8.5	8.4	7.4	5.9
			Slot	1	≤ 1	170	RPM	5195	2598	1732	1299	1039	866	649
						(136-204)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	4.2	5.2	6.9	6.8	6.6	5.9	4.7
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	75	RPM	2292	1146	764	573	458	382	287
						(60-90)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	1.8	2.3	3.1	3.0	2.9	2.6	2.1
			Slot	1	≤ 1	60	RPM	1834	917	611	458	367	306	229
						(48-72)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	1.5	1.8	2.4	2.4	2.3	2.1	1.7


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
maximum Slotting Ap for Z1PLC / Z1PLB is .25 x D_1
maximum Profile Ae for Z1PLC / Z1PLB is .2 x D_1
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

CARB-AP
Patented Variable Rake End Mills

	Series Z1MPCR, Z1MPLC Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Profile	≤ 0.5	≤ 1.5	169	RPM	17934	8967	6725	5380	4484	3363	2690	2152
						(135-203)	Fz	0.010	0.024	0.041	0.051	0.060	0.079	0.085	0.088
							Feed (mm/min)	689	861	1091	1090	1076	1067	918	753
			Slot	1	≤ 1	134	RPM	14218	7109	5332	4265	3555	2666	2133	1706
						(107-161)	Fz	0.010	0.024	0.041	0.051	0.060	0.079	0.085	0.088
							Feed (mm/min)	546	682	865	864	853	846	728	597
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Profile	≤ 0.5	≤ 1.5	96	RPM	10179	5089	3817	3054	2545	1909	1527	1221
						(77-115)	Fz	0.008	0.019	0.030	0.037	0.046	0.061	0.067	0.068
							Feed (mm/min)	332	391	456	456	464	469	407	330
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.008	0.019	0.030	0.037	0.046	0.061	0.067	0.068
							Feed (mm/min)	264	310	362	362	368	372	323	262
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.5	≤ 1.5	56	RPM	5978	2989	2242	1793	1495	1121	897	717
						(45-68)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	115	143	191	191	186	184	163	129
			Slot	1	≤ 1	44	RPM	4686	2343	1757	1406	1171	879	703	562
						(35-53)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	90	112	150	150	146	144	127	101
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Profile	≤ 0.5	≤ 1.5	108	RPM	11471	5736	4302	3441	2868	2151	1721	1377
						(87-130)	Fz	0.010	0.024	0.038	0.048	0.058	0.077	0.083	0.085
							Feed (mm/min)	462	551	661	661	661	661	569	468
			Slot	1	≤ 1	136	RPM	14380	7190	5392	4314	3595	2696	2157	1726
						(109-163)	Fz	0.010	0.024	0.038	0.048	0.058	0.077	0.083	0.085
							Feed (mm/min)	580	690	828	828	828	828	713	587
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	316	369	492	492	475	485	422	330
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	251	293	391	391	377	385	385	262
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Profile	≤ 0.5	≤ 1.5	149	RPM	15834	7917	5938	4750	3958	2969	2375	1900
						(119-179)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	456	532	709	709	684	699	608	475
			Slot	1	≤ 1	119	RPM	12602	6301	4726	3781	3151	2363	1890	1512
						(95-143)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	363	423	565	565	544	557	484	378

continued on next page


CARB-AP
Patented Variable Rake End Mills



	Series Z1MPCR, Z1MPLC Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	211	316	387	387	369	380	334	264
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	168	251	307	307	293	302	265	209
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	94	RPM	10017	5009	3756	3005	2504	1878	1503	1202
						(76-113)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	192	288	353	353	337	346	305	240
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	155	233	284	284	271	279	246	194
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	24	RPM	2585	1293	969	776	646	485	388	310
						(20-29)	Fz	0.004	0.010	0.017	0.021	0.024	0.033	0.037	0.038
							Feed (mm/min)	37	50	66	66	62	65	58	47
			Slot	1	≤ 1	20	RPM	2100	1050	788	630	525	394	315	252
						(16-24)	Fz	0.004	0.010	0.017	0.021	0.024	0.033	0.037	0.038
							Feed (mm/min)	30	40	54	54	50	52	47	38
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	19	RPM	2003	1002	751	601	501	376	301	240
						(15-23)	Fz	0.002	0.007	0.011	0.013	0.017	0.023	0.027	0.028
							Feed (mm/min)	19	29	32	32	34	35	32	26
			Slot	1	≤ 1	15	RPM	1616	808	606	485	404	303	242	194
						(12-18)	Fz	0.002	0.007	0.011	0.013	0.017	0.023	0.027	0.028
							Feed (mm/min)	16	23	26	26	27	28	26	21
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	66	RPM	6947	3474	2605	2084	1737	1303	1042	834
						(52-79)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	133	167	222	222	217	213	189	150
			Slot	1	≤ 1	52	RPM	5493	2747	2060	1648	1373	1030	824	659
						(41-62)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	105	132	176	176	171	169	149	119
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	23	RPM	2424	1212	909	727	606	454	364	291
						(18-27)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	47	58	78	78	76	74	66	52
			Slot	1	≤ 1	18	RPM	1939	969	727	582	485	364	291	233
						(15-22)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	37	47	62	62	60	60	53	42


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
maximum Slotting Ap for Z1PLC / Z1PLB is .25 x D_1
maximum Profile Ae for Z1PLC / Z1PLB is .2 x D_1
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series Z1, Z1B, Z16CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.5	≤ 1.5	555	RPM	16961	8480	5654	4240	3392	2827	2120
						(444-666)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	25.8	33.9	43.0	42.4	42.1	36.5	29.7
			Slot	1	≤ 1	440	RPM	13446	6723	4482	3362	2689	2241	1681
						(352-528)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	20.4	26.9	34.1	33.6	33.3	29.0	23.5
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 375	Profile	≤ 0.5	≤ 1.5	315	RPM	9626	4813	3209	2407	1925	1604	1203
						(252-378)	Fz	0.0003	0.0008	0.0014	0.0019	0.0024	0.0025	0.0027
							Feed (IPM)	10.8	15.4	18.0	18.3	18.5	16.0	13.0
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0003	0.0008	0.0014	0.0019	0.0024	0.0025	0.0027
							Feed (IPM)	8.6	12.2	14.3	14.5	14.7	12.7	10.3
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 375	Profile	≤ 0.5	≤ 1.5	185	RPM	5654	2827	1885	1413	1131	942	707
						(148-222)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	4.5	5.7	7.5	7.3	7.2	6.4	5.1
			Slot	1	≤ 1	145	RPM	4431	2216	1477	1108	886	739	554
						(116-174)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	3.5	4.4	5.9	5.8	5.7	5.0	4.0
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	445	RPM	13599	6800	4533	3400	2720	2267	1700
						(356-534)	Fz	0.0004	0.0010	0.0018	0.0024	0.0030	0.0031	0.0034
							Feed (IPM)	19.0	27.2	32.6	32.6	32.6	28.1	23.1
			Slot	1	≤ 1	355	RPM	10849	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0004	0.0010	0.0018	0.0024	0.0030	0.0031	0.0034
							Feed (IPM)	15.2	21.7	26.0	26.0	26.0	22.4	18.4
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	340	RPM	10390	5195	3463	2598	2078	1732	1299
						(272-408)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	12.5	14.5	19.4	18.7	19.1	16.6	13.0
			Slot	1	≤ 1	270	RPM	8251	4126	2750	2063	1650	1375	1031
						(216-324)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	9.9	11.6	15.4	14.9	15.2	13.2	10.3
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	490	RPM	14974	7487	4991	3744	2995	2496	1872
						(392-588)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	18.0	21.0	28.0	27.0	27.6	24.0	18.7
			Slot	1	≤ 1	390	RPM	11918	5959	3973	2980	2384	1986	1490
						(312-468)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	14.3	16.7	22.2	21.5	21.9	19.1	14.9


continued on next page

CARB
SOLID CARBIDE END MILLS



	Series Z1, Z1B, Z16CR Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	340	RPM	10390	5195	3463	2598	2078	1732	1299
						(272-408)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	8.3	12.5	15.2	14.5	15.0	13.2	10.4
			Slot	1	≤ 1	270	RPM	8251	4126	2750	2063	1650	1375	1031
						(216-324)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	6.6	9.9	12.1	11.6	11.9	10.5	8.3
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	310	RPM	9474	4737	3158	2368	1895	1579	1184
						(248-372)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	7.6	11.4	13.9	13.3	13.6	12.0	9.5
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0002	0.0006	0.0011	0.0014	0.0018	0.0019	0.0020
							Feed (IPM)	6.1	9.2	11.2	10.7	11.0	9.7	7.6
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	80	RPM	2445	1222	815	611	489	407	306
						(64-96)	Fz	0.0002	0.0004	0.0008	0.0010	0.0013	0.0014	0.0015
							Feed (IPM)	2.2	2.0	2.6	2.4	2.5	2.3	1.8
			Slot	1	≤ 1	65	RPM	1986	993	662	497	397	331	248
						(52-78)	Fz	0.0002	0.0004	0.0008	0.0010	0.0013	0.0014	0.0015
							Feed (IPM)	1.6	1.6	2.1	2.0	2.1	1.9	1.5
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	62	RPM	1895	947	632	474	379	316	237
						(50-74)	Fz	0.0001	0.0003	0.0005	0.0007	0.0008	0.0009	0.0010
							Feed (IPM)	0.8	1.1	1.3	1.3	1.2	1.1	0.9
			Slot	1	≤ 1	50	RPM	1497	749	499	374	299	250	187
						(40-60)	Fz	0.0001	0.0003	0.0005	0.0007	0.0008	0.0009	0.0010
							Feed (IPM)	0.6	0.9	1.0	1.0	1.0	0.9	0.7
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	215	RPM	6570	3285	2190	1643	1314	1095	821
						(172-258)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	5.3	6.6	8.8	8.5	8.4	7.4	5.9
			Slot	1	≤ 1	170	RPM	5195	2598	1732	1299	1039	866	649
						(136-204)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	4.2	5.2	6.9	6.8	6.6	5.9	4.7
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	75	RPM	2292	1146	764	573	458	382	287
						(60-90)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	1.8	2.3	3.1	3.0	2.9	2.6	2.1
			Slot	1	≤ 1	60	RPM	1834	917	611	458	367	306	229
						(48-72)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	1.5	1.8	2.4	2.4	2.3	2.1	1.7


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series Z1M, Z1MB Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.5	≤ 1.5	169	RPM	17934	8967	6725	5380	4484	3363	2690	2152
						(135-203)	Fz	0.009	0.024	0.041	0.051	0.060	0.079	0.086	0.088
							Feed (mm/min)	654	861	1091	1090	1076	1067	927	753
			Slot	1	≤ 1	134	RPM	14218	7109	5332	4265	3555	2666	2133	1706
						(107-161)	Fz	0.009	0.024	0.041	0.051	0.060	0.079	0.086	0.088
							Feed (mm/min)	519	682	865	864	853	846	735	597
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 375	Profile	≤ 0.5	≤ 1.5	96	RPM	10179	5089	3817	3054	2545	1909	1527	1221
						(77-115)	Fz	0.007	0.019	0.030	0.037	0.046	0.061	0.067	0.068
							Feed (mm/min)	274	391	456	456	464	469	407	330
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.007	0.019	0.030	0.037	0.046	0.061	0.067	0.068
							Feed (mm/min)	217	310	362	362	368	372	323	262
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 375	Profile	≤ 0.5	≤ 1.5	56	RPM	5978	2989	2242	1793	1495	1121	897	717
						(45-68)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	115	143	191	191	186	184	163	129
			Slot	1	≤ 1	44	RPM	4686	2343	1757	1406	1171	879	703	562
						(35-53)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	90	112	150	150	146	144	127	101
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	136	RPM	14380	7190	5392	4314	3595	2696	2157	1726
						(109-163)	Fz	0.008	0.024	0.038	0.048	0.058	0.077	0.083	0.085
							Feed (mm/min)	483	690	828	828	828	828	713	587
			Slot	1	≤ 1	108	RPM	11471	5736	4302	3441	2868	2151	1721	1377
						(87-130)	Fz	0.008	0.024	0.038	0.048	0.058	0.077	0.083	0.085
							Feed (mm/min)	385	551	661	661	661	661	569	468
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	316	369	492	492	475	485	422	330
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	251	293	391	391	377	385	335	262
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	149	RPM	15834	7917	5938	4750	3958	2969	2375	1900
						(119-179)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	456	532	709	709	684	699	608	475
			Slot	1	≤ 1	119	RPM	12602	6301	4726	3781	3151	2363	1890	1512
						(95-143)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	363	423	565	565	544	557	484	378


continued on next page

CARB
SOLID CARBIDE END MILLS




	Series Z1M, Z1MB Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	211	316	387	387	369	380	334	264
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	168	251	307	307	293	302	265	209
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	94	RPM	10017	5009	3756	3005	2504	1878	1503	1202
						(76-113)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	192	288	353	353	337	346	305	240
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.005	0.014	0.023	0.029	0.034	0.046	0.051	0.050
							Feed (mm/min)	155	233	284	284	271	279	246	194
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	24	RPM	2585	1293	969	776	646	485	388	310
						(20-29)	Fz	0.005	0.010	0.017	0.021	0.024	0.033	0.037	0.038
							Feed (mm/min)	55	50	66	53	62	65	58	47
			Slot	1	≤ 1	20	RPM	2100	1050	788	630	525	394	315	252
						(16-24)	Fz	0.005	0.010	0.017	0.021	0.024	0.033	0.037	0.038
							Feed (mm/min)	40	40	54	54	50	52	47	38
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	19	RPM	2003	1002	751	601	501	376	301	240
						(15-23)	Fz	0.002	0.007	0.011	0.013	0.017	0.020	0.024	0.025
							Feed (mm/min)	19	29	32	32	34	31	29	24
			Slot	1	≤ 1	15	RPM	1583	792	594	475	396	297	238	190
						(12-18)	Fz	0.002	0.007	0.011	0.013	0.017	0.020	0.024	0.025
							Feed (mm/min)	15	23	25	25	27	24	23	19
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	66	RPM	6947	3474	2605	2084	1737	1303	1042	834
						(52-79)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	133	167	222	222	217	213	189	150
			Slot	1	≤ 1	52	RPM	5493	2747	2060	1648	1373	1030	824	659
						(41-62)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	105	132	176	176	171	169	149	119
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	23	RPM	2424	1212	909	727	606	454	364	291
						(18-27)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	47	58	78	78	76	74	66	52
			Slot	1	≤ 1	18	RPM	1939	969	727	582	485	364	291	233
						(15-22)	Fz	0.005	0.012	0.021	0.027	0.031	0.041	0.045	0.045
							Feed (mm/min)	37	47	62	62	60	60	53	42


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series ZH1CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	3/8	1/2	3/4	1
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	85	RPM	1299	866	649	433	325
						(68-102)	Fz	0.0007	0.0012	0.0017	0.0020	0.0023
							Feed (IPM)	3.6	4.2	4.4	3.5	3.0
			Slot	1	≤ 1	70	RPM	1070	713	535	357	267
						(56-84)	Fz	0.0007	0.0012	0.0017	0.0020	0.0023
							Feed (IPM)	3.0	3.4	3.6	2.9	2.5
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	70	RPM	1070	713	535	357	267
						(56-84)	Fz	0.0005	0.0009	0.0012	0.0014	0.0016
							Feed (IPM)	2.1	2.6	2.6	2.0	1.7
			Slot	1	≤ 1	55	RPM	840	560	420	280	210
						(44-66)	Fz	0.0005	0.0009	0.0012	0.0014	0.0016
							Feed (IPM)	1.7	2.0	2.0	1.6	1.3


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series ZH1MCR Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	10	12	20	25
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	26	RPM	1373	824	687	412	330
						(21-31)	Fz	0.017	0.032	0.041	0.053	0.058
							Feed (mm/min)	93	105	113	87	76
			Slot	1	≤ 1	21	RPM	1131	679	565	339	271
						(17-26)	Fz	0.017	0.032	0.041	0.053	0.058
							Feed (mm/min)	77	87	93	72	63
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	21	RPM	1131	679	565	339	271
						(17-26)	Fz	0.012	0.024	0.029	0.037	0.040
							Feed (mm/min)	54	65	66	50	43
			Slot	1	≤ 1	17	RPM	889	533	444	267	213
						(13-20)	Fz	0.012	0.024	0.029	0.037	0.040
							Feed (mm/min)	43	51	52	39	34

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


	Series ZD1CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.4	≤ 1	405	RPM	12377	6188	4126	3094	2475	2063
						(324-486)	Fz	0.0005	0.0012	0.0023	0.0030	0.0039	0.0042
							Feed (IPM)	24.8	29.7	38.0	37.1	38.6	34.7
			Slot	1	≤ 0.4	320	RPM	9779	4890	3260	2445	1956	1630
						(256-384)	Fz	0.0005	0.0012	0.0023	0.0030	0.0039	0.0042
							Feed (IPM)	19.6	23.5	30.0	29.3	30.5	27.4
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 375 ≤ 475	Profile	≤ 0.4	≤ 1	210	RPM	6418	3209	2139	1604	1284	1070
						(168-252)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0035
							Feed (IPM)	10.3	12.8	16.3	16.0	16.4	15.0
			Slot	1	≤ 0.4	170	RPM	5195	2598	1732	1299	1039	866
						(136-204)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0035
							Feed (IPM)	8.3	10.4	13.2	13.0	13.3	12.1
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 475 ≤ 655	Profile	≤ 0.4	≤ 1	90	RPM	2750	1375	917	688	550	458
						(72-108)	Fz	0.0002	0.0005	0.0010	0.0013	0.0017	0.0018
							Feed (IPM)	2.2	2.8	3.7	3.6	3.7	3.3
			Slot	1	≤ 0.4	70	RPM	2139	1070	713	535	428	357
						(56-84)	Fz	0.0002	0.0005	0.0010	0.0013	0.0017	0.0018
							Feed (IPM)	1.7	2.1	2.9	2.8	2.9	2.6

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series ZD1MCR Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.4	≤ 1	123	RPM	13087	6544	4908	3926	3272	2454	1963
						(99-148)	Fz	0.012	0.029	0.049	0.061	0.072	0.083	0.112
							Feed (mm/min)	628	754	963	963	942	817	879
			Slot	1	≤ 0.4	98	RPM	10340	5170	3878	3102	2585	1939	1551
						(78-117)	Fz	0.012	0.029	0.049	0.061	0.072	0.083	0.112
							Feed (mm/min)	496	596	761	761	744	645	695
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 375 ≤ 475	Profile	≤ 0.4	≤ 1	64	RPM	6786	3393	2545	2036	1696	1272	1018
						(51-77)	Fz	0.010	0.024	0.041	0.051	0.060	0.068	0.093
							Feed (mm/min)	261	326	413	413	407	347	380
			Slot	1	≤ 0.4	52	RPM	5493	2747	2060	1648	1373	1030	824
						(41-62)	Fz	0.010	0.024	0.041	0.051	0.060	0.068	0.093
							Feed (mm/min)	211	264	334	334	330	281	308
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 475 ≤ 655	Profile	≤ 0.4	≤ 1	27	RPM	2908	1454	1091	872	727	545	436
						(22-33)	Fz	0.005	0.012	0.021	0.027	0.031	0.036	0.048
							Feed (mm/min)	56	70	93	93	91	79	84
			Slot	1	≤ 0.4	21	RPM	2262	1131	848	679	565	424	339
						(17-26)	Fz	0.005	0.012	0.021	0.027	0.031	0.036	0.048
							Feed (mm/min)	43	54	72	72	71	62	65


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
maximum Slotting Ap for Z1PLC / Z1PLB is .25 x D_1
maximum Profile Ae for Z1PLC / Z1PLB is .2 x D_1
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

SERIES 7 HIGH PERFORMANCE END MILLS



	Series 7, 7B Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Finish	≤ 0.02	≤ 2	480	RPM	14669	7334	4890	3667	2934	2445	1834
						(384-576)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0033	0.0035
							Feed (IPM)	23.5	29.3	37.2	36.7	37.6	32.3	25.7
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Finish	≤ 0.02	≤ 2	275	RPM	8404	4202	2801	2101	1681	1401	1051
						(220-330)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	10.1	11.8	15.7	15.1	15.5	13.4	10.9
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Finish	≤ 0.02	≤ 2	230	RPM	7029	3514	2343	1757	1406	1171	879
						(184-276)	Fz	0.0002	0.0006	0.0012	0.0016	0.0020	0.0021	0.0022
							Feed (IPM)	5.6	8.4	11.2	11.2	11.2	9.8	7.7
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Finish	≤ 0.02	≤ 2	605	RPM	18489	9244	6163	4622	3698	3081	2311
						(484-726)	Fz	0.0006	0.0015	0.0028	0.0037	0.0046	0.0047	0.0051
							Feed (IPM)	44.4	55.5	69.0	68.4	68.0	57.9	47.1
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Finish	≤ 0.02	≤ 2	465	RPM	14210	7105	4737	3553	2842	2368	1776
						(372-558)	Fz	0.0004	0.0011	0.0021	0.0028	0.0034	0.0036	0.0039
							Feed (IPM)	22.7	31.3	39.8	39.8	38.7	34.1	27.7
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Finish	≤ 0.02	≤ 2	420	RPM	12835	6418	4278	3209	2567	2139	1604
						(336-504)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0033	0.0035
							Feed (IPM)	20.5	25.7	32.5	32.1	32.9	28.2	22.5
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Finish	≤ 0.02	≤ 2	290	RPM	8862	4431	2954	2216	1772	1477	1108
						(232-348)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	10.6	12.4	16.5	16.0	16.3	14.2	11.5
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Finish	≤ 0.02	≤ 2	265	RPM	8098	4049	2699	2025	1620	1350	1012
						(212-318)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	9.7	11.3	15.1	14.6	14.9	13.0	10.5
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Finish	≤ 0.02	≤ 2	80	RPM	2445	1222	815	611	489	407	306
						(64-96)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	2.9	3.4	4.6	4.4	4.5	3.9	3.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Finish	≤ 0.02	≤ 2	65	RPM	1986	993	662	497	397	331	248
						(52-78)	Fz	0.0002	0.0006	0.0010	0.0014	0.0017	0.0018	0.0019
							Feed (IPM)	1.6	2.4	2.6	2.8	2.7	2.4	1.9
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Finish	≤ 0.02	≤ 2	300	RPM	9168	4584	3056	2292	1834	1528	1146
						(240-360)	Fz	0.0004	0.0011	0.0021	0.0028	0.0034	0.0036	0.0039
							Feed (IPM)	14.7	20.2	25.7	25.7	24.9	22.0	17.9
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Finish	≤ 0.02	≤ 2	105	RPM	3209	1604	1070	802	642	535	401
						(84-126)	Fz	0.0004	0.0011	0.0021	0.0028	0.0034	0.0036	0.0039
							Feed (IPM)	5.1	7.1	9.0	9.0	8.7	7.7	6.3


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series 7M, 7MB Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Finish	≤ 0.02	≤ 2	146	RPM	15511	7755	5816	4653	3878	2908	2327	1861
						(117-176)	Fz	0.0166	0.043	0.075	0.093	0.110	0.125	0.147	0.160
							Feed (mm/min)	1030	1334	1745	1731	1706	1454	1368	1191
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Finish	≤ 0.02	≤ 2	84	RPM	8886	4443	3332	2666	2222	1666	1333	1066
						(67-101)	Fz	0.0122	0.034	0.051	0.069	0.082	0.091	0.109	0.120
							Feed (mm/min)	434	604	680	736	729	606	581	512
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Finish	≤ 0.02	≤ 2	70	RPM	7432	3716	2787	2230	1858	1394	1115	892
						(56-84)	Fz	0.0070	0.019	0.040	0.043	0.048	0.057	0.064	0.070
							Feed (mm/min)	208	282	446	384	357	318	285	250
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Finish	≤ 0.02	≤ 2	184	RPM	19550	9775	7331	5865	4887	3666	2932	2346
						(148-221)	Fz	0.0132	0.036	0.052	0.075	0.089	0.099	0.117	0.130
							Feed (mm/min)	10322	1408	1525	1759	1740	1452	1372	1220
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Finish	≤ 0.02	≤ 2	142	RPM	15026	7513	5635	4508	3756	2817	2254	1803
						(113-170)	Fz	0.0132	0.036	0.052	0.075	0.089	0.099	0.117	0.130
							Feed (mm/min)	793	1082	1172	1352	1337	1116	1055	938
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Finish	≤ 0.02	≤ 2	128	RPM	13572	6786	5089	4072	3393	2545	2036	1629
						(102-154)	Fz	0.0086	0.024	0.040	0.048	0.058	0.065	0.077	0.087
							Feed (mm/min)	467	651	814	782	787	662	627	567
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Finish	≤ 0.02	≤ 2	88	RPM	9371	4686	3514	2811	2343	1757	1406	1125
						(71-106)	Fz	0.0082	0.022	0.037	0.045	0.048	0.060	0.072	0.078
							Feed (mm/min)	307	412	520	506	450	422	405	351
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Finish	≤ 0.02	≤ 2	81	RPM	8563	4282	3211	2569	2141	1606	1284	1028
						(65-97)	Fz	0.0070	0.019	0.029	0.040	0.048	0.055	0.064	0.070
							Feed (mm/min)	240	325	372	411	411	353	329	288
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Finish	≤ 0.02	≤ 2	24	RPM	2585	1293	969	776	646	485	388	310
						(20-29)	Fz	0.0072	0.019	0.029	0.037	0.046	0.053	0.061	0.085
							Feed (mm/min)	74	98	112	90	119	103	95	105
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Finish	≤ 0.02	≤ 2	20	RPM	2100	1050	788	630	525	394	315	252
						(16-24)	Fz	0.0075	0.016	0.021	0.030	0.038	0.044	0.051	0.070
							Feed (mm/min)	63	67	66	76	80	69	64	71
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Finish	≤ 0.02	≤ 2	91	RPM	9694	4847	3635	2908	2424	1818	1454	1163
						(73-110)	Fz	0.0091	0.024	0.004	0.005	0.060	0.070	0.080	0.088
							Feed (mm/min)	353	465	51	59	582	509	465	409
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Finish	≤ 0.02	≤ 2	32	RPM	3393	1696	1272	1018	848	636	509	407
						(26-38)	Fz	0.0082	0.019	0.029	0.037	0.046	0.053	0.061	0.085
							Feed (mm/min)	111	129	148	151	156	135	124	138

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


CARB Five Flute End Mills



	Series 55, 55CR Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.25	≤ 1.5	385	RPM	11766	5883	3922	2941	2353	1961	1471
						(308-462)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0028	0.0032
							Feed (IPM)	20.6	26.5	33.3	33.8	34.1	27.5	23.5
			HSM	≤ 0.05	≤ 2	630	RPM	19253	9626	6418	4813	3851	3209	2407
						(504-756)	Fz	0.0007	0.0018	0.0034	0.0046	0.0057	0.0055	0.0064
							Feed (IPM)	67.4	86.6	109.1	110.7	109.7	88.2	77.0
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 375	Profile	≤ 0.25	≤ 1.5	325	RPM	9932	4966	3311	2483	1986	1655	1242
						(260-390)	Fz	0.0003	0.0007	0.0013	0.0017	0.0022	0.0021	0.0024
							Feed (IPM)	12.9	17.4	21.5	21.1	21.9	17.4	14.9
			HSM	≤ 0.05	≤ 2	530	RPM	16197	8098	5399	4049	3239	2699	2025
						(424-636)	Fz	0.0005	0.0014	0.0026	0.0034	0.0043	0.0041	0.0048
							Feed (IPM)	42.1	56.7	70.2	68.8	69.6	55.3	48.6
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 375	Profile	≤ 0.25	≤ 1.5	175	RPM	5348	2674	1783	1337	1070	891	669
						(140-210)	Fz	0.0002	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	5.3	6.7	8.9	8.7	8.6	7.6	6.0
			HSM	≤ 0.05	≤ 2	290	RPM	8862	4431	2954	2216	1772	1477	1108
						(232-348)	Fz	0.0004	0.0010	0.0019	0.0025	0.0032	0.0033	0.0035
							Feed (IPM)	17.7	22.2	28.1	27.7	28.4	24.4	19.4
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.25	≤ 1.5	470	RPM	14363	7182	4788	3591	2873	2394	1795
						(376-564)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	25.1	32.3	40.7	41.3	41.7	35.9	28.7
			HSM	≤ 0.05	≤ 2	705	RPM	21545	10772	7182	5386	4309	3591	2693
						(564-846)	Fz	0.0007	0.0018	0.0034	0.0046	0.0057	0.0059	0.0064
							Feed (IPM)	75.4	97.0	122.1	123.9	122.8	105.9	86.2
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.25	≤ 1.5	360	RPM	11002	5501	3667	2750	2200	1834	1375
						(288-432)	Fz	0.0003	0.0007	0.0013	0.0017	0.0022	0.0023	0.0024
							Feed (IPM)	14.3	19.3	23.8	23.4	24.2	21.1	16.5
			HSM	≤ 0.05	≤ 2	540	RPM	16502	8251	5501	4126	3300	2750	2063
						(432-648)	Fz	0.0005	0.0014	0.0026	0.0034	0.0043	0.0044	0.0048
							Feed (IPM)	42.9	57.8	71.5	70.1	71.0	60.5	49.5
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.25	≤ 1.5	370	RPM	11307	5654	3769	2827	2261	1885	1413
						(296-444)	Fz	0.0003	0.0007	0.0013	0.0017	0.0022	0.0023	0.0024
							Feed (IPM)	14.7	19.8	24.5	24.0	24.9	21.7	17.0
			HSM	≤ 0.05	≤ 2	560	RPM	17114	8557	5705	4278	3423	2852	2139
						(448-672)	Fz	0.0005	0.0014	0.0026	0.0034	0.0043	0.0044	0.0048
							Feed (IPM)	44.5	59.9	74.2	72.7	73.6	62.7	51.3

continued on next page


CARB Five Flute End Mills



	Series 55, 55CR Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.25	≤ 1.5	255	RPM	7793	3896	2598	1948	1559	1299	974
						(204-306)	Fz	0.0002	0.0006	0.0012	0.0016	0.0020	0.0021	0.0023
							Feed (IPM)	9.4	11.7	15.6	15.6	15.6	13.6	11.2
			HSM	≤ 0.05	≤ 2	385	RPM	11766	5883	3922	2941	2353	1961	1471
						(308-462)	Fz	0.0005	0.0013	0.0024	0.0032	0.0040	0.0041	0.0045
							Feed (IPM)	28.2	38.2	47.1	47.1	47.1	40.2	33.1
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.25	≤ 1.5	235	RPM	7182	3591	2394	1795	1436	1197	898
						(188-282)	Fz	0.0002	0.0006	0.0010	0.0014	0.0017	0.0018	0.0019
							Feed (IPM)	7.5	10.8	12.0	12.6	12.2	10.8	8.5
			HSM	≤ 0.05	≤ 2	355	RPM	10849	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0004	0.0011	0.0021	0.0028	0.0034	0.0036	0.0039
							Feed (IPM)	22.2	29.8	38.0	38.0	36.9	32.5	26.4
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.25	≤ 1.5	70	RPM	2139	1070	713	535	428	357	267
						(56-84)	Fz	0.0002	0.0006	0.0010	0.0014	0.0017	0.0018	0.0019
							Feed (IPM)	2.2	3.2	3.6	3.7	3.6	3.2	2.5
			HSM	≤ 0.05	≤ 2	107	RPM	3270	1635	1090	817	654	545	409
						(86-128)	Fz	0.0004	0.0011	0.0021	0.0028	0.0034	0.0036	0.0039
							Feed (IPM)	6.7	9.0	11.4	11.4	11.1	9.8	8.0
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.25	≤ 1.5	55	RPM	1681	840	560	420	336	280	210
						(44-66)	Fz	0.0002	0.0004	0.0008	0.0010	0.0013	0.0014	0.0015
							Feed (IPM)	1.3	1.7	2.2	2.1	2.2	2.0	1.6
			HSM	≤ 0.05	≤ 2	85	RPM	2598	1299	866	649	520	433	325
						(68-102)	Fz	0.0003	0.0008	0.0015	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	4.0	5.2	6.5	6.8	6.8	5.8	4.7
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.25	≤ 1.5	235	RPM	7182	3591	2394	1795	1436	1197	898
						(188-282)	Fz	0.0002	0.0006	0.0012	0.0016	0.0020	0.0021	0.0023
							Feed (IPM)	7.2	10.8	14.4	14.4	14.4	12.6	10.3
			HSM	≤ 0.05	≤ 2	390	RPM	11918	5959	3973	2980	2384	1986	1490
						(312-468)	Fz	0.0005	0.0013	0.0024	0.0032	0.0040	0.0041	0.0045
							Feed (IPM)	29.8	38.7	47.7	47.7	47.7	40.7	33.5
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.25	≤ 1.5	85	RPM	2598	1299	866	649	520	433	325
						(68-102)	Fz	0.0002	0.0006	0.0012	0.0016	0.0020	0.0021	0.0023
							Feed (IPM)	2.6	3.9	5.2	5.2	5.2	4.5	3.7
			HSM	≤ 0.05	≤ 2	140	RPM	4278	2139	1426	1070	856	713	535
						(112-168)	Fz	0.0005	0.0013	0.0024	0.0032	0.0040	0.0042	0.0045
							Feed (IPM)	10.7	13.9	17.1	17.1	17.1	15.0	12.0


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 5 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
reduce Ap to 1 x D_1 (maximum) when profile milling with long or extra long flute length tools
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

CARB Five Flute End Mills



	Series 55M Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.25	≤ 1.5	117	RPM	6220	4665	3732	3110	2333	1866
						(94-141)	Fz	0.022	0.036	0.061	0.070	0.072	0.085
							Feed (mm/min)	672	846	1145	1082	836	796
			HSM	≤ 0.05	≤ 2	192	RPM	10179	7634	6107	5089	3817	3054
						(154-230)	Fz	0.043	0.073	0.123	0.137	0.141	0.154
							Feed (mm/min)	2198	2769	3746	3481	2687	2345
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 375	Profile	≤ 0.25	≤ 1.5	99	RPM	5251	3938	3151	2626	1969	1575
						(79-119)	Fz	0.017	0.028	0.045	0.053	0.054	0.064
							Feed (mm/min)	441	546	571	693	529	504
			HSM	≤ 0.05	≤ 2	162	RPM	8563	6422	5138	4282	3211	2569
						(129-194)	Fz	0.034	0.055	0.091	0.103	0.105	0.128
							Feed (mm/min)	1438	1781	2329	2209	1685	1644
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 375	Profile	≤ 0.25	≤ 1.5	53	RPM	2827	2121	1696	1414	1060	848
						(43-64)	Fz	0.012	0.021	0.035	0.038	0.044	0.048
							Feed (mm/min)	170	226	294	271	231	204
			HSM	≤ 0.05	≤ 2	88	RPM	4686	3514	2811	2343	1757	1406
						(71-106)	Fz	0.024	0.041	0.067	0.077	0.084	0.093
							Feed (mm/min)	562	712	937	900	742	656
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.25	≤ 1.5	143	RPM	7594	5695	4556	3797	2848	2278
						(115-172)	Fz	0.022	0.036	0.061	0.070	0.077	0.085
							Feed (mm/min)	820	1033	1397	1321	1093	972
			HSM	≤ 0.05	≤ 2	215	RPM	11391	8543	6834	5695	4271	3417
						(172-258)	Fz	0.043	0.073	0.123	0.137	0.151	0.171
							Feed (mm/min)	2460	3099	4192	3895	3226	2916
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.25	≤ 1.5	110	RPM	5816	4362	3490	2908	2181	1745
						(88-132)	Fz	0.017	0.028	0.045	0.053	0.059	0.064
							Feed (mm/min)	489	605	791	768	642	558
			HSM	≤ 0.05	≤ 2	165	RPM	8725	6544	5235	4362	3272	2617
						(132-198)	Fz	0.034	0.055	0.091	0.103	0.113	0.128
							Feed (mm/min)	1466	1815	2373	2251	1843	1675
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.25	≤ 1.5	113	RPM	5978	4484	3587	2989	2242	1793
						(90-135)	Fz	0.017	0.028	0.045	0.053	0.059	0.064
							Feed (mm/min)	502	622	813	789	660	574
			HSM	≤ 0.05	≤ 2	171	RPM	9048	6786	5429	4524	3393	2714
						(137-205)	Fz	0.034	0.055	0.091	0.103	0.113	0.128
							Feed (mm/min)	1520	1882	2461	2334	1911	1737


continued on next page



	Series 55M Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.25	≤ 1.5	78	RPM	4120	3090	2472	2060	1545	1236
						(62-93)	Fz	0.014	0.026	0.043	0.048	0.054	0.061
							Feed (mm/min)	297	396	527	494	415	379
			HSM	≤ 0.05	≤ 2	117	RPM	6220	4665	3732	3110	2333	1866
						(94-141)	Fz	0.031	0.051	0.085	0.096	0.105	0.120
							Feed (mm/min)	970	1194	1592	1493	1224	1120
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.25	≤ 1.5	72	RPM	3797	2848	2278	1898	1424	1139
						(57-86)	Fz	0.014	0.021	0.037	0.041	0.046	0.051
							Feed (mm/min)	273	13260	425	387	328	289
			HSM	≤ 0.05	≤ 2	108	RPM	5736	4302	3441	2868	2151	1721
						(87-130)	Fz	0.026	0.045	0.075	0.082	0.092	0.104
							Feed (mm/min)	757	14850	1285	1170	991	895
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.25	≤ 1.5	21	RPM	1131	848	679	565	424	339
						(17-26)	Fz	0.014	0.021	0.037	0.041	0.046	0.051
							Feed (mm/min)	81	16530	196792	115	98	86
			HSM	≤ 0.05	≤ 2	33	RPM	1729	1297	1037	864	648	519
						(26-39)	Fz	0.026	0.045	0.075	0.082	0.092	0.104
							Feed (mm/min)	228	290	387	353	299	270
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.25	≤ 1.5	17	RPM	889	666	533	444	333	267
						(13-20)	Fz	0.010	0.017	0.027	0.031	0.036	0.040
							Feed (mm/min)	43	57	71	69	60	53
			HSM	≤ 0.05	≤ 2	26	RPM	1373	1030	824	687	515	412
						(21-31)	Fz	0.019	0.032	0.056	0.062	0.069	0.077
							Feed (mm/min)	132	165	231	214	178	159
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.25	≤ 1.5	72	RPM	3797	2848	2278	1898	1424	1139
						(57-86)	Fz	0.014	0.026	0.043	0.048	0.054	0.061
							Feed (mm/min)	273	365	486	456	383	349
			HSM	≤ 0.05	≤ 2	119	RPM	6301	4726	3781	3151	2363	1890
						(95-143)	Fz	0.031	0.051	0.085	0.096	0.105	0.120
							Feed (mm/min)	983	1210	1613	1512	1240	1134
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.25	≤ 1.5	26	RPM	1373	1030	824	687	515	412
						(21-31)	Fz	0.014	0.026	0.043	0.048	0.054	0.061
							Feed (mm/min)	99	132	176	165	138	126
			HSM	≤ 0.05	≤ 2	43	RPM	2262	1696	1357	1131	848	679
						(34-51)	Fz	0.031	0.051	0.085	0.096	0.108	0.120
							Feed (mm/min)	353	434	579	543	456	407


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 5 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
reduce Ap to 1 x D_1 (maximum) when profile milling with long or extra long flute length tools
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

CARB Six Flute End Mills


	Series 51, 51CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	3/8	1/2	5/8	3/4	1
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.1	≤ 1	720	RPM	11002	7334	5501	4401	3667	2750
						(576-864)	Fz	0.0020	0.0035	0.0050	0.0055	0.0061	0.0071
							Feed (IPM)	132	154	165	145	134	117
			HSM	≤ 0.05	≤ 2	915	RPM	13981	9321	6991	5592	4660	3495
						(732-1098)	Fz	0.0028	0.0053	0.0070	0.0077	0.0085	.0100
							Feed (IPM)	235	296	294	258	238	21
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 375	Profile	≤ 0.1	≤ 1	490	RPM	7487	4991	3744	2995	2496	1872
						(392-588)	Fz	0.0015	0.0029	0.0038	0.0042	0.0046	0.0054
							Feed (IPM)	67	87	85	75	69	61
			HSM	≤ 0.05	≤ 2	620	RPM	9474	6316	4737	3789	3158	2368
						(496-744)	Fz	0.0021	0.0039	0.0052	0.0057	0.0062	0.0073
							Feed (IPM)	119	148	148	130	117	104
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 375	Profile	≤ 0.1	≤ 1	240	RPM	3667	2445	1834	1467	1222	917
						(192-288)	Fz	0.0012	0.0023	0.0030	0.0034	0.0037	0.0043
							Feed (IPM)	26	34	33	30	27	24
			HSM	≤ 0.05	≤ 2	305	RPM	4660	3107	2330	1864	1553	1165
						(244-366)	Fz	0.0017	0.0032	0.0042	0.0046	0.0050	0.0059
							Feed (IPM)	48	60	59	51	47	41
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.1	≤ 1	510	RPM	7793	5195	3896	3117	2598	1948
						(459-561)	Fz	0.0015	0.0028	0.0038	0.0041	0.0045	0.0053
							Feed (IPM)	70	87	89	77	70	62
			HSM	≤ 0.05	≤ 2	650	RPM	9932	6621	4966	3973	3311	2483
						(585-715)	Fz	0.0021	0.0038	0.0051	0.0056	0.0061	0.0072
							Feed (IPM)	125	151	152	133	121	107
M	**STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L**	≤ 275	Profile	≤ 0.1	≤ 1	350	RPM	5348	3565	2674	2139	1783	1337
						(315-385)	Fz	0.0012	0.0023	0.0030	0.0033	0.0036	0.0042
							Feed (IPM)	39	49	48	42	39	34
			HSM	≤ 0.05	≤ 2	450	RPM	6876	4584	3438	2750	2292	1719
						(405-495)	Fz	0.0017	0.0032	0.0042	0.0046	0.0050	0.0059
							Feed (IPM)	70	88	87	76	69	61
M	**STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450**	< 325	Profile	≤ 0.1	≤ 1	325	RPM	4966	3311	2483	1986	1655	1242
						(293-358)	Fz	0.0012	0.0023	0.0030	0.0033	0.0036	0.0042
							Feed (IPM)	36	46	45	39	36	31
			HSM	≤ 0.05	≤ 2	410	RPM	6265	4177	3132	2506	2088	1566
						(369-451)	Fz	0.0017	0.0032	0.0042	0.0046	0.0050	0.0059
							Feed (IPM)	64	80	79	69	63	55

continued on next page

CARB Six Flute End Mills

	Series 51, 51CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	3/8	1/2	5/8	3/4	1
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.1	≤ 1	105	RPM	1604	1070	802	642	535	401
						(84-126)	Fz	0.0014	0.0027	0.0036	0.0039	0.0043	0.0050
							Feed (IPM)	13	17	17	15	14	12
			HSM	≤ 0.05	≤ 2	130	RPM	1986	1324	993	795	662	497
						(104-156)	Fz	0.0016	0.0036	0.0048	0.0053	0.0058	0.0067
							Feed (IPM)	19	29	29	25	23	20
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.1	≤ 1	80	RPM	1222	815	611	489	407	306
						(64-96)	Fz	0.0010	0.0018	0.0025	0.0027	0.0029	0.0034
							Feed (IPM)	7	9	9	8	7	6
			HSM	≤ 0.05	≤ 2	100	RPM	1528	1019	764	611	509	382
						(80-120)	Fz	0.0013	0.0025	0.0034	0.0037	0.0041	0.0047
							Feed (IPM)	12	15	16	14	13	11
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.1	≤ 1	280	RPM	4278	2852	2139	1711	1426	1070
						(224-336)	Fz	0.0010	0.0018	0.0025	0.0027	0.0029	0.0034
							Feed (IPM)	26	31	32	28	25	22
			HSM	≤ 0.05	≤ 2	355	RPM	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0013	0.0025	0.0034	0.0037	0.0041	0.0047
							Feed (IPM)	42	54	55	48	44	38
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.1	≤ 1	155	RPM	2368	1579	1184	947	789	592
						(124-186)	Fz	0.0010	0.0018	0.0025	0.0027	0.0029	0.0034
							Feed (IPM)	14	17	18	15	14	12
			HSM	≤ 0.05	≤ 2	200	RPM	3056	2037	1528	1222	1019	764
						(160-240)	Fz	0.0013	0.0025	0.0034	0.0037	0.0041	0.0047
							Feed (IPM)	24	31	31	27	25	22


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 6 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series 51M, 51MCR Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Profile	≤ 0.1	≤ 1	219	RPM	11633	8725	6980	5816	4362	3490
						(176-263)	Fz	0.048	0.081	0.101	0.121	0.142	0.158
							Feed (mm/min)	3350	4240	4230	4223	3717	3308
			HSM	≤ 0.05	≤ 2	279	RPM	14784	11088	8870	7392	5544	4435
						(223-335)	Fz	0.066	0.113	0.141	0.169	0.197	0.220
							Feed (mm/min)	5854	7517	7504	7495	6553	5854
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Profile	≤ 0.1	≤ 1	149	RPM	7917	5938	4750	3958	2969	2375
						(119-179)	Fz	0.036	0.061	0.077	0.092	0.107	0.119
							Feed (mm/min)	1710	2173	2195	2185	1906	1696
			HSM	≤ 0.05	≤ 2	189	RPM	10017	7513	6010	5009	3756	3005
						(151-227)	Fz	0.049	0.083	0.104	0.125	0.146	0.163
							Feed (mm/min)	2945	3741	3750	3756	3291	2939
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.1	≤ 1	73	RPM	3878	2908	2327	1939	1454	1163
						(59-88)	Fz	0.029	0.049	0.061	0.073	0.086	0.096
							Feed (mm/min)	675	855	852	849	750	670
			HSM	≤ 0.05	≤ 2	93	RPM	4928	3696	2957	2464	1848	1478
						(74-112)	Fz	0.040	0.069	0.086	0.103	0.120	0.134
							Feed (mm/min)	1183	1530	1526	1523	1331	1189
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Profile	≤ 0.1	≤ 1	155	RPM	8240	6180	4944	4120	3090	2472
						(140-171)	Fz	0.035	0.060	0.075	0.090	0.105	0.117
							Feed (mm/min)	1730	2225	2225	2225	1947	1735
			HSM	≤ 0.05	≤ 2	198	RPM	10502	7877	6301	5251	3938	3151
						(178-218)	Fz	0.048	0.082	0.102	0.122	0.143	0.159
							Feed (mm/min)	3025	3875	3856	3844	3379	3006
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.1	≤ 1	107	RPM	5655	4241	3393	2827	2121	1696
						(96-117)	Fz	0.029	0.049	0.061	0.073	0.086	0.096
							Feed (mm/min)	984	1247	1242	1238	1094	977
			HSM	≤ 0.05	≤ 2	137	RPM	7271	5453	4362	3635	2726	2181
						(123-151)	Fz	0.040	0.069	0.086	0.103	0.120	0.134
							Feed (mm/min)	1745	2258	2251	2247	1963	1754
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.1	≤ 1	99	RPM	5251	3938	3151	2626	1969	1575
						(89-109)	Fz	0.029	0.049	0.061	0.073	0.086	0.096
							Feed (mm/min)	914	1158	1153	1150	1016	907
			HSM	≤ 0.05	≤ 2	125	RPM	6624	4968	3975	3312	2484	1987
						(112-137)	Fz	0.040	0.069	0.086	0.103	0.120	0.134
							Feed (mm/min)	1590	2057	2051	2047	1789	1598


continued on next page

CARB Six Flute End Mills

	Series 51M, 51MCR Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.1	≤ 1	32	RPM	1696	1272	1018	848	636	509
						(26-38)	Fz	0.034	0.057	0.071	0.085	0.100	0.110
							Feed (mm/min)	346	435	434	433	382	336
			HSM	≤ 0.05	≤ 2	40	RPM	2100	1575	1260	1050	788	630
						(32-48)	Fz	0.046	0.077	0.097	0.120	0.140	0.150
							Feed (mm/min)	580	728	733	756	662	567
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.1	≤ 1	24	RPM	1293	969	776	646	485	388
						(20-29)	Fz	0.023	0.039	0.049	0.059	0.068	0.077
							Feed (mm/min)	178	227	228	229	198	179
			HSM	≤ 0.05	≤ 2	30	RPM	1616	1212	969	808	606	485
						(24-37)	Fz	0.032	0.054	0.068	0.081	0.095	0.110
							Feed (mm/min)	310	393	396	393	345	320
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.1	≤ 1	85	RPM	4524	3393	2714	2262	1696	1357
						(68-102)	Fz	0.023	0.039	0.049	0.059	0.068	0.077
							Feed (mm/min)	624	794	798	801	692	627
			HSM	≤ 0.05	≤ 2	108	RPM	5736	4302	3441	2868	2151	1721
						(87-130)	Fz	0.032	0.054	0.068	0.081	0.095	0.110
							Feed (mm/min)	1101	1394	1404	1394	1226	1136
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.1	≤ 1	47	RPM	2504	1878	1503	1252	939	751
						(38-57)	Fz	0.023	0.039	0.049	0.059	0.068	0.077
							Feed (mm/min)	346	440	442	443	383	347
			HSM	≤ 0.05	≤ 2	61	RPM	3231	2424	1939	1616	1212	969
						(49-73)	Fz	0.032	0.054	0.068	0.081	0.095	0.110
							Feed (mm/min)	620	785	791	785	691	640


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 6 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

MULTI Carb
HIGH PERFORMANCE FINISHING END MILLS



	Series 66, 66CR Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 3/16	1/4	3/8	1/2	5/8	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Profile	≤ 0.05	≤ 1	635	RPM	12937	9703	6469	4851	3881	3234	2426
						(508-762)	Fz	0.0008	0.0012	0.0022	0.0030	0.0037	0.0038	0.0042
							Feed (IPM)	72.4	81.5	99.6	131.0	129.2	135.2	112.1
			Finish	≤ 0.02	≤ 2	762	RPM	15524	11643	7762	5822	4657	3881	2911
						(610-914)	Fz	0.0006	0.0010	0.0018	0.0024	0.0030	0.0030	0.0034
							Feed (IPM)	69.5	78.2	95.6	125.7	124.1	129.8	107.6
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Profile	≤ 0.05	≤ 1	360	RPM	7334	5501	3667	2750	2200	1834	1375
						(288-432)	Fz	0.0006	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	30.8	34.7	43.6	56.9	57.4	60.5	48.4
			Finish	≤ 0.02	≤ 2	432	RPM	8801	6601	4401	3300	2640	2200	1650
						(346-518)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	29.6	33.3	41.9	54.7	55.1	58.1	46.5
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.05	≤ 1	290	RPM	5908	4431	2954	2216	1772	1477	1108
						(232-348)	Fz	0.0004	0.0006	0.0012	0.0016	0.0020	0.0021	0.0022
							Feed (IPM)	16.5	18.6	24.8	31.9	31.9	34.1	26.8
			Finish	≤ 0.02	≤ 2	348	RPM	7090	5317	3545	2659	2127	1772	1329
						(278-418)	Fz	0.0003	0.0005	0.0010	0.0013	0.0016	0.0017	0.0018
							Feed (IPM)	15.9	17.9	23.8	30.6	30.6	32.8	25.7
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Profile	≤ 0.05	≤ 1	705	RPM	14363	10772	7182	5386	4309	3591	2693
						(564-846)	Fz	0.0008	0.0012	0.0022	0.0030	0.0037	0.0038	0.0042
							Feed (IPM)	80.4	90.5	110.6	145.4	143.5	150.1	124.4
			Finish	≤ 0.02	≤ 2	846	RPM	17236	12927	8618	6463	5171	4309	3232
						(677-1015)	Fz	0.0006	0.0010	0.0018	0.0024	0.0030	0.0030	0.0034
							Feed (IPM)	77.2	86.9	106.2	139.6	137.7	144.1	119.4
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Profile	≤ 0.05	≤ 1	540	RPM	11002	8251	5501	4126	3300	2750	2063
						(432-648)	Fz	0.0006	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	46.2	52.0	65.5	85.4	86.1	90.8	72.6
			Finish	≤ 0.02	≤ 2	648	RPM	13202	9901	6601	4951	3961	3300	2475
						(518-778)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	44.4	49.9	62.8	82.0	82.7	87.1	69.7
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Profile	≤ 0.05	≤ 1	560	RPM	11409	8557	5705	4278	3423	2852	2139
						(448-672)	Fz	0.0006	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	47.9	53.9	67.9	88.6	89.3	94.1	75.3
			Finish	≤ 0.02	≤ 2	448	RPM	9127	6845	4564	3423	2738	2282	1711
						(358-538)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	30.7	34.5	43.4	56.7	57.2	60.2	48.2


continued on next page



	Series 66, 66CR Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 3/16	1/4	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.05	≤ 1	385	RPM	7844	5883	3922	2941	2353	1961	1471
						(308-462)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	27.5	28.8	38.4	47.7	48.7	51.8	42.1
			Finish	≤ 0.02	≤ 2	462	RPM	9412	7059	4706	3530	2824	2353	1765
						(370-554)	Fz	0.0004	0.0006	0.0011	0.0014	0.0018	0.0019	0.0021
							Feed (IPM)	26.4	27.7	36.9	45.7	46.8	49.7	40.4
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.05	≤ 1	355	RPM	7233	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	25.3	26.6	35.4	43.9	44.9	47.7	38.8
			Finish	≤ 0.02	≤ 2	426	RPM	8679	6509	4340	3255	2604	2170	1627
						(341-511)	Fz	0.0004	0.0006	0.0011	0.0014	0.0018	0.0019	0.0021
							Feed (IPM)	24.3	25.5	34.0	42.2	43.1	45.8	37.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.05	≤ 1	105	RPM	2139	1604	1070	802	642	535	401
						(84-126)	Fz	0.0005	0.0007	0.0014	0.0018	0.0023	0.0024	0.0026
							Feed (IPM)	7.5	7.9	10.5	13.0	13.3	14.1	11.5
			Finish	≤ 0.02	≤ 2	126	RPM	2567	1925	1284	963	770	642	481
						(101-151)	Fz	0.0004	0.0006	0.0011	0.0014	0.0018	0.0019	0.0021
							Feed (IPM)	7.2	7.5	10.1	12.5	12.8	13.6	11.0
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.05	≤ 1	85	RPM	1732	1299	866	649	520	433	325
						(68-102)	Fz	0.0003	0.0005	0.0009	0.0011	0.0014	0.0015	0.0016
							Feed (IPM)	3.6	4.5	5.5	6.4	6.5	7.1	5.7
			Finish	≤ 0.02	≤ 2	102	RPM	2078	1559	1039	779	623	520	390
						(82-122)	Fz	0.0002	0.0004	0.0007	0.0009	0.0011	0.0012	0.0013
							Feed (IPM)	3.5	4.4	5.2	6.2	6.3	6.9	5.5
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.05	≤ 1	390	RPM	7946	5959	3973	2980	2384	1986	1490
						(312-468)	Fz	0.0005	0.0008	0.0015	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	27.8	33.4	41.7	56.3	55.8	59.0	47.5
			Finish	≤ 0.02	≤ 2	468	RPM	9535	7151	4767	3576	2860	2384	1788
						(374-562)	Fz	0.0004	0.0006	0.0012	0.0017	0.0021	0.0022	0.0023
							Feed (IPM)	26.7	32.0	40.0	54.1	53.5	56.6	45.6
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.05	≤ 1	140	RPM	2852	2139	1426	1070	856	713	535
						(112-168)	Fz	0.0005	0.0008	0.0015	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	10.0	12.0	15.0	20.2	20.0	21.2	17.1
			Finish	≤ 0.02	≤ 2	168	RPM	3423	2567	1711	1284	1027	856	642
						(134-202)	Fz	0.0004	0.0006	0.0012	0.0017	0.0021	0.0022	0.0023
							Feed (IPM)	9.6	11.5	14.4	19.4	19.2	20.3	16.4


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

MULTI Carb
HIGH PERFORMANCE FINISHING END MILLS




	Series 66M, 66MCR Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20	25
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 275	Profile	≤ 0.05	≤ 1	194	RPM	10260	7695	6156	5130	3847	3078	2462
						(155-232)	Fz	0.029	0.047	0.059	0.072	0.095	0.101	0.105
							Feed (mm/min)	2068	2528	2528	3324	3280	3431	2844
			Finish	≤ 0.02	≤ 2	232	RPM	12312	9234	7387	6156	4617	3693	2955
						(186-279)	Fz	0.023	0.038	0.047	0.058	0.076	0.081	0.084
							Feed (mm/min)	1985	2427	2427	3191	3149	3294	2730
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 375	Profile	≤ 0.05	≤ 1	110	RPM	5816	4362	3490	2908	2181	1745	1396
						(88-132)	Fz	0.022	0.036	0.045	0.055	0.074	0.080	0.080
							Feed (mm/min)	879	1108	1107	1445	1457	1536	1229
			Finish	≤ 0.02	≤ 2	132	RPM	6980	5235	4188	3490	2617	2094	1675
						(105-158)	Fz	0.017	0.029	0.036	0.044	0.059	0.064	0.064
							Feed (mm/min)	844	1063	1063	1387	1399	1474	1179
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 375	Profile	≤ 0.05	≤ 1	88	RPM	4686	3514	2811	2343	1757	1406	1125
						(71-106)	Fz	0.014	0.026	0.032	0.038	0.051	0.056	0.055
							Feed (mm/min)	472	630	630	810	810	866	680
			Finish	≤ 0.02	≤ 2	106	RPM	5622.615 12	4217	3374	2811	2108	1687	1349
						(85-127)	Fz	0.012	0.020	0.026	0.031	0.041	0.045	0.044
							Feed (mm/min)	453	605	605	777	777	831	653
K	CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile	≤ 220	Profile	≤ 0.05	≤ 1	215	RPM	11391	8543	6834	5695	4271	3417	2734
						(172-258)	Fz	0.029	0.047	0.059	0.072	0.095	0.101	0.105
							Feed (mm/min)	2296	2807	2807	3690	3641	3809	3158
			Finish	≤ 0.02	≤ 2	258	RPM	13669	10252	8201	6834	5126	4101	3281
						(206-309)	Fz	0.023	0.038	0.047	0.058	0.076	0.081	0.084
							Feed (mm/min)	2204	2695	2694	3543	3496	3657	3031
K	CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile	> 220 ≤ 260	Profile	≤ 0.05	≤ 1	165	RPM	8725	6544	5235	4362	3272	2617	2094
						(132-198)	Fz	0.022	0.036	0.045	0.055	0.074	0.080	0.080
							Feed (mm/min)	1319	1661	1661	2167	2186	2303	1843
			Finish	≤ 0.02	≤ 2	198	RPM	10470	7852	6282	5235	3926	3141	2513
						(158-237)	Fz	0.017	0.029	0.036	0.044	0.059	0.064	0.064
							Feed (mm/min)	1266	1595	1595	2080	2099	2211	1769
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275	Profile	≤ 0.05	≤ 1	171	RPM	9048	6786	5429	4524	3393	2714	2171
						(137-205)	Fz	0.022	0.036	0.045	0.055	0.074	0.080	0.080
							Feed (mm/min)	1368	1723	1723	2247	2267	2389	1911
			Finish	≤ 0.02	≤ 2	137	RPM	7238	5429	4343	3619	2714	2171	1737
						(109-164)	Fz	0.017	0.029	0.036	0.044	0.059	0.064	0.064
							Feed (mm/min)	875	1103	1103	1438	1451	1529	1223

continued on next page



	Series 66M, 66MCR Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16	20	25
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.05	≤ 1	117	RPM	6220	4665	3732	3110	2333	1866	1493
						(94-141)	Fz	0.017	0.030	0.037	0.043	0.059	0.064	0.065
							Feed (mm/min)	731	975	975	1209	1236	1314	1067
			Finish	≤ 0.02	≤ 2	141	RPM	7465	5598	4479	3732	2799	2239	1791
						(113-169)	Fz	0.013	0.024	0.030	0.035	0.047	0.051	0.052
							Feed (mm/min)	702	17	936	1161	1187	1261	1025
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.05	≤ 1	108	RPM	5736	4302	3441	2868	2151	1721	1377
						(87-130)	Fz	0.017	0.030	0.037	0.043	0.059	0.064	0.065
							Feed (mm/min)	674	899	899	1115	1140	1211	984
			Finish	≤ 0.02	≤ 2	130	RPM	6883	5162	4130	3441	2581	2065	1652
						(104-156)	Fz	0.013	0.024	0.030	0.035	0.047	0.051	0.052
							Feed (mm/min)	647	863	863	1070	1094	1163	945
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.05	≤ 1	32	RPM	1696	1272	1018	848	636	509	407
						(26-38)	Fz	0.017	0.030	0.037	0.043	0.059	0.064	0.065
							Feed (mm/min)	199	266	213	330	337	358	291
			Finish	≤ 0.02	≤ 2	38	RPM	2036	1527	1221	1018	763	611	489
						(31-46)	Fz	0.013	0.024	0.030	0.035	0.047	0.051	0.052
							Feed (mm/min)	192	255	255	317	324	344	279
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.05	≤ 1	26	RPM	1373	1030	824	687	515	412	330
						(21-31)	Fz	0.012	0.019	0.024	0.026	0.036	0.040	0.040
							Feed (mm/min)	115	138	138	163	166	181	145
			Finish	≤ 0.02	≤ 2	31	RPM	1648	1236	989	824	618	494	396
						(25-37)	Fz	0.010	0.015	0.019	0.021	0.029	0.032	0.032
							Feed (mm/min)	111	133	133	157	159	174	139
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.05	≤ 1	119	RPM	6301	4726	3781	3151	2363	1890	1512
						(95-143)	Fz	0.019	0.032	0.040	0.050	0.067	0.072	0.073
							Feed (mm/min)	847	1059	1059	1429	1415	1497	1206
			Finish	≤ 0.02	≤ 2	143	RPM	7561	5671	4537	3781	2836	2268	1815
						(114-171)	Fz	0.015	0.026	0.032	0.040	0.053	0.058	0.058
							Feed (mm/min)	813	1016	1016	1372	1359	1437	1158
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.05	≤ 1	43	RPM	2262	1696	1357	1131	848	679	543
						(34-51)	Fz	0.019	0.032	0.040	0.050	0.067	0.072	0.073
							Feed (mm/min)	304	380	380	513	508	537	433
			Finish	≤ 0.02	≤ 2	51	RPM	2714	2036	1629	1357	1018	814	651
						(41-61)	Fz	0.015	0.026	0.032	0.040	0.053	0.058	0.058
							Feed (mm/min)	292	365	365	492	488	516	416


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 56B Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/32	1/16	1/8	3/16	1/4	3/8	1/2	3/4
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 370	Rough	≤ 0.4	≤ 0.1	625	RPM	76400	38200	19100	12733	9550	6367	4775	3183
						(500-750)	Fz	0.0006	0.0015	0.0030	0.0040	0.0050	0.0080	0.0100	0.0120
							Feed (IPM)	92	115	115	102	96	102	96	76
			HSM	≤ 0.4	≤ 0.03	950	RPM	116128	58064	29032	19355	14516	9677	7258	4839
						(760-1140)	Fz	0.0007	0.0017	0.0033	0.0044	0.0060	0.0088	0.0110	0.0013
							Feed (IPM)	163	197	192	170	174	170	160	126
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 370 ≤ 475	Rough	≤ 0.4	≤ 0.05	750	RPM	91680	45840	22920	15280	11460	7640	5730	3820
						(600-900)	Fz	0.0005	0.0011	0.0023	0.0030	0.0038	0.0060	0.0075	0.0085
							Feed (IPM)	92	101	105	92	87	92	86	65
			HSM	≤ 0.4	≤ 0.02	1150	RPM	140576	70288	35144	23429	17572	11715	8786	5857
						(920-1380)	Fz	0.0006	0.0012	0.0025	0.0033	0.0042	0.0066	0.0082	0.0100
							Feed (IPM)	169	169	176	155	148	155	144	117
H	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 475 ≤ 655	Rough	≤ 0.4	≤ 0.04	500	RPM	61120	30560	15280	10187	7640	5093	3820	2547
						(400-600)	Fz	0.0004	0.0008	0.0017	0.0023	0.0029	0.0045	0.0057	0.0063
							Feed (IPM)	49	49	52	47	44	46	44	32
			HSM	≤ 0.4	≤ 0.01	1000	RPM	122240	61120	30560	20373	15280	10187	7640	5093
						(800-1200)	Fz	0.0005	0.0009	0.0019	0.0025	0.0032	0.0050	0.0063	0.0071
							Feed (IPM)	122	110	116	102	98	102	96	72

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 2 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


Turbo-Carb HIGH PERFORMANCE CARBIDE END MILLS

	Series 56MB Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 1	1.5	3	5	6	10	12	20
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 370	Rough	≤ 0.4	≤ 0.1	191	RPM	60748	40498	20249	12150	10125	6075	5062	3037
						(153-229)	Fz	0.015	0.038	0.076	0.102	0.127	0.203	0.254	0.305
							Feed (mm/min)	1822	3078	3078	2479	2572	2466	2572	1853
			HSM	≤ 0.4	≤ 0.03	290	RPM	92235	61490	46117	18447	15372	9223	7686	4612
						(232-348)	Fz	0.018	0.043	0.084	0.112	0.117	0.224	0.279	0.330
							Feed (mm/min)	3320	5288	7748	4132	3597	4132	4289	3044
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 370 ≤ 475	Rough	≤ 0.4	≤ 0.05	229	RPM	72833	48556	24278	14567	12139	7283	6069	3642
						(183-275)	Fz	0.013	0.028	0.058	0.076	0.097	0.152	0.191	0.216
							Feed (mm/min)	1894	2719	2816	2214	2355	2214	2319	1573
			HSM	≤ 0.4	≤ 0.02	351	RPM	111636	74424	37212	22327	18606	11164	9303	5582
						(281-421)	Fz	0.015	0.030	0.064	0.084	0.107	0.168	0.208	0.254
							Feed (mm/min)	3349	4465	4763	3751	3982	3751	3870	2836
H	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 475 ≤ 655	Rough	≤ 0.4	≤ 0.04	152	RPM	48344	32229	16115	9669	8057	4834	4029	2417
						(122-182)	Fz	0.010	0.020	0.043	0.058	0.074	0.114	0.145	0.160
							Feed (mm/min)	967	1289	1386	1122	1192	1102	1168	773
			HSM	≤ 0.4	≤ 0.01	305	RPM	97005	64670	32335	19401	16168	9701	8084	4850
						(244-366)	Fz	0.013	0.023	0.048	0.064	0.081	0.127	0.160	0.180
							Feed (mm/min)	2522	2975	3104	2483	2619	2464	2587	1746

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 2 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 57 Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	5/16	3/8	1/2
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 280 ≤ 420	Slot	1	≤ 0.3	215	RPM	3285	2628	2190	1643
						(172-258)	Fz	0.0013	0.0019	0.0025	0.0031
							Feed (IPM)	26	30	33	31
			Profile	≤ 0.1	≤ 1.5	265	RPM	4049	3239	2699	2025
						(212-318)	Fz	0.0018	0.0026	0.0035	0.0440
							Feed (IPM)	44	51	57	53
			HSM	≤ 0.04	≤ 1.5	560	RPM	8557	6845	5705	4278
						(448-672)	Fz	0.0022	0.0033	0.0044	0.0055
							Feed (IPM)	113	136	151	141
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 420 ≤ 560	Slot	1	≤ 0.3	120	RPM	1834	1467	1222	917
						(96-144)	Fz	0.0010	0.0015	0.0020	0.0025
							Feed (IPM)	11	13	15	14
			Profile	≤ 0.1	≤ 1.5	150	RPM	2292	1834	1528	1146
						(120-180)	Fz	0.0014	0.0021	0.0028	0.0035
							Feed (IPM)	19	23	26	24
			HSM	≤ 0.04	≤ 1.5	490	RPM	7487	5990	4991	3744
						(392-588)	Fz	0.0018	0.0026	0.0035	0.0044
							Feed (IPM)	81	93	105	99
H	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 560 < 745	Slot	1	≤ 0.3	65	RPM	993	795	662	497
						(52-78)	Fz	0.0008	0.0011	0.0015	0.0019
							Feed (IPM)	5	5	6	6
			Profile	≤ 0.1	≤ 1.5	80	RPM	1222	978	815	611
						(64-96)	Fz	0.0011	0.0016	0.0021	0.0026
							Feed (IPM)	8	9	10	10
			HSM	≤ 0.04	≤ 1.5	250	RPM	3820	3056	2547	1910
						(200-300)	Fz	0.0013	0.0019	0.0025	0.0031
							Feed (IPM)	30	35	38	36


rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 6 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series 57M Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 280 ≤ 420	Slot	1	≤ 0.3	66	RPM	3499	2624	2099	1749
						(53-79)	Fz	0.032	0.048	0.064	0.079
							Feed (mm/min)	672	756	806	829
			Profile	≤ 0.1	≤ 1.5	81	RPM	4294	3220	2576	2147
						(65-97)	Fz	0.046	0.066	0.089	0.112
							Feed (mm/min)	1185	1275	1376	1443
			HSM	≤ 0.04	≤ 1.5	171	RPM	9064	6798	5439	4532
						(137-205)	Fz	0.056	0.084	0.112	0.140
							Feed (mm/min)	3046	3426	3655	3807
P	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 420 ≤ 560	Slot	1	≤ 0.3	37	RPM	1961	1471	1177	981
						(30-44)	Fz	0.025	0.038	0.051	0.064
							Feed (mm/min)	294	335	360	377
			Profile	≤ 0.1	≤ 1.5	46	RPM	2438	1829	1463	1219
						(37-55)	Fz	0.036	0.053	0.071	0.089
							Feed (mm/min)	527	582	623	651
			HSM	≤ 0.04	≤ 1.5	149	RPM	7898	5924	4739	3949
						(119-179)	Fz	0.046	0.066	0.089	0.112
							Feed (mm/min)	2180	2346	2531	2654
H	TOOL STEELS MOLD AND DIE STEEL 300M, 4340, 52100, HP-9-4-20, M50, A2, D2, H13, L2, M2, P20, S7, T15, W2	> 560 < 745	Slot	1	≤ 0.3	20	RPM	1060	795	636	530
						(16-24)	Fz	0.020	0.028	0.038	0.048
							Feed (mm/min)	127	134	145	153
			Profile	≤ 0.1	≤ 1.5	24	RPM	1272	954	763	636
						(19-29)	Fz	0.028	0.041	0.053	0.066
							Feed (mm/min)	214	235	243	252
			HSM	≤ 0.04	≤ 1.5	76	RPM	4029	3021	2417	2014
						(61-91)	Fz	0.033	0.048	0.064	0.079
							Feed (mm/min)	798	870	928	955


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 6 x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

SERIES 33 THREE FLUTE END MILLS

	Series 33CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 275	Profile	≤ 0.5	≤ 1.5	550	RPM	16808	8404	5603	4202	3362	2801	2101
						(440-660)	Fz	0.0005	0.0012	0.0023	0.0031	0.0039	0.0040	0.0043
							Feed (IPM)	25.2	30.3	38.7	39.1	39.3	33.6	27.1
			Slot	1	≤ 1	440	RPM	13446	6723	4482	3362	2689	2241	1681
						(352-528)	Fz	0.0005	0.0012	0.0023	0.0031	0.0039	0.0040	0.0043
							Feed (IPM)	20.2	24.2	30.9	31.3	31.5	26.9	21.7
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	> 275 ≤ 375	Profile	≤ 0.5	≤ 1.5	315	RPM	9626	4813	3209	2407	1925	1604	1203
						(252-378)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	11.6	13.0	16.4	16.6	16.7	14.4	11.6
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	9.2	10.3	13.0	13.2	13.3	11.5	9.2
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	> 250 ≤ 375	Profile	≤ 0.5	≤ 1.5	185	RPM	5654	2827	1885	1413	1131	942	707
						(148-222)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	5.1	5.9	7.9	7.6	7.8	6.8	5.3
			Slot	1	≤ 1	145	RPM	4431	2216	1477	1108	886	739	554
						(116-174)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	4.0	4.7	6.2	6.0	6.1	5.3	4.2
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	445	RPM	13599	6800	4533	3400	2720	2267	1700
						(356-534)	Fz	0.0004	0.0011	0.0021	0.0028	0.0035	0.0036	0.0039
							Feed (IPM)	14.3	22.4	28.6	28.6	28.6	24.5	19.9
			Slot	1	≤ 1	355	RPM	10849	5424	3616	2712	2170	1808	1356
						(284-426)	Fz	0.0004	0.0011	0.0021	0.0028	0.0035	0.0036	0.0039
							Feed (IPM)	11.4	17.9	22.8	22.8	22.8	19.5	15.9
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	340	RPM	10390	5195	3463	2598	2078	1732	1299
						(272-408)	Fz	0.0003	0.0008	0.0016	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	9.4	12.5	16.6	16.4	16.2	14.0	11.3
			Slot	1	≤ 1	270	RPM	8251	4126	2750	2063	1650	1375	1031
						(216-324)	Fz	0.0003	0.0008	0.0016	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	7.4	9.9	13.2	13.0	12.9	11.1	9.0
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	490	RPM	14974	7487	4991	3744	2995	2496	1872
						(392-588)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	17.1	22.5	28.5	28.1	27.9	24.0	19.7
			Slot	1	≤ 1	390	RPM	11918	5959	3973	2980	2384	1986	1490
						(312-468)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	13.6	17.9	22.6	22.3	22.2	19.1	15.6


continued on next page

SERIES 33 THREE FLUTE END MILLS

	Series 33CR Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	340	RPM	16808	8404	5603	4202	3362	2801	2101
						(272-408)	Fz	0.0005	0.0012	0.0023	0.0031	0.0039	0.0040	0.0043
							Feed (IPM)	25.2	30.3	38.7	39.1	39.3	33.6	27.1
			Slot	1	≤ 1	270	RPM	13446	6723	4482	3362	2689	2241	1681
						(216-324)	Fz	0.0005	0.0012	0.0023	0.0031	0.0039	0.0040	0.0043
							Feed (IPM)	20.2	24.2	30.9	31.3	31.5	26.9	21.7
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	310	RPM	9626	4813	3209	2407	1925	1604	1203
						(248-372)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	11.6	13.0	16.4	16.6	16.7	14.4	11.6
			Slot	1	≤ 1	250	RPM	7640	3820	2547	1910	1528	1273	955
						(200-300)	Fz	0.0004	0.0009	0.0017	0.0023	0.0029	0.0030	0.0032
							Feed (IPM)	9.2	10.3	13.0	13.2	13.3	11.5	9.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	80	RPM	5654	2827	1885	1413	1131	942	707
						(64-96)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	5.1	5.9	7.9	7.6	7.8	6.8	5.3
			Slot	1	≤ 1	65	RPM	4431	2216	1477	1108	886	739	554
						(52-78)	Fz	0.0003	0.0007	0.0014	0.0018	0.0023	0.0024	0.0025
							Feed (IPM)	4.0	4.7	6.2	6.0	6.1	5.3	4.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	62	RPM	13599	6800	4533	3400	2720	2267	1700
						(50-74)	Fz	0.0004	0.0011	0.0021	0.0028	0.0035	0.0036	0.0039
							Feed (IPM)	14.3	22.4	28.6	28.6	28.6	24.5	19.9
			Slot	1	≤ 1	49	RPM	10849	5424	3616	2712	2170	1808	1356
						(39-59)	Fz	0.0004	0.0011	0.0021	0.0028	0.0035	0.0036	0.0039
							Feed (IPM)	11.4	17.9	22.8	22.8	22.8	19.5	15.9
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	215	RPM	10390	5195	3463	2598	2078	1732	1299
						(172-258)	Fz	0.0003	0.0008	0.0016	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	9.4	12.5	16.6	16.4	16.2	14.0	11.3
			Slot	1	≤ 1	170	RPM	8251	4126	2750	2063	1650	1375	1031
						(136-204)	Fz	0.0003	0.0008	0.0016	0.0021	0.0026	0.0027	0.0029
							Feed (IPM)	7.4	9.9	13.2	13.0	12.9	11.1	9.0
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	75	RPM	14974	7487	4991	3744	2995	2496	1872
						(60-90)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	17.1	22.5	28.5	28.1	27.9	24.0	19.7
			Slot	1	≤ 1	60	RPM	11918	5959	3973	2980	2384	1986	1490
						(48-72)	Fz	0.0004	0.0010	0.0019	0.0025	0.0031	0.0032	0.0035
							Feed (IPM)	13.6	17.9	22.6	22.3	22.2	19.1	15.6

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 3 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


SERIES 33 THREE FLUTE END MILLS



	Series 33MCR Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	> 175 ≤ 275	Profile	≤ 0.5	≤ 1.5	168	RPM	17773	8886	6665	5332	4443	3332	2666	2133
						(134-201)	Fz	0.012	0.029	0.049	0.061	0.074	0.100	0.107	0.108
							Feed (mm/min)	640	768	981	981	992	998	853	688
			Slot	1	≤ 1	134	RPM	14218	7109	5332	4265	3555	2666	2133	1706
						(107-161)	Fz	0.012	0.029	0.049	0.061	0.074	0.100	0.107	0.108
							Feed (mm/min)	512	614	785	785	793	798	682	550
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	> 275 ≤ 375	Profile	≤ 0.5	≤ 1.5	96	RPM	10179	5089	3817	3054	2545	1909	1527	1221
						(77-115)	Fz	0.010	0.022	0.036	0.045	0.055	0.074	0.080	0.080
							Feed (mm/min)	293	330	415	415	421	425	366	293
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.010	0.022	0.036	0.045	0.055	0.074	0.080	0.080
							Feed (mm/min)	233	262	330	330	334	337	291	233
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	> 250 ≤ 375	Profile	≤ 0.5	≤ 1.5	56	RPM	5978	2989	2242	1793	1495	1121	897	717
						(45-68)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	129	151	201	201	194	198	172	135
			Slot	1	≤ 1	44	RPM	4686	2343	1757	1406	1171	879	703	562
						(35-53)	Fz	0.007	0.017	0.030	0.037	0.043	0.059	0.064	0.063
							Feed (mm/min)	101	118	157	157	152	155	135	105
K	**CAST IRONS (LOW & MEDIUM ALLOY) Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	136	RPM	14380	7190	5392	4314	3595	2696	2157	1726
						(109-163)	Fz	0.008	0.026	0.045	0.056	0.067	0.090	0.096	0.098
							Feed (mm/min)	362	569	725	725	725	725	621	505
			Slot	1	≤ 1	108	RPM	11471	5736	4302	3441	2868	2151	1721	1377
						(87-130)	Fz	0.008	0.026	0.045	0.056	0.067	0.090	0.096	0.098
							Feed (mm/min)	289	454	578	578	578	578	496	403
K	**CAST IRONS (HIGH ALLOY) Gray, Malleable, Ductile**	> 220 ≤ 260	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.007	0.019	0.034	0.043	0.050	0.067	0.072	0.073
							Feed (mm/min)	237	316	422	422	415	411	356	287
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.007	0.019	0.034	0.043	0.050	0.067	0.072	0.073
							Feed (mm/min)	188	251	335	335	330	327	283	228
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	149	RPM	15834	7917	5938	4750	3958	2969	2375	1900
						(119-179)	Fz	0.009	0.024	0.041	0.051	0.060	0.079	0.085	0.088
							Feed (mm/min)	433	570	722	722	712	707	608	499
			Slot	1	≤ 1	119	RPM	12602	6301	4726	3781	3151	2363	1890	1512
						(95-143)	Fz	0.009	0.024	0.041	0.051	0.060	0.079	0.085	0.088
							Feed (mm/min)	345	454	575	575	567	563	484	397


continued on next page

SERIES 33 THREE FLUTE END MILLS




	Series 33MCR Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20	25
M	STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L	≤ 275	Profile	≤ 0.5	≤ 1.5	104	RPM	10987	5493	4120	3296	2747	2060	1648	1318
						(83-124)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	237	316	396	396	395	396	343	277
			Slot	1	≤ 1	82	RPM	8725	4362	3272	2617	2181	1636	1309	1047
						(66-99)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	188	251	314	314	314	314	272	220
M	STAINLESS STEELS (PH) 13-8 PH,15-5PH,17-4 PH, Custom 450	< 325	Profile	≤ 0.5	≤ 1.5	94	RPM	10017	5009	3756	3005	2504	1878	1503	1202
						(76-113)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	216	288	361	361	361	361	313	252
			Slot	1	≤ 1	76	RPM	8078	4039	3029	2424	2020	1515	1212	969
						(61-91)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	174	233	291	291	291	291	252	204
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400	≤ 300	Profile	≤ 0.5	≤ 1.5	24	RPM	2585	1293	969	776	646	485	388	310
						(20-29)	Fz	0.006	0.017	0.028	0.035	0.041	0.054	0.059	0.060
							Feed (mm/min)	48	65	81	65	79	78	68	56
			Slot	1	≤ 1	20	RPM	2100	1050	788	630	525	394	315	252
						(16-24)	Fz	0.006	0.017	0.028	0.035	0.041	0.054	0.059	0.060
							Feed (mm/min)	39	53	66	66	64	64	55	45
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 718, 750X, Incoly 925, Waspaloy, Hastelloy, Rene	> 300	Profile	≤ 0.5	≤ 1.5	19	RPM	2003	1002	751	601	501	376	301	240
						(15-23)	Fz	0.005	0.012	0.019	0.024	0.029	0.038	0.043	0.043
							Feed (mm/min)	29	36	43	43	43	43	38	31
			Slot	1	≤ 1	15	RPM	11471	5736	4302	3441	2868	2151	1721	1377
						(12-18)	Fz	0.008	0.026	0.045	0.056	0.067	0.090	0.096	0.098
							Feed (mm/min)	289	454	578	578	578	578	496	403
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si	≤ 350	Profile	≤ 0.5	≤ 1.5	66	RPM	6947	3474	2605	2084	1737	1303	1042	834
						(52-79)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	150	200	250	250	250	250	217	175
			Slot	1	≤ 1	52	RPM	5493	2747	2060	1648	1373	1030	824	659
						(41-62)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	119	158	198	198	198	198	171	138
S	TITANIUM ALLOYS (DIFFICULT) Ti10Al2Fe3Al, Ti5Al5V5Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti15V3 Cr3Sn3Al	> 350 ≤ 440	Profile	≤ 0.5	≤ 1.5	23	RPM	2424	1212	909	727	606	454	364	291
						(18-27)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	52	70	87	87	87	87	76	61
			Slot	1	≤ 1	18	RPM	1939	969	727	582	485	364	291	233
						(15-22)	Fz	0.007	0.019	0.032	0.040	0.048	0.064	0.069	0.070
							Feed (mm/min)	42	56	70	70	70	70	60	49

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 3 x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


Series 44, 45, 43CR, 43CB, 43LC, 43, 43L, 47, 47B, 47ES, 47EB Fractional		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	3/4	1
N	ALUMINUM ALLOYS 2024, 5052, 5086, 6061, 6073, 7975	Slot	1	≤ 1	1600	RPM	48896	24448	16299	12224	8149	6112
					(1280-1920)	Fz	0.0009	0.0025	0.0045	0.0060	0.0070	0.0085
						Feed 2 flutes (IPM)	88	122	147	147	114	104
						Feed 3 flutes (IPM)	132	183	220	220	171	156
		Profile	≤ 0.5	≤ 1.5	2000	RPM	61120	30560	20373	15280	10187	7640
					(1600-2400)	Fz	0.0009	0.0025	0.0045	0.0060	0.0070	0.0085
						Feed 2 flutes (IPM)	110	153	183	183	143	130
						Feed 3 flutes (IPM)	165	229	275	275	214	195
		HSM	≤ 0.5	≤ 2	3300	RPM	100848	50424	33616	25212	16808	12606
					(2640-3960)	Fz	0.0021	0.0055	0.0105	0.0140	0.0165	0.0195
						Feed 2 flutes (IPM)	424	555	706	706	555	492
						Feed 3 flutes (IPM)	635	832	1059	1059	832	737
N	ALUMINUM DIE CAST ALLOYS (HIGH SILICONE) A-390, A-392, B- 390	Slot	1	≤ 1	600	RPM	18336	9168	6112	4584	3056	2292
					(480-720)	Fz	0.0009	0.0025	0.0045	0.0060	0.0070	0.0085
						Feed 2 flutes (IPM)	33	46	55	55	43	39
						Feed 3 flutes (IPM)	50	69	83	83	64	58
		Profile	≤ 0.5	≤ 1.5	750	RPM	22920	11460	7640	5730	3820	2865
					(600-900)	Fz	0.0009	0.0025	0.0045	0.0060	0.0070	0.0085
						Feed 2 flutes (IPM)	41	57	69	69	53	49
						Feed 3 flutes (IPM)	62	86	103	103	80	73
		HSM	≤ 0.5	≤ 2	1240	RPM	37894	18947	12631	9474	6316	4737
					(992-1488)	Fz	0.0021	0.0055	0.0105	0.0140	0.0165	0.0195
						Feed 2 flutes (IPM)	159	208	265	265	208	185
						Feed 3 flutes (IPM)	239	313	398	398	313	277
N	COPPER ALLOYS Aluminum Bronze Brass Naval Brass Red Brass	Slot	1	≤ 1	865	RPM	26434	13217	8811	6609	8149	6112
					(692-1038)	Fz	0.0008	0.0020	0.0040	0.0050	0.0060	0.0070
						Feed 2 flutes (IPM)	42	53	70	66	98	86
						Feed 3 flutes (IPM)	63	79	106	99	147	128
		Profile	≤ 0.5	≤ 1.5	1080	RPM	33005	16502	11002	8251	5501	4126
					(864-1296)	Fz	0.0008	0.0020	0.0040	0.0050	0.0060	0.0070
						Feed 2 flutes (IPM)	53	66	88	83	66	58
						Feed 3 flutes (IPM)	79	99	132	124	99	87
		HSM	≤ 0.5	≤ 2	1780	RPM	54397	27198	18132	13599	9066	6800
					(1424-2136)	Fz	0.0017	0.0045	0.0085	0.0115	0.0140	0.0160
						Feed 2 flutes (IPM)	185	245	308	313	254	218
						Feed 3 flutes (IPM)	277	367	462	469	381	326

continued on next page

SGS SKI-CARB

Series 44, 45, 43CR, 43CB, 43LC, 43, 43L, 47, 47B, 47ES, 47EB Fractional		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	3/4	1
N	**COPPER ALLOYS Beryllium Copper C110, Maganese Bronze, Tin Bronze**	Slot	1	≤ 1	345	RPM	10543	5272	3514	2636	1757	1318
					(276-414)	Fz	0.0008	0.0020	0.0040	0.0050	0.0060	0.0070
						Feed 2 flutes (IPM)	17	21	28	26	21	18
						Feed 3 flutes (IPM)	25	32	42	40	32	28
		Profile	≤ 0.5	≤ 1.5	430	RPM	13141	6570	4380	3285	2190	1643
					(344-516)	Fz	0.0008	0.0020	0.0040	0.0050	0.0060	0.0070
						Feed 2 flutes (IPM)	21	26	35	33	26	23
						Feed 3 flutes (IPM)	32	39	53	49	39	34
		HSM	≤ 0.5	≤ 2	710	RPM	21698	10849	7233	5424	3616	2712
					(568-852)	Fz	0.0017	0.0045	0.0085	0.0115	0.0140	0.0160
						Feed 2 flutes (IPM)	74	98	123	125	101	87
						Feed 3 flutes (IPM)	111	146	184	187	152	130
	PLASTICS ABS, Polycarbonate, PVC, Polypropylene	Slot	1	≤ 1	1600	RPM	48896	24448	16299	12224	8149	6112
					(1280-1920)	Fz	0.0015	0.0040	0.0075	0.0100	0.0120	0.0140
						Feed 2 flutes (IPM)	147	196	244	244	196	171
						Feed 3 flutes (IPM)	220	293	367	367	293	257
		Profile	≤ 0.5	≤ 1.5	2000	RPM	61120	30560	20373	15280	10187	7640
					(1600-2400)	Fz	0.0015	0.0040	0.0075	0.0100	0.0120	0.0140
						Feed 2 flutes (IPM)	183	244	306	306	244	214
						Feed 3 flutes (IPM)	275	367	458	458	367	321
		HSM	≤ 0.5	≤ 2	3300	RPM	100848	50424	33616	25212	16808	12606
					(2640-3960)	Fz	0.0034	0.0090	0.0170	0.0230	0.0275	0.0320
						Feed 2 flutes (IPM)	686	908	1143	1160	924	807
						Feed 3 flutes (IPM)	1029	1361	1714	1740	1387	1210

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 44M, 43MCR, 43MCB, 43M, 47M, 47MB, 47MES, 47MEB Metric		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	10	12	20	25
N	ALUMINUM ALLOYS 2024, 5052, 5086, 6061, 6073, 7975	Slot	1	≤ 1	490	RPM	52022	26011	15607	13005	7803	6243
					(392-588)	Fz	0.022	0.060	0.120	0.144	0.187	0.213
						Feed 2 flutes (m/min)	2247	3121	3746	3745	2913	2653
						Feed 3 flutes (m/min)	3371	4682	5618	5618	4370	3980
		Profile	≤ 0.5	≤ 1.5	610	RPM	64762	32381	19429	16190	9714	7771
					(488-732)	Fz	0.022	0.060	0.120	0.144	0.187	0.213
						Feed 2 flutes (m/min)	2797	3885	4663	4662	3627	3303
						Feed 3 flutes (m/min)	4196	5828	6994	6994	5440	4955
		HSM	≤ 0.5	≤ 2	1005	RPM	106698	53349	32009	26674	16005	12804
					(804-1206)	Fz	0.050	0.132	0.280	0.336	0.440	0.488
						Feed 2 flutes (m/min)	10754	14083	17925	17924	14084	12484
						Feed 3 flutes (m/min)	16131	21124	26888	26885	21126	18726
N	ALUMINUM DIE CAST ALLOYS (HIGH SILICONE) A-390, A-392, B- 390	Slot	1	≤ 1	185	RPM	19641	9820	15607	13005	7803	6243
					(148-222)	Fz	0.022	0.060	0.120	0.144	0.187	0.213
						Feed 2 flutes (m/min)	848	1178	3746	3745	2913	2653
						Feed 3 flutes (m/min)	1273	1768	5618	5618	4370	3980
		Profile	≤ 0.5	≤ 1.5	230	RPM	24418	12209	7326	6105	3663	2930
					(184-276)	Fz	0.022	0.060	0.120	0.144	0.187	0.213
						Feed 2 flutes (m/min)	1055	1465	1758	1758	1367	1245
						Feed 3 flutes (m/min)	1582	2197	2637	2637	2051	1868
		HSM	≤ 0.5	≤ 2	380	RPM	40343	20172	12103	10086	6052	4841
					(304-456)	Fz	0.050	0.132	0.280	0.336	0.440	0.488
						Feed 2 flutes (m/min)	4066	5325	6778	6777	5325	4720
						Feed 3 flutes (m/min)	6099	7987	10166	10166	7988	7081
N	COPPER ALLOYS Aluminum Bronze Brass Naval Brass Red Brass	Slot	1	≤ 1	265	RPM	28134	14067	8440	7034	7803	6243
					(212-318)	Fz	0.019	0.048	0.107	0.120	0.160	0.175
						Feed 2 flutes (m/min)	1080	1350	1801	1688	2497	2185
						Feed 3 flutes (m/min)	1620	2025	2701	2532	3746	3278
		Profile	≤ 0.5	≤ 1.5	330	RPM	35035	17518	10511	8759	5255	4204
					(264-396)	Fz	0.019	0.048	0.107	0.120	0.160	0.175
						Feed 2 flutes (m/min)	1345	1682	2242	2102	1682	1472
						Feed 3 flutes (m/min)	2018	2522	3363	3153	2523	2207
		HSM	≤ 0.5	≤ 2	545	RPM	57861	28930	17358	14465	8679	6943
					(436-654)	Fz	0.041	0.108	0.227	0.276	0.373	0.400
						Feed 2 flutes (m/min)	4721	6248	7869	7984	6480	5555
						Feed 3 flutes (m/min)	7082	9373	11804	11976	9721	8332


continued on next page



Series 44M, 43MCR, 43MCB, 43M, 47M, 47MB, 47MES, 47MEB Metric			Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	10	12	20	25
N	COPPER ALLOYS Beryllium Copper C110, Maganese Bronze, Tin Bronze	Slot	1	≤ 1	105	RPM	11148	5574	3344	2787	1672	1338
					(84-126)	Fz	0.019	0.048	0.107	0.120	0.160	0.175
						Feed 2 flutes (m/min)	428	535	713	669	535	468
						Feed 3 flutes (m/min)	642	803	1070	1003	803	702
		Profile	≤ 0.5	≤ 1.5	130	RPM	13802	6901	4141	3450	2070	1656
					(104-156)	Fz	0.019	0.048	0.107	0.120	0.160	0.175
						Feed 2 flutes (m/min)	530	662	883	828	662	580
						Feed 3 flutes (m/min)	795	994	1325	1242	994	870
		HSM	≤ 0.5	≤ 2	215	RPM	22826	11413	6848	5706	3424	2739
					(172-258)	Fz	0.041	0.108	0.227	0.276	0.373	0.400
						Feed 2 flutes (m/min)	1862	2465	3104	3150	2556	2191
						Feed 3 flutes (m/min)	2794	3697	4656	4725	3835	3287
	PLASTICS ABS, Polycarbonate, PVC, Polypropylene	Slot	1	≤ 1	490	RPM	52022	26011	15607	13005	7803	6243
					(392-588)	Fz	0.036	0.096	0.200	0.240	0.320	0.350
						Feed 2 flutes (m/min)	3745	4994	6243	6242	4994	4370
						Feed 3 flutes (m/min)	5618	7490	9364	9363	7491	6555
		Profile	≤ 0.5	≤ 1.5	610	RPM	64762	32381	19429	16190	9714	7771
					(488-732)	Fz	0.036	0.096	0.200	0.240	0.320	0.350
						Feed 2 flutes (m/min)	4662	6217	7771	7771	6217	5440
						Feed 3 flutes (m/min)	6994	9325	11657	11656	9326	8160
		HSM	≤ 0.5	≤ 2	1005	RPM	106698	53349	32009	26674	16005	12804
					(804-1206)	Fz	0.082	0.216	0.453	0.552	0.733	0.800
						Feed 2 flutes (m/min)	17412	23045	29022	29446	23473	20487
						Feed 3 flutes (m/min)	26117	34567	43532	44169	35210	30730

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x number of flutes x rpm
HSM (high speed machining)
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

DYNAMITE CRYSTALLINE DIAMOND COATING




Series 27 Fractional		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	5/16	3/8	1/2	3/4
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Slot	1	≤ 1	400	RPM	6112	4890	4075	3056	2037
				(320-480)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	39.1	48.9	48.9	48.9	39.1
	Profile	≤ 0.5	≤ 1.5	500	RPM	7640	6112	5093	3820	2547
				(400-600)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	48.9	61.1	61.1	61.1	48.9
	HSM	≤ 0.5	≤ 2	825	RPM	12606	10085	8404	6303	4202
				(660-990)	Fz	0.0037	0.0057	0.0069	0.0092	0.0110
					Feed (IPM)	186.6	229.9	232.0	232.0	184.9
GFRP (FIBERGLASS)	Slot	1	≤ 1	320	RPM	4890	3912	3260	2445	1630
				(256-384)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	31.3	39.1	39.1	39.1	31.3
	Profile	≤ 0.5	≤ 1.5	400	RPM	6112	4890	4075	3056	2037
				(320-480)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	39.1	48.9	48.9	48.9	39.1
	HSM	≤ 0.5	≤ 2	660	RPM	10085	8068	6723	5042	3362
				(528-792)	Fz	0.0037	0.0057	0.0069	0.0092	0.0110
					Feed (IPM)	149.3	183.9	185.6	185.6	147.9
CARBON, GRAPHITE	Slot	1	≤ 1	480	RPM	7334	5868	4890	3667	2445
				(384-576)	Fz	0.0020	0.0031	0.0038	0.0050	0.0060
					Feed (IPM)	58.7	72.8	74.3	73.3	58.7
	Profile	≤ 0.5	≤ 1.5	600	RPM	9168	7334	6112	4584	3056
				(480-720)	Fz	0.0020	0.0031	0.0038	0.0050	0.0060
					Feed (IPM)	73.3	90.9	92.9	91.7	73.3
	HSM	≤ 0.5	≤ 2	990	RPM	15127	12102	10085	7564	5042
				(792-1188)	Fz	0.0046	0.0072	0.0086	0.0115	0.0138
					Feed (IPM)	278.3	348.5	346.9	347.9	278.3
PLASTICS	Slot	1	≤ 1	800	RPM	12224	9779	8149	6112	4075
				(640-690)	Fz	0.0020	0.0031	0.0038	0.0050	0.0060
					Feed (IPM)	97.8	121.3	123.9	122.2	97.8
	Profile	≤ 0.5	≤ 1.5	1000	RPM	15280	12224	10187	7640	5093
				(800-1200)	Fz	0.0020	0.0031	0.0038	0.0050	0.0060
					Feed (IPM)	122.2	151.6	154.8	152.8	122.2
	HSM	≤ 0.5	≤ 2	1650	RPM	25212	20170	16808	12606	8404
				(1320-1980)	Fz	0.0046	0.0072	0.0086	0.0115	0.0138
					Feed (IPM)	463.9	580.9	578.2	579.9	463.9
MACHINABLE CERAMICS MACHINABLE GLASS	Slot	1	≤ 1	40	RPM	611	489	407	306	204
				(32-48	Fz	0.0008	0.0013	0.0015	0.0020	0.0024
					Feed (IPM)	2.0	2.5	2.4	2.4	2.0
	Profile	≤ 0.5	≤ 1.5	50	RPM	764	611	509	382	255
				(40-60)	Fz	0.0008	0.0013	0.0015	0.0020	0.0024
					Feed (IPM)	2.4	3.2	3.1	3.1	2.4
	HSM	≤ 0.5	≤ 2	85	RPM	1299	1039	866	649	433
				(68-102)	Fz	0.0018	0.0029	0.0034	0.0046	0.0055
					Feed (IPM)	9.4	12.1	11.8	11.9	9.5

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur

finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

DYNAMITE CRYSTALLINE DIAMOND COATING





Series 27M Metric		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Slot	1	≤ 1	120	RPM	6361	4771	3817	3181	2385
				(96-164)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	1018	1240	1145	1272	1145
	Profile	≤ 0.5	≤ 1.5	150	RPM	7951	5963	4771	3976	2982
				(120-180)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	1272	1550	1431	1590	1431
	HSM	≤ 0.5	≤ 2	250	RPM	13252	9939	7951	6626	4970
				(200-300)	Fz	0.095	0.145	0.175	0.235	0.280
					Feed (mm/min)	5036	5765	5566	6228	5566
GFRP (FIBERGLASS)	Slot	1	≤ 1	100	RPM	5301	3976	3181	2650	1988
				(80-120)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	848	1034	954	1060	954
	Profile	≤ 0.5	≤ 1.5	120	RPM	6361	4771	3817	3181	2385
				(96-164)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	1018	1240	1145	1272	1145
	HSM	≤ 0.5	≤ 2	200	RPM	10602	7951	6361	5301	3976
				(160-240)	Fz	0.095	0.145	0.175	0.235	0.280
					Feed (mm/min)	4029	4612	4453	4983	4453
CARBON, GRAPHITE	Slot	1	≤ 1	145	RPM	7686	5765	4612	3843	2882
				(116-174)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	1537	1845	1752	1922	1729
	Profile	≤ 0.5	≤ 1.5	185	RPM	9807	7355	5884	4903	3677
				(148-222)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	1961	2354	2236	2452	2206
	HSM	≤ 0.5	≤ 2	300	RPM	15903	11927	9542	7951	5963
				(240-360)	Fz	0.115	0.185	0.220	0.290	0.350
					Feed (mm/min)	7315	8826	8397	9223	8349
PLASTICS	Slot	1	≤ 1	245	RPM	12987	9740	7792	6494	4870
				(196-294)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	2597	3117	2961	3247	2922
	Profile	≤ 0.5	≤ 1.5	305	RPM	16168	12126	9701	8084	6063
				(244-366)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	3234	3880	3686	4042	3638
	HSM	≤ 0.5	≤ 2	505	RPM	26769	20077	16062	13385	10038
				(404-606)	Fz	0.115	0.185	0.220	0.290	0.350
					Feed (mm/min)	12314	14857	14134	15526	14054
MACHINABLE CERAMICS MACHINABLE GLASS	Slot	1	≤ 1	10	RPM	530	398	318	265	199
				(8-12)	Fz	0.020	0.035	0.040	0.050	0.060
					Feed (mm/min)	42	56	51	53	48
	Profile	≤ 0.5	≤ 1.5	15	RPM	795	596	477	398	298
				(12-18)	Fz	0.020	0.035	0.040	0.050	0.060
					Feed (mm/min)	64	83	76	80	72
	HSM	≤ 0.5	≤ 2	25	RPM	1325	994	795	663	497
				(20-30)	Fz	0.045	0.075	0.085	0.115	0.140
					Feed (mm/min)	239	298	270	305	278

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur

finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)







16
FRACTIONAL SERIES

TECH INFO 139

TOLERANCES (inch)

D_1 = +0.0000/–0.0020
D_2 = h_6

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/16	1/8	1-1/2	1/8	31601	31650	31238	31251
3/32	3/16	1-1/2	1/8	31603	31651	31239	31252
1/8	1/4	1-1/2	1/8	31605	31652	31240	31253
5/32	5/16	2	3/16	31607	31653	31241	31254
3/16	3/8	2	3/16	31609	31654	31242	31255
7/32	7/16	2	1/4	31611	31655	31243	31256
1/4	1/2	2	1/4	31613	31656	31244	31257
5/16	1/2	2	5/16	31615	31657	31245	31258
3/8	5/8	2	3/8	31617	31658	31246	31259
7/16	5/8	2-1/2	7/16	31619	31659	31247	31260
1/2	5/8	2-1/2	1/2	31621	31660	31248	31261
5/8	3/4	3	5/8	31623	31661	31249	31262
3/4	1	3	3/4	31625	31662	31250	31263

16M
METRIC SERIES


TECH INFO 141

TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED EDP NO.	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41605	49136	49157	49178
1,5	3,0	38,0	3,0	41609	49137	49158	49179
2,0	4,0	38,0	3,0	41613	49138	49159	49180
2,5	5,0	38,0	3,0	41617	49139	49160	49181
3,0	6,0	38,0	3,0	41621	49140	49161	49182
3,5	7,0	50,0	4,0	41625	49141	49162	49183
4,0	8,0	50,0	4,0	41629	49142	49163	49184
4,5	9,5	50,0	4,5	41633	49143	49164	49185
5,0	10,0	50,0	5,0	41637	49144	49165	49186
6,0	12,0	50,0	6,0	41641	49145	49166	49187
7,0	12,0	50,0	8,0	41645	49146	49167	49188
8,0	12,0	50,0	8,0	41649	49147	49168	49189
9,0	14,0	50,0	9,0	41653	49148	49169	49190
10,0	16,0	50,0	10,0	41657	49149	49170	49191
11,0	19,0	63,0	12,0	41661	49150	49171	49192
12,0	19,0	63,0	12,0	40165	49151	49172	49193






TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6



1 • 1L • 1EL

FRACTIONAL SERIES


TECH INFO 139

inch				EDP NO.							SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	UNCOATED W/FLAT	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	Di-NAMITE (Diamond)	
1/64	1/32	1-1/2	1/8	30101	–	39101	39001	30191	–	–	1
1/32	5/64	1-1/2	1/8	30103	–	39103	39003	30192	–	–	1
3/64	7/64	1-1/2	1/8	30105	–	39105	39005	30193	–	–	1
1/16	3/16	1-1/2	1/8	30107	–	39107	39007	30194	–	91268	1
5/64	3/16	1-1/2	1/8	30109	–	39109	39009	30195	–	–	1
3/32	9/32	1-1/2	1/8	30111	–	39111	39011	30196	–	–	1
7/64	3/8	1-1/2	1/8	30113	–	39113	39013	30197	–	–	1
1/8	3/8	1-1/2	1/8	30177	–	39177	39077	30029	–	–	1
*1/8	1/2	1-1/2	1/8	30115	–	39115	39015	30198	–	91272	1
1/8	3/4	2-1/4	1/8	33141	–	31727	31737	31747	–	–	1L
1/8	1	3	1/8	33143	–	31860	31870	31880	–	–	1EL
9/64	1/2	2	3/16	30117	–	39117	39017	30199	–	–	1
5/32	1/2	2	3/16	30119	–	39119	39019	30000	–	–	1
11/64	5/8	2	3/16	30121	–	39121	39021	30001	–	–	1
*3/16	5/8	2	3/16	30123	–	39123	39023	30002	–	91276	1
3/16	3/4	2-1/2	3/16	33101	–	31728	31738	31748	–	–	1L
3/16	1-1/8	3	3/16	33121	–	31861	31871	31881	–	–	1EL
13/64	5/8	2-1/2	1/4	30125	–	39125	39025	30003	–	–	1
7/32	5/8	2-1/2	1/4	30127	–	39127	39027	30004	–	–	1
15/64	3/4	2-1/2	1/4	30129	–	39129	39029	30005	–	–	1
*1/4	3/4	2-1/2	1/4	30131	–	39131	39031	30006	–	91280	1
1/4	1-1/8	3	1/4	33103	–	31729	31739	31749	–	–	1L
1/4	1-1/2	4	1/4	33123	–	31862	31872	31882	–	–	1EL
17/64	3/4	2-1/2	5/16	30133	–	39133	39033	30007	–	–	1
9/32	3/4	2-1/2	5/16	30135	–	39135	39035	30008	–	–	1
19/64	13/16	2-1/2	5/16	30137	–	39137	39037	30009	–	–	1
*5/16	13/16	2-1/2	5/16	30139	–	39139	39039	30010	–	91284	1
5/16	1-1/8	3	5/16	33105	–	31730	31740	31763	–	–	1L
5/16	1-5/8	4	5/16	33125	–	31863	31873	31883	–	–	1EL
21/64	1	2-1/2	3/8	30141	–	39141	39041	30011	–	–	1
11/32	1	2-1/2	3/8	30143	–	39143	39043	30012	–	–	1
23/64	1	2-1/2	3/8	30145	–	39145	39045	30013	–	–	1
*3/8	1	2-1/2	3/8	30147	30179	39147	39047	30014	30379	91288	1
3/8	1-1/8	3	3/8	33107	–	31731	31741	31764	–	–	1L
3/8	1-3/4	4	3/8	33127	–	31864	31874	31884	–	–	1EL
25/64	1	2-3/4	7/16	30149	–	39149	39049	30015	–	–	1

continued on next page


- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES





1 • 1L • 1EL

FRACTIONAL SERIES



TOLERANCES (inch)

D_1 = +0.0000/–0.0020


D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.							SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	UNCOATED W/FLAT	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	Di-NAMITE (Diamond)	
13/32	1	2-3/4	7/16	30151	–	39151	39051	30016	–	–	1
27/64	1	2-3/4	7/16	30153	–	39153	39053	30017	–	–	1
7/16	1	2-3/4	7/16	30155	–	39155	39055	30018	–	–	1
7/16	2	4-1/2	7/16	33109	–	31732	31742	31765	–	–	1L
7/16	3	6	7/16	33129	–	31865	31875	31885	–	–	1EL
29/64	1	3	1/2	30157	–	39157	39057	30019	–	–	1
15/32	1	3	1/2	30159	–	39159	39059	30020	–	–	1
31/64	1	3	1/2	30161	–	39161	39061	30021	–	–	1
1/2	1	3	1/2	30163	30180	39163	39063	30022	30380	91292	1
1/2	2	4-1/2	1/2	33111	–	31733	31743	31766	–	–	1L
1/2	3	6	1/2	33131	–	31866	31876	31886	–	–	1EL
9/16	1-1/8	3-1/2	9/16	30165	–	39165	39065	30023	–	–	1
5/8	1-1/4	3-1/2	5/8	30167	30181	39167	39067	30024	30381	–	1
5/8	2-1/4	5	5/8	33113	–	31734	31744	31767	–	–	1L
5/8	3	6	5/8	33133	–	31867	31877	31887	–	–	1EL
11/16	1-3/8	4	3/4	30169	–	39169	39069	30025	–	–	1
3/4	1-1/2	4	3/4	30171	30182	39171	39071	30026	30382	–	1
3/4	2-1/4	5	3/4	33115	–	31735	31745	31768	–	–	1L
3/4	3	6	3/4	33135	–	31868	31878	31888	–	–	1EL
7/8	1-1/2	4	7/8	30173	–	39173	39073	30027	–	–	1
1	1-1/2	4	1	30175	30183	39175	39075	30028	30383	–	1
1	2-1/4	5	1	33117	–	31736	31746	31769	–	–	1L
1	3	6	1	33137	–	31869	31879	31889	–	–	1EL
*Series 1 Set				30189	–	39189	39089	30030	–	–	1






TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6



1M • 1XLM

METRIC SERIES


TECH INFO 141

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED EDP NO.	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40105	48500	48522	48543	1M
1,5	4,5	38,0	3,0	40109	48501	48523	48544	1M
2,0	6,3	38,0	3,0	40113	48502	48524	48545	1M
2,5	9,5	38,0	3,0	40117	48503	48525	48546	1M
3,0	12,0	38,0	3,0	40121	48504	48526	48547	1M
3,0	25,0	75,0	3,0	43101	49388	49401	49414	1XLM
3,5	12,0	50,0	4,0	40125	48505	48527	48548	1M
4,0	14,0	50,0	4,0	40129	48506	48528	48549	1M
4,0	25,0	75,0	4,0	43103	49389	49402	49415	1XLM
4,5	16,0	50,0	6,0	40133	48507	48529	48550	1M
5,0	16,0	50,0	6,0	40137	48508	48530	48551	1M
5,0	25,0	75,0	5,0	43107	49391	49404	49417	1XLM
6,0	19,0	50,0	6,0	40141	48509	48531	48552	1M
6,0	25,0	75,0	6,0	43105	49390	49403	49416	1XLM
7,0	19,0	63,0	8,0	40145	48510	48532	48553	1M
8,0	20,0	63,0	8,0	40149	48511	48533	48554	1M
8,0	25,0	75,0	8,0	43115	49392	49405	49418	1XLM
9,0	22,0	75,0	10,0	40153	48512	48534	48555	1M
10,0	22,0	75,0	10,0	40157	48513	48535	48556	1M
10,0	38,0	100,0	10,0	43125	49393	49406	49419	1XLM
11,0	25,0	75,0	12,0	40161	48514	48536	48557	1M
12,0	25,0	75,0	12,0	41665	48515	48537	48558	1M
12,0	50,0	100,0	12,0	43135	49394	49407	49420	1XLM
12,0	75,0	150,0	12,0	43145	49395	49408	49421	1XLM
14,0	32,0	89,0	14,0	40169	48516	48538	48559	1M
14,0	75,0	150,0	14,0	43155	49396	49409	49422	1XLM
16,0	32,0	89,0	16,0	40173	48517	48539	48560	1M
16,0	75,0	150,0	16,0	43165	49397	49410	49423	1XLM
18,0	38,0	100,0	18,0	40177	48518	48540	48561	1M
18,0	75,0	150,0	18,0	43175	49398	49411	49424	1XLM
20,0	38,0	100,0	20,0	40181	48519	48541	48562	1M
20,0	75,0	150,0	20,0	43185	49399	49412	49425	1XLM
25,0	38,0	100,0	25,0	40185	48520	48542	48563	1M
25,0	75,0	150,0	25,0	43195	49400	49413	49426	1XLM

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES







14
FRACTIONAL SERIES

TOLERANCES (inch)


D_1 = +0.0000/–0.0020
D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/32	1/16	1-1/2	1/8	31401	31441	39601	31170
3/64	3/32	1-1/2	1/8	31403	31443	39603	31171
1/16	1/8	1-1/2	1/8	31405	31445	39605	31172
5/64	1/8	1-1/2	1/8	31407	31447	39607	31173
3/32	3/16	1-1/2	1/8	31409	31449	39609	31174
7/64	3/16	1-1/2	1/8	31411	31451	39611	31175
1/8	1/4	1-1/2	1/8	31413	31453	39613	31176
9/64	5/16	2	3/16	31415	31455	39615	31177
5/32	5/16	2	3/16	31417	31457	39617	31178
11/64	5/16	2	3/16	31419	31459	39619	31179
3/16	3/8	2	3/16	31421	31461	39621	31180
13/64	1/2	2-1/2	1/4	31423	31463	39623	31181
7/32	1/2	2-1/2	1/4	31425	31465	39625	31182
15/64	1/2	2-1/2	1/4	31427	31467	39627	31183
1/4	1/2	2-1/2	1/4	31429	31469	39629	31184
9/32	1/2	2-1/2	5/16	31431	31471	39631	31185
5/16	1/2	2-1/2	5/16	31433	31473	39633	31186
3/8	9/16	2-1/2	3/8	31435	31475	39635	31187
7/16	9/16	2-3/4	7/16	31437	31477	39637	31188
1/2	5/8	3	1/2	31439	31479	39639	31189





TOLERANCES (mm)


D_1 = +0,000/–0,050
D_2 = h_6

14M
METRIC SERIES

TECH INFO 141

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41405	48884	48905	48926
1,5	3,0	38,0	3,0	41409	48885	48906	48927
2,0	4,0	38,0	3,0	41413	48886	48907	48928
2,5	5,0	38,0	3,0	41417	48887	48908	48929
3,0	6,0	38,0	3,0	41421	48888	48909	48930
3,5	7,0	50,0	4,0	41425	48889	48910	48931
4,0	8,0	50,0	4,0	41429	48890	48911	48932
4,5	9,5	63,0	4,5	41433	48891	48912	48933
5,0	10,0	63,0	5,0	41437	48892	48913	48934
6,0	12,0	63,0	6,0	41441	48893	48914	48935
7,0	12,0	63,0	8,0	41445	48894	48915	48936
8,0	12,0	63,0	8,0	41449	48895	48916	48937
9,0	14,0	75,0	9,0	41453	48896	48917	48938
10,0	14,0	75,0	10,0	41457	48897	48918	48939
11,0	14,0	75,0	12,0	41461	48898	48919	48940
12,0	16,0	75,0	12,0	41465	48899	48920	48941


- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES





1B • 1LB • 1ELB

FRACTIONAL SERIES



TOLERANCES (inch)

D_1 = +0.0000/–0.0020


D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.							SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	UNCOATED W/FLAT	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	Di-NAMITE (Diamond)	
1/64	1/32	1-1/2	1/8	30102	–	39102	39002	30031	–	–	1B
1/32	5/64	1-1/2	1/8	30104	–	39104	39004	30032	–	–	1B
3/64	7/64	1-1/2	1/8	30106	–	39106	39006	30033	–	–	1B
1/16	3/16	1-1/2	1/8	30108	–	39108	39008	30034	–	91269	1B
5/64	3/16	1-1/2	1/8	30110	–	39110	39010	30035	–	–	1B
3/32	9/32	1-1/2	1/8	30112	–	39112	39012	30036	–	–	1B
7/64	3/8	1-1/2	1/8	30114	–	39114	39014	30037	–	–	1B
*1/8	3/8	1-1/2	1/8	30069	–	39178	39078	–	–	–	1B
1/8	1/2	1-1/2	1/8	30116	–	39116	39016	30038	–	91273	1B
1/8	3/4	2-1/4	1/8	33142	–	31770	31780	31790	–	–	1LB
1/8	1	3	1/8	33144	–	31900	31918	31928	–	–	1ELB
9/64	1/2	2	3/16	30118	–	39118	39018	30039	–	–	1B
5/32	1/2	2	3/16	30120	–	39120	39020	30040	–	–	1B
11/64	5/8	2	3/16	30122	–	39122	39022	30041	–	–	1B
*3/16	5/8	2	3/16	30124	–	39124	39024	30042	–	–	1B
3/16	3/4	2-1/2	3/16	33102	–	31771	31781	31791	–	91277	1LB
3/16	1-1/8	3	3/16	33122	–	31902	31919	31929	–	–	1ELB
13/64	5/8	2-1/2	1/4	30126	–	39126	39026	30043	–	–	1B
7/32	5/8	2-1/2	1/4	30128	–	39128	39028	30044	–	–	1B
15/64	3/4	2-1/2	1/4	30130	–	39130	39030	30045	–	–	1B
*1/4	3/4	2-1/2	1/4	30132	–	39132	39032	30046	–	91281	1B
1/4	1-1/8	3	1/4	33104	–	31772	31782	31792	–	–	1LB
1/4	1-1/2	4	1/4	33124	–	31904	31920	31930	–	–	1ELB
17/64	3/4	2-1/2	5/16	30134	–	39134	39034	30047	–	–	1B
9/32	3/4	2-1/2	5/16	30136	–	39136	39036	30048	–	–	1B
19/64	13/16	2-1/2	5/16	30138	–	39138	39038	30049	–		1B
*5/16	13/16	2-1/2	5/16	30140	–	39140	39040	30050	–	91285	1B
5/16	1-1/8	3	5/16	33106	–	31773	31783	31793	–	–	1LB

continued on next page



1B • 1LB • 1ELB


FRACTIONAL SERIES

CONTINUED

inch				EDP NO.							SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	UNCOATED W/FLAT	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Ti-NAMITE-A (AlTiN) W/FLAT	Di-NAMITE (Diamond)	
5/16	1-5/8	4	5/16	33126	–	31906	31921	31931	–	–	1ELB
21/64	1	2-1/2	3/8	30142	–	39142	39042	30051	–	–	1B
11/32	1	2-1/2	3/8	30144	–	39144	39044	30052	–	–	1B
23/64	1	2-1/2	3/8	30146	–	39146	39046	30053	–	–	1B
*3/8	1	2-1/2	3/8	30148	30184	39148	39048	30054	30384	91289	1B
3/8	1-1/8	3	3/8	33108	–	31774	31784	31794	–	–	1LB
3/8	1-3/4	4	3/8	33128	–	31908	31922	31932	–	–	1ELB
25/64	1	2-3/4	7/16	30150	–	39150	39050	30055	–	–	1B
13/32	1	2-3/4	7/16	30152	–	39152	39052	30056	–	–	1B
27/64	1	2-3/4	7/16	30154	–	39154	39054	30057	–	–	1B
7/16	1	2-3/4	7/16	30156	–	39156	39056	30058	–	–	1B
7/16	2	4-1/2	7/16	33110	–	31775	31785	31795	–	–	1LB
7/16	3	6	7/16	33130	–	31910	31923	31933	–	–	1ELB
29/64	1	3	1/2	30158	–	39158	39058	30059	–	–	1B
15/32	1	3	1/2	30160	–	39160	39060	30060	–	–	1B
31/64	1	3	1/2	30162	–	39162	39062	30061	–	–	1B
*1/2	1	3	1/2	30164	30185	39164	39064	30062	30385	91293	1B
1/2	2	4-1/2	1/2	33112	–	31776	31786	31796	–	–	1LB
1/2	3	6	1/2	33132	–	31912	31924	31934	–	–	1ELB
9/16	1-1/8	3-1/2	9/16	30166	–	39166	39066	30063	–	–	1B
5/8	1-1/4	3-1/2	5/8	30168	30186	39168	39068	30064	30386	–	1B
5/8	2-1/4	5	5/8	33114	–	31777	31787	31797	–	–	1LB
5/8	3	6	5/8	33134	–	31914	31925	31935	–	–	1ELB
11/16	1-3/8	4	3/4	30170	–	39170	39070	30065	–	–	1B
3/4	1-1/2	4	3/4	30172	30187	39172	39072	30066	30387	–	1B
3/4	2-1/4	5	3/4	33116	–	31778	31788	31798	–	–	1LB
3/4	3	6	3/4	33136	–	31916	31926	31936	–	–	1ELB
7/8	1-1/2	4	7/8	30174	–	39174	39074	30067	–	–	1B
1	1-1/2	4	1	30176	30188	39176	39076	30068	30388	–	1B
1	2-1/4	5	1	33118	–	31779	31789	31799	–	–	1LB
1	3	6	1	33138	–	31917	31927	31937	–	–	1ELB
*Series 1B Set				30190	–	39190	39090	30070	–	–	1B



1MB


1XLMB



1MB • 1XLMB

METRIC SERIES



TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6

TECH INFO 141

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED EDP NO.	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40106	48564	48586	48607	1MB
1,5	4,5	38,0	3,0	40110	48565	48587	48608	1MB
2,0	6,3	38,0	3,0	40114	48566	48588	48609	1MB
2,5	9,5	38,0	3,0	40118	48567	48589	48610	1MB
3,0	12,0	38,0	3,0	40122	48568	48590	48611	1MB
3,0	25,0	75,0	3,0	43102	49505	49518	49531	1XLMB
3,5	12,0	50,0	4,0	40126	48569	48591	48612	1MB
4,0	14,0	50,0	4,0	40130	48570	48592	48613	1MB
4,0	25,0	75,0	4,0	43104	49506	49519	49532	1XLMB
4,5	16,0	50,0	6,0	40134	48571	48593	48614	1MB
5,0	16,0	50,0	6,0	40138	48572	48594	48615	1MB
5,0	25,0	75,0	5,0	43108	49508	49521	49534	1XLMB
6,0	19,0	50,0	6,0	40142	48573	48595	48616	1MB
6,0	25,0	75,0	6,0	43106	49507	49520	49533	1XLMB
7,0	19,0	63,0	8,0	40146	48574	48596	48617	1MB
8,0	20,0	63,0	8,0	40150	48575	48597	48618	1MB
8,0	25,0	75,0	8,0	43116	49509	49522	49535	1XLMB
9,0	22,0	75,0	10,0	40154	48576	48598	48619	1MB
10,0	22,0	75,0	10,0	40158	48577	48599	48620	1MB
10,0	38,0	100,0	10,0	43126	49510	49523	49536	1XLMB
11,0	25,0	75,0	12,0	40162	48578	48600	48621	1MB
12,0	25,0	75,0	12,0	40166	48579	48601	48622	1MB
12,0	50,0	100,0	12,0	43136	49511	49524	49537	1XLMB
12,0	75,0	150,0	12,0	43146	49512	49525	49538	1XLMB
14,0	32,0	89,0	14,0	40170	48580	48602	48623	1MB
14,0	75,0	150,0	14,0	43156	49513	49526	49539	1XLMB
16,0	32,0	89,0	16,0	40174	48581	48603	48624	1MB
16,0	75,0	150,0	16,0	43166	49514	49527	49540	1XLMB
18,0	38,0	100,0	18,0	40178	48582	48604	48625	1MB
18,0	75,0	150,0	18,0	43176	49515	49528	49541	1XLMB
20,0	38,0	100,0	20,0	40182	48583	48605	48626	1MB
20,0	75,0	150,0	20,0	43186	49516	49529	49542	1XLMB
25,0	38,0	100,0	25,0	40186	48584	48606	48627	1MB
25,0	75,0	150,0	25,0	43196	49517	49530	49543	1XLMB






TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6



14B
FRACTIONAL SERIES


TECH INFO 139

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/32	1/16	1-1/2	1/8	31402	31442	39602	31218
3/64	3/32	1-1/2	1/8	31404	31444	39604	31219
1/16	1/8	1-1/2	1/8	31406	31446	39606	31220
5/64	1/8	1-1/2	1/8	31408	31448	39608	31221
3/32	3/16	1-1/2	1/8	31410	31450	39610	31222
7/64	3/16	1-1/2	1/8	31412	31452	39612	31223
*1/8	1/4	1-1/2	1/8	31414	31454	39614	31224
9/64	5/16	2	3/16	31416	31456	39616	31225
5/32	5/16	2	3/16	31418	31458	39618	31226
11/64	5/16	2	3/16	31420	31460	39620	31227
*3/16	3/8	2	3/16	31422	31462	39622	31228
13/64	1/2	2-1/2	1/4	31424	31464	39624	31229
7/32	1/2	2-1/2	1/4	31426	31466	39626	31230
15/64	1/2	2-1/2	1/4	31428	31468	39628	31231
*1/4	1/2	2-1/2	1/4	31430	31470	39630	31232
9/32	1/2	2-1/2	5/16	31432	31472	39632	31233
*5/16	1/2	2-1/2	5/16	31434	31474	39634	31234
*3/8	9/16	2-1/2	3/8	31436	31476	39636	31235
7/16	9/16	2-3/4	7/16	31438	31478	39638	31236
*1/2	5/8	3	1/2	31440	31480	39640	31237
*Series 14B Set				31490	31482	39642	31217

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES







14MB
METRIC SERIES


TOLERANCES (mm)
D_1 = +0,000/–0,050
D_2 = h_6

TECH INFO 141

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES


mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41406	48947	48968	48989
1,5	3,0	38,0	3,0	41410	48948	48969	48990
2,0	4,0	38,0	3,0	41414	48949	48970	48991
2,5	5,0	38,0	3,0	41418	48950	48971	48992
3,0	6,0	38,0	3,0	41422	48951	48972	48993
3,5	7,0	50,0	4,0	41426	48952	48973	48994
4,0	8,0	50,0	4,0	41430	48953	48974	48995
4,5	9,5	63,0	4,5	41434	48954	48975	48996
5,0	10,0	63,0	5,0	41438	48955	48976	48997
6,0	12,0	63,0	6,0	41442	48956	48977	48998
7,0	12,0	63,0	8,0	41446	48957	48978	48999
8,0	12,0	63,0	8,0	41450	48958	48979	49000
9,0	14,0	75,0	9,0	41454	48959	48980	49001
10,0	14,0	75,0	10,0	41458	48960	48981	49002
11,0	14,0	75,0	12,0	41462	48961	48982	49003
12,0	16,0	75,0	12,0	41466	48962	48983	49004





TOLERANCES (inch)

D_1 = –0.0010/–0.0020
D_2 = h_6
R = +0.0000/–0.0020



1CR
FRACTIONAL SERIES

TECH INFO 139


inch					EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/8*	1/2	1-1/2	1/8	.015	38001	38002	38115	38157
1/8*	1/2	1-1/2	1/8	.020	38003	38004	38116	38158
3/16*	5/8	2	3/16	.015	38009	38010	38117	38159
3/16*	5/8	2	3/16	.020	38011	38012	38118	38160
3/16*	5/8	2	3/16	.030	38013	38014	38119	38161
1/4*	3/4	2-1/2	1/4	.015	38019	38020	38120	38162
1/4*	3/4	2-1/2	1/4	.020	38021	38022	38121	38163
1/4*	3/4	2-1/2	1/4	.030	38023	38024	38122	38164
1/4*	3/4	2-1/2	1/4	.045	38025	38026	38123	38165
5/16*	13/16	2-1/2	5/16	.015	38031	38032	38124	38166
5/16*	13/16	2-1/2	5/16	.020	38033	38034	38125	38167
5/16*	13/16	2-1/2	5/16	.030	38035	38036	38126	38168
5/16*	13/16	2-1/2	5/16	.045	38037	38038	38127	38169
3/8	1	2-1/2	3/8	.015	38045	38046	38128	38170
3/8	1	2-1/2	3/8	.020	38047	38048	38129	38171
3/8	1	2-1/2	3/8	.030	38049	38050	38130	38172
3/8	1	2-1/2	3/8	.045	38051	38052	38131	38173
1/2	1	3	1/2	.015	38059	38060	38132	38174
1/2	1	3	1/2	.020	38061	38062	38133	38175
1/2	1	3	1/2	.030	38063	38064	38134	38176
1/2	1	3	1/2	.045	38065	38066	38135	38177
1/2	1	3	1/2	.060	38067	38068	38136	38178
5/8	1-1/4	3-1/2	5/8	.015	38073	38074	38137	38179
5/8	1-1/4	3-1/2	5/8	.020	38075	38076	38138	38180
5/8	1-1/4	3-1/2	5/8	.030	38077	38078	38139	38181
5/8	1-1/4	3-1/2	5/8	.045	38079	38080	38140	38182
5/8	1-1/4	3-1/2	5/8	.060	38081	38082	38141	38183
5/8	1-1/4	3-1/2	5/8	.090	38083	38084	38142	38184
3/4	1-1/2	4	3/4	.015	38087	38088	38143	38185
3/4	1-1/2	4	3/4	.020	38089	38090	38144	38186


*Without Flat

continued on next page

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES







1CR
FRACTIONAL SERIES

TOLERANCES (inch)

D_1 = −0.0010/−0.0020
D_2 = h_6
R = +0.0000/−0.0020

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES


inch					EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
3/4	1-1/2	4	3/4	.030	38091	38092	38145	38187
3/4	1-1/2	4	3/4	.045	38093	38094	38146	38188
3/4	1-1/2	4	3/4	.060	38095	38096	38147	38189
3/4	1-1/2	4	3/4	.090	38097	38098	38148	38190
3/4	1-1/2	4	3/4	.125	38099	38100	38149	38191
1	1-1/2	4	1	.015	38101	38102	38150	38192
1	1-1/2	4	1	.020	38103	38104	38151	38193
1	1-1/2	4	1	.030	38105	38106	38152	38194
1	1-1/2	4	1	.045	38107	38108	38153	38195
1	1-1/2	4	1	.060	38109	38110	38154	38196
1	1-1/2	4	1	.090	38111	38112	38155	38197
1	1-1/2	4	1	.125	38113	38114	38156	38198





TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6
R = +0,000/–0,050



1MCR
METRIC SERIES


TECH INFO 141

mm					EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	CORNER RADIUS R	SHANK DIAMETER D_2	Ti-NAMITE-A (AlTiN)
4,0	14,0	50,0	0,25	4,0	40000
4,0	14,0	50,0	0,50	4,0	40001
4,0	14,0	50,0	1,00	4,0	40003
5,0	16,0	50,0	0,25	6,0	40004
5,0	16,0	50,0	0,50	6,0	40005
5,0	16,0	50,0	1,00	6,0	40007
6,0	19,0	50,0	0,25	6,0	40009
6,0	19,0	50,0	0,50	6,0	40010
6,0	19,0	50,0	0,75	6,0	40011
6,0	19,0	50,0	1,00	6,0	40012
8,0	20,0	63,0	0,50	8,0	40015
8,0	20,0	63,0	0,75	8,0	40016
8,0	20,0	63,0	1,00	8,0	40017
8,0	20,0	63,0	1,50	8,0	40019
8,0	20,0	63,0	2,00	8,0	40020
10,0	22,0	75,0	0,50	10,0	40021
10,0	22,0	75,0	1,00	10,0	40023
10,0	22,0	75,0	1,50	10,0	40024
10,0	22,0	75,0	2,00	10,0	40025
12,0	25,0	75,0	0,50	12,0	40028
12,0	25,0	75,0	1,00	12,0	40030
12,0	25,0	75,0	1,50	12,0	40031
12,0	25,0	75,0	2,00	12,0	40032
16,0	32,0	89,0	0,50	16,0	40035
16,0	32,0	89,0	1,00	16,0	40037
16,0	32,0	89,0	1,50	16,0	40038
16,0	32,0	89,0	2,00	16,0	40039

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES







54
FRACTIONAL SERIES

TECH INFO 144

TOLERANCES (inch)

D1 = +0.0000/–0.0020

D2 = h_6

NON-FERROUS

PLASTICS/COMPOSITES

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-C (TiCN)
1/16	3/16	1-1/2	1/8	35473	35500
3/32	3/8	1-1/2	1/8	35475	35501
1/8	7/16	1-1/2	1/8	35477	35502
5/32	9/16	2	3/16	35478	35503
3/16	9/16	2	3/16	35479	35504
7/32	5/8	2-1/2	1/4	35480	35505
1/4	3/4	2-1/2	1/4	35481	35506
9/32	3/4	2-1/2	5/16	35482	35507
5/16	13/16	2-1/2	5/16	35483	35508
3/8	7/8	2-1/2	3/8	35485	35509
7/16	1	2-3/4	7/16	35487	35510
1/2	1	3	1/2	35489	35511
9/16	1-1/8	3-1/2	9/16	35491	35512
5/8	1-1/4	3-1/2	5/8	35493	35513
3/4	1-1/2	4	3/4	35495	35514
1	1-1/2	4	1	35497	35515

54M
METRIC SERIES

TECH INFO 145

TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6


mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-C (TiCN)
3,0	8,0	38,0	3,0	45477	45478
3,5	10,0	57,0	6,0	45479	45480
4,0	11,0	57,0	6,0	45481	45482
4,5	11,0	57,0	6,0	45483	45484
5,0	13,0	57,0	6,0	45485	45486
6,0	13,0	57,0	6,0	45487	45488
8,0	19,0	63,0	8,0	45489	45490
10,0	22,0	72,0	10,0	45491	45492
12,0	26,0	83,0	12,0	45493	45494
14,0	26,0	83,0	14,0	45495	45496
16,0	32,0	92,0	16,0	45497	45498
20,0	38,0	104,0	20,0	45499	45500





TOLERANCES (inch)

D1 = +0.0000/–0.0020
D2 = h_6



17
FRACTIONAL SERIES

TECH INFO 139

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/16	1/8	1-1/2	1/8	31701	31750	31303	31358
3/32	3/16	1-1/2	1/8	31703	31751	31304	31359
1/8	1/4	1-1/2	1/8	31705	31752	31305	31360
5/32	5/16	2	3/16	31707	31753	31306	31361
3/16	3/8	2	3/16	31709	31754	31307	31362
7/32	7/16	2	1/4	31711	31755	31308	31363
1/4	1/2	2	1/4	31713	31756	31309	31364
5/16	1/2	2	5/16	31715	31757	31310	31365
3/8	5/8	2	3/8	31717	31758	31311	31366
7/16	5/8	2-1/2	7/16	31719	31759	31312	31367
1/2	5/8	2-1/2	1/2	31721	31760	31313	31368
5/8	3/4	3	5/8	31723	31761	31314	31369
3/4	1	3	3/4	31725	31762	31315	31370

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES


TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6

17M
METRIC SERIES

TECH INFO 141


mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41705	49262	49283	49304
1,5	3,0	38,0	3,0	41709	49263	49284	49305
2,0	4,0	38,0	3,0	41713	49264	49285	49306
2,5	5,0	38,0	3,0	41717	49265	49286	49307
3,0	6,0	38,0	3,0	41721	49266	49287	49308
3,5	7,0	50,0	4,0	41725	49267	49288	49309
4,0	8,0	50,0	4,0	41729	49268	49289	49310
4,5	9,5	50,0	4,5	41733	49269	49290	49311
5,0	10,0	50,0	5,0	41737	49270	49291	49312
6,0	12,0	50,0	6,0	41741	49271	49292	49313
7,0	12,0	50,0	8,0	41745	49272	49293	49314
8,0	12,0	50,0	8,0	41749	49273	49294	49315
9,0	14,0	50,0	9,0	41753	49274	49295	49316
10,0	16,0	50,0	10,0	41757	49275	49296	49317
11,0	19,0	63,0	12,0	41761	49276	49297	49318
12,0	19,0	63,0	12,0	41765	49277	49298	49319





3 • 3L • 3EL

FRACTIONAL SERIES



TOLERANCES (inch)

D_1 = +0.0000/–0.0020


D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.					SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Di-NAMITE (Diamond)	
1/64	1/32	1-1/2	1/8	30301	39301	39501	30397	–	3
1/32	5/64	1-1/2	1/8	30303	39303	39503	30398	–	3
3/64	7/64	1-1/2	1/8	30305	39305	39505	30399	–	3
1/16	3/16	1-1/2	1/8	30307	39307	39507	30400	91266	3
5/64	3/16	1-1/2	1/8	30309	39309	39509	30435	–	3
3/32	9/32	1-1/2	1/8	30311	39311	39511	30436	–	3
7/64	3/8	1-1/2	1/8	30313	39313	39513	30437	–	3
1/8	3/8	1-1/2	1/8	30377	39377	39577	30469	–	3
*1/8	1/2	1-1/2	1/8	30315	39315	39515	30438	91270	3
1/8	3/4	2-1/4	1/8	33341	31800	31810	31850	–	3L
1/8	1	3	1/8	33343	31938	31948	31958	–	3EL
9/64	1/2	2	3/16	30317	39317	39517	30439	–	3
5/32	1/2	2	3/16	30319	39319	39519	30440	–	3
11/64	5/8	2	3/16	30321	39321	39521	30441	–	3
*3/16	5/8	2	3/16	30323	39323	39523	30442	91274	3
3/16	3/4	2-1/2	3/16	33301	31820	31825	31851	–	3L
3/16	1-1/8	3	3/16	33321	31939	31949	31959	–	3EL
13/64	5/8	2-1/2	1/4	30325	39325	39525	30443	–	3
7/32	5/8	2-1/2	1/4	30327	39327	39527	30444	–	3
15/64	3/4	2-1/2	1/4	30329	39329	39529	30445	–	3
*1/4	3/4	2-1/2	1/4	30331	39331	39531	30446	91278	3
1/4	1-1/8	3	1/4	33303	31802	31812	31852	–	3L
1/4	1-1/2	4	1/4	33323	31940	31950	31960	–	3EL
17/64	3/4	2-1/2	5/16	30333	39333	39533	30447	–	3
9/32	3/4	2-1/2	5/16	30335	39335	39535	30448	–	3
19/64	13/16	2-1/2	5/16	30337	39337	39537	30449	–	3
*5/16	13/16	2-1/2	5/16	30339	39339	39539	30450	91282	3
5/16	1-1/8	3	5/16	33305	31821	31826	31853	–	3L

continued on next page




3 • 3L • 3EL

FRACTIONAL SERIES

CONTINUED


inch				EDP NO.					SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	Di-NAMITE (Diamond)	
5/16	1-5/8	4	5/16	33325	31941	31951	31961	–	3EL
21/64	1	2-1/2	3/8	30341	39341	39541	30451	–	3
11/32	1	2-1/2	3/8	30343	39343	39543	30452	–	3
23/64	1	2-1/2	3/8	30345	39345	39545	30453	–	3
*3/8	1	2-1/2	3/8	30347	39347	39547	30454	91286	3
3/8	1-1/8	3	3/8	33307	31804	31814	31854	–	3L
3/8	1-3/4	4	3/8	33327	31942	31952	31962	–	3EL
25/64	1	2-3/4	7/16	30349	39349	39549	30455	–	3
13/32	1	2-3/4	7/16	30351	39351	39551	30456	–	3
27/64	1	2-3/4	7/16	30353	39353	39553	30457	–	3
7/16	1	2-3/4	7/16	30355	39355	39555	30458	–	3
7/16	2	4-1/2	7/16	33309	31822	31827	31855	–	3L
7/16	3	6	7/16	33329	31943	31953	31963	–	3EL
29/64	1	3	1/2	30357	39357	39557	30459	–	3
15/32	1	3	1/2	30359	39359	39559	30460	–	3
31/64	1	3	1/2	30361	39361	39561	30461	–	3
*1/2	1	3	1/2	30363	39363	39563	30462	91290	3
1/2	2	4-1/2	1/2	33311	31806	31816	31856	–	3L
1/2	3	6	1/2	33331	31944	31954	31964	–	3EL
9/16	1-1/8	3-1/2	9/16	30365	39365	39565	30463	–	3
5/8	1-1/4	3-1/2	5/8	30367	39367	39567	30464	–	3
5/8	2-1/4	5	5/8	33313	31823	31817	31857	–	3L
5/8	3	6	5/8	33333	31945	31955	31965	–	3EL
11/16	1-3/8	4	3/4	30369	39369	39569	30465	–	3
3/4	1-1/2	4	3/4	30371	39371	39571	30466	–	3
3/4	2-1/4	5	3/4	33315	31808	31818	31858	–	3L
3/4	3	6	3/4	33335	31946	31956	31966	–	3EL
7/8	1-1/2	4	7/8	30373	39373	39573	30467	–	3
1	1-1/2	4	1	30375	39375	39575	30468	–	3
1	2-1/4	5	1	33317	31824	31819	31859	–	3L
1	3	6	1	33337	31947	31957	31967	–	3EL
*Series 3 Set				30389	39389	39589	30470	–	3





3M • 3XLM

METRIC SERIES



TOLERANCES (mm)

D_1 = +0,000/–0,050


D_2 = h_6

TECH INFO 141

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40305	48628	48650	48671	3M
1,5	4,5	38,0	3,0	40309	48629	48651	48672	3M
2,0	6,3	38,0	3,0	40313	48630	48652	48673	3M
2,5	9,5	38,0	3,0	40317	48631	48653	48674	3M
3,0	12,0	38,0	3,0	40321	48632	48654	48675	3M
3,0	25,0	75,0	3,0	43301	49427	49440	49453	3XLM
3,5	12,0	50,0	4,0	40325	48633	48655	48676	3M
4,0	14,0	50,0	4,0	40329	48634	48656	48677	3M
4,0	25,0	75,0	4,0	43303	49428	49441	49454	3XLM
4,5	16,0	50,0	6,0	40333	48635	48657	48678	3M
5,0	16,0	50,0	6,0	40337	48636	48658	48679	3M
5,0	25,0	75,0	5,0	43307	49430	49443	49456	3XLM
6,0	19,0	50,0	6,0	40341	48637	48659	48680	3M
6,0	25,0	75,0	6,0	43305	49429	49442	49455	3XLM
7,0	19,0	63,0	8,0	40345	48638	48660	48681	3M
8,0	20,0	63,0	8,0	40349	48639	48661	48682	3M
8,0	25,0	75,0	8,0	43315	49431	49444	49457	3XLM
9,0	22,0	75,0	10,0	40353	48640	48662	48683	3M
10,0	22,0	75,0	10,0	40357	48641	48663	48684	3M
10,0	38,0	100,0	10,0	43325	49432	49445	49458	3XLM
11,0	25,0	75,0	12,0	40361	48642	48664	48685	3M
12,0	25,0	75,0	12,0	40365	48643	48665	48686	3M
12,0	50,0	100,0	12,0	43335	49433	49446	49459	3XLM
12,0	75,0	150,0	12,0	43345	49434	49447	49460	3XLM
14,0	32,0	89,0	14,0	40369	48644	48666	48687	3M
14,0	75,0	150,0	14,0	43355	49435	49448	49461	3XLM
16,0	32,0	89,0	16,0	40373	48645	48667	48688	3M
16,0	75,0	150,0	16,0	43365	49436	49449	49462	3XLM
18,0	38,0	100,0	18,0	40377	48646	48668	48689	3M
18,0	75,0	150,0	18,0	43375	49437	49450	49463	3XLM
20,0	38,0	100,0	20,0	40381	48647	48669	48690	3M
20,0	75,0	150,0	20,0	43385	49438	49451	49464	3XLM
25,0	38,0	100,0	25,0	40385	48648	48670	48691	3M
25,0	75,0	150,0	25,0	43395	49439	49452	49465	3XLM






TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6



59
FRACTIONAL SERIES

TECH INFO 139

inch				EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/8	3/8	2-1/2	1/4	32280	32260	32270
3/16	9/16	3	1/4	32281	32261	32271
1/4	5/8	3-1/2	1/4	32282	32262	32272
5/16	11/16	4	5/16	32283	32263	32273
3/8	7/8	4	3/8	32284	32264	32274
1/2	1	4-1/2	1/2	32285	32265	32275
5/8	1-1/8	5	5/8	32286	32266	32276
3/4	1-3/8	5-1/4	3/4	32287	32267	32277

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES
- HARDENED STEELS

TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6


59M
METRIC SERIES

TECH INFO 141

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
3,0	9,0	60,0	6,0	43910	43920	43930	43950
4,0	12,0	70,0	6,0	43911	43921	43931	43951
6,0	15,0	80,0	6,0	43912	43922	43932	43952
8,0	20,0	89,0	8,0	43913	43923	43933	43953
10,0	25,0	100,0	10,0	43914	43924	43934	43954
12,0	30,0	110,0	12,0	43915	43925	43935	43955
14,0	35,0	120,0	16,0	43916	43926	43936	43956
16,0	40,0	120,0	16,0	43917	43927	43937	43957
18,0	40,0	130,0	20,0	43918	43928	43938	43958
20,0	45,0	130,0	20,0	43919	43929	43939	43959







15
FRACTIONAL SERIES

TOLERANCES (inch)


D_1 = +0.0000/–0.0020
D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES


inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/32	1/16	1-1/2	1/8	31501	31541	39651	31316
3/64	3/32	1-1/2	1/8	31503	31543	39653	31317
1/16	1/8	1-1/2	1/8	31505	31545	39655	31318
5/64	1/8	1-1/2	1/8	31507	31547	39657	31319
3/32	3/16	1-1/2	1/8	31509	31549	39659	31320
7/64	3/16	1-1/2	1/8	31511	31551	39661	31321
*1/8	1/4	1-1/2	1/8	31513	31553	39663	31322
9/64	5/16	2	3/16	31515	31555	39665	31323
5/32	5/16	2	3/16	31517	31557	39667	31324
11/64	5/16	2	3/16	31519	31559	39669	31325
*3/16	3/8	2	3/16	31521	31561	39671	31326
13/64	1/2	2-1/2	1/4	31523	31563	39673	31327
7/32	1/2	2-1/2	1/4	31525	31565	39675	31328
15/64	1/2	2-1/2	1/4	31527	31567	39677	31329
*1/4	1/2	2-1/2	1/4	31529	31569	39679	31330
9/32	1/2	2-1/2	5/16	31531	31571	39681	31331
*5/16	1/2	2-1/2	5/16	31533	31573	39683	31332
*3/8	9/16	2-1/2	3/8	31535	31575	39685	31333
7/16	9/16	2-3/4	7/16	31537	31577	39687	31334
*1/2	5/8	3	1/2	31539	31579	39689	31335
*Series 15 Set				31589	31581	39691	31336





TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6




15M
METRIC SERIES

TECH INFO 141

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41505	49010	49031	49052
1,5	3,0	38,0	3,0	41509	49011	49032	49053
2,0	4,0	38,0	3,0	41513	49012	49033	49054
2,5	5,0	38,0	3,0	41517	49013	49034	49055
3,0	6,0	38,0	3,0	41521	49014	49035	49056
3,5	7,0	50,0	4,0	41525	49015	49036	49057
4,0	8,0	50,0	4,0	41529	49016	49037	49058
4,5	9,5	63,0	4,5	41533	49017	49038	49059
5,0	10,0	63,0	5,0	41537	49018	49039	49060
6,0	12,0	63,0	6,0	41541	49019	49040	49061
7,0	12,0	63,0	8,0	41545	49020	49041	49062
8,0	12,0	63,0	8,0	41549	49021	49042	49063
9,0	14,0	75,0	9,0	41553	49022	49043	49064
10,0	14,0	75,0	10,0	41557	49023	49044	49065
11,0	14,0	75,0	12,0	41561	49024	49045	49066
12,0	16,0	75,0	12,0	41565	49025	49046	49067


- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES





3B • 3LB • 3ELB

FRACTIONAL SERIES



TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES
- HARDENED STEELS

inch				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1/64	1/32	1-1/2	1/8	30302	39302	39502	30471	3B
1/32	5/64	1-1/2	1/8	30304	39304	39504	30472	3B
3/64	7/64	1-1/2	1/8	30306	39306	39506	30473	3B
1/16	3/16	1-1/2	1/8	30308	39308	39508	30474	3B
5/64	3/16	1-1/2	1/8	30310	39310	39510	30475	3B
3/32	9/32	1-1/2	1/8	30312	39312	39512	30476	3B
7/64	3/8	1-1/2	1/8	30314	39314	39514	30477	3B
1/8	3/8	1-1/2	1/8	30378	39378	39578	30599	3B
*1/8	1/2	1-1/2	1/8	30316	39316	39516	30478	3B
1/8	3/4	2-1/4	1/8	33342	31830	31840	31890	3LB
1/8	1	3	1/8	33344	31968	31978	31988	3ELB
9/64	1/2	2	3/16	30318	39318	39518	30479	3B
5/32	1/2	2	3/16	30320	39320	39520	30480	3B
11/64	5/8	2	3/16	30322	39322	39522	30481	3B
*3/16	5/8	2	3/16	30324	39324	39524	30482	3B
3/16	3/4	2-1/2	3/16	33302	31831	31841	31891	3LB
3/16	1-1/8	3	3/16	33322	31969	31979	31989	3ELB
13/64	5/8	2-1/2	1/4	30326	39326	39526	30483	3B
7/32	5/8	2-1/2	1/4	30328	39328	39528	30484	3B
15/64	3/4	2-1/2	1/4	30330	39330	39530	30485	3B
*1/4	3/4	2-1/2	1/4	30332	39332	39532	30486	3B
1/4	1-1/8	3	1/4	33304	31832	31842	31892	3LB
1/4	1-1/2	4	1/4	33324	31970	31980	31990	3ELB
17/64	3/4	2-1/2	5/16	30334	39334	39534	30487	3B
9/32	3/4	2-1/2	5/16	30336	39336	39536	30488	3B
19/64	13/16	2-1/2	5/16	30338	39338	39538	30489	3B
*5/16	13/16	2-1/2	5/16	30340	39340	39540	30490	3B
5/16	1-1/8	3	5/16	33306	31833	31843	31893	3LB

continued on next page




3B • 3LB • 3ELB


FRACTIONAL SERIES

CONTINUED

inch				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
5/16	1-5/8	4	5/16	33326	31971	31981	31991	3ELB
21/64	1	2-1/2	3/8	30342	39342	39542	30491	3B
11/32	1	2-1/2	3/8	30344	39344	39544	30492	3B
23/64	1	2-1/2	3/8	30346	39346	39546	30493	3B
*3/8	1	2-1/2	3/8	30348	39348	39548	30494	3B
3/8	1-1/8	3	3/8	33308	31834	31844	31894	3LB
3/8	1-3/4	4	3/8	33328	31972	31982	31992	3ELB
25/64	1	2-3/4	7/16	30350	39350	39550	30495	3B
13/32	1	2-3/4	7/16	30352	39352	39552	30496	3B
27/64	1	2-3/4	7/16	30354	39354	39554	30497	3B
7/16	1	2-3/4	7/16	30356	39356	39556	30498	3B
7/16	2	4-1/2	7/16	33310	31835	31845	31895	3LB
7/16	3	6	7/16	33330	31973	31983	31993	3ELB
29/64	1	3	1/2	30358	39358	39558	30499	3B
15/32	1	3	1/2	30360	39360	39560	30500	3B
31/64	1	3	1/2	30362	39362	39562	30591	3B
*1/2	1	3	1/2	30364	39364	39564	30592	3B
1/2	2	4-1/2	1/2	33312	31836	31846	31896	3LB
1/2	3	6	1/2	33332	31974	31984	31994	3ELB
9/16	1-1/8	3-1/2	9/16	30366	39366	39566	30593	3B
5/8	1-1/4	3-1/2	5/8	30368	39368	39568	30594	3B
5/8	2-1/4	5	5/8	33314	31837	31847	31897	3LB
5/8	3	6	5/8	33334	31975	31985	31995	3ELB
11/16	1-3/8	4	3/4	30370	39370	39570	30595	3B
3/4	1-1/2	4	3/4	30372	39372	39572	30596	3B
3/4	2-1/4	5	3/4	33316	31838	31848	31898	3LB
3/4	3	6	3/4	33336	31976	31986	31996	3ELB
7/8	1-1/2	4	7/8	30374	39374	39574	30597	3B
1	1-1/2	4	1	30376	39376	39576	30598	3B
1	2-1/4	5	1	33318	31839	31849	31899	3LB
1	3	6	1	33338	31977	31987	31997	3ELB
*Series 3B Set				30390	39390	39590	30600	3B







3MB • 3XLMB

METRIC SERIES

TOLERANCES (mm)

D_1 = +0,000/–0,050


D_2 = h_6

TECH INFO 141

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40306	48692	48714	48735	3MB
1,5	4,5	38,0	3,0	40310	48693	48715	48736	3MB
2,0	6,3	38,0	3,0	40314	48694	48716	48737	3MB
2,5	9,5	38,0	3,0	40318	48695	48717	48738	3MB
3,0	12,0	38,0	3,0	40322	48696	48718	48739	3MB
3,0	25,0	75,0	3,0	43302	49544	49557	49570	3XLMB
3,5	12,0	50,0	4,0	40326	48697	48719	48740	3MB
4,0	14,0	50,0	4,0	40330	48698	48720	48741	3MB
4,0	25,0	75,0	4,0	43304	49545	49558	49571	3XLMB
4,5	16,0	50,0	6,0	40334	48699	48721	48742	3MB
5,0	16,0	50,0	6,0	40338	48700	48722	48743	3MB
5,0	25,0	75,0	5,0	43308	49547	49560	49573	3XLMB
6,0	19,0	50,0	6,0	40342	48701	48723	48744	3MB
6,0	25,0	75,0	6,0	43306	49546	49559	49572	3XLMB
7,0	19,0	63,0	8,0	40346	48702	48724	48745	3MB
8,0	20,0	63,0	8,0	40350	48703	48725	48746	3MB
8,0	25,0	75,0	8,0	43316	49548	49561	49574	3XLMB
9,0	22,0	75,0	10,0	40354	48704	48726	48747	3MB
10,0	22,0	75,0	10,0	40358	48705	48727	48748	3MB
10,0	38,0	100,0	10,0	43326	49549	49562	49575	3XLMB
11,0	25,0	75,0	12,0	40362	48706	48728	48749	3MB
12,0	25,0	75,0	12,0	40366	48707	48729	48750	3MB
12,0	50,0	100,0	12,0	43336	49550	49563	49576	3XLMB
12,0	75,0	150,0	12,0	43346	49551	49564	49577	3XLMB
14,0	32,0	89,0	14,0	40370	48708	48730	48751	3MB
14,0	75,0	150,0	14,0	43356	49552	49565	49578	3XLMB
16,0	32,0	89,0	16,0	40374	48709	48731	48752	3MB
16,0	75,0	150,0	16,0	43366	49553	49566	49579	3XLMB
18,0	38,0	100,0	18,0	40378	48710	48732	48753	3MB
18,0	75,0	150,0	18,0	43376	49554	49567	49580	3XLMB
20,0	38,0	100,0	20,0	40382	48711	48733	48754	3MB
20,0	75,0	150,0	20,0	43386	49555	49568	49581	3XLMB
25,0	38,0	100,0	25,0	40386	48712	48734	48755	3MB
25,0	75,0	150,0	25,0	43396	49556	49569	49582	3XLMB






TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6



59B
FRACTIONAL SERIES

TECH INFO 139

inch				EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/8	3/8	2-1/2	1/4	32210	32290	32200
3/16	9/16	3	1/4	32211	32291	32201
1/4	5/8	3-1/2	1/4	32212	32292	32202
5/16	11/16	4	5/16	32213	32293	32203
3/8	7/8	4	3/8	32214	32294	32204
1/2	1	4-1/2	1/2	32215	32295	32205
5/8	1-1/8	5	5/8	32216	32296	32206
3/4	1-3/8	5-1/4	3/4	32217	32297	32207

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES

TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6

59MB
METRIC SERIES


TECH INFO 141

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
3,0	9,0	60,0	6,0	43900	49622	49632	49642
4,0	12,0	70,0	6,0	43901	49623	49633	49643
6,0	15,0	80,0	6,0	43902	49624	49634	49644
8,0	20,0	89,0	8,0	43903	49625	49635	49645
10,0	25,0	100,0	10,0	43904	49626	49636	49646
12,0	30,0	110,0	12,0	43905	49627	49637	49647
14,0	35,0	120,0	16,0	43906	49628	49638	49648
16,0	40,0	120,0	16,0	43907	49629	49639	49649
18,0	40,0	130,0	20,0	43908	49630	49640	49650
20,0	45,0	130,0	20,0	43909	49631	49641	49651

Neck Option Available







15B
FRACTIONAL SERIES


TOLERANCES (inch)
D_1 = +0.0000/–0.0020
D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/32	1/16	1-1/2	1/8	31502	31542	39652	31337
3/64	3/32	1-1/2	1/8	31504	31544	39654	31338
1/16	1/8	1-1/2	1/8	31506	31546	39656	31339
5/64	1/8	1-1/2	1/8	31508	31548	39658	31340
3/32	3/16	1-1/2	1/8	31510	31550	39660	31341
7/64	3/16	1-1/2	1/8	31512	31552	39662	31342
*1/8	1/4	1-1/2	1/8	31514	31554	39664	31343
9/64	5/16	2	3/16	31516	31556	39666	31344
5/32	5/16	2	3/16	31518	31558	39668	31345
11/64	5/16	2	3/16	31520	31560	39760	31346
*3/16	3/8	2	3/16	31522	31562	39672	31347
13/64	1/2	2-1/2	1/4	31524	31564	39674	31348
7/32	1/2	2-1/2	1/4	31526	31566	39676	31349
15/64	1/2	2-1/2	1/4	31528	31568	39678	31350
*1/4	1/2	2-1/2	1/4	31530	31570	39680	31351
9/32	1/2	2-1/2	5/16	31532	31572	39682	31352
*5/16	1/2	2-1/2	5/16	31534	31574	39684	31353
*3/8	9/16	2-1/2	3/8	31536	31576	39686	31354
7/16	9/16	2-3/4	7/16	31538	31578	39688	31355
*1/2	5/8	3	1/2	31540	31580	39690	31356
*Series 15B Set				31590	31582	39692	31357






TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6




15MB
METRIC SERIES


TECH INFO 141

mm				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1,0	2,0	38,0	3,0	41506	49073	49094	49115
1,5	3,0	38,0	3,0	41510	49074	49095	49116
2,0	4,0	38,0	3,0	41514	49075	49096	49117
2,5	5,0	38,0	3,0	41518	49076	49097	49118
3,0	6,0	38,0	3,0	41522	49077	49098	49119
3,5	7,0	50,0	4,0	41526	49078	49099	49120
4,0	8,0	50,0	4,0	41530	49079	49100	49121
4,5	9,5	63,0	4,5	41534	49080	49101	49122
5,0	10,0	63,0	5,0	41538	49081	49102	49123
6,0	12,0	63,0	6,0	41542	49082	49103	49124
7,0	12,0	63,0	8,0	41546	49083	49104	49125
8,0	12,0	63,0	8,0	41550	49084	49105	49126
9,0	14,0	75,0	9,0	41554	49085	49106	49127
10,0	14,0	75,0	10,0	41558	49086	49107	49128
11,0	14,0	75,0	12,0	41562	49087	49108	49129
12,0	16,0	75,0	12,0	41566	49088	49109	49130

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES







3CR
FRACTIONAL SERIES

TOLERANCES (inch)

D_1 = −0.0010/−0.0020
D_2 = h_6
R = +0.0000/−0.0020

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch					EDP NO.			
NOMINAL CUTTING DIA. D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIA. D_2	CORNER RADIUS R	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/8*	1/2	1-1/2	1/8	.015	38201	38202	38315	38357
1/8*	1/2	1-1/2	1/8	.020	38203	38204	38316	38358
3/16*	5/8	2	3/16	.015	38209	38210	38317	38359
3/16*	5/8	2	3/16	.020	38211	38212	38318	38360
3/16*	5/8	2	3/16	.030	38213	38214	38319	38361
1/4*	3/4	2-1/2	1/4	.015	38219	38220	38320	38362
1/4*	3/4	2-1/2	1/4	.020	38221	38222	38321	38363
1/4*	3/4	2-1/2	1/4	.030	38223	38224	38322	38364
1/4*	3/4	2-1/2	1/4	.045	38225	38226	38323	38365
5/16*	13/16	2-1/2	5/16	.015	38231	38232	38324	38366
5/16*	13/16	2-1/2	5/16	.020	38233	38234	38325	38367
5/16*	13/16	2-1/2	5/16	.030	38235	38236	38326	38368
5/16*	13/16	2-1/2	5/16	.045	38237	38238	38327	38369
3/8	1	2-1/2	3/8	.015	38245	38246	38328	38370
3/8	1	2-1/2	3/8	.020	38247	38248	38329	38371
3/8	1	2-1/2	3/8	.030	38249	38250	38330	38372
3/8	1	2-1/2	3/8	.045	38251	38252	38331	38373
1/2	1	3	1/2	.015	38259	38260	38332	38374
1/2	1	3	1/2	.020	38261	38262	38333	38375
1/2	1	3	1/2	.030	38263	38264	38334	38376
1/2	1	3	1/2	.045	38265	38266	38335	38377
1/2	1	3	1/2	.060	38267	38268	38336	38378
5/8	1-1/4	3-1/2	5/8	.015	38273	38274	38337	38379
5/8	1-1/4	3-1/2	5/8	.020	38275	38276	38338	38380
5/8	1-1/4	3-1/2	5/8	.030	38277	38278	38339	38381
5/8	1-1/4	3-1/2	5/8	.045	38279	38280	38340	38382
5/8	1-1/4	3-1/2	5/8	.060	38281	38282	38341	38383
5/8	1-1/4	3-1/2	5/8	.090	38283	38284	38342	38384
3/4	1-1/2	4	3/4	.015	38287	38288	38343	38385
3/4	1-1/2	4	3/4	.020	38289	38290	38344	38386
3/4	1-1/2	4	3/4	.030	38291	38292	38345	38387
3/4	1-1/2	4	3/4	.045	38293	38294	38346	38388
3/4	1-1/2	4	3/4	.060	38295	38296	38347	38389
3/4	1-1/2	4	3/4	.090	38297	38298	38348	38390
3/4	1-1/2	4	3/4	.125	38299	38300	38349	38391
1	1-1/2	4	1	.015	38301	38302	38350	38392
1	1-1/2	4	1	.020	38303	38304	38351	38393
1	1-1/2	4	1	.030	38305	38306	38352	38394
1	1-1/2	4	1	.045	38307	38308	38353	38395
1	1-1/2	4	1	.060	38309	38310	38354	38396
1	1-1/2	4	1	.090	38311	38312	38355	38397
1	1-1/2	4	1	.125	38313	38314	38356	38398


*Without Flat





TOLERANCES (inch)

D_1 = +0.0000/–0.0020
D_2 = h_6



52
FRACTIONAL SERIES

TECH INFO 144

inch				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-C (TiCN)
1/16	3/16	1-1/2	1/8	35273	35300
3/32	3/8	1-1/2	1/8	35275	35301
1/8	7/16	1-1/2	1/8	35277	35302
5/32	9/16	2	3/16	35278	35303
3/16	9/16	2	3/16	35279	35304
7/32	5/8	2-1/2	1/4	35280	35305
1/4	3/4	2-1/2	1/4	35281	35306
9/32	3/4	2-1/2	5/16	35282	35307
5/16	13/16	2-1/2	5/16	35283	35308
3/8	7/8	2-1/2	3/8	35285	35309
7/16	1	2-3/4	7/16	35287	35310
1/2	1	3	1/2	35289	35311
9/16	1-1/8	3-1/2	9/16	35291	35312
5/8	1-1/4	3-1/2	5/8	35293	35313
3/4	1-1/2	4	3/4	35295	35314
1	1-1/2	4	1	35297	35315

NON-FERROUS
PLASTICS/COMPOSITES

TOLERANCES (mm)

D_1 = +0,000/–0,050
D_2 = h_6


52M
FRACTIONAL SERIES

TECH INFO 145

mm				EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE-C (TiCN)
3,0	7,0	38,0	3,0	45277	49829
3,5	7,0	57,0	6,0	45279	49830
4,0	8,0	57,0	6,0	45281	49831
4,5	8,0	57,0	6,0	45283	49832
5,0	10,0	57,0	6,0	45285	49833
6,0	10,0	57,0	6,0	45287	49834
8,0	16,0	63,0	8,0	45289	49835
10,0	19,0	72,0	10,0	45291	49836
12,0	22,0	83,0	12,0	45293	49837
14,0	22,0	83,0	14,0	45295	49838
16,0	26,0	92,0	16,0	45297	49839
20,0	32,0	104,0	20,0	45299	49840







TOLERANCES (inch)

D_1 = +0.0000/–0.0020

D_2 = h_6

5 FRACTIONAL SERIES

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/64	1/32	1-1/2	1/8	30501	39701	30771	30811
1/32	5/64	1-1/2	1/8	30503	39703	30772	30812
3/64	7/64	1-1/2	1/8	30505	39705	30773	30813
1/16	3/16	1-1/2	1/8	30507	39707	30774	30814
5/64	3/16	1-1/2	1/8	30509	39709	30775	30815
3/32	9/32	1-1/2	1/8	30511	39711	30776	30816
7/64	3/8	1-1/2	1/8	30513	39713	30777	30817
1/8	3/8	1-1/2	1/8	30577	39777	30809	30849
1/8	1/2	1-1/2	1/8	30515	39715	30778	30818
9/64	1/2	2	3/16	30517	39717	30779	30819
5/32	1/2	2	3/16	30519	39719	30780	30820
11/64	5/8	2	3/16	30521	39721	30781	30821
3/16	5/8	2	3/16	30523	39723	30782	30822
13/64	5/8	2-1/2	1/4	30525	39725	30783	30823
7/32	5/8	2-1/2	1/4	30527	39727	30784	30824
15/64	3/4	2-1/2	1/4	30529	39729	30785	30825
1/4	3/4	2-1/2	1/4	30531	39731	30786	30826
17/64	3/4	2-1/2	5/16	30533	39733	30787	30827
9/32	3/4	2-1/2	5/16	30535	39735	30788	30828
19/64	13/16	2-1/2	5/16	30537	39737	30789	30829
5/16	13/16	2-1/2	5/16	30539	39739	30790	30830
21/64	1	2-1/2	3/8	30541	39741	30791	30831
11/32	1	2-1/2	3/8	30543	39743	30792	30832
23/64	1	2-1/2	3/8	30545	39745	30793	30833
3/8	1	2-1/2	3/8	30547	39747	30794	30834
25/64	1	2-3/4	7/16	30549	39749	30795	30835
13/32	1	2-3/4	7/16	30551	39751	30796	30836
27/64	1	2-3/4	7/16	30553	39753	30797	30837
7/16	1	2-3/4	7/16	30555	39755	30798	30838
29/64	1	3	1/2	30557	39757	30799	30839
15/32	1	3	1/2	30559	39759	30800	30840
31/64	1	3	1/2	30561	39761	30801	30841
1/2	1	3	1/2	30563	39763	30802	30842
9/16	1-1/8	3-1/2	9/16	30565	39765	30803	30843
5/8	1-1/4	3-1/2	5/8	30567	39767	30804	30844
11/16	1-3/8	4	3/4	30569	39769	30805	30845
3/4	1-1/2	4	3/4	30571	39771	30806	30846
7/8	1-1/2	4	7/8	30573	39773	30807	30847
1	1-1/2	4	1	30575	39775	30808	30848


5M



5XLM



TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6



5M • 5XLM

METRIC SERIES

TECH INFO 141

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40505	48756	48778	48799	5M
1,5	4,5	38,0	3,0	40509	48757	48779	48800	5M
2,0	6,3	38,0	3,0	40513	48758	48780	48801	5M
2,5	9,5	38,0	3,0	40517	48759	48781	48802	5M
3,0	12,0	38,0	3,0	40521	48760	48782	48803	5M
3,0	25,0	75,0	3,0	43501	49466	49479	49492	5XLM
3,5	12,0	50,0	4,0	40525	48761	48783	48804	5M
4,0	14,0	50,0	4,0	40529	48762	48784	48805	5M
4,0	25,0	75,0	4,0	43503	49467	49480	49493	5XLM
4,5	16,0	50,0	6,0	40533	48763	48785	48806	5M
5,0	16,0	50,0	6,0	40537	48764	48786	48807	5M
5,0	25,0	75,0	5,0	43507	49469	49482	49495	5XLM
6,0	19,0	50,0	6,0	40541	48765	48787	48808	5M
6,0	25,0	75,0	6,0	43505	49468	49481	49494	5XLM
7,0	19,0	63,0	8,0	40545	48766	48788	48809	5M
8,0	20,0	63,0	8,0	40549	48767	48789	48810	5M
8,0	25,0	75,0	8,0	43515	49470	49483	49496	5XLM
9,0	22,0	75,0	10,0	40553	48768	48790	48811	5M
10,0	22,0	75,0	10,0	40557	48769	48791	48812	5M
10,0	38,0	100,0	10,0	43525	49471	49484	49497	5XLM
11,0	25,0	75,0	12,0	40561	48770	48792	48813	5M
12,0	25,0	75,0	12,0	40565	48771	48793	48814	5M
12,0	50,0	100,0	12,0	43535	49472	49485	49498	5XLM
12,0	75,0	150,0	12,0	43545	49473	49486	49499	5XLM
14,0	32,0	89,0	14,0	40569	48772	48794	48815	5M
14,0	75,0	150,0	14,0	43555	49474	49487	49500	5XLM
16,0	32,0	89,0	16,0	40573	48773	48795	48816	5M
16,0	75,0	150,0	16,0	43565	49475	49488	49501	5XLM
18,0	38,0	100,0	18,0	40577	48774	48796	48817	5M
18,0	75,0	150,0	18,0	43575	49476	49489	49502	5XLM
20,0	38,0	100,0	20,0	40581	48775	48797	48818	5M
20,0	75,0	150,0	20,0	43585	49477	49490	49503	5XLM
25,0	38,0	100,0	25,0	40585	48776	48798	48819	5M
25,0	75,0	150,0	25,0	43595	49478	49491	49504	5XLM

STEELS

STAINLESS STEELS

CAST IRON

HIGH TEMP ALLOYS


TITANIUM

NON-FERROUS

PLASTICS/COMPOSITES







5B
FRACTIONAL SERIES

TOLERANCES (inch)


D_1 = +0.0000/–0.0020
D_2 = h_6

TECH INFO 139

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.			
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/64	1/32	1-1/2	1/8	30502	30851	30602	31130
1/32	5/64	1-1/2	1/8	30504	30852	30604	31131
3/64	7/64	1-1/2	1/8	30506	30853	30606	31132
1/16	3/16	1-1/2	1/8	30508	30854	30608	31133
5/64	3/16	1-1/2	1/8	30510	30855	30610	31134
3/32	9/32	1-1/2	1/8	30512	30856	30612	31135
7/64	3/8	1-1/2	1/8	30514	30857	30902	31136
1/8	3/8	1-1/2	1/8	30578	30889	30943	31168
1/8	1/2	1-1/2	1/8	30516	30858	30904	31137
9/64	1/2	2	3/16	30518	30859	30906	31138
5/32	1/2	2	3/16	30520	30860	30908	31139
11/64	5/8	2	3/16	30522	30861	30910	31140
3/16	5/8	2	3/16	30524	30862	30912	31141
13/64	5/8	2-1/2	1/4	30526	30863	30914	31142
7/32	5/8	2-1/2	1/4	30528	30864	30916	31143
15/64	3/4	2-1/2	1/4	30530	30865	30918	31144
1/4	3/4	2-1/2	1/4	30532	30866	30920	31145
17/64	3/4	2-1/2	5/16	30534	30867	30921	31146
9/32	3/4	2-1/2	5/16	30536	30868	30922	31147
19/64	13/16	2-1/2	5/16	30538	30869	30923	31148
5/16	13/16	2-1/2	5/16	30540	30870	30924	31149
21/64	1	2-1/2	3/8	30542	30871	30925	31150
11/32	1	2-1/2	3/8	30544	30872	30926	31151
23/64	1	2-1/2	3/8	30546	30873	30927	31152
3/8	1	2-1/2	3/8	30548	30874	30928	31153
25/64	1	2-3/4	7/16	30550	30875	30929	31154
13/32	1	2-3/4	7/16	30552	30876	30930	31155
27/64	1	2-3/4	7/16	30554	30877	30931	31156
7/16	1	2-3/4	7/16	30556	30878	30932	31157
29/64	1	3	1/2	30558	30879	30933	31158
15/32	1	3	1/2	30560	30880	30934	31159
31/64	1	3	1/2	30562	30881	30935	31160
1/2	1	3	1/2	30564	30882	30936	31161
9/16	1-1/8	3-1/2	9/16	30566	30883	30937	31162
5/8	1-1/4	3-1/2	5/8	30568	30884	30938	31163
11/16	1-3/8	4	3/4	30570	30885	30939	31164
3/4	1-1/2	4	3/4	30572	30886	30940	31165
7/8	1-1/2	4	7/8	30574	30887	30941	31166
1	1-1/2	4	1	30576	30888	30942	31167
*Series 5B Set				30590	30900	30944	31169






TOLERANCES (mm)

D_1 = +0,000/–0,050

D_2 = h_6



5MB • 5XLMB


METRIC SERIES


TECH INFO 141

mm				EDP NO.				SERIES
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)	
1,0	4,0	38,0	3,0	40506	48820	48842	48863	5MB
1,5	4,5	38,0	3,0	40510	48821	48843	48864	5MB
2,0	6,3	38,0	3,0	40514	48822	48844	48865	5MB
2,5	9,5	38,0	3,0	40518	48823	48845	48866	5MB
3,0	12,0	38,0	3,0	40522	48824	48846	48867	5MB
3,0	25,0	75,0	3,0	43502	49583	49596	49609	5XLMB
3,5	12,0	50,0	4,0	40526	48825	48847	48868	5MB
4,0	14,0	50,0	4,0	40530	48826	48848	48869	5MB
4,0	25,0	75,0	4,0	43504	49584	49597	49610	5XLMB
4,5	16,0	50,0	6,0	40534	48827	48849	48870	5MB
5,0	16,0	50,0	6,0	40538	48828	48850	48871	5MB
5,0	25,0	75,0	5,0	43508	49586	49599	49612	5XLMB
6,0	19,0	50,0	6,0	40542	48829	48851	48872	5MB
6,0	25,0	75,0	6,0	43506	49585	49598	49611	5XLMB
7,0	19,0	63,0	8,0	40546	48830	48852	48873	5MB
8,0	20,0	63,0	8,0	40550	48831	48853	48874	5MB
8,0	25,0	75,0	8,0	43516	49587	49600	49613	5XLMB
9,0	22,0	75,0	10,0	40554	48832	48854	48875	5MB
10,0	22,0	75,0	10,0	40558	48833	48855	48876	5MB
10,0	38,0	100,0	10,0	43526	49588	49601	49614	5XLMB
11,0	25,0	75,0	12,0	40562	48834	48856	48877	5MB
12,0	25,0	75,0	12,0	40566	48835	48857	48878	5MB
12,0	50,0	100,0	12,0	43536	49589	49602	49615	5XLMB
12,0	75,0	150,0	12,0	43546	49590	49603	49616	5XLMB
14,0	32,0	89,0	14,0	40570	48836	48858	48879	5MB
14,0	75,0	150,0	14,0	43556	49591	49604	49617	5XLMB
16,0	32,0	89,0	16,0	40574	48837	48859	48880	5MB
16,0	75,0	150,0	16,0	43566	49592	49605	49618	5XLMB
18,0	38,0	100,0	18,0	40578	48838	48860	48881	5MB
18,0	75,0	150,0	18,0	43576	49593	49606	49619	5XLMB
20,0	38,0	100,0	20,0	40582	48839	48861	48882	5MB
20,0	75,0	150,0	20,0	43586	49594	49607	49620	5XLMB
25,0	38,0	100,0	25,0	40586	48840	48862	48883	5MB
25,0	75,0	150,0	25,0	43596	49595	49608	49621	5XLMB

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES







61
FRACTIONAL SERIES

TECH INFO 146

TOLERANCES (inch)

D_1 = +0.0000/–0.0040
D_2 = h_6
R = +0.0050/–0.0050

inch						EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	NO. OF FLUTES	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/4*	3/4	2-1/2	1/4	.045	3	36107	36106	36110
5/16*	3/4	2-1/2	5/16	.045	3	36109	36108	36111
3/8	7/8	2-1/2	3/8	.060	3	36113	36112	36114
1/2	1	3	1/2	.060	4	36117	36116	36118
5/8	1-1/4	3-1/2	5/8	.060	4	36121	36120	36222
3/4	1-5/8	4	3/4	.060	4	36125	36124	36126
1	1-3/4	4	1	.060	5	36129	36128	36130

*Without Flat

STEELS
STAINLESS STEELS
CAST IRON

61M
METRIC SERIES

TECH INFO 147

TOLERANCES h10 (mm)

D_1 = +0,000/–0,100
D_2 = h_6
R = +0,127/–0,127

mm						EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	CORNER RADIUS R	NO. OF FLUTES	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
6,0	19,0	63,0	6,0	1,14	3	46107	46106	46110
8,0	19,0	63,0	8,0	1,14	3	46109	46108	46111
10,0	22,0	72,0	10,0	1,52	3	46113	46112	46114
12,0	26,0	83,0	12,0	1,52	4	46117	46116	46118
16,0	32,0	92,0	16,0	1,52	4	46121	46120	46122
20,0	38,0	104,0	20,0	1,52	4	46129	46128	46132
25,0	44,0	104,0	25,0	1,52	5	46131	46130	46133





TOLERANCES (inch)

D_1 = +0.0000/–0.0040
D_2 = h_6
R = +0.0050/–0.0050

62
FRACTIONAL SERIES

TECH INFO 148

inch					EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/4*	3/4	2-1/2	1/4	3	36207	36206	36210
5/16*	3/4	2-1/2	5/16	3	36209	36208	36211
3/8	7/8	2-1/2	3/8	3	36213	36212	36214
1/2	1	3	1/2	4	36217	36216	36218
5/8	1-1/4	3-1/2	5/8	4	36221	36220	36222
3/4	1-5/8	4	3/4	4	36225	36224	36226
1	1-3/4	4	1	6	36229	36228	36230

*Without Flat

STEELS
STAINLESS STEELS
CAST IRON

TOLERANCES h10 (mm)

D_1 = +0,000/–0,100
D_2 = h_6
R = +0,127/–0,127

62M
METRIC SERIES

TECH INFO 149


mm					EDP NO.		
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
6	19	63	6	3	46207	46206	46210
8	19	63	8	3	46209	46208	46211
10	22	72	10	3	46213	46212	46214
12	26	83	12	4	46217	46216	46218
16	32	92	16	4	46221	46220	46222
20	38	104	20	4	46229	46228	46232
25	44	104	25	6	46231	46230	46233





MK2

FRACTIONAL SERIES



TECH INFO 150

TOLERANCES (inch)

D_1 = +/–0.0005


D_2 = h_6

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
0.008	0.012	1-1/2	1/8	39208
0.009	0.014	1-1/2	1/8	39209
0.010	0.015	1-1/2	1/8	39210
0.011	0.017	1-1/2	1/8	39211
0.012	0.018	1-1/2	1/8	39212
0.013	0.020	1-1/2	1/8	39213
0.014	0.021	1-1/2	1/8	39214
0.015	0.023	1-1/2	1/8	39215
0.016	0.024	1-1/2	1/8	39216
0.017	0.026	1-1/2	1/8	39217
0.018	0.027	1-1/2	1/8	39218
0.019	0.029	1-1/2	1/8	39219
0.020	0.030	1-1/2	1/8	39220
0.021	0.032	1-1/2	1/8	39221
0.022	0.033	1-1/2	1/8	39222
0.023	0.035	1-1/2	1/8	39223
0.024	0.036	1-1/2	1/8	39224
0.025	0.038	1-1/2	1/8	39225
0.026	0.039	1-1/2	1/8	39226
0.027	0.041	1-1/2	1/8	39227
0.028	0.042	1-1/2	1/8	39228
0.029	0.044	1-1/2	1/8	39229
0.030	0.045	1-1/2	1/8	39230
0.031	0.047	1-1/2	1/8	39231
0.035	0.053	1-1/2	1/8	39235
0.040	0.060	1-1/2	1/8	39240
0.047	0.071	1-1/2	1/8	39247
0.050	0.075	1-1/2	1/8	39250
0.055	0.083	1-1/2	1/8	39255
0.060	0.090	1-1/2	1/8	39260







TOLERANCES (mm)

D_1 = +/–0,013

D_2 = h_6


MK2M
METRIC SERIES


TECH INFO 152

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
0,20	0,30	38,0	3,17	39208
0,23	0,36	38,0	3,17	39209
0,25	0,38	38,0	3,17	39210
0,28	0,43	38,0	3,17	39211
0,30	0,46	38,0	3,17	39212
0,33	0,51	38,0	3,17	39213
0,36	0,53	38,0	3,17	39214
0,38	0,58	38,0	3,17	39215
0,41	0,61	38,0	3,17	39216
0,43	0,66	38,0	3,17	39217
0,46	0,69	38,0	3,17	39218
0,48	0,74	38,0	3,17	39219
0,51	0,76	38,0	3,17	39220
0,53	0,81	38,0	3,17	39221
0,56	0,84	38,0	3,17	39222
0,58	0,89	38,0	3,17	39223
0,61	0,91	38,0	3,17	39224
0,63	0,96	38,0	3,17	39225
0,66	0,99	38,0	3,17	39226
0,69	1,04	38,0	3,17	39227
0,71	1,07	38,0	3,17	39228
0,74	1,12	38,0	3,17	39229
0,76	1,14	38,0	3,17	39230
0,79	1,19	38,0	3,17	39231
0,89	1,35	38,0	3,17	39235
1,02	1,52	38,0	3,17	39240
1,19	1,80	38,0	3,17	39247
1,27	1,90	38,0	3,17	39250
1,40	2,11	38,0	3,17	39255
1,52	2,29	38,0	3,17	39260

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES







23
FRACTIONAL SERIES

TECH INFO 139


TOLERANCES (inch)

D_1 = +0.0010/–0.0020
D_2 = h_6

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch					EDP NO.			
SHANK DIAMETER D_2	CENTER LINE ANGLE α	SMALL DIAMETER D_1	APPROX. LENGTH OF CUT L_2	OVERALL LENGTH L_1	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/4	1°	1/8	1-1/2	3	32301	32370	32302	32345
1/4	1°30'	1/8	1-1/2	3	32303	32371	32304	32346
1/4	2°	1/8	1-1/4	3	32305	32372	32306	32347
1/4	3°	1/8	1	3	32307	32373	32308	32348
1/4	5°	1/8	3/4	3	32309	32374	32310	32349
1/4	7°	1/8	1/2	3	32311	32375	32312	32350
1/4	10°	3/32	1/2	3	32313	32376	32314	32351
3/8	1°	3/16	1-3/4	3-1/2	32315	32377	32316	32352
3/8	1°30'	3/16	1-3/4	3-1/2	32317	32378	32318	32353
3/8	2°	3/16	1-3/4	3-1/2	32319	32379	32320	32354
3/8	3°	5/32	1-3/4	3-1/2	32321	32380	32322	32355
3/8	5°	1/8	1-1/2	3-1/2	32323	32381	32324	32356
3/8	7°	1/8	1	3-1/2	32325	32382	32326	32357
3/8	10°	1/8	3/4	3-1/2	32327	32383	32328	32358
1/2	1°	1/4	2	4	32329	32384	32330	32359
1/2	2°	1/4	2	4	32333	32385	32334	32360
1/2	3°	1/4	2	4	32335	32386	32336	32361
1/2	5°	1/4	1-1/4	4	32337	32387	32388	32362
1/2	7°	1/4	1-1/4	4	32339	32388	32340	32363
1/2	10°	1/8	1	4	32341	32389	32342	32364





TOLERANCES (inch)

D_2 = h_6

R = +0.0005/–0.0010


24
FRACTIONAL SERIES

TECH INFO 139

inch					EDP NO.			
SHANK DIAMETER D_2	CENTER LINE ANGLE α	RADIUS R	LENGTH OF CUT L_2	OVERALL LENGTH L_1	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
1/4	1°	0.062	1-1/2	3	32402	32403	32445	32470
1/4	1°30'	0.062	1-1/2	3	32404	32405	32446	32471
1/4	2°	0.062	1-1/4	3	32406	32407	32447	32472
1/4	3°	0.062	1	3	32408	32409	32448	32473
1/4	5°	0.062	3/4	3	32410	32411	32449	32474
1/4	7°	0.062	1/2	3	32412	32413	32450	32475
1/4	10°	0.047	1/2	3	32414	32415	32451	32476
3/8	1°	0.093	1-3/4	3-1/2	32416	32417	32452	32477
3/8	1°30'	0.093	1-3/4	3-1/2	32418	32419	32453	32478
3/8	2°	0.093	1-3/4	3-1/2	32420	32421	32454	32479
3/8	3°	0.078	1-3/4	3-1/2	32422	32423	32455	32480
3/8	5°	0.062	1-1/2	3-1/2	32424	32425	32456	32481
3/8	7°	0.062	1	3-1/2	32426	32427	32457	32482
3/8	10°	0.062	3/4	3-1/2	32428	32429	32458	32483
1/2	1°	0.125	2	4	32430	32431	32459	32484
1/2	2°	0.125	2	4	32434	32435	32460	32485
1/2	3°	0.125	2	4	32436	32437	32461	32486
1/2	5°	0.125	1-1/4	4	32438	32439	32462	32487
1/2	7°	0.093	1-1/4	4	32440	32441	32463	32488
1/2	10°	0.062	1	4	32442	32443	32464	32489

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES





CUTTING DIAMETER D_1	SINGLE END LENGTH OF CUT L_2	DOUBLE END LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2
1/8	1/2	1/4	1-1/2	1/8
3/16	5/8	3/8	2	3/16
1/4	3/4	1/2	2-1/2	1/4
5/16	13/16	1/2	2-1/2	5/16
3/8	1	9/16	2-1/2	3/8
1/2	1	5/8	3	1/2

Square End

FRACTIONAL SERIES




DESCRIPTION	EDP NO.			
	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
Series 1 – 4 Flute, Single End	30189	39189	39089	30030
Series 3 – 2 Flute, Single End	30389	39389	39589	30470
Series 5 – 3 Flute, Single End	30589	39789	30810	30850
Series 14 – 4 Flute, Double End	31489	31481	39641	31190
Series 15 – 2 Flute, Double End	31589	31581	39691	31336

Ball End

FRACTIONAL SERIES




DESCRIPTION	EDP NO.			
	UNCOATED	Ti-NAMITE (TiN)	Ti-NAMITE-C (TiCN)	Ti-NAMITE-A (AlTiN)
Series 1B – 4 Flute, Single End	30190	39109	39090	30070
Series 3B – 2 Flute, Single End	30390	39390	39590	30600
Series 5B – 3 Flute, Single End	30590	30900	30944	31169
Series 14B – 4 Flute, Double End	31490	31482	39642	31217
Series 15B – 2 Flute, Double End	31590	31582	39692	31357




	Series 1, 3, 5, 14, 15, 16, 17, 23, 24, 59 Fractional	Hardness BRINELL		Flutes	Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/64	1/32	1/16	1/8	1/4	3/8	1/2	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 175					460	RPM	112461	56230	28115	14058	7029	4686	3514	2343	1757
			Profile					Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	≤ 0.50	≤ 1.5	(368-552)	Feed (IPM)	6.7	6.7	7.3	8.4	11.2	14.1	14.1	11.2	9.8
				3	≤ 0.25	≤ 1.5			10.1	10.1	11.0	12.7	16.9	21.1	21.1	16.9	14.8
				4	≤ 0.25	≤ 1.5			13.5	13.5	14.6	16.9	22.5	28.1	28.1	22.5	19.7
							335	RPM	81901	40950	20475	10238	5119	3413	2559	1706	1280
			Slot					Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	1	≤ 1	(268-402)	Feed (IPM)	4.9	4.9	5.3	6.1	8.2	10.2	10.2	8.2	7.2
				3	1	≤ 0.5			7.4	7.4	8.0	9.2	12.3	15.4	15.4	12.3	10.7
				4	1	≤ 0.4			9.8	9.8	10.6	12.3	16.4	20.5	20.5	16.4	14.3
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275					335	RPM	81901	40950	20475	10238	5119	3413	2559	1706	1280
			Profile					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	≤ 0.50	≤ 1.5	(268-402)	Feed (IPM)	3.3	4.1	3.7	4.1	6.1	7.5	7.7	6.1	5.4
				3	≤ 0.25	≤ 1.5			4.9	6.1	5.5	6.1	9.2	11.3	11.5	9.2	8.1
				4	≤ 0.25	≤ 1.5			6.6	8.2	7.4	8.2	12.3	15.0	15.4	12.3	10.7
							245	RPM	59898	29949	14974	7487	3744	2496	1872	1248	936
			Slot					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	1	≤ 1	(196-294)	Feed (IPM)	2.4	3.0	2.7	3.0	4.5	5.5	5.6	4.5	3.9
				3	1	≤ 0.5			3.6	4.5	4.0	4.5	6.7	8.2	8.4	6.7	5.9
				4	1	≤ 0.4			4.8	6.0	5.4	6.0	9.0	11.0	11.2	9.0	7.9
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250					315	RPM	77011	38506	19253	9626	4813	3209	2407	1604	1203
			Profile					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	≤ 0.50	≤ 1.5	(252-378)	Feed (IPM)	3.1	3.9	3.5	3.9	5.8	7.1	7.2	5.8	5.1
				3	≤ 0.25	≤ 1.5			4.6	5.8	5.2	5.8	8.7	10.6	10.8	8.7	7.6
				4	≤ 0.25	≤ 1.5			6.2	7.7	6.9	7.7	11.6	14.1	14.4	11.6	10.1
							230	RPM	56230	28115	14058	7029	3514	2343	1757	1171	879
			Slot					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	1	≤ 1	(184-276)	Feed (IPM)	2.2	2.8	2.5	2.8	4.2	5.2	5.3	4.2	3.7
				3	1	≤ 0.5			3.4	4.2	3.8	4.2	6.3	7.7	7.9	6.3	5.5
				4	1	≤ 0.4			4.5	5.6	5.1	5.6	8.4	10.3	10.5	8.4	7.4
K	CAST IRONS Gray, Malleable, Ductile	≤ 220					335	RPM	81901	40950	20475	10238	5119	3413	2559	1706	1280
			Profile					Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	≤ 0.50	≤ 1.5	(268-402)	Feed (IPM)	4.9	4.9	5.3	6.1	8.2	10.2	10.2	8.2	7.2
				3	≤ 0.25	≤ 1.5			7.4	7.4	8.0	9.2	12.3	15.4	15.4	12.3	10.7
				4	≤ 0.25	≤ 1.5			9.8	9.8	10.6	12.3	16.4	20.5	20.5	16.4	14.3
							245	RPM	59898	29949	14974	7487	3744	2496	1872	1248	936
			Slot					Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	1	≤ 1	(196-294)	Feed (IPM)	3.6	3.6	3.9	4.5	6.0	7.5	7.5	6.0	5.2
				3	1	≤ 0.5			5.4	5.4	5.8	6.7	9.0	11.2	11.2	9.0	7.9
				4	1	≤ 0.4			7.2	7.2	7.8	9.0	12.0	15.0	15.0	12.0	10.5
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275					370	RPM	90458	45229	22614	11307	5654	3769	2827	1885	1413
			Profile					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	≤ 0.50	≤ 1.5	(296-444)	Feed (IPM)	3.6	4.5	4.1	4.5	6.8	8.3	8.5	6.8	5.9
				3	≤ 0.25	≤ 1.5			5.4	6.8	6.1	6.8	10.2	12.4	12.7	10.2	8.9
				4	≤ 0.25	≤ 1.5			7.2	9.0	8.1	9.0	13.6	16.6	17.0	13.6	11.9
							270	RPM	66010	33005	16502	8251	4126	2750	2063	1375	1031
			Slot					Fz	0.00002	0.00005	0.00009	0.0002	0.0006	0.0011	0.0015	0.0018	0.0021
				2	1	≤ 1	(216-324)	Feed (IPM)	2.6	3.3	3.0	3.3	5.0	6.1	6.2	5.0	4.3
				3	1	≤ 0.5			4.0	5.0	4.5	5.0	7.4	9.1	9.3	7.4	6.5
				4	1	≤ 0.4			5.3	6.6	5.9	6.6	9.9	12.1	12.4	9.9	8.7
M	STAINLESS STEELS (DIFFICULT) 304, 304L, 316, 316L, 17-4 PH, 15-5, 13-4, Custom 450	≤ 275					255	RPM	62342	31171	15586	7793	3896	2598	1948	1299	974
			Profile					Fz	0.00002	0.00004	0.00008	0.0002	0.0005	0.0009	0.0012	0.0014	0.0017
				2	≤ 0.50	≤ 1.5	(204-306)	Feed (IPM)	2.5	2.5	2.5	2.6	3.9	4.7	4.7	3.6	3.3
				3	≤ 0.25	≤ 1.5			3.7	3.7	3.7	4.0	5.8	7.0	7.0	5.5	5.0
				4	≤ 0.25	≤ 1.5			5.0	5.0	5.0	5.3	7.8	9.4	9.4	7.3	6.6
							185	RPM	45229	22614	11307	5654	2827	1885	1413	942	707
			Slot					Fz	0.00002	0.00004	0.00008	0.0002	0.0005	0.0009	0.0012	0.0014	0.0017
				2	1	≤ 1	(148-222)	Feed (IPM)	1.8	1.8	1.8	1.9	2.8	3.4	3.4	2.6	2.4
				3	1	≤ 0.5			2.7	2.7	2.7	2.9	4.2	5.1	5.1	4.0	3.6
				4	1	≤ 0.4			3.6	3.6	3.6	3.8	5.7	6.8	6.8	5.3	4.8

continued on next page




	Series 1, 3, 5, 14, 15, 16, 17, 23, 24, 59 Fractional	Hardness BRINELL		Flutes	Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/64	1/32	1/16	1/8	1/4	3/8	1/2	3/4	1
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, 718, Incoly 800, Monel 400,Rene, Waspalloy	≤ 300	Profile				65	RPM	15891	7946	3973	1986	993	662	497	331	248
								Fz	0.00002	0.00003	0.00006	0.0002	0.0004	0.0008	0.0010	0.0012	0.0014
				2	≤ 0.50	≤ 1.5	(52-78)	Feed (IPM)	0.6	0.5	0.5	0.7	0.7	1.1	1.0	0.8	0.7
				3	≤ 0.25	≤ 1.5			1.0	0.7	0.7	1.1	1.0	1.6	1.5	1.2	1.0
				4	≤ 0.25	≤ 1.5			1.3	1.0	1.0	1.4	1.4	2.1	2.0	1.6	1.4
			Slot				45	RPM	11002	5501	2750	1375	688	458	344	229	172
								Fz	0.00002	0.00003	0.00006	0.0002	0.0004	0.0008	0.0010	0.0012	0.0014
				2	1	≤ 1	(36-54)	Feed (IPM)	0.4	0.3	0.3	0.5	0.5	0.7	0.7	0.6	0.5
				3	1	≤ 0.5			0.7	0.5	0.5	0.7	0.7	1.1	1.0	0.8	0.7
				4	1	≤ 0.4			0.9	0.7	0.7	1.0	1.0	1.5	1.4	1.1	1.0
S	TITANIUM ALLOYS Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al	≤ 350	Profile				180	RPM	44006	22003	11002	5501	2750	1834	1375	917	688
								Fz	0.00002	0.00004	0.00008	0.0002	0.0005	0.0009	0.0012	0.0014	0.0017
				2	≤ 0.50	≤ 1.5	(144-216)	Feed (IPM)	1.8	1.8	1.8	2.2	2.8	3.3	3.3	2.6	2.3
				3	≤ 0.25	≤ 1.5			2.6	2.6	2.6	3.3	4.1	5.0	5.0	3.9	3.5
				4	≤ 0.25	≤ 1.5			3.5	3.5	3.5	4.4	5.5	6.6	6.6	5.1	4.7
			Slot				130	RPM	31782	15891	7946	3973	1986	1324	993	662	497
								Fz	0.00002	0.00004	0.00008	0.0002	0.0005	0.0009	0.0012	0.0014	0.0017
				2	1	≤ 1	(104-156)	Feed (IPM)	1.3	1.3	1.3	1.6	2.0	2.4	2.4	1.9	1.7
				3	1	≤ 0.5			1.9	1.9	1.9	2.4	3.0	3.6	3.6	2.8	2.5
				4	1	≤ 0.4			2.5	2.5	2.5	3.2	4.0	4.8	4.8	3.7	3.4
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 150	Profile				880	RPM	215142	107571	53786	26893	13446	8964	6723	4482	3362
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	≤ 0.50	≤ 1.5	(704-1056)	Feed (IPM)	25.8	28.0	26.9	32.3	43.0	53.8	53.8	43.0	37.6
				3	≤ 0.25	≤ 1.5			38.7	42.0	40.3	48.4	64.5	80.7	80.7	64.5	56.5
			Slot				640	RPM	156467	78234	39117	19558	9779	6519	4890	3260	2445
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	1	≤ 1	(512-768)	Feed (IPM)	18.8	20.3	19.6	23.5	31.3	39.1	39.1	31.3	27.4
				3	1	≤ 0.5			28.2	30.5	29.3	35.2	46.9	58.7	58.7	46.9	41.1
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	Profile				485	RPM	118573	59286	29643	14822	7411	4941	3705	2470	1853
								Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	≤ 0.50	≤ 1.5	(388-582)	Feed (IPM)	7.1	7.1	7.7	8.9	11.9	14.8	14.8	11.9	10.4
				3	≤ 0.25	≤ 1.5			10.7	10.7	11.6	13.3	17.8	22.2	22.2	17.8	15.6
				4	≤ 0.25	≤ 1.5			14.2	14.2	15.4	17.8	23.7	29.6	29.6	23.7	20.8
			Slot				350	RPM	85568	42784	21392	10696	5348	3565	2674	1783	1337
								Fz	0.00003	0.00006	0.00013	0.0003	0.0008	0.0015	0.0020	0.0024	0.0028
				2	1	≤ 1	(280-420)	Feed (IPM)	5.1	5.1	5.6	6.4	8.6	10.7	10.7	8.6	7.5
				3	1	≤ 0.5			7.7	7.7	8.3	9.6	12.8	16.0	16.0	12.8	11.2
				4	1	≤ 0.4			10.3	10.3	11.1	12.8	17.1	21.4	21.4	17.1	15.0
	PLASTICS Polycarbonate, PVC, Polypropylene		Profile				880	RPM	215142	107571	53786	26893	13446	8964	6723	4482	3362
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	≤ 0.50	≤ 1.5	(704-1056)	Feed (IPM)	25.8	28.0	26.9	32.3	43.0	53.8	53.8	43.0	37.6
				3	≤ 0.25	≤ 1.5			38.7	42.0	40.3	48.4	64.5	80.7	80.7	64.5	56.5
				4	≤ 0.25	≤ 1.5			51.6	55.9	53.8	64.5	86.1	107.6	107.6	86.1	75.3
			Slot				640	RPM	156467	78234	39117	19558	9779	6519	4890	3260	2445
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	1	≤ 1	(512-768)	Feed (IPM)	18.8	20.3	19.6	23.5	31.3	39.1	39.1	31.3	27.4
				3	1	≤ 0.5			28.2	30.5	29.3	35.2	46.9	58.7	58.7	46.9	41.1
				4	1	≤ 0.4			37.6	40.7	39.1	46.9	62.6	78.2	78.2	62.6	54.8
	GRAPHITE		Profile				660	RPM	161357	80678	40339	20170	10085	6723	5042	3362	2521
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	≤ 0.50	≤ 1.5	(528-792)	Feed (IPM)	19.4	21.0	20.2	24.2	32.3	40.3	40.3	32.3	28.2
				3	≤ 0.25	≤ 1.5			29.0	31.5	30.3	36.3	48.4	60.5	60.5	48.4	42.4
				4	≤ 0.25	≤ 1.5			38.7	42.0	40.3	48.4	64.5	80.7	80.7	64.5	56.5
			Slot				480	RPM	117350	58675	29338	14669	7334	4890	3667	2445	1834
								Fz	0.00006	0.00013	0.00025	0.0006	0.0016	0.0030	0.0040	0.0048	0.0056
				2	1	≤ 1	(384-576)	Feed (IPM)	14.1	15.3	14.7	17.6	23.5	29.3	29.3	23.5	20.5
				3	1	≤ 0.5			21.1	22.9	22.0	26.4	35.2	44.0	44.0	35.2	30.8
				4	1	≤ 0.4			28.2	30.5	29.3	35.2	46.9	58.7	58.7	46.9	41.1

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
for tapered end mills, base the speed on the largest diameter contacting the workpiece and the feed on the smallest diameter
limit cut depths of long and extra long flute mills to .05 x D1 when slotting or profiling
reduce feed and Ae when finish milling (.02 x D1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 1M, 3M, 5M, 14M, 15M, 16M, 17M, 59M Metric	Hardness BRINELL		Flutes	Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 0.4	0.75	1.5	3	6	10	12	20	25
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 175					140	RPM	111483	59458	29729	14864	7432	4459	3716	2230	1784
			Profile					Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	≤ 0.50	≤ 1.5	(112-168)	Feed (mm/min)	178	178	184	208	282	357	357	285	250
				3	≤ 0.25	≤ 1.5			268	268	276	312	424	535	535	428	375
				4	≤ 0.25	≤ 1.5			357	357	369	416	565	713	713	571	499
							102	RPM	81189	43301	21650	10825	5413	3248	2706	1624	1299
			Slot					Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	1	≤ 1	(82-123)	Feed (mm/min)	130	130	134	152	206	260	260	208	182
				3	1	≤ 0.5			195	195	201	227	309	390	390	312	273
				4	1	≤ 0.4			260	260	268	303	411	520	520	416	364
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275					102	RPM	81189	43301	21650	10825	5413	3248	2706	1624	1299
			Profile					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	≤ 0.50	≤ 1.5	(82-123)	Feed (mm/min)	81	104	95	130	152	188	195	156	135
				3	≤ 0.25	≤ 1.5			122	156	143	195	227	283	292	234	203
				4	≤ 0.25	≤ 1.5			162	208	191	260	303	377	390	312	270
							75	RPM	59377	31668	15834	7917	3958	2375	1979	1188	950
			Slot					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	1	≤ 1	(60-90)	Feed (mm/min)	59	76	70	95	111	138	143	114	99
				3	1	≤ 0.5			119	152	139	190	222	276	285	228	198
				4	1	≤ 0.4			119	152	139	190	222	276	285	228	198
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250					96	RPM	76342	40715	20358	10179	5089	3054	2545	1527	1221
			Profile					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	≤ 0.50	≤ 1.5	(77-115)	Feed (mm/min)	76	98	90	122	143	177	183	147	127
				3	≤ 0.25	≤ 1.5			115	147	134	183	214	266	275	220	191
				4	≤ 0.25	≤ 1.5			153	195	179	244	285	354	366	293	254
							70	RPM	55741	29729	14864	7432	3716	2230	1858	1115	892
			Slot					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	1	≤ 1	(56-84)	Feed (mm/min)	56	71	65	89	104	129	134	107	93
				3	1	≤ 0.5			84	107	98	134	156	194	201	161	139
				4	1	≤ 0.4			111	143	131	178	208	259	268	214	186
K	CAST IRONS Gray, Malleable, Ductile	≤ 220					102	RPM	81189	43301	21650	10825	5413	3248	2706	1624	1299
			Profile					Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	≤ 0.50	≤ 1.5	(82-123)	Feed (mm/min)	130	130	134	152	206	260	260	208	182
				3	≤ 0.25	≤ 1.5			195	195	201	227	309	390	390	312	273
				4	≤ 0.25	≤ 1.5			260	260	268	303	411	520	520	416	364
							75	RPM	59377	31668	15834	7917	3958	2375	1979	1188	950
			Slot					Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	1	≤ 1	(60-90)	Feed (mm/min)	95	95	98	111	150	190	190	152	133
				3	1	≤ 0.5			143	143	147	166	226	285	285	228	200
				4	1	≤ 0.4			190	190	196	222	301	380	380	304	266
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 275					113	RPM	89671	47825	23912	11956	5978	3587	2989	1793	1435
			Profile					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	≤ 0.50	≤ 1.5	(90-135)	Feed (mm/min)	90	115	105	143	167	208	215	172	149
				3	≤ 0.25	≤ 1.5			135	172	158	215	251	312	323	258	224
				4	≤ 0.25	≤ 1.5			179	230	210	287	335	416	430	344	298
							82	RPM	65436	34899	17449	8725	4362	2617	2181	1309	1047
			Slot					Fz	0.0005	0.0012	0.0022	0.006	0.014	0.029	0.036	0.048	0.052
				2	1	≤ 1	(66-99)	Feed (mm/min)	65	84	77	105	122	152	157	126	109
				3	1	≤ 0.5			98	126	115	157	183	228	236	188	163
				4	1	≤ 0.4			131	168	154	209	244	304	314	251	218
M	STAINLESS STEELS (DIFFICULT) 304, 304L, 316, 316L, 17-4 PH, 15-5, 13-4, Custom 450	≤ 275					78	RPM	61800	32960	16480	8240	4120	2472	2060	1236	989
			Profile					Fz	0.0005	0.0010	0.0019	0.004	0.012	0.024	0.029	0.037	0.042
				2	≤ 0.50	≤ 1.5	(62-93)	Feed (mm/min)	62	66	63	66	99	119	119	91	83
				3	≤ 0.25	≤ 1.5			93	99	94	99	148	178	179	137	125
				4	≤ 0.25	≤ 1.5			124	132	125	132	198	237	239	183	166
							56	RPM	44836	23912	11956	5978	2989	1793	1495	897	717
			Slot					Fz	0.0005	0.0010	0.0019	0.004	0.012	0.024	0.029	0.037	0.042
				2	1	≤ 1	(45-68)	Feed (mm/min)	45	48	45	48	72	86	87	66	60
				3	1	≤ 0.5			67	72	68	72	108	129	130	100	90
				4	1	≤ 0.4			90	96	91	96	143	172	173	133	121

continued on next page




	Series 1M, 3M, 5M, 14M, 15M, 16M, 17M, 59M Metric	Hardness BRINELL		Flutes	Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 0.4	0.75	1.5	3	6	10	12	20	25
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, 718, Incoly 800, Monel 400,Rene, Waspalloy	≤ 300	Profile				20	RPM	15753	8402	4201	2100	1050	630	525	315	252
								Fz	0.0005	0.0007	0.0014	0.004	0.010	0.021	0.024	0.032	0.035
				2	≤ 0.50	≤ 1.5	(16-24)	Feed (mm/min)	16	12	12	17	21	26	25	20	18
				3	≤ 0.25	≤ 1.5			24	18	18	25	32	40	38	30	26
				4	≤ 0.25	≤ 1.5			32	24	24	34	42	53	50	40	35
			Slot				14	RPM	10906	5816	2908	1454	727	436	364	218	174
								Fz	0.0005	0.0007	0.0014	0.004	0.010	0.021	0.024	0.032	0.035
				2	1	≤ 1	(11-16)	Feed (mm/min)	11	8	8	12	15	18	17	14	12
				3	1	≤ 0.5			16	12	12	17	22	27	26	21	18
				4	1	≤ 0.4			22	16	16	23	29	37	35	28	24
S	TITANIUM ALLOYS Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al	≤ 350	Profile				55	RPM	43624	23266	11633	5816	2908	1745	1454	872	698
								Fz	0.0005	0.0010	0.0019	0.004	0.012	0.024	0.029	0.037	0.042
				2	≤ 0.50	≤ 1.5	(44-66)	Feed (mm/min)	44	47	44	47	70	84	84	65	59
				3	≤ 0.25	≤ 1.5			65	70	66	70	105	126	127	97	88
				4	≤ 0.25	≤ 1.5			87	93	88	93	140	168	169	129	117
			Slot				40	RPM	31506	16803	8402	4201	2100	1260	1050	630	504
								Fz	0.0005	0.0010	0.0019	0.004	0.012	0.024	0.029	0.037	0.042
				2	1	≤ 1	(32-48)	Feed (mm/min)	32	34	32	34	50	60	61	47	42
				3	1	≤ 0.5			47	50	48	50	76	91	91	70	64
				4	1	≤ 0.4			63	67	64	67	101	121	122	93	85
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 150	Profile				268	RPM	213272	113745	56872	28436	14218	8531	7109	4265	3412
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	≤ 0.50	≤ 1.5	(215-322)	Feed (mm/min)	640	728	682	796	1081	1365	1365	1092	955
				3	≤ 0.25	≤ 1.5			960	1092	1024	1194	1621	2047	2047	1638	1433
			Slot				195	RPM	155107	82724	41362	20681	10340	6204	5170	3102	2482
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	1	≤ 1	(156-234)	Feed (mm/min)	465	529	496	579	786	993	993	794	695
				3	1	≤ 0.5			698	794	745	869	1179	1489	1489	1191	1042
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	Profile				148	RPM	117542	62689	31344	15672	7836	4702	3918	2351	1881
								Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	≤ 0.50	≤ 1.5	(118-177)	Feed (mm/min)	188	188	194	219	298	376	376	301	263
				3	≤ 0.25	≤ 1.5			282	282	292	329	447	564	564	451	395
				4	≤ 0.25	≤ 1.5			376	376	389	439	596	752	752	602	527
			Slot					RPM	84824	45239	22620	11310	5655	3393	2827	1696	1357
								Fz	0.0008	0.0015	0.0031	0.007	0.019	0.040	0.048	0.064	0.070
				2	1	≤ 1		Feed (mm/min)	136	136	140	158	215	271	271	217	190
				3	1	≤ 0.5			204	204	210	238	322	407	407	326	285
				4	1	≤ 0.4			271	271	280	317	430	543	543	434	380
	PLASTICS Polycarbonate, PVC, Polypropylene		Profile				268	RPM	213272	113745	56872	28436	14218	8531	7109	4265	3412
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	≤ 0.50	≤ 1.5	(215-322)	Feed (mm/min)	640	728	682	796	1081	1365	1365	1092	955
				3	≤ 0.25	≤ 1.5			960	1092	1024	1194	1621	2047	2047	1638	1433
				4	≤ 0.25	≤ 1.5			1280	1456	1365	1592	2161	2730	2730	2184	1911
			Slot				195	RPM	155107	82724	41362	20681	10340	6204	5170	3102	2482
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	1	≤ 1	(156-234)	Feed (mm/min)	465	529	496	579	786	993	993	794	695
				3	1	≤ 0.5			698	794	745	869	1179	1489	1489	1191	1042
				4	1	≤ 0.4			931	1059	993	1158	1572	1985	1985	1588	1390
	GRAPHITE		Profile				201	RPM	159954	85309	42654	21327	10664	6398	5332	3199	2559
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	≤ 0.50	≤ 1.5	(161-241)	Feed (mm/min)	480	546	512	597	810	1024	1024	819	717
				3	≤ 0.25	≤ 1.5			720	819	768	896	1216	1536	1536	1228	1075
				4	≤ 0.25	≤ 1.5			960	1092	1024	1194	1621	2047	2047	1638	1433
			Slot				146	RPM	116330	62043	31021	15511	7755	4653	3878	2327	1861
								Fz	0.0015	0.0032	0.0060	0.014	0.038	0.080	0.096	0.128	0.140
				2	1	≤ 1	(117-176)	Feed (mm/min)	349	397	372	434	589	745	745	596	521
				3	1	≤ 0.5			523	596	558	651	884	1117	1117	893	782
				4	1	≤ 0.4			698	794	745	869	1179	1489	1489	1191	1042

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
for tapered end mills, base the speed on the largest diameter contacting the workpiece and the feed on the smallest diameter
limit cut depths of long and extra long flute mills to .05 x D1 when slotting or profiling
reduce feed and Ae when finish milling (.02 x D1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


Diamond 1, 1B, 3, 3B Fractional	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	5/16	3/8	1/2
GRAPHITE Ultrafine, Superfine	N/A	Profile	≤ 0.25	≤ 1.5	720	RPM	22003	11002	8801	7334	5501
					(576-864)	Fz	0.0009	0.0023	0.0036	0.0043	0.0058
						Feed 2 flutes (IPM)	38.3	50.6	63.4	63.1	63.8
						Feed 3 flutes (IPM)	76.6	101.2	126.7	126.2	127.6
		Slot	≤ 1	≤ 1	580	RPM	17725	8862	7090	5908	4431
					(464-696)	Fz	0.0075	0.0020	0.0031	0.0038	0.0050
						Feed 2 flutes (IPM)	265.9	35.4	44.0	44.9	44.3
						Feed 3 flutes (IPM)	531.7	70.9	87.9	89.8	88.6
COMPOSITES FRP, CFRP, GRP	N/A	Profile	≤ 0.25	≤ 1.5	385	RPM	11766	5883	4706	3922	2941
					(308-462)	Fz	0.0005	0.0014	0.0022	0.0026	0.0035
						Feed 2 flutes (IPM)	12.2	16.5	20.7	20.4	20.6
						Feed 3 flutes (IPM)	24.5	32.9	41.4	40.8	41.2
		Slot	≤ 1	≤ 1	350	RPM	10696	5348	4278	3565	2674
					(280-420)	Fz	0.0005	0.0012	0.0019	0.0023	0.0030
						Feed 2 flutes (IPM)	9.6	12.8	16.3	16.4	16.0
						Feed 3 flutes (IPM)	19.3	25.7	32.5	32.8	32.1
PLASTICS Polycarbonate, PVC, Polypropylene	N/A	Profile	≤ 0.25	≤ 1.5	1200	RPM	36672	18336	14669	12224	9168
					(960-1440)	Fz	0.0009	0.0023	0.0036	0.0043	0.0058
						Feed 2 flutes (IPM)	63.8	84.3	105.6	105.1	106.3
						Feed 3 flutes (IPM)	127.6	168.7	211.2	210.3	212.7
		Slot	≤ 1	≤ 1	960	RPM	29338	14669	11735	9779	7334
					(768-1152)	Fz	0.0008	0.0020	0.0031	0.0038	0.0050
						Feed 2 flutes (IPM)	44.0	58.7	72.8	74.3	73.3
						Feed 3 flutes (IPM)	88.0	117.4	145.5	148.6	146.7

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
limit cut depths on long and extra long flute mills to .05 x D_1 when slotting or profiling
finish cuts typically require reduced feed and cut depths (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 52, 54 Fractional		Flutes	Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	3/4	1
N	ALUMINUM ALLOYS 2024, 5052, 5086, 6061, 6063, 7075	Profile				1360	RPM	41562	20781	13854	10390	6927	5195
							Fz	0.00069	0.0018	0.0034	0.0046	0.0055	0.0064
			2	≤ 0.3	≤ 1.5	(1088-1632)	Feed (IPM)	57.4	74.8	94.2	95.6	76.2	66.5
			4	≤ 0.3	≤ 1.5			114.7	149.6	188.4	191.2	152.4	133.0
		Slot				1090	RPM	33310	16655	11103	8328	5552	4164
							Fz	0.00063	0.0017	0.0032	0.0042	0.0050	0.0059
			2	1	≤ 1	(872-1308)	Feed (IPM)	42.0	56.6	71.1	70.0	55.5	49.1
			4	1	≤ 0.25			83.9	113.3	142.1	139.9	111.0	98.3
N	ALUMINUM DIE CAST ALLOYS (HIGH SILICON) A-390, A-392, B-390	Profile				510	RPM	15586	7793	5195	3896	2598	1948
							Fz	0.00069	0.0018	0.0034	0.0046	0.0055	0.0064
			2	≤ 0.3	≤ 1.5	(408-612)	Feed (IPM)	21.5	28.1	35.3	35.8	28.6	24.9
			4	≤ 0.3	≤ 1.5			43.0	56.1	70.7	71.7	57.1	49.9
		Slot				410	RPM	12530	6265	4177	3132	2088	1566
							Fz	0.00063	0.0017	0.0032	0.0042	0.0050	0.0059
			2	1	≤ 1	(328-492)	Feed (IPM)	15.8	21.3	26.7	26.3	20.9	18.5
			4	1	≤ 0.25			31.6	42.6	53.5	52.6	41.8	37.0
N	COPPER ALLOYS Aluminum Bronze, Nuntz Brass, Naval, Brass, Red Brass	Profile				590	RPM	18030	9015	6010	4508	3005	2254
							Fz	0.00039	0.0010	0.0020	0.0026	0.0031	0.0037
			2	≤ 0.3	≤ 1.5	(472-708)	Feed (IPM)	14.1	18.0	24.0	23.4	18.6	16.7
			4	≤ 0.3	≤ 1.5			28.1	36.1	48.1	46.9	37.3	33.4
		Slot				475	RPM	14516	7258	4839	3629	2419	1815
							Fz	0.00036	0.0010	0.0018	0.0024	0.0029	0.0034
			2	1	≤ 1	(380-570)	Feed (IPM)	10.5	14.5	17.4	17.4	14.0	12.3
			4	1	≤ 0.25			20.9	29.0	34.8	34.8	28.1	24.7
N	COPPER ALLOYS Beryllium Copper, C110, Manganese Bronze, Tin Bronze	Profile				235	RPM	7182	3591	2394	1795	1197	898
							Fz	0.00039	0.0010	0.0020	0.0026	0.0031	0.0037
			2	≤ 0.3	≤ 1.5	(188-282)	Feed (IPM)	5.6	7.2	9.6	9.3	7.4	6.6
			4	≤ 0.3	≤ 1.5			11.2	14.4	19.2	18.7	14.8	13.3
		Slot				190	RPM	5806	2903	1935	1452	968	726
							Fz	0.00036	0.0010	0.0018	0.0024	0.0029	0.0034
			2	1	≤ 1	(152-228)	Feed (IPM)	4.2	5.8	7.0	7.0	5.6	4.9
			4	1	≤ 0.25			8.4	11.6	13.9	13.9	11.2	9.9
	PLASTICS ABS, Polycarbonate, PVC, Polypropylene	Profile				1600	RPM	48896	24448	16299	12224	8149	6112
							Fz	0.00110	0.0030	0.0056	0.0074	0.0089	0.0100
			2	≤ 0.3	≤ 1.5	(1280-1920)	Feed (IPM)	107.6	146.7	182.5	180.9	145.1	122.2
			4	≤ 0.3	≤ 1.5			215.1	293.4	365.1	361.8	290.1	244.5
		Slot				1280	RPM	39117	19558	13039	9779	6519	4890
							Fz	0.00100	0.0027	0.0051	0.0068	0.0082	0.0095
			2	1	≤ 1	(1024-1536)	Feed (IPM)	78.2	105.6	133.0	133.0	106.9	92.9
			4	1	≤ 0.25			156.5	211.2	266.0	266.0	213.8	185.8
	PLASTICS Fiberglass, Glass Filled	Profile				1600	RPM	22003	11002	7334	5501	3667	2750
							Fz	0.00082	0.0022	0.0041	0.0055	0.0065	0.0076
			2	≤ 0.3	≤ 1.5	(1280-1920)	Feed (IPM)	36.1	48.4	60.1	60.5	47.7	41.8
			4	≤ 0.3	≤ 1.5			72.2	96.8	120.3	121.0	95.3	83.6
		Slot				1280	RPM	17572	8786	5857	4393	2929	2197
							Fz	0.00075	0.0020	0.0037	0.0050	0.0060	0.0070
			2	1	≤ 1	(1024-1536)	Feed (IPM)	26.4	35.1	43.3	43.9	35.1	30.8
			4	1	≤ 0.25			52.7	70.3	86.7	87.9	70.3	61.5

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 52, 54 Metric		Flutes	Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	10	12	20	25
N	ALUMINUM ALLOYS 2024, 5052, 5086, 6061, 6063, 7075	Profile				415	RPM	43947	21973	13184	10987	6592	5274
							Fz	0.0166	0.043	0.091	0.110	0.147	0.160
			2	≤ 0.3	≤ 1.5	(332-497)	Feed (mm/min)	1459	1890	2399	2417	1938	1688
			4	≤ 0.3	≤ 1.5			2918	3779	4799	4834	3876	3375
		Slot				332	RPM	35222	17611	10567	8806	5283	4227
							Fz	0.0151	0.041	0.085	0.101	0.133	0.148
			2	1	≤ 1	(266-399)	Feed (mm/min)	1064	1444	1796	1779	1405	1251
			4	1	≤ 0.25			2127	2888	3593	3557	2811	2502
N	ALUMINUM DIE CAST ALLOYS (HIGH SILICON) A-390, A-392, B-390	Profile				155	RPM	16480	8240	4944	4120	2472	1978
							Fz	0.0166	0.043	0.091	0.110	0.147	0.160
			2	≤ 0.3	≤ 1.5	(124-187)	Feed (mm/min)	547	709	900	906	727	633
			4	≤ 0.3	≤ 1.5			1094	1417	1800	1813	1454	1266
		Slot				125	RPM	13249	6624	3975	3312	1987	1590
							Fz	0.0151	0.041	0.085	0.101	0.133	0.148
			2	1	≤ 1	(100-150)	Feed (mm/min)	400	543	676	669	529	471
			4	1	≤ 0.25			800	1086	1351	1338	1057	941
N	COPPER ALLOYS Aluminum Bronze, Nuntz Brass, Naval, Brass, Red Brass	Profile				180	RPM	19065	9533	5720	4766	2860	2288
							Fz	0.0094	0.024	0.053	0.062	0.083	0.093
			2	≤ 0.3	≤ 1.5	(144-216)	Feed (mm/min)	358	458	606	591	475	426
			4	≤ 0.3	≤ 1.5			717	915	1213	1182	949	851
		Slot				145	RPM	15349	7675	4605	3837	2302	1842
							Fz	0.0086	0.024	0.048	0.058	0.077	0.085
			2	1	≤ 1	(116-174)	Feed (mm/min)	264	368	442	445	355	313
			4	1	≤ 0.25			528	737	884	890	709	626
N	COPPER ALLOYS Beryllium Copper, C110, Manganese Bronze, Tin Bronze	Profile				72	RPM	7594	3797	2278	1898	1139	911
							Fz	0.0094	0.024	0.053	0.062	0.083	0.093
			2	≤ 0.3	≤ 1.5	(57-86)	Feed (mm/min)	143	182	241	235	189	169
			4	≤ 0.3	≤ 1.5			286	365	483	471	378	339
		Slot				58	RPM	6140	3070	1842	1535	921	737
							Fz	0.0086	0.024	0.048	0.058	0.077	0.085
			2	1	≤ 1	(46-69)	Feed (mm/min)	106	147	177	178	142	125
			4	1	≤ 0.25			211	295	354	356	284	250
	PLASTICS ABS, Polycarbonate, PVC, Polypropylene	Profile				488	RPM	51702	25851	15511	12926	7755	6204
							Fz	0.0264	0.072	0.149	0.178	0.237	0.250
			2	≤ 0.3	≤ 1.5	(390-585)	Feed (mm/min)	2730	3723	4622	4601	3676	3102
			4	≤ 0.3	≤ 1.5			5460	7445	9244	9203	7352	6204
		Slot				390	RPM	41362	20681	12409	10340	6204	4963
							Fz	0.0240	0.065	0.136	0.163	0.210	0.238
			2	1	≤ 1	(312-468)	Feed (mm/min)	1985	2689	3375	3371	2606	2363
			4	1	≤ 0.25			3971	5377	6750	6742	5212	4725
	PLASTICS Fiberglass, Glass Filled	Profile				219	RPM	23266	11633	6980	5816	3490	2792
							Fz	0.0197	0.053	0.109	0.132	0.173	0.190
			2	≤ 0.3	≤ 1.5	(176-263)	Feed (mm/min)	917	1233	1522	1536	1208	1061
			4	≤ 0.3	≤ 1.5			1833	2466	3043	3071	2415	2122
		Slot				175	RPM	18580	9290	5574	4645	2787	2230
							Fz	0.0180	0.048	0.101	0.120	0.160	0.175
			2	1	≤ 1	(140-210)	Feed (mm/min)	669	892	1126	1115	892	780
			4	1	≤ 0.25			1338	1784	2252	2230	1784	1561

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 61 Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	3/8	1/2	3/4	1
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 175	Profile	≤ 0.5	≤ 1.5	500	RPM	7640	5093	3820	2547	1910
						(400-600)	Fz	0.0006	0.0011	0.0014	0.0017	0.0020
							Feed (IPM)	13.8	16.8	21.4	17.3	19.1
			Slot	1	≤ 1	400	RPM	6112	4075	3056	2037	1528
						(320-480)	Fz	0.0006	0.0011	0.0014	0.0017	0.0020
							Feed (IPM)	7.3	9.0	8.6	6.9	6.1
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 275	Profile	≤ 0.5	≤ 1.5	365	RPM	5577	3718	2789	1859	1394
						(292-438)	Fz	0.0004	0.0008	0.0011	0.0013	0.0015
							Feed (IPM)	4.5	5.9	6.1	4.8	4.2
			Slot	1	≤ 1	295	RPM	4508	3005	2254	1503	1127
						(236-354)	Fz	0.0004	0.0008	0.0011	0.0013	0.0015
							Feed (IPM)	3.6	4.8	5.0	3.9	3.4
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 250	Profile	≤ 0.5	≤ 1.5	345	RPM	5272	3514	2636	1757	1318
						(276-414)	Fz	0.0006	0.0009	0.0015	0.0018	0.0021
							Feed (IPM)	6.3	6.3	7.9	6.3	5.5
			Slot	1	≤ 1	275	RPM	4202	2801	2101	1401	1051
						(220-330)	Fz	0.0006	0.0009	0.0015	0.0018	0.0021
							Feed (IPM)	5.0	5.0	6.3	5.0	4.4
K	**CAST IRONS Gray, Mallable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	365	RPM	5577	3718	2789	1859	1394
						(292-438)	Fz	0.0008	0.0015	0.0020	0.0024	0.0028
							Feed (IPM)	8.9	11.2	11.2	8.9	7.8
			Slot	1	≤ 1	295	RPM	4508	3005	2254	1503	1127
						(236-354)	Fz	0.0008	0.0015	0.0020	0.0024	0.0028
							Feed (IPM)	7.2	9.0	9.0	7.2	6.3

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 61M Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	10	12	20	25
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 175	Profile	≤ 0.5	≤ 1.5	152	RPM	8078	4847	4039	2424	1939
						(122-183)	Fz	0.014	0.029	0.034	0.045	0.050
							Feed (mm/min)	339	422	549	436	485
			Slot	1	≤ 1	122	RPM	6463	3878	3231	1939	1551
						(98-146)	Fz	0.014	0.029	0.034	0.045	0.050
							Feed (mm/min)	271	337	439	349	388
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 275	Profile	≤ 0.5	≤ 1.5	111	RPM	5897	3538	2949	1769	1415
						(89-134)	Fz	0.010	0.021	0.026	0.035	0.038
							Feed (mm/min)	177	223	307	248	269
			Slot	1	≤ 1	90	RPM	4766	2860	2383	1430	1144
						(72-108)	Fz	0.010	0.021	0.026	0.035	0.038
							Feed (mm/min)	143	180	248	200	217
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 250	Profile	≤ 0.5	≤ 1.5	105	RPM	5574	3344	2787	1672	1338
						(84-126)	Fz	0.014	0.024	0.036	0.048	0.053
							Feed (mm/min)	234	241	401	321	355
			Slot	1	≤ 1	84	RPM	4443	2666	2222	1333	1066
						(67-101)	Fz	0.014	0.024	0.036	0.048	0.053
							Feed (mm/min)	187	192	320	256	283
K	**CAST IRONS Gray, Mallable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	111	RPM	5897	3538	2949	1769	1415
						(89-134)	Fz	0.019	0.040	0.048	0.064	0.070
							Feed (mm/min)	336	425	566	453	495
			Slot	1	≤ 1	90	RPM	4766	2860	2383	1430	1144
						(72-108)	Fz	0.019	0.040	0.048	0.064	0.070
							Feed (mm/min)	272	343	458	366	400

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series 62 Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	3/8	1/2	3/4	1
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F, 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	405	RPM	6188	4126	3094	2063	1547
						(324-486)	Fz	0.0006	0.0011	0.0015	0.0019	0.0021
							Feed (IPM)	11.1	13.6	18.6	15.7	19.5
			Slot	1	≤ 1	325	RPM	4966	3311	2483	1655	1242
						(260-390)	Fz	0.0006	0.0011	0.0015	0.0019	0.0021
							Feed (IPM)	8.9	10.9	14.9	12.6	15.6
M	**STAINLESS STEELS (DIFFICULT) 304, 304L, 316, 316L, 17-4PH, 15-5PH, 13-4PH, Custom 450**	≤ 275	Profile	≤ 0.5	≤ 1.5	280	RPM	4278	2852	2139	1426	1070
						(224-336)	Fz	0.0005	0.0009	0.0012	0.0015	0.0017
							Feed (IPM)	6.4	7.7	10.3	8.6	10.9
			Slot	1	≤ 1	225	RPM	3438	2292	1719	1146	860
						(180-270)	Fz	0.0005	0.0009	0.0012	0.0015	0.0017
							Feed (IPM)	5.2	6.2	8.3	6.9	8.8
S	**SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspalloy**	≤ 300	Profile	≤ 0.5	≤ 1.5	70	RPM	1070	713	535	357	267
						(56-84)	Fz	0.0004	0.0008	0.0010	0.0013	0.0014
							Feed (IPM)	1.3	1.7	2.1	1.9	2.2
			Slot	1	≤ 1	56	RPM	856	570	428	285	214
						(45-67)	Fz	0.0004	0.0008	0.0010	0.0013	0.0014
							Feed (IPM)	1.0	1.4	1.7	1.5	1.8
S	**TITANIUM ALLOYS Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al**	≤ 350	Profile	≤ 0.5	≤ 1.5	155	RPM	2368	1579	1184	789	592
						(124-186)	Fz	0.0005	0.0009	0.0012	0.0015	0.0017
							Feed (IPM)	3.6	4.3	5.7	4.7	6.0
			Slot	1	≤ 1	195	RPM	2980	1986	1490	993	745
						(156-234)	Fz	0.0005	0.0009	0.0012	0.0015	0.0017
							Feed (IPM)	4.5	5.4	7.2	6.0	7.6

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


	Series 62M Metric	Hardness BRINELL		 Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	10	12	20	25
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F, 440F	≤ 175	Profile	≤ 0.5	≤ 1.5	123	RPM	6544	3926	3272	1963	1570
						(99-148)	Fz	0.014	0.029	0.036	0.051	0.053
							Feed (mm/min)	283	345	471	398	495
			Slot	1	≤ 1	99	RPM	5251	3151	2626	1575	1260
						(79-119)	Fz	0.014	0.029	0.036	0.051	0.053
							Feed (mm/min)	227	277	378	319	397
M	STAINLESS STEELS (DIFFICULT) 304, 304L, 316, 316L, 17-4PH, 15-5PH, 13-4PH, Custom 450	≤ 275	Profile	≤ 0.5	≤ 1.5	85	RPM	4524	2714	2262	1357	1086
						(68-102)	Fz	0.012	0.024	0.029	0.040	0.043
							Feed (mm/min)	163	195	261	217	277
			Slot	1	≤ 1	69	RPM	3635	2181	1818	1091	872
						(55-82)	Fz	0.012	0.024	0.029	0.040	0.043
							Feed (mm/min)	131	157	209	174	222
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspalloy	≤ 250	Profile	≤ 0.5	≤ 1.5	21	RPM	1131	679	565	339	271
						(17-26)	Fz	0.010	0.021	0.024	0.035	0.035
							Feed (mm/min)	33	43	54	47	57
			Slot	1	≤ 1	17	RPM	905	543	452	271	217
						(14-20)	Fz	0.010	0.021	0.024	0.035	0.035
							Feed (mm/min)	26	35	43	38	46
S	TITANIUM ALLOYS Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al	≤ 220	Profile	≤ 0.5	≤ 1.5	47	RPM	2504	1503	1252	751	601
						(38-57)	Fz	0.012	0.024	0.029	0.040	0.043
							Feed (mm/min)	90	108	144	120	153
			Slot	1	≤ 1	59	RPM	3151	1890	1575	945	756
						(48-71)	Fz	0.012	0.024	0.029	0.040	0.043
							Feed (mm/min)	113	136	181	151	193

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x number of flutes x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




	Series MK2 Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 0.008	0.016	0.031	0.04	0.06
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 175	Profile	≤ 0.5	≤ 1.5	320	RPM	152800	76400	39432	30560	20373
						(256-384)	Fz	0.000018	0.000040	0.000070	0.000110	0.000140
							Feed (IPM)	5.5	6.1	5.5	6.7	5.7
			Slot	1	≤ 1	255	RPM	121763	60881	31423	24353	16235
						(204-306)	Fz	0.000016	0.000030	0.000060	0.000090	0.000130
							Feed (IPM)	3.9	3.7	3.8	4.4	4.2
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 275	Profile	≤ 0.5	≤ 1.5	235	RPM	112213	56106	28958	22443	14962
						(188-282)	Fz	0.000014	0.000030	0.000050	0.000080	0.000110
							Feed (IPM)	3.1	3.4	2.9	3.6	3.3
			Slot	1	≤ 1	190	RPM	90725	45363	23413	18145	12097
						(152-228)	Fz	0.000012	0.000020	0.000050	0.000070	0.000090
							Feed (IPM)	2.2	1.8	2.3	2.5	2.2
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 250	Profile	≤ 0.5	≤ 1.5	220	RPM	105050	52525	27110	21010	14007
						(176-264)	Fz	0.000014	0.000030	0.000050	0.000080	0.000110
							Feed (IPM)	2.9	3.2	2.7	3.4	3.1
			Slot	1	≤ 1	175	RPM	83563	41781	21565	16713	11142
						(140-210)	Fz	0.000012	0.000020	0.000050	0.000070	0.000090
							Feed (IPM)	2.0	1.7	2.2	2.3	2.0
K	**CAST IRONS Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	235	RPM	112213	56106	28958	22443	14962
						(188-282)	Fz	0.000018	0.000040	0.000070	0.000110	0.000140
							Feed (IPM)	4.0	4.5	4.1	4.9	4.2
			Slot	1	≤ 1	190	RPM	90725	45363	23413	18145	12097
						(152-228)	Fz	0.000016	0.000030	0.000060	0.000090	0.000130
							Feed (IPM)	2.9	2.7	2.8	3.3	3.1
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	260	RPM	124150	62075	32039	24830	16553
						(208-312)	Fz	0.000014	0.000030	0.000050	0.000080	0.000110
							Feed (IPM)	3.5	3.7	3.2	4.0	3.6
			Slot	1	≤ 1	210	RPM	100275	50138	25877	20055	13370
						(168-252)	Fz	0.000012	0.000020	0.000050	0.000070	0.000090
							Feed (IPM)	2.4	2.0	2.6	2.8	2.4
M	**STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L**	≤ 275	Profile	≤ 0.5	≤ 1.5	180	RPM	85950	42975	22181	17190	11460
						(144-216)	Fz	0.000011	0.000020	0.000040	0.000060	0.000090
							Feed (IPM)	1.9	1.7	1.8	2.1	2.1
			Slot	1	≤ 1	145	RPM	69238	34619	17868	13848	9232
						(116-174)	Fz	0.000010	0.000020	0.000040	0.000060	0.000080
							Feed (IPM)	1.4	1.4	1.4	1.7	1.5

continued on next page




	Series MK2 Fractional	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 0.008	0.016	0.031	0.04	0.06
S	**SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, 718, Incoly 800, Monel 400, Rene, Waspalloy**	≤ 300	Profile	≤ 0.5	≤ 1.5	45	RPM	21488	10744	5545	4298	2865
						(36-54)	Fz	0.000009	0.000020	0.000040	0.000050	0.000070
							Feed (IPM)	0.4	0.4	0.4	0.4	0.4
			Slot	1	≤ 1	35	RPM	16713	8356	4313	3343	2228
						(28-42)	Fz	0.000008	0.000015	0.000030	0.000040	0.000060
							Feed (IPM)	0.3	0.3	0.3	0.3	0.3
S	**TITANIUM ALLOYS (DIFFICULT) Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al**	≤ 350	Profile	≤ 0.5	≤ 1.5	125	RPM	59688	29844	15403	11938	7958
						(100-150)	Fz	0.000011	0.000020	0.000040	0.000060	0.000090
							Feed (IPM)	1.3	1.2	1.2	1.4	1.4
			Slot	1	≤ 1	100	RPM	47750	23875	12323	9550	6367
						(80-120)	Fz	0.000010	0.000020	0.000040	0.000060	0.000080
							Feed (IPM)	1.0	1.0	1.0	1.1	1.0
N	**ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075**	≤ 150	Profile	≤ 0.5	≤ 1.5	800	RPM	382000	191000	98581	76400	50933
						(640-960)	Fz	0.000037	0.000070	0.000140	0.000220	0.000290
							Feed (IPM)	28.3	26.7	27.6	33.6	29.5
			Slot	1	≤ 1	640	RPM	305600	152800	78865	61120	40747
						(512-768)	Fz	0.000032	0.000060	0.000130	0.000190	0.000250
							Feed (IPM)	19.6	18.3	20.5	23.2	20.4
N	**COPPER ALLOYS Alum Bronze, C110, Muntz Brass**	≤ 140	Profile	≤ 0.5	≤ 1.5	240	RPM	114600	57300	29574	22920	15280
						(192-288)	Fz	0.000018	0.000040	0.000070	0.000110	0.000140
							Feed (IPM)	4.1	4.6	4.1	5.0	4.3
			Slot	1	≤ 1	190	RPM	90725	45363	23413	18145	12097
						(152-228)	Fz	0.000016	0.000030	0.000060	0.000090	0.000130
							Feed (IPM)	2.9	2.7	2.8	3.3	3.1
	PLASTICS Polycarbonate, PVC, Polypropylene		Profile	≤ 0.5	≤ 1.5	800	RPM	382000	191000	98581	76400	50933
						(640-960)	Fz	0.000037	0.000070	0.000140	0.000220	0.000290
							Feed (IPM)	28.3	26.7	27.6	33.6	29.5
			Slot	1	≤ 1	640	RPM	305600	152800	78865	61120	40747
						(512-768)	Fz	0.000032	0.000060	0.000130	0.000190	0.000250
							Feed (IPM)	19.6	18.3	20.5	23.2	20.4
	GRAPHITE	≤ 140	Profile	≤ 0.5	≤ 1.5	600	RPM	286500	143250	73935	57300	38200
						(480-720)	Fz	0.000037	0.000070	0.000140	0.000220	0.000290
							Feed (IPM)	21.2	20.1	20.7	25.2	22.2
			Slot	1	≤ 1	480	RPM	229200	114600	59148	45840	30560
						(384-576)	Fz	0.000032	0.000060	0.000130	0.000190	0.000250
							Feed (IPM)	14.7	13.8	15.4	17.4	15.3

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 2 x rpm
reduce speed and feed for materials harder than listed
reduce speed to meet machine limitations
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



	Series MK2 Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 0.2	0.41	0.79	1.02	1.52
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 175	Profile	≤ 0.5	≤ 1.5	98	RPM	155107	75662	39267	30413	20409
						(78-117)	Fz	0.00046	0.0010	0.0018	0.0028	0.0036
							Feed (mm/min)	143	151	141	170	147
			Slot	1	≤ 1	78	RPM	123601	60293	31291	24235	16263
						(62-93)	Fz	0.00041	0.0008	0.0015	0.0023	0.0033
							Feed (IPM)	101	96	94	111	107
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 275	Profile	≤ 0.5	≤ 1.5	72	RPM	113906	55564	28837	22335	14988
						(57-86)	Fz	0.00036	0.0008	0.0013	0.0002	0.0028
							Feed (IPM)	82	89	75	9	84
			Slot	1	≤ 1	58	RPM	92095	44924	23315	18058	12118
						(46-69)	Fz	0.00030	0.0005	0.0013	0.0018	0.0023
							Feed (IPM)	55	45	61	65	56
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 250	Profile	≤ 0.5	≤ 1.5	67	RPM	106636	52017	26996	20909	14031
						(54-80)	Fz	0.00036	0.0008	0.0013	0.0002	0.0028
							Feed (IPM)	77	83	70	8	79
			Slot	1	≤ 1	53	RPM	84824	41378	21474	16632	11161
						(43-64)	Fz	0.00030	0.0005	0.0013	0.0018	0.0023
							Feed (IPM)	51	41	56	60	51
K	**CAST IRONS Gray, Malleable, Ductile**	≤ 220	Profile	≤ 0.5	≤ 1.5	72	RPM	113906	55564	28837	22335	14988
						(57-86)	Fz	0.00046	0.0010	0.0018	0.0028	0.0036
							Feed (IPM)	105	111	104	125	108
			Slot	1	≤ 1	58	RPM	92095	44924	23315	18058	12118
						(46-69)	Fz	0.00041	0.0008	0.0015	0.0023	0.0033
							Feed (IPM)	76	72	70	83	80
M	**STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F**	≤ 275	Profile	≤ 0.5	≤ 1.5	79	RPM	126024	61475	31905	24711	16582
						(63-95)	Fz	0.00036	0.0008	0.0013	0.0002	0.0028
							Feed (IPM)	91	98	83	10	93
			Slot	1	≤ 1	64	RPM	101789	49653	25769	19959	13393
						(51-77)	Fz	0.00030	0.0005	0.0013	0.0018	0.0023
							Feed (IPM)	61	50	67	72	62
M	**STAINLESS STEELS (DIFFICULT) 304, 304L,316, 316L**	≤ 275	Profile	≤ 0.5	≤ 1.5	55	RPM	87247	42560	22088	17107	11480
						(44-66)	Fz	0.00028	0.0005	0.0010	0.0015	0.0023
							Feed (IPM)	49	43	44	51	53
			Slot	1	≤ 1	44	RPM	70283	34284	17793	13781	9248
						(35-53)	Fz	0.00025	0.0005	0.0010	0.0015	0.0020
							Feed (IPM)	35	34	36	41	37

continued on next page



	Series MK2 Metric	Hardness BRINELL		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 0.2	0.41	0.79	1.02	1.52
S	**SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, 718, Incoly 800, Monel 400, Rene, Waspalloy**	≤ 300	Profile	≤ 0.5	≤ 1.5	14	RPM	21812	10640	5522	4277	2870
						(11-16)	Fz	0.00023	0.0005	0.0010	0.0013	0.0018
							Feed (IPM)	10	11	11	11	10
			Slot	1	≤ 1	11	RPM	16965	8276	4295	3326	2232
						(9-13)	Fz	0.00020	0.0005	0.0008	0.0013	0.0015
							Feed (IPM)	7	8	7	9	7
S	**TITANIUM ALLOYS (DIFFICULT) Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti10Al2Fe3Al, Ti5Al53Mo3Cr, Ti7Al4Mo, Ti3Al8V6Cr4Zr4Mo, Ti6Al6V6Sn, Ti152 Cr3Sn3Al**	≤ 350	Profile	≤ 0.5	≤ 1.5	38	RPM	60589	29555	15339	11880	7972
						(30-46)	Fz	0.00028	0.0005	0.0010	0.0015	0.0023
							Feed (IPM)	34	30	31	36	37
			Slot	1	≤ 1	30	RPM	48471	23644	12271	9504	6378
						(24-37)	Fz	0.00025	0.0005	0.0010	0.0015	0.0020
							Feed (IPM)	24	24	25	29	26
N	**ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075**	≤ 150	Profile	≤ 0.5	≤ 1.5	244	RPM	387767	189154	98169	76033	51022
						(195-293)	Fz	0.00094	0.0018	0.0036	0.0056	0.0074
							Feed (IPM)	729	681	707	852	755
			Slot	1	≤ 1	195	RPM	310213	151324	78535	60826	40818
						(156-234)	Fz	0.00081	0.0015	0.0033	0.0048	0.0064
							Feed (IPM)	503	454	518	584	522
N	**COPPER ALLOYS Alum Bronze, C110, Muntz Brass**	≤ 140	Profile	≤ 0.5	≤ 1.5	73	RPM	116330	56746	29451	22810	15307
						(59-88)	Fz	0.00046	0.0010	0.0018	0.0028	0.0036
							Feed (IPM)	107	113	106	128	110
			Slot	1	≤ 1	58	RPM	92095	44924	23315	18058	12118
						(46-69)	Fz	0.00041	0.0008	0.0015	0.0023	0.0033
							Feed (IPM)	76	72	70	83	80
	PLASTICS Polycarbonate, PVC, Polypropylene		Profile	≤ 0.5	≤ 1.5	244	RPM	387767	189154	98169	76033	51022
						(195-293)	Fz	0.00094	0.0018	0.0036	0.0056	0.0074
							Feed (IPM)	729	681	707	852	755
			Slot	1	≤ 1	195	RPM	310213	151324	78535	60826	40818
						(156-234)	Fz	0.00081	0.0015	0.0033	0.0048	0.0064
							Feed (IPM)	503	454	518	584	522
	GRAPHITE	≤ 140	Profile	≤ 0.5	≤ 1.5	183	RPM	290825	141866	73627	57024	38266
						(146-219)	Fz	0.00094	0.0018	0.0036	0.0056	0.0074
							Feed (IPM)	547	511	530	639	566
			Slot	1	≤ 1	146	RPM	232660	113493	58901	45620	30613
						(117-176)	Fz	0.00081	0.0015	0.0033	0.0048	0.0064
							Feed (IPM)	377	340	389	438	392

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 2 x rpm
reduce speed and feed for materials harder than listed
reduce speed to meet machine limitations
reduce feed and Ae when finish milling (.02 x D_1 maximum)
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

Application Tips

Tool	• Whenever possible, select an end mill with the largest diameter, shortest flute length, and shortest overall length for the best rigidity • Long flute tools are not intended for pocketing, slotting, or heavy profiling – limit Rw to .02D • High Performance tools minimize cycle time and extend tool life
Tool Holders	• Holders with adequate gripping pressure and TIR are required • Stub holders or zero length collet style holders are recommended for heavy stock removal • When using solid holders, hand ground screw flats are not recommended
Workpiece	• Secure clamping of the workpiece will reduce chatter and deflection
Machine	• Spindle must be in optimum condition for precise TIR and maximum tool life • Sufficient horsepower is required to perform at recommended speeds and feeds • Reduce rates for low power machines to prevent workpiece and / or tool damage
Coolant	• Avoid re-milling chips through use of air blast or liquid coolant as necessary • Maintain clean coolant with appropriate concentration • General recommendations: –Water Soluble Oil or Air Blast: Tool Steels, Mold & Die Steels, Carbon or Alloy Steels –Water Soluble Oil: Stainless Steels, Titanium, High Temperature Alloys, Non-Ferrous Alloys
Methods	• Climb milling is generally preferred • Attention to programming details, tool holders, TIR, balance, fixturing, etc. improve cutting tool performance and extend tool life

END MILLING GUIDELINE

D_1 = cutting diameter L_2 = flute length

Speeds and Feeds for Cut Types are based on Radial Width (Rw) and Axial Depth (Ad)

Reductions to Speeds and Feeds may be necessary when:
- Rw and Ad exceed recommendations
- Using long flute or extended reach tools
- Using long tool holders
- Machining materials harder than listed

ENTRY METHODS

Pre-Drilled Hole




Pre-drilling is the preferred entry method for most applications.

Helical Ramp



Straight Ramp



Alternative methods are helical and straight ramping. High ramp angles require reduced feed. Lower ramp angles will allow higher feed rates and extend tool life. Use slotting speeds and feeds for ramp angles of 1° to 2°. Reduce feed to 25% when ramp angles approach 6°. General purpose tools and/or difficult to machine materials will require lower ramp angles and reduced feed.

Plunge



Plunge only in non-ferrous and short-chipping materials using slotting speeds and 25% slotting feeds.

Puntas para aplicaciones

Herramientas	• Siempre que sea posible, seleccione el cortador con el mayor diámetro, largo de filo y largo total mas corto posible para obtener una mejor rigidez. • Las herramientas con filos largos no son recomendadas para operaciones de apertura de cajas en el maquinado, operación de ranurado o perfilado pesado – limitar la profundidad radial (Rw) a .02D • Las herramientas de alto desempeño minimizan el tiempo de ciclo del maquinado y extienden la vida útil de la herramienta
Portaherramientas	• Los Portaherramientas deberán tener buena presión de agarre para la sujeción de la herramienta y una concentricidad máxima indicada (TIR) • Se recomienda usar portaherramientas de agarre directo cortos, o de boquilla con longitud cero para lograr un máximo arranque de viruta • Cuando se utilicen portaherramientas de agarre directo, no se recomienda hacer manualmente el plano para la sujeción del tornillo en el zanco de la herramienta
Pieza a maquinar	• La buena sujeción de la pieza a maquinar reducirá la vibración y la desviación de la herramienta
Máquina	• El usillo de la maquina debe estar en condiciones optimas, para asegurar la concentricidad de giro (TIR) y asegurar el máximo rendimiento de la herramienta • Para lograr los avances y velocidades recomendados, se necesita suficiente potencia (HP) en la maquina • Reducir los parámetros de corte en maquinas de baja potencia (HP) para prevenir el daño en la herramienta o pieza de trabajo
Refrigerante	• Evite el re-maquinado de virutas usando aire a presión o líquido refrigerante según sea necesario • Mantener limpio el refrigerante con su concentración adecuada • Recomendaciones generales: –Para el maquinado de Aceros Grado Herramienta, para Moldes y Dados o Aleaciones de Bajo Carbón, utilice Aceite Soluble en Agua o aire a presión –Para el maquinado de Aleaciones Inoxidables, Aleaciones de Alta Temperatura, Titanio y Aleaciones No Ferrosas, utilice solamente Aceite Soluble en Agua
Métodos	• Se recomienda el maquinado en sentido ascendente o trepado • El cuidado en los detalles de la programación, la concentricidad de giro (TIR) el balance de los portaherramientas, la sujeción de la pieza a maquinar, etc. son factores que contribuyen a prolongar la vida de la herramienta

GUÍAS DE FRESADO

D_1 = diámetro de corte L_2 = largo de filo

Las velocidades y avances para cortes están basados en la profundidad radial (→|Rw|←), y profundidad axial ($\overset{\downarrow}{\underset{\uparrow}{Ad}}$)

Reducciones en velocidades y avances serán necesarias cuando:
- Rw y Ad exceda las recomendaciones
- Se utilicen filos largos o herramientas de largo alcance
- Se utilicen portaherramientas largos
- Se maquinen materiales más duros que los recomendados

MÉTODOS DE ENTRADA

Barreno previo




Preferentemente usar un barreno previo como método de entrada para la mayor parte de las aplicaciones.

Rampa helicoidal



Rampa recta



Los métodos alternativos son las rampas helicoidales y rectas. Un ángulo elevado de rampa necesita un avance reducido. Un ángulo de rampa inferior permitirá tasas de avance más elevadas y una mayor duración de la herramienta. Usar velocidades y alcances de ranurado para ángulos de rampa de 1° a 2°. Disminuir el avance un 25% cuando los ángulos de rampa se aproximan a 6°. Las herramientas de uso general y/o materiales difíciles de mecanizar precisarán ángulos de rampa inferiores y un avance reducido.

Agujero o Barrenado



Este método se puede utilizar únicamente en materiales no ferrosos y materiales de formación de virutas cortas, usando la velocidad de ranurado y el 25% de su avance.

Outil	• Chaque fois que possible, choisissez une fraise de plus grand diamètre possible, la plus courte possible, elle garantira la meilleure rigidité • Les outils longs ne sont pas optimum pour l'ébauche, le pocketing, le rainurage – ae limité à 0,02 D • Les outils Haute performance optimisent les temps de cycle et de augmentent la durée de vie
Porte-outils	• Des attachements à serrage puissant et à faux rond précis sont recommandés • Attachements à méplats ou pinces à serrage nominale sont recommandées pour les ébauches • Lorsque vous utilisez des attachement rigides, les serrage de l'outil par vis ne sont pas recommandés
Pièce	• Le système de fixation et de bridage de la pièce devra permettre de réduire les vibrations et la déformation
Machine	• Broche doit être en bon état optimal au niveau de son faux rond • Suffisamment puissance est nécessaire pour effectuer à des vitesses recommandées et se nourrit • Réduire les efforts pour les machines de faible puissance pour éviter l'endommagement de la pièce et / ou de l'outil
Liquide de refroidissement	• Évitez les recyclage de copeaux par l'utilisation de soufflage d'air comprimé ou de liquide de refroidissement. • Maintenir le lubrifiant propre à la concentration appropriée • Recommandations générales – –Huile soluble ou Air comprimé: aciers à outils, aciers pour moules, aciersau carbone ou alliés –Huile soluble: aciers inoxydables, titane, alliages à haute température, alliages non ferreux
Méthodes	• L'usinage en avalant est généralement préconisé • Attention à la programmation, porte-outils, faux rond, équilibrage, fixation, etc améliorent les performances de l'outil en coupe et prolonge la durée de vie

GUIDE DU FRAISAGE

D_1 = diamètre de coupe L_2 = longueur de coupe

Vitesses & avances pour ces cas d'usinage sont basées sur l'engagement radial (←|ae|→), et axial ($\frac{ap}{}$)

La réduction de la vitesse et de l'avance doit être nécessaire quand:
- Les engagements ap et ae sont importants
- Des dentures longues ou des séries longues sont utilisées
- Des attachement longs sont utilisés
- Lors d'usinage de matériaux durs

TYPES D'ENTREE MATIERE

Preperçage




Le pré-perçage est la méthode préférable dans la plupart de applications.

Ramping hélicoïdal



Ramping droit



Les autres méthodes sont un ramping hélicoïdal et un ramping droit. Les angles de ramping élevés exigent une avance inférieure. Les angles de ramping inférieurs permettent les taux d'avance supérieurs et prolongeront la vie de l'outil. Utilisez des avances et vitesses de mortaisage pour les angles de ramping de 1° à 2°. Réduisez l'avance à 25 % lorsque les angles de ramping avoisinent 6°. Les outils tout usage et/ou les matériaux difficiles à usiner exigeront des angles de ramping inférieurs et une charge réduite.

Plongée



Plongée uniquement dans les non ferreux. Vitesse rainurage et avances réduites de 25%.

SGS

DRILLS



Hole Making

HIGH PERFORMANCE DRILLS	SERIES	PAGE
Hi-PerCarb Double Margin Drills	135 3xD, 135 5xD	163
ICe-Carb Internal Coolant Drills	140 5xD, 140 8xD	170
CFRP 8 Facet Drills	120	178
TECHNICAL INFORMATION		
Speed & Feed Recommendations		179
Drilling Operations		194
Coolant Recommendations		194

GENERAL PURPOSE DRILLS	SERIES	PAGE
2 Flute Drills	101	197
Short Length Self Centering Drill • DIN 6539	108M Plus	203
Straight Flute Drills	106	206
3 Flute Drills with 150 Point Geometry	103	209
TECHNICAL INFORMATION		
Speed & Feed Recommendations		214

COUNTERSINKS	SERIES	PAGE
Combined Drill & Countersink	301, 301M	221
Single Flute Countersink	601	222
3 Flute Countersink	603	223
6 Flute Countersink	606	224
TECHNICAL INFORMATION		
Speed & Feed Recommendations		225

REAMERS	SERIES	PAGE
Straight Flute Reamer	201M	235
Straight Flute Accu-Reamer	200	236
TECHNICAL INFORMATION		
Speed & Feed Recommendations		238

Taladrado

TALADROS DE ALTO RENDIMIENTO	SERIE	PÁGINA
Taladros de doble margen Hi-PerCarb	135 3xD, 135 5xD	163
Taladros con refrigerante interno ICe-Carb	140 5xD, 140 8xD	170
Taladros de 8 caras CFRP	120	178
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		179
Operaciones de taladrado		194
Refrigerantes recomendados		194

TALADROS DE USO GENERAL	SERIE	PÁGINA
Taladros de 2 filos	101	197
Taladro autocentrante de longitud corta • DIN 6539	108M Plus	203
Taladros de filo recto	106	206
Taladros de 3 filos con geometría de 150 puntos	103	209
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		214

AVELLANADORES	SERIE	PÁGINA
Taladro y avellanador combinados	301, 301M	221
Avellanador de filo único	601	222
Avellanador de 3 filos	603	223
Avellanador de 6 filos	606	224
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		225

ESCARIADORES	SERIE	PÁGINA
Escariador de filo recto	201M	235
Escariador Accu de filo recto	200	236
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		238

Outils de perçage

PERCEUSES HAUTE PERFORMANCE	SERIES	PAGE
Foret à double listel Hi-PerCarb	135 3xD, 135 5xD	163
Perceuse ICe-Carb à refroidissement interne	140 5xD, 140 8xD	170
Perceuse CFRP à 8 facettes	120	178
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		179
Opérations de forage		194
Agents de refroidissement recommandés		194

PERCEUSES UNIVERSELLE	SERIES	PAGE
2 forets à hélice	101	197
Foret court à centrage automatique DIN 6539	108M Plus	203
Perceuses taille droite	106	206
3 forets à hélice à point géométriques 150	103	209
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		214

FORETS FRAISEUSES	SERIES	PAGE
Foret fraiseuse	301, 301M	221
Foret fraiseuse à dent simple	601	222
Foret fraiseuse 3 dents	603	223
foret fraiseuse 6 dents	606	224
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		225

ALESOIRS	SERIES	PAGE
Alésoir denture droit	201M	235
Alésoirs denture droite Accu-Reamer	200	236
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		238

Drill Icon Legend
Leyenda del icono de los taladros
Légende d'icone de perçage

END CONFIGURATIONS
CONFIGURACIONES DE LA PUNTA
CONFIGURATIONS TERMINALES



Drill
Fresa
Fraise

SHANK TYPE
TIPO DE VÁSTAGO
TYPE DE TIGE



Common
Normal
Commune



Straight
Recto
Droite

REACH
ALCANCE
LONGUEUR

3xD

>3xD Reach
Alcance >3xD
>Longueur 3xD

5xD

5xD Reach
Alcance 5xD
Longueur 5xD

8xD

8xD Reach
Alcance 8xD
Longueur 8xD

HELIX ANGLES
ÁNGULOS HELICOIDALES
ANGLES DE L'HÉLICE



Right Spiral
Espiral sentido derecho
Spirale droite



None
Ninguno
Aucun

ADDITIONAL GEOMETRY
CARACTERÍSTICAS GEOMÉTRICAS ADICIONALES
GÉOMÉTRIE SUPPLÉMENTAIRE



Right Cut Direction
Fresado sentido derecha
Coupe vers la droite

COOLANT OPTIONS
OPCIONES DE REFRIGERACIÓN
OPTIONS DE REFROIDISSEMENT



Internal Coolant
Refrigerante externo
Refroidissement interne



External Coolant
Refrigerante interno
Refroidissement externe

COATINGS
REVESTIMIENTOS
REVÊTEMENTS



Uncoated



Ti-NAMITE-A
(AlTiN)




Di-NAMITE
(Diamond)

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS







135 3xD

FRACTIONAL & METRIC SERIES

TECH INFO 179–182

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6

CUTTING DIAMETER D_1	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	SHANK DIAMETER D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	SHANK LENGTH L_4	Ti-NAMITE-A (AlTiN) EDP NO.
1/64*	0.0156		1/8	1-1/2	1/8	5/64	1	51752
1/32*	0.0312		1/8	1-1/2	1/4	3/16	1	51269
3/64*	0.0469	1/16-64	1/8	1-1/2	3/8	5/16	1	51270
1/16*	0.0625	5/64-60	1/8	2	7/16	3/8	1-1/4	51271
5/64*	0.0781		1/8	2	1/2	7/16	1-1/4	51272
3/32	0.0938	1/8-32	1/8	2	1/2	7/16	1-1/4	51273
#40	0.0980		1/8	2	9/16	1/2	1-1/4	51274
#39	0.0995		1/8	2	9/16	1/2	1-1/4	51753
#38	0.1015	5-40	1/8	2	9/16	1/2	1-1/4	51754
#37	0.1040	5-44	1/8	2	9/16	1/2	1-1/4	51755
#36	0.1065	6-32	1/8	2	9/16	1/2	1-1/4	51756
7/64	0.1094		1/8	2	5/8	9/16	1-1/4	51275
#35	0.1100		1/8	2	5/8	9/16	1-1/4	51276
#34	0.1110		1/8	2	5/8	9/16	1-1/4	51277
#33	0.1130	6-40	1/8	2	5/8	9/16	1-1/4	51757
#32	0.1160		1/8	2	5/8	9/16	1-1/4	51758
3,0mm	0.1181		6,0mm	62,0mm	20,1mm	17,0	36,0mm	63155
#31	0.1200		1/8	2	5/8	9/16	1-1/4	51759
3.1mm	0.1220		6,0mm	62,0mm	20,0mm	17,0	36,0mm	63741
1/8	0.1250		1/4	2-9/16	3/4	21/32	1-7/16	51330
3.2mm	0.1260	M3,5 X 0,35	6,0mm	62,0mm	20,0mm	17,0	36,0mm	63156
#30	0.1285		1/4	2-9/16	3/4	21/32	1-7/16	51278
3.3mm	0.1299	M4 X 0, 7	6,0mm	62,0mm	20,0mm	17,0	36,0mm	63157
3.4mm	0.1339		6,0mm	62,0mm	20,0mm	17,0	36,0mm	63158
#29	0.1360	8-32,8-36	1/4	2-1/2	3/4	21/32	1-7/16	51331
3.5mm	0.1378	M4 X 0, 5	6,0mm	62,0mm	20,0mm	17,0	36,0mm	63159
#28	0.1405	8-40	1/4	2-1/2	3/4	21/32	1-7/16	51760
9/64	0.1406		1/4	2-1/2	3/4	21/32	1-7/16	51332
3.6mm	0.1417	M4 X 0,35	6,0mm	62,0mm	20,0mm	17,0	36,0mm	63160
#27	0.1440		1/4	2-1/2	3/4	21/32	1-7/16	51761
3.7mm	0.1457	M4.5 X 0,75	6,0mm	62,0mm	20,0mm	17,0	36,0mm	63161
#26	0.1470	3/16-24	1/4	2-1/2	3/4	21/32	1-7/16	51762
#25	0.1495	10-24	1/4	2-5/8	7/8	23/32	1-7/16	51333
3.8mm	0.1496		6,0	66,0	24,0	21,0	36,0	63742
#24	0.1520	10-28	1/4	2-5/8	7/8	23/32	1-7/16	51763
3.9mm	0.1535		6,0mm	66,0mm	20,0mm	21,0	43,5mm	63743
#23	0.1540		1/4	2-5/8	7/8	23/32	1-7/16	51764
5/32	0.1562		1/4	2-5/8	7/8	23/32	1-7/16	51334
#22	0.1570	10-30	1/4	2-5/8	7/8	23/32	1-7/16	51765
4.0mm	0.1575	M4,5 X 0,5	6,0mm	66,0mm	24,1mm	21,0	36,0mm	63162
#21	0.1590	10-32	1/4	2-5/8	7/8	23/32	1-7/16	51335
#20	0.1610	13/64-24	1/4	2-5/8	7/8	23/32	1-7/16	51279
4.1mm	0.1614		6,0mm	66,0mm	20,0mm	21,0	36,0mm	63744
4.2mm	0.1654	M5 / M5 X 0,75	6,0mm	66,0mm	24,1mm	21,0	36,0mm	63163

*Single Margin


continued on next page

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
HARDENED STEELS

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS







135 3xD

FRACTIONAL & METRIC SERIES

TECH INFO 179–182

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER D_1	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	SHANK DIAMETER D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	SHANK LENGTH L_4	Ti-NAMITE-A (AlTiN) EDP NO.
#19	0.1660		1/4	2-5/8	7/8	23/32	1-7/16	51766
4.3mm	0.1693		6,0mm	66,0mm	24,1mm	21,0	36,0mm	63164
#18	0.1695		1/4	2-5/8	7/8	23/32	1-7/16	51767
11/64	0.1719		1/4	2-5/8	7/8	23/32	1-7/16	51336
#17	0.1730		1/4	2-5/8	7/8	23/32	1-7/16	51768
4.4mm	0.1732		6,0mm	66,0mm	20,0mm	21,0	36,0mm	63745
#16	0.1770	12-24	1/4	2-5/8	7/8	23/32	1-7/16	51769
4.5mm	0.1772	M5 X 0,5	6,0mm	66,0mm	24,1mm	21,0	36,0mm	63165
#15	0.1800		1/4	2-5/8	7/8	23/32	1-7/16	51770
4.6mm	0.1811	12-28	6,0mm	66,0mm	24,1mm	21,0	36,0mm	63166
#14	0.1820		1/4	2-5/8	7/8	23/32	1-7/16	51771
#13	0.1850	12-32	1/4	2-5/8	7/8	23/32	1-7/16	51772
4.7mm	0.1850		6,0mm	66,0mm	20,0mm	21,0	36,0mm	63746
3/16	0.1875		1/4	2-5/8	1	53/64	1-7/16	51337
#12	0.1890	7/32-32	1/4	2-5/8	1	53/64	1-7/16	51773
4.8mm	0.1890		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63167
#11	0.1910		1/4	2-5/8	1	53/64	1-7/16	51774
4.9mm	0.1929		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63747
#10	0.1935	14-20	1/4	2-5/8	1	53/64	1-7/16	51775
#09	0.1960		1/4	2-5/8	1	53/64	1-7/16	51776
5mm	0.1969	M6 X 1	6,0mm	66,0mm	28,0mm	24,0	36,0mm	63168
#08	0.1990		1/4	2-5/8	1	53/64	1-7/16	51777
5.1mm	0.2008		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63748
#07	0.2010	1/4-20	1/4	2-5/8	1	53/64	1-7/16	51338
13/64	0.2031		1/4	2-5/8	1	53/64	1-7/16	51339
#06	0.2040		1/4	2-5/8	1	53/64	1-7/16	51778
5.2mm	0.2047	M6 X 0,75	6,0mm	66,0mm	28,0mm	24,0	36,0mm	63749
#05	0.2055		1/4	2-5/8	1	53/64	1-7/16	51779
5.25mm	0.2067		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63169
5.3mm	0.2087		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63170
#04	0.2090	1/4-24	1/4	2-5/8	1	53/64	1-7/16	51780
5.4mm	0.2126		6,0mm	66,0mm	28,0mm	24,0	36,0	63750
#03	0.2130	1/4-28	1/4	2-5/8	1	53/64	1-7/16	51340
5.5mm	0.2165	M6 X 0,5	6,0mm	66,0mm	28,0mm	24,0	36,0mm	63171
7/32	0.2188	1/4-32	1/4	2-5/8	1	53/64	1-7/16	51341
5.6mm	0.2205		6,0mm	66,0mm	28,0mm	24,0	36,0	63751
#02	0.2210		1/4	2-5/8	1	53/64	1-7/16	51781
5.7mm	0.2244		6,0mm	66,0mm	28,0mm	24,0	36,0	63752
#01	0.2280		1/4	2-5/8	1	53/64	1-7/16	51782
5.8mm	0.2283		6,0mm	66,0mm	28,0mm	24,0	36,0mm	63172
5.9mm	0.2323		6,0mm	66,0mm	28,0mm	24,0	36,0	63753
A	0.2340		1/4	2-5/8	1	53/64	1-7/16	51601
15/64	0.2344		1/4	2-5/8	1	53/64	1-7/16	51342
6mm	0.2362	M7 X 1	6,0mm	66,0mm	28,0mm	24,0	36,0mm	63173

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS



135 3xD

FRACTIONAL & METRIC SERIES

CONTINUED


CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	EDP NO.
B	0.2380		1/4	3-1/8	1-5/16	1-3/64	1-7/16	51602
6.1mm	0.2402		8,0mm	79,0mm	34,0mm	28,0	36,0	63754
C	0.2420		1/4	3-1/8	1-5/16	1-3/64	1-7/16	51603
6.2mm	0.2441		8,0mm	79,0mm	34,0mm	28,0	36,0	63755
D	0.2460		1/4	3-1/8	1-5/16	1-3/64	1-7/16	51604
6.25mm	0.2461	M7 X 0, 75	8,0mm	79,0mm	34,0mm	28,0	36,0mm	63174
6.3mm	0.2480		8,0mm	79,0mm	34,0mm	28,0	36,0	63756
1/4	0.2500		1/4	3-1/8	1-5/16	1-3/64	1-7/16	51343
6.4mm	0.2520		8,0mm	79,0mm	34,0mm	28,0	36,0mm	63175
6.5mm	0.2559		8,0mm	79,0mm	34,0mm	28,0	36,0mm	63213
F	0.2570	5/16-18	5/16	3-1/8	1-5/16	1-3/64	1-7/16	51344
6.6mm	0.2598		8,0mm	79,0mm	34,0mm	28,0	36,0	63757
G	0.2610		5/16	3-1/8	1-5/16	1-3/64	1-7/16	51606
6.7mm	0.2638		8,0mm	79,0mm	28,0	28,0	36,0	63758
17/64	0.2656	5/16-20	5/16	3-1/8	1-5/16	1-3/64	1-7/16	51345
H	0.2660		5/16	3-1/8	1-5/16	1-3/64	1-7/16	51607
6.8mm	0.2677	M8 X 1,25	8,0mm	79,0mm	34,0mm	28,0	36,0mm	63176
6.9mm	0.2717		8,0mm	79,0mm	34,0mm	28,0	36,0	63759
I	0.2720	5/16-24	5/16	3-1/8	1-5/16	1-3/64	1-7/16	51346
7mm	0.2756	M8 X 1	8,0mm	79,0mm	34,0mm	28,0	36,0mm	63177
J	0.2770		5/16	3-1/8	1-5/16	1-3/64	1-7/16	51608
7.1mm	0.2795		8,0mm	79,0mm	41,0mm	34,0	36,0	63760
K	0.2810		5/16	3-1/8	1-9/16	1-3/16	1-7/16	51609
9/32	0.2812	5/16-32	5/16	3-1/8	1-9/16	1-3/16	1-7/16	51347
7.2mm	0.2835		8,0mm	79,0mm	41,0mm	34,0	36,0	63761
7.25mm	0.2854	M8 X 0, 75	8,0mm	79,0mm	41,0mm	34,0	36,0mm	63178
7.3mm	0.2874		8,0mm	79,0mm	41,0mm	34,0	36,0	63762
L	0.2900		5/16	3-1/8	1-9/16	1-3/16	1-7/16	51610
7.4mm	0.2913		8,0mm	79,0mm	41,0	34,0	36,0	63763
M	0.2950		5/16	3-1/8	1-9/16	1-3/16	1-7/16	51611
7.5mm	0.2953	M8 X 0,5	8,0mm	79,0mm	41,0mm	34,0	36,0mm	63179
19/64	0.2969		5/16	3-1/8	1-9/16	1-3/16	1-7/16	51348
7.6mm	0.2992		8,0mm	79,0mm	41,0	34,0	30,0mm	63764
N	0.3020		5/16	3-1/8	1-9/16	1-3/16	1-7/16	51612
7.7mm	0.3031		8,0mm	79,0mm	41,0	34,0	36,0	63765
7.8mm	0.3071	M9 X 1,25	8,0mm	79,0mm	41,0mm	34,0	36,0mm	63180
7.9mm	0.3110		8,0mm	79,0mm	41,0	34,0	36,0	63766
5/16	0.3125	3/8-16	5/16	3-1/8	1-9/16	1-3/16	1-7/16	51349
8mm	0.3150	M9 X 1	8,0mm	79,0mm	41,0mm	34,0	36,0mm	63181
O	0.3160		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51613
8.1mm	0.3189		10,0mm	89,0mm	47,0mm	40,0	40,0	63767
8.2mm	0.3228		10,0mm	89,0mm	47,0mm	40,0	40,0	63768
P	0.3230		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51614
8.3mm	0.3268		10,0mm	89,0mm	41,0	40,0	40,0	63769
21/64	0.3281	3/8-20	3/8	3-1/2	1-27/32	1-37/64	1-9/16	51350
8.4mm	0.3307		10,0mm	89,0	47,0mm	40,0	40,0mm	63182
Q	0.3320	3/8-24	3/8	3-1/2	1-27/32	1-37/64	1-9/16	51351
8.5mm	0.3346	M10 X 1,5	10,0mm	89,0	47,0mm	40,0	40,0mm	63183
8.6mm	0.3386		10,0mm	89,0mm	47,0	40,0	40,0	63770
R	0.3390		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51615

continued on next page

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS







135 3xD

FRACTIONAL & METRIC SERIES

TECH INFO 179–182

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	EDP NO.
8.7mm	0.3425		10,0mm	89,0mm	47,0	40,0	40,0	63771
11/32	0.3438	3/8-32	3/8	3-1/2	1-27/32	1-37/64	1-9/16	51352
8.8mm	0.3465	M10 X 1,25	10,0mm	89,0	47,0mm	40,0	40,0mm	63184
S	0.3480		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51616
8.9mm	0.3504		10,0mm	89,0mm	47,0	40,0	40,0	63772
9mm	0.3543	M10 X 1	10,0mm	89,0	47,0mm	40,0	40,0mm	63185
T	0.3580		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51617
9.1mm	0.3583		10,0mm	89,0mm	47,0	40,0	40,0	63773
23/64	0.3594		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51353
9.2mm	0.3622	M10 X 0,75	10,0mm	89,0mm	47,0	40,0	40,0	63774
9.25mm	0.3642		10,0mm	89,0	47,0mm	40,0	40,0mm	63186
9.3mm	0.3661		10,0mm	89,0mm	47,0	40,0	40,0	63775
U	0.3680	7/16-14	3/8	3-1/2	1-27/32	1-37/64	1-9/16	51354
9.4mm	0.3701		10,0mm	89,0mm	47,0	40,0	40,0	63776
9.5mm	0.3740	M10 X 0,5	10,0mm	89,0	47,0mm	40,0	40,0mm	63187
3/8	0.3750		3/8	3-1/2	1-27/32	1-37/64	1-9/16	51355
V	0.3770		1/2	3-1/2	1-27/32	1-37/64	1-9/16	51618
9.6mm	0.3780		10,0mm	89,0mm	47,0	40,0	40,0	63777
9.7mm	0.3819		10,0mm	89,0mm	47,0	40,0	40,0	63778
9.8mm	0.3858		10,0mm	89,0mm	47,0	40,0	40,0	63779
W	0.3860		1/2	3-1/2	1-27/32	1-37/64	2-9/16	51619
9.9mm	0.3898		10,0mm	89,0mm	47,0	40,0	40,0	63780
25/64	0.3906	7/16-20	1/2	3-1/2	1-27/32	1-37/64	1-9/16	51356
10mm	0.3937		10,0mm	89,0	47,0mm	40,0	40,0mm	63188
X	0.3970	7/16-24	1/2	4-1/16	2-3/11	1-51/64	1-49/64	51620
10.1mm	0.3976		12,0mm	102,0mm	33,0mm	55,0	45,0	63781
10.2mm	0.4016	M12 X 1,75	12,0mm	102,0	55,0mm	45,0	45,0mm	63189
Y	0.4040	7/16-28	1/2	4-1/16	2-3/16	1-51/64	1-49/64	51621
10.3mm	0.4055		12,0mm	102,0mm	55,0	45,0	45,0	63782
13/32	0.4062		1/2	4-1/16	2-3/16	1-51/64	1-49/64	51357
10.4mm	0.4095		12,0mm	102,0mm	55,0mm	45,0	45,0	63783
Z	0.4130		1/2	4-1/16	2-3/16	1-51/64	1-49/64	51622
10.5mm	0.4134	M12 X 1,5	12,0mm	102,0	55,0mm	45,0	45,0mm	63190
10.6mm	0.4173		12,0mm	102,0mm	55,0	45,0	45,0	63784
10.7mm	0.4213		12,0mm	102,0mm	55,0	45,0	45,0	63785
27/64	0.4219	1/2-13	1/2	4-1/16	2-3/16	1-51/64	1-49/64	51358
10.8mm	0.4252	M12 X 1,25	12,0mm	102,0	55,0mm	45,0	45,0mm	63191
10.9mm	0.4291		12,0mm	102,0mm	55,0	45,0	45,0	63786
11mm	0.4331	M12 X 1	12,0mm	102,0	55,0mm	45,0	45,0mm	63192
11.1mm	0.4370		12,0mm	102,0mm	55,0	45,0	45,0	63787
7/16	0.4375	1/4-18 NPT	1/2	4-1/16	2-3/16	1-51/64	1-49/64	51359
11.2mm	0.4409		12,0mm	102,0mm	55,0	45,0	45,0	63788
11.25mm	0.4429		12,0mm	102,0	55,0mm	45,0	45,0	63193
11.3mm	0.4449		12,0mm	102,0mm	55,0	45,0	45,0	63789

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS



135 3xD


FRACTIONAL & METRIC SERIES

CONTINUED

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	EDP NO.
11.4mm	0.4488		12,0mm	102,0mm	55,0	45,0	45,0	63790
11.5mm	0.4528	M12 X 0,5	12,0mm	102,0	55,0mm	45,0	45,0mm	63194
29/64	0.4531	1/2-20	1/2	4-1/16	2-3/16	1-51/64	1-49/64	51360
11.6mm	0.4567		12,0mm	102,0mm	55,0	45,0	45,0	63791
11.7mm	0.4606		12,0mm	102,0mm	55,0	45,0	45,0	63792
11.8mm	0.4646		12,0mm	102,0mm	55,0	45,0	45,0	63793
11.9mm	0.4685		12,0mm	102,0mm	55,0	45,0	45,0	63794
15/32	0.4688	1/2-28	1/2	4-1/16	2-3/16	1-51/64	1-49/64	51361
12mm	0.4724	M14 X 2	12,0mm	102,0	55,0mm	45,0	45,0mm	63195
31/64	0.4844	9/16-12	1/2	4-1/4	2-5/16	1-7/8	1-49/64	51362
12.5mm	0.4921	M14 X 1,5	14,0mm	107,0	60,0mm	45,0	45,0mm	63196
1/2	0.5000		1/2	4-1/4	2-5/16	1-7/8	1-49/64	51363
12.8mm	0.5039	M14 X 1,25	14,0mm	107,0	60,0mm	45,0	45,0mm	63197
13mm	0.5118	M14 X 1	14,0mm	107,0	60,0mm	45,0	45,0mm	63198
33/64	0.5156	9/16-18	5/8	4-1/4	2-5/16	1-7/8	1-49/64	51364
17/32	0.5312	5/8-11	5/8	4-1/4	2-5/16	1-7/8	1-49/64	51365
13.5mm	0.5315		14,0mm	107,0	60,0mm	45,0	45,0mm	63199
35/64	0.5469	5/8-12	5/8	4-1/4	2-5/16	1-7/8	1-49/64	51783
14mm	0.5512	M16 X 2	14,0mm	107,0mm	60,0mm	49,0	45,0mm	63200
9/16	0.5625		5/8	4-9/16	2-1/2	2	1-57/64	51366
14.5mm	0.5709	M16 X 1,5	16,0mm	115,0mm	65,0mm	51,0	48,0mm	63201
37/64	0.5781	5/8-18	5/8	4-9/16	2-1/2	2	1-57/64	51367
15mm	0.5906	M16 X 1	16,0mm	115,0mm	65,0mm	51,0	48,0mm	63202
19/32	0.5938	11/16-11	5/8	4-9/16	2-1/2	2	1-57/64	51784
39/64	0.6094	11/16-12	5/8	4-9/16	2-1/2	2	1-57/64	51785
15.5mm	0.6102	M18 X 2,5	16,0mm	115,0mm	65,0mm	51,0	48,0mm	63203
5/8	0.6250	11/16-16	5/8	4-9/16	2-1/2	2	1-57/64	51368
16mm	0.6299		16,0mm	115,0mm	65,0mm	51,0	48,0mm	63204
41/64	0.6406	11/16-24	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51786
16.5mm	0.6496	M18 X 1,5	18,0mm	123,0mm	73,0mm	58,0	48,0mm	63205
21/32	0.6562	3/4-10	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51369
17mm	0.6693		18,0mm	123,0mm	73,0mm	58,0	48,0mm	63206
43/64	0.6719	3/4-12	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51787
11/16	0.6875	3/4-16	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51370
17.5mm	0.6890	M20 X 2,5	18,0mm	123,0mm	73,0mm	58,0	48,0mm	63207
45/64	0.7031	3/4-20, 1/2-14	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51788
18mm	0.7087		18,0mm	131,0mm	73,0mm	58,0	48,0mm	63208
23/32	0.7188		3/4	4-7/8	2-3/4	2-5/16	1-57/64	51789
18.5mm	0.7283	M20 X 1,5	20,0mm	131,0mm	79,0mm	63,0	50,0mm	63209
47/64	0.7344	13/16-12	3/4	4-7/8	2-3/4	2-5/16	1-57/64	51790
19mm	0.7480		20,0mm	131,0mm	79,0mm	63,0	50,0mm	63210
3/4	0.7500	13/16-16	3/4	5-1/4	3-1/16	2-7/16	1-31/32	51371
49/64	0.7656	7/8-9	7/8	5-1/4	3-1/16	2-7/16	1-31/32	51372
19.5mm	0.7677	M22 X 2,5	20,0mm	131,0mm	79,0mm	63,0	50,0mm	63211
25/32	0.7812		7/8	6	3-11/16	2-11/16	2-1/8	51791
20mm	0.7874		20,0mm	131,0mm	79,0mm	63,0	50,0mm	63212
51/64	0.7969	7/8-12	7/8	6	3-11/16	2-11/16	2-1/8	51792
13/16	0.8125	7/8-14	7/8	6	3-11/16	2-11/16	2-1/8	51373
7/8	0.8750	15/16-16, 1-8	7/8	6	3-11/16	2-11/16	2-1/8	51374
59/64	0.9219	1-12	1	6	3-11/16	2-11/16	2-1/8	51375







135 5xD

FRACTIONAL SERIES

TECH INFO 183–184

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	inch					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
1/8	0.1250		1/4	3	1	53/64	1-15/16	51580
#30	0.1285		1/4	3	1	53/64	1-15/16	51581
#29	0.1360	8-32,8-36	1/4	3	1	53/64	1-15/16	51582
9/64	0.1406		1/4	3	1	53/64	1-15/16	51583
#25	0.1495	10-24	1/4	3-1/4	1-1/4	1-5/64	1-15/16	51584
5/32	0.1562		1/4	3-1/4	1-1/4	1-5/64	1-15/16	51585
#21	0.1590	10-32	1/4	3-1/4	1-1/4	1-5/64	1-15/16	51586
#20	0.1610	13/64-24	1/4	3-1/4	1-1/4	1-5/64	1-15/16	51587
11/64	0.1719		1/4	3-1/4	1-1/4	1-5/64	1-15/16	51588
3/16	0.1875		1/4	3-1/4	1-3/4	1-37/64	1-7/16	51589
#07	0.2010	1/4-20	1/4	3-1/4	1-3/4	1-37/64	1-7/16	51506
13/64	0.2031		1/4	3-1/4	1-3/4	1-37/64	1-7/16	51507
#05	0.2055		1/4	3-1/4	1-3/4	1-37/64	1-7/16	51590
#04	0.2090	1/4-24	1/4	3-1/4	1-3/4	1-37/64	1-7/16	51508
#03	0.2090	1/4-28	1/4	3-1/4	1-3/4	1-37/64	1-7/16	51509
7/32	0.2188	1/4-32	1/4	3-1/4	1-3/4	1-37/64	1-7/16	51510
15/64	0.2344		1/4	3-1/4	1-3/4	1-37/64	1-7/16	51591
1/4	0.2500		1/4	3-5/8	2-5/64	1-51/64	1-7/16	51511
F	0.2570	5/16-18	5/16	3-5/8	2-5/64	1-51/64	1-7/16	51512
17/64	0.2656	5/16-20	5/16	3-5/8	2-5/64	1-51/64	1-7/16	51513
I	0.2720	5/16-24	5/16	3-5/8	2-5/64	1-51/64	1-7/16	51514
9/32	0.2812	5/16-32	5/16	3-5/8	2-5/64	1-51/64	1-7/16	51515
19/64	0.2969		5/16	3-5/8	2-5/64	1-51/64	1-7/16	51516
5/16	0.3125	3/8-16	5/16	3-5/8	2-5/64	1-51/64	1-7/16	51517
P	0.3230		3/8	4	2-13/32	2-1/8	1-9/16	51518
21/64	0.3281	3/8-20	3/8	4	2-13/32	2-1/8	1-9/16	51519
Q	0.3320	3/8-24	3/8	4	2-13/32	2-1/8	1-9/16	51520
11/32	0.3438	3/8-32	3/8	4	2-13/32	2-1/8	1-9/16	51521
S	0.3480		3/8	4	2-13/32	2-1/8	1-9/16	51522
23/64	0.3594		3/8	4	2-13/32	2-1/8	1-9/16	51523

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS





135 5xD
FRACTIONAL SERIES

CONTINUED

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	inch					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
U	0.3680	7/16-14	3/8	4	2-13/32	2-1/8	1-9/16	51524
3/8	0.3750		3/8	4	2-13/32	2-1/8	1-9/16	51525
W	0.3860		1/2	4	2-13/32	2-1/8	1-9/16	51526
25/64	0.3906	7/16-20	1/2	4	2-13/32	2-1/8	1-9/16	51527
13/32	0.4062		1/2	4-11/16	2-3/4	2-23/64	1-49/64	51528
27/64	0.4219	1/2-13	1/2	4-11/16	2-3/4	2-23/64	1-49/64	51529
7/16	0.4375	1/4-18 NPT	1/2	4-11/16	2-3/4	2-23/64	1-49/64	51530
29/64	0.4531	1/2-20	1/2	4-11/16	2-3/4	2-23/64	1-49/64	51531
15/32	0.4688	1/2-28	1/2	4-11/16	2-3/4	2-23/64	1-49/64	51532
31/64	0.4844	9/16-12	1/2	4-7/8	3-1/32	2-19/32	1-49/64	51533
1/2	0.5000		1/2	4-7/8	3-1/32	2-19/32	1-49/64	51534
33/64	0.5156	9/16-18	5/8	4-7/8	3-1/32	2-19/32	1-49/64	51535
17/32	0.5312	5/8-11	5/8	4-7/8	3-1/32	2-19/32	1-49/64	51536
35/64	0.5469	5/8-12	5/8	4-7/8	3-1/32	2-19/32	1-49/64	51537
9/16	0.5625		5/8	5-1/4	3-1/4	2-3/4	1-57/64	51538
37/64	0.5781	5/8-18	5/8	5-1/4	3-1/4	2-3/4	1-57/64	51539
19/32	0.5938	11/16-11	5/8	5-1/4	3-1/4	2-3/4	1-57/64	51592
39/64	0.6094	11/16-12	5/8	5-1/4	3-1/4	2-3/4	1-57/64	51593
5/8	0.6250	11/16-16	5/8	5-1/4	3-1/4	2-3/4	1-57/64	51540
41/64	0.6406	11/16-24	3/4	5-5/8	3-5/8	3-3/16	1-57/64	51594
21/32	0.6562	3/4-10	3/4	5-5/8	3-5/8	3-3/16	1-57/64	51541
43/64	0.6719	3/4-12	3/4	5-5/8	3-5/8	3-3/16	1-57/64	51595
11/16	0.6875	3/4-16	3/4	5-5/8	3-5/8	3-3/16	1-57/64	51542
45/64	0.7031	3/4-20, 1/2-14 NPT	3/4	5-5/8	3-5/8	3-3/16	1-57/64	51543
23/32	0.7188		3/4	6	4	3-3/8	1-31/32	51596
47/64	0.7344	13/16-12	3/4	6	4	3-3/8	1-31/32	51544
3/4	0.7500	13/16-16	3/4	6	4	3-3/8	1-31/32	51545







140 5xD

FRACTIONAL & METRIC SERIES

TECH INFO 185–188

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	EDP NO. Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
3,0 mm	0.1181		6,0	66,0	28,0	23,0	36,0	63901
3,1 mm	0.1220		6,0	66,0	28,0	23,0	36,0	63902
1/8	0.1250		6,0	66,0	28,0	23,0	36,0	51901
3,2 mm	0.1260	M3,5 X 0,35	6,0	66,0	28,0	23,0	36,0	63903
3,3 mm	0.1299	M4 X 0,7	6,0	66,0	28,0	23,0	36,0	63904
3,4 mm	0.1339		6,0	66,0	28,0	23,0	36,0	63905
29	0.1360	8-32,8-36	6,0	66,0	28,0	23,0	36,0	51902
3,5 mm	0.1378	M4 X 0,5	6,0	66,0	28,0	23,0	36,0	63906
9/64	0.1406		6,0	66,0	28,0	23,0	36,0	51903
3,6 mm	0.1417	M4 X 0,35	6,0	66,0	28,0	23,0	36,0	63907
3,7 mm	0.1457	M4,5 X 0,75	6,0	66,0	28,0	23,0	36,0	63908
3,8 mm	0.1496	10-24	6,0	74,0	36,0	29,0	36,0	51904
3,9 mm	0.1535		6,0	74,0	36,0	29,0	36,0	63909
5/32	0.1562		6,0	74,0	36,0	29,0	36,0	51905
4,0 mm	0.1575	M4,5 X 0,5	6,0	74,0	36,0	29,0	36,0	63910
21	0.1590	10-32	6,0	74,0	36,0	29,0	36,0	51906
4,1 mm	0.1614		6,0	74,0	36,0	29,0	36,0	63911
4,2 mm	0.1654	M5 / M5 x 0,75	6,0	74,0	36,0	29,0	36,0	63912
4,3 mm	0.1693		6,0	74,0	36,0	29,0	36,0	63913
11/64	0.1719		6,0	74,0	36,0	29,0	36,0	51907
4,4 mm	0.1732	12-24	6,0	74,0	36,0	29,0	36,0	63914
4,5 mm	0.1772	M5 X 0,5	6,0	74,0	36,0	29,0	36,0	63915
4,6 mm	0.1811	12-28,0	6,0	74,0	36,0	29,0	36,0	63916
4,7 mm	0.1850	12-32	6,0	74,0	36,0	29,0	36,0	63917
3/16	0.1875		6,0	82,0	44,0	35,0	36,0	51908
4,8 mm	0.1890	7/32-32	6,0	82,0	44,0	35,0	36,0	63918
4,9 mm	0.1929		6,0	82,0	44,0	35,0	36,0	63919
5,0 mm	0.1969	M6 X 1	6,0	82,0	44,0	35,0	36,0	63920
5,1 mm	0.2008	1/4-20	6,0	82,0	44,0	35,0	36,0	63900
13/64	0.2031		6,0	82,0	44,0	35,0	36,0	51910
5,2 mm	0.2047	M6 X 0,75	6,0	82,0	44,0	35,0	36,0	63921
5,3 mm	0.2087		6,0	82,0	44,0	35,0	36,0	63922

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6



140 5xD

FRACTIONAL & METRIC SERIES


CONTINUED

CUTTING DIAMETER D_1	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm SHANK DIAMETER D_2	mm OVERALL LENGTH L_1	mm FLUTE LENGTH L_2	mm CLEARED LENGTH L_3	mm SHANK LENGTH L_4	EDP NO. Ti-NAMITE-A (AlTiN)
5,4 mm	0.2126		6,0	82,0	44,0	35,0	36,0	63998
5,5 mm	0.2165	M6 X 0,5	6,0	82,0	44,0	35,0	36,0	63923
7/32	0.2188	1/4-32	6,0	82,0	44,0	35,0	36,0	51912
5,6 mm	0.2205		6,0	82,0	44,0	35,0	36,0	63924
5,7 mm	0.2244		6,0	82,0	44,0	35,0	36,0	63925
5,8 mm	0.2283		6,0	82,0	44,0	35,0	36,0	63926
5,9 mm	0.2323		6,0	82,0	44,0	35,0	36,0	63927
15/64	0.2344		6,0	82,0	44,0	35,0	36,0	51913
6,0 mm	0.2362	M7 X 1	6,0	82,0	44,0	35,0	36,0	63928,0
6,1 mm	0.2402		8,0	91,0	53,0	43,0	36,0	63929
6,2 mm	0.2441	M7 X 0,75	8,0	91,0	53,0	43,0	36,0	63930
6,3 mm	0.2480		8,0	91,0	53,0	43,0	36,0	63931
1/4	0.2500		8,0	91,0	53,0	43,0	36,0	51914
6,4 mm	0.2520		8,0	91,0	53,0	43,0	36,0	63932
6,5 mm	0.2559		8,0	91,0	53,0	43,0	36,0	63933
F	0.2570	5/16-18	8,0	91,0	53,0	43,0	36,0	51915
6,6 mm	0.2598		8,0	91,0	53,0	43,0	36,0	63934
6,7 mm	0.2638		8,0	91,0	53,0	43,0	36,0	63935
17/64	0.2657	5/16-20	8,0	91,0	53,0	43,0	36,0	51916
6,8 mm	0.2677	M8 X 1,25	8,0	91,0	53,0	43,0	36,0	63936
6,9 mm	0.2717	5/16-24	8,0	91,0	53,0	43,0	36,0	63999
7,0 mm	0.2756	M8 X 1	8,0	91,0	53,0	43,0	36,0	63937
7,1 mm	0.2795		8,0	91,0	53,0	43,0	36,0	63938
9/32	0.2812	5/16-32	8,0	91,0	53,0	43,0	36,0	51918
7,2 mm	0.2835	M8 X 0,75	8,0	91,0	53,0	43,0	36,0	63939
7,3 mm	0.2874		8,0	91,0	53,0	43,0	36,0	63940
7,4 mm	0.2913		8,0	91,0	53,0	43,0	36,0	63941
7,5 mm	0.2953	M8 X 0,5	8,0	91,0	53,0	43,0	36,0	63942
19/64	0.2969		8,0	91,0	53,0	43,0	36,0	51919
7,6 mm	0.2992		8,0	91,0	53,0	43,0	36,0	63943
7,7 mm	0.3031		8,0	91,0	53,0	43,0	36,0	63944
7,8 mm	0.3071	M9 X 1,25	8,0	91,0	53,0	43,0	36,0	63945
7,9 mm	0.3110		8,0	91,0	53,0	43,0	36,0	63946
5/16	0.3125	3/8-16	8,0	91,0	53,0	43,0	36,0	51920
8,0 mm	0.3150	M9 X 1	8,0	91,0	53,0	43,0	36,0	63947
8,1 mm	0.3189		10,0	103,0	61,0	49,0	40,0	63948
8,2 mm	0.3228		10,0	103,0	61,0	49,0	40,0	63949
8,3 mm	0.3268		10,0	103,0	61,0	49,0	40,0	63950

continued on next page







140 5xD

FRACTIONAL & METRIC SERIES

TECH INFO 185–188

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	EDP NO. Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
21/64	0.3281	3/8-20	10,0	103,0	61,0	49,0	40,0	51921
8,4 mm	0.3307		10,0	103,0	61,0	49,0	40,0	63951
Q	0.3320	3/8-24	10,0	103,0	61,0	49,0	40,0	51922
8,5 mm	0.3346	M10 X 1,5	10,0	103,0	61,0	49,0	40,0	63952
8,6 mm	0.3386		10,0	103,0	61,0	49,0	40,0	63953
8,7 mm	0.3425		10,0	103,0	61,0	49,0	40,0	63954
11/32	0.3438	3/8-32	10,0	103,0	61,0	49,0	40,0	51923
8,8 mm	0.3465	M10 X 1,25	10,0	103,0	61,0	49,0	40,0	63955
8,9 mm	0.3504		10,0	103,0	61,0	49,0	40,0	63956
9,0 mm	0.3543	M10 X 1	10,0	103,0	61,0	49,0	40,0	63957
9,1 mm	0.3583		10,0	103,0	61,0	49,0	40,0	63958
23/64	0.3594		10,0	103,0	61,0	49,0	40,0	51924
9,2 mm	0.3622	M10 X 0,75	10,0	103,0	61,0	49,0	40,0	63959
9,3 mm	0.3661		10,0	103,0	61,0	49,0	40,0	63960
U	0.3680	7/16-14	10,0	103,0	61,0	49,0	40,0	51925
9,4 mm	0.3701		10,0	103,0	61,0	49,0	40,0	63961
9,5 mm	0.3740	M11 / M10 X 0,5	10,0	103,0	61,0	49,0	40,0	63962
3/8	0.3750		10,0	103,0	61,0	49,0	40,0	51926
9,6 mm	0.3780		10,0	103,0	61,0	49,0	40,0	63963
9,7 mm	0.3819		10,0	103,0	61,0	49,0	40,0	63964
9,8 mm	0.3858		10,0	103,0	61,0	49,0	40,0	63965
9,9 mm	0.3898		10,0	103,0	61,0	49,0	40,0	63966
25/64	0.3906	7/16-20	10,0	103,0	61,0	49,0	40,0	51927
10,0 mm	0.3937		10,0	103,0	61,0	49,0	40,0	63967
10,1 mm	0.3976		12,0	118,0	71,0	56,0	45,0	63968
10,2 mm	0.4016	M12 X 1,75	12,0	118,0	71,0	56,0	45,0	63969
10,3 mm	0.4055		12,0	118,0	71,0	56,0	45,0	63970
13/32	0.4062		12,0	118,0	71,0	56,0	45,0	51928
10,4 mm	0.4094		12,0	118,0	71,0	56,0	45,0	63971
10,5 mm	0.4134	M12 X 1,5	12,0	118,0	71,0	56,0	45,0	63972
10,6 mm	0.4173		12,0	118,0	71,0	56,0	45,0	63973
10,7 mm	0.4213		12,0	118,0	71,0	56,0	45,0	63974

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6



140 5xD


FRACTIONAL & METRIC SERIES

CONTINUED

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
27/64	0.4219	1/2-13	12,0	118,0	71,0	56,0	45,0	51929
10,8 mm	0.4252	M12 X 1,25	12,0	118,0	71,0	56,0	45,0	63975
10,9 mm	0.4291		12,0	118,0	71,0	56,0	45,0	63976
11,0 mm	0.4331	M12 X 1	12,0	118,0	71,0	56,0	45,0	63977
11,1 mm	0.4370		12,0	118,0	71,0	56,0	45,0	63978
7/16	0.4375	1/4-18NPT	12,0	118,0	71,0	56,0	45,0	51930
11,2 mm	0.4409		12,0	118,0	71,0	56,0	45,0	63979
11,3 mm	0.4449		12,0	118,0	71,0	56,0	45,0	63980
11,4 mm	0.4488		12,0	118,0	71,0	56,0	45,0	63981
11,5 mm	0.4528	M12 X 0,5	12,0	118,0	71,0	56,0	45,0	64000
11,6 mm	0.4567		12,0	118,0	71,0	56,0	45,0	63982
11,7 mm	0.4606		12,0	118,0	71,0	56,0	45,0	63983
11,8 mm	0.4646		12,0	118,0	71,0	56,0	45,0	63984
11,9 mm	0.4685		12,0	118,0	71,0	56,0	45,0	63985
15/32	0.4688	1/2-28,0	12,0	118,0	71,0	56,0	45,0	51932
12,0 mm	0.4724	M14 X 2	12,0	118,0	71,0	56,0	45,0	63986
31/64	0.4844	9/16-12	14,0	124,0	77,0	60,0	45,0	51933
12,5 mm	0.4921	M14 X 1,5	14,0	124,0	77,0	60,0	45,0	63987
1/2	0.5000		14,0	124,0	77,0	60,0	45,0	51934
12,8 mm	0.5039	M14 X 1,25	14,0	124,0	77,0	60,0	45,0	63988
13,0 mm	0.5118	M14 X 1	14,0	124,0	77,0	60,0	45,0	63989
33/64	0.5156	9/16-18	14,0	124,0	77,0	60,0	45,0	51935
13,5 mm	0.5315	5/8-11	14,0	124,0	77,0	60,0	45,0	64001
13,8 mm	0.5433		14,0	124,0	77,0	60,0	45,0	63990
14,0 mm	0.5512	M16 X 2	14,0	124,0	77,0	60,0	45,0	63991
9/16	0.5625		16,0	133,0	83,0	63,0	48,0	51937
14,5 mm	0.5709	M16 X 1,5	16,0	133,0	83,0	63,0	48,0	63992
37/64	0.5781	5/8-18	16,0	133,0	83,0	63,0	48,0	51938
14,8 mm	0.5827		16,0	133,0	83,0	63,0	48,0	63993
15,0 mm	0.5906	M16 X 1	16,0	133,0	83,0	63,0	48,0	63994
15,5 mm	0.6102	M18 X 2,5	16,0	133,0	83,0	63,0	48,0	63995
15,8 mm	0.6220		16,0	133,0	83,0	63,0	48,0	63996
5/8	0.6250	11/16-16	16,0	133,0	83,0	63,0	48,0	51939
16,0 mm	0.6299		16,0	133,0	83,0	63,0	48,0	63997
21/32	0.6562	3/4-10	18,0	143,0	93,0	71,0	48,0	51940
11/16	0.6875	3/4-16	18,0	143,0	93,0	71,0	48,0	51941
3/4	0.7500	13/16-16	20,0	153,0	101,0	77,0	50,0	51942







140 8xD

FRACTIONAL & METRIC SERIES

TECH INFO 189–192

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
3,0 mm	0.1181		6,0	72,0	34,0	29,0	36,0	63575
3,1 mm	0.1220		6,0	72,0	34,0	29,0	36,0	63576
1/8	0.1250		6,0	72,0	34,0	29,0	36,0	51801
3,2 mm	0.1260	M3,5 X 0,35	6,0	72,0	34,0	29,0	36,0	63577
3,3 mm	0.1299	M4 X 0,7	6,0	72,0	34,0	29,0	36,0	63578
3,4 mm	0.1339		6,0	72,0	34,0	29,0	36,0	63579
#29	0.1360	8-32,8-36	6,0	72,0	34,0	29,0	36,0	51802
3,5 mm	0.1378	M4 X 0, 5	6,0	72,0	34,0	29,0	36,0	63580
9/64	0.1406		6,0	72,0	34,0	29,0	36,0	51803
3,6 mm	0.1417	M4 X 0,35	6,0	72,0	34,0	29,0	36,0	63581
3,7 mm	0.1457	M4,5 X 0,75	6,0	72,0	34,0	29,0	36,0	63582
3,8 mm	0.1496	10-24	6,0	81,0	43,0	36,0	36,0	63583
3,9 mm	0.1535		6,0	81,0	43,0	36,0	36,0	63584
5/32	0.1562		6,0	81,0	43,0	36,0	36,0	51804
4,0 mm	0.1575	M4,5 X 0,5	6,0	81,0	43,0	36,0	36,0	63585
#21	0.1590	10-32	6,0	81,0	43,0	36,0	36,0	51805
4,1 mm	0.1614		6,0	81,0	43,0	36,0	36,0	63586
4,2 mm	0.1654	M5 / M5 x 0,75	6,0	81,0	43,0	36,0	36,0	63587
4,3 mm	0.1693		6,0	81,0	43,0	36,0	36,0	63588
11/64	0.1719		6,0	81,0	43,0	36,0	36,0	51806
4,4 mm	0.1732	12-24	6,0	81,0	43,0	36,0	36,0	63589
4,5 mm	0.1772	M5 X 0,5	6,0	81,0	43,0	36,0	36,0	63590
4,6 mm	0.1811	12-28	6,0	81,0	43,0	36,0	36,0	63591
4,7 mm	0.1850	12-32	6,0	81,0	43,0	36,0	36,0	63592
3/16	0.1875		6,0	95,0	57,0	48,0	36,0	51807
4,8 mm	0.1890	7/32-32	6,0	95,0	57,0	48,0	36,0	63593
4,9 mm	0.1929		6,0	95,0	57,0	48,0	36,0	63594
5,0 mm	0.1969	M6 X 1	6,0	95,0	57,0	48,0	36,0	63595
5,1 mm	0.2008	1/4-20	6,0	95,0	57,0	48,0	36,0	63596
13/64	0.2031		6,0	95,0	57,0	48,0	36,0	51808
5,2 mm	0.2047	M6 X 0,75	6,0	95,0	57,0	48,0	36,0	63597
5,3 mm	0.2087		6,0	95,0	57,0	48,0	36,0	63598

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6



140 8xD

FRACTIONAL & METRIC SERIES


CONTINUED

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
5,4 mm	0.2126		6,0	95,0	57,0	48,0	36,0	63599
5,5 mm	0.2165	M6 X 0,5	6,0	95,0	57,0	48,0	36,0	63600
7/32	0.2188	1/4-32	6,0	95,0	57,0	48,0	36,0	51809
5,6 mm	0.2205		6,0	95,0	57,0	48,0	36,0	63601
5,7 mm	0.2244		6,0	95,0	57,0	48,0	36,0	63602
5,8 mm	0.2283		6,0	95,0	57,0	48,0	36,0	63603
5,9 mm	0.2323		6,0	95,0	57,0	48,0	36,0	63604
15/64	0.2344		6,0	95,0	57,0	48,0	36,0	51810
6,0 mm	0.2362	M7 X 1	6,0	95,0	57,0	48,0	36,0	63605
6,1 mm	0.2402		8,0	114,0	76,0	64,0	36,0	63606
6,2 mm	0.2441	M7 X 0,75	8,0	114,0	76,0	64,0	36,0	63607
6,3 mm	0.2480		8,0	114,0	76,0	64,0	36,0	63608
1/4	0.2500		8,0	114,0	76,0	64,0	36,0	51811
6,4 mm	0.2520		8,0	114,0	76,0	64,0	36,0	63609
6,5 mm	0.2559		8,0	114,0	76,0	64,0	36,0	63610
F	0.2570	5/16-18	8,0	114,0	76,0	64,0	36,0	51812
6,6 mm	0.2598		8,0	114,0	76,0	64,0	36,0	63611
6,7 mm	0.2638		8,0	114,0	76,0	64,0	36,0	63612
17/64	0.2657	5/16-20	8,0	114,0	76,0	64,0	36,0	51813
6,8 mm	0.2677	M8 X 1,25	8,0	114,0	76,0	64,0	36,0	63613
6,9 mm	0.2717		8,0	114,0	76,0	64,0	36,0	63614
7,0 mm	0.2756	M8 X 1	8,0	114,0	76,0	64,0	36,0	63615
7,1 mm	0.2795		8,0	114,0	76,0	64,0	36,0	63616
9/32	0.2812	5/16-32	8,0	114,0	76,0	64,0	36,0	51814
7,2 mm	0.2835	M8 X 0,75	8,0	114,0	76,0	64,0	36,0	63617
7,3 mm	0.2874		8,0	114,0	76,0	64,0	36,0	63618
7,4 mm	0.2913		8,0	114,0	76,0	64,0	36,0	63619
7,5 mm	0.2953	M8 X 0,5	8,0	114,0	76,0	64,0	36,0	63620
19/64	0.2969		8,0	114,0	76,0	64,0	36,0	51815
7,6 mm	0.2992		8,0	114,0	76,0	64,0	36,0	63621
7,7 mm	0.3031		8,0	114,0	76,0	64,0	36,0	63622
7,8 mm	0.3071	M9 X 1,25	8,0	114,0	76,0	64,0	36,0	63623
7,9 mm	0.3110		8,0	114,0	76,0	64,0	36,0	63624
5/16	0.3125	3/8-16	8,0	114,0	76,0	64,0	36,0	51816
8,0 mm	0.3150	M9 X 1	8,0	114,0	76,0	64,0	36,0	63625
8,1 mm	0.3189		10,0	142,0	95,0	80,0	40,0	63626
8,2 mm	0.3228		10,0	142,0	95,0	80,0	40,0	63627
8,3 mm	0.3268		10,0	142,0	95,0	80,0	40,0	63628

continued on next page







140 8xD

FRACTIONAL & METRIC SERIES

TECH INFO 189–192

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	EDP NO. Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
21/64	0.3281	3/8-20	10,0	142,0	95,0	80,0	40,0	51817
8,4 mm	0.3307		10,0	142,0	95,0	80,0	40,0	63629
Q	0.3320	3/8-24	10,0	142,0	95,0	80,0	40,0	51818
8,5 mm	0.3346	M10 X 1,5	10,0	142,0	95,0	80,0	40,0	63630
8,6 mm	0.3386		10,0	142,0	95,0	80,0	40,0	63631
8,7 mm	0.3425		10,0	142,0	95,0	80,0	40,0	63632
11/32	0.3438	3/8-32	10,0	142,0	95,0	80,0	40,0	51819
8,8 mm	0.3465	M10 X 1,25	10,0	142,0	95,0	80,0	40,0	63633
8,9 mm	0.3504		10,0	142,0	95,0	80,0	40,0	63634
9,0 mm	0.3543	M10 X 1	10,0	142,0	95,0	80,0	40,0	63635
9,1 mm	0.3583		10,0	142,0	95,0	80,0	40,0	63636
23/64	0.3594		10,0	142,0	95,0	80,0	40,0	51820
9,2 mm	0.3622	M10 X 0,75	10,0	142,0	95,0	80,0	40,0	63637
9,3 mm	0.3661		10,0	142,0	95,0	80,0	40,0	63638
U	0.3680	7/16-14	10,0	142,0	95,0	80,0	40,0	51821
9,4 mm	0.3701		10,0	142,0	95,0	80,0	40,0	63639
9,5 mm	0.3740	M11 / M10 X 0,5	10,0	142,0	95,0	80,0	40,0	63640
3/8	0.3750		10,0	142,0	95,0	80,0	40,0	51822
9,6 mm	0.3780		10,0	142,0	95,0	80,0	40,0	63641
9,7 mm	0.3819		10,0	142,0	95,0	80,0	40,0	63642
9,8 mm	0.3858		10,0	142,0	95,0	80,0	40,0	63643
9,9 mm	0.3898		10,0	142,0	95,0	80,0	40,0	63644
25/64	0.3906	7/16-20	10,0	142,0	95,0	80,0	40,0	51823
10,0 mm	0.3937		10,0	142,0	95,0	80,0	40,0	63645
10,1 mm	0.3976		12,0	162,0	114,0	96,0	45,0	63646
10,2 mm	0.4016	M12 X 1,75	12,0	162,0	114,0	96,0	45,0	63647
10,3 mm	0.4055		12,0	162,0	114,0	96,0	45,0	63648
13/32	0.4062		12,0	162,0	114,0	96,0	45,0	51824
10,4 mm	0.4094		12,0	162,0	114,0	96,0	45,0	63649
10,5 mm	0.4134	M12 X 1,5	12,0	162,0	114,0	96,0	45,0	63650
10,6 mm	0.4173		12,0	162,0	114,0	96,0	45,0	63651
10,7 mm	0.4213		12,0	162,0	114,0	96,0	45,0	63652

continued on next page

TOLERANCES (inch)

≤.1181 DIAMETER
D_1 = +.00008/+.00047
D_2 = h_6

>.1181–.2362 DIAMETER
D_1 = +.00016/+.00063
D_2 = h_6

>.2362–.3937 DIAMETER
D_1 = +.00024/+.00083
D_2 = h_6

>.3937–.7087 DIAMETER
D_1 = +.00028/+.00098
D_2 = h_6

>.7087–1.1811 DIAMETER
D_1 = +.00031/+.00114
D_2 = h_6

TOLERANCES (mm)

≤3 DIAMETER
D_1 = +0,002/+0,012
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,004/+0,016
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,006/+0,021
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,007/+0,025
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,008/+0,029
D_2 = h_6



140 8xD


FRACTIONAL & METRIC SERIES

CONTINUED

CUTTING DIAMETER	DECIMAL EQUIV.	TAP SIZE REFERENCE ONLY	mm					EDP NO.
			SHANK DIAMETER	OVERALL LENGTH	FLUTE LENGTH	CLEARED LENGTH	SHANK LENGTH	Ti-NAMITE-A (AlTiN)
D_1			D_2	L_1	L_2	L_3	L_4	
27/64	0.4219	1/2-13	12,0	162,0	114,0	96,0	45,0	51825
10,8 mm	0.4252	M12 X 1,25	12,0	162,0	114,0	96,0	45,0	63653
10,9 mm	0.4291		12,0	162,0	114,0	96,0	45,0	63654
11,0 mm	0.4331	M12 X 1	12,0	162,0	114,0	96,0	45,0	63655
11,1 mm	0.4370		12,0	162,0	114,0	96,0	45,0	63656
7/16	0.4375	1/4-18NPT	12,0	162,0	114,0	96,0	45,0	51826
11,2 mm	0.4409		12,0	162,0	114,0	96,0	45,0	63657
11,3 mm	0.4449		12,0	162,0	114,0	96,0	45,0	63658
11,4 mm	0.4488		12,0	162,0	114,0	96,0	45,0	63659
11,5 mm	0.4528	M12 X 0,5	12,0	162,0	114,0	96,0	45,0	63660
11,6 mm	0.4567		12,0	162,0	114,0	96,0	45,0	63661
11,7 mm	0.4606		12,0	162,0	114,0	96,0	45,0	63662
11,8 mm	0.4646		12,0	162,0	114,0	96,0	45,0	63663
11,9 mm	0.4685		12,0	162,0	114,0	96,0	45,0	63664
15/32	0.4688	1/2-28	12,0	162,0	114,0	96,0	45,0	51827
12,0 mm	0.4724	M14 X 2	12,0	162,0	114,0	96,0	45,0	63665
31/64	0.4844	9/16-12	14,0	178,0	133,0	112,0	45,0	51828
12,5 mm	0.4921	M14 X 1,5	14,0	178,0	133,0	112,0	45,0	63666
1/2	0.5000		14,0	178,0	133,0	112,0	45,0	51829
12,8 mm	0.5039	M14 X 1,25	14,0	178,0	133,0	112,0	45,0	63667
13,0 mm	0.5118	M14 X 1	14,0	178,0	133,0	112,0	45,0	63668
33/64	0.5156	9/16-18	14,0	178,0	133,0	112,0	45,0	51830
13,5 mm	0.5315	5/8-11	14,0	178,0	133,0	112,0	45,0	63669
13,8 mm	0.5433		14,0	178,0	133,0	112,0	45,0	63670
14,0 mm	0.5512	M16 X 2	14,0	178,0	133,0	112,0	45,0	63671
9/16	0.5625		16,0	203,0	152,0	128,0	48,0	51831
14,5 mm	0.5709	M16 X 1,5	16,0	203,0	152,0	128,0	48,0	63672
37/64	0.5781	5/8-18	16,0	203,0	152,0	128,0	48,0	51832
14,8 mm	0.5827		16,0	203,0	152,0	128,0	48,0	63673
15,0 mm	0.5906	M16 X 1,5	16,0	203,0	152,0	128,0	48,0	63674
15,5 mm	0.6102	M18 X 2,5	16,0	203,0	152,0	128,0	48,0	63675
15,8 mm	0.6220		16,0	203,0	152,0	128,0	48,0	63676
5/8	0.6250	11/16-16	16,0	203,0	152,0	128,0	48,0	51833
16,0 mm	0.6299		16,0	203,0	152,0	128,0	48,0	63677
21/32	0.6562	3/4-10	18,0	222,0	171,0	144,0	48,0	51834
11/16	0.6875	3/4-16	18,0	222,0	171,0	144,0	48,0	51835
3/4	0.7500	13/16-16	20,0	243,0	190,0	160,0	50,0	51836







120

FRACTIONAL & METRIC SERIES

TECH INFO 193

PLASTICS/COMPOSITES

CUTTING DIAMETER D_1	DECIMAL EQUIV.	SHANK DIAMETER D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2 / L_3	SHANK LENGTH L_4	Di-NAMITE (Diamond) EDP NO.
#40	0.0980	1/8	2	9/16	1-1/4	50000
2,7 mm	0.1063	6,0	63,0	20,0	32,0	50001
3,0 mm	0.1181	6,0	63,0	20,0	36,0	50002
1/8	0.1250	1/4	2-1/2	3/4	1-7/16	50003
3,2 mm	0.1260	6,0	63,0	20,0	36,0	50004
#30	0.1285	1/4	2-1/2	3/4	1-7/16	50005
#28	0.1405	1/4	2-1/2	3/4	1-7/16	50006
#22	0.1570	1/4	2-5/8	7/8	1-7/16	50007
#21	0.1590	1/4	2-5/8	7/8	1-7/16	50008
4,1 mm	0.1614	6,0	66,0	24,0	36,0	50009
#19	0.1660	1/4	2-5/8	7/8	1-7/16	50010
11/64	0.1719	1/4	2-5/8	7/8	1-7/16	50011
3/16	0.1875	1/4	2-5/8	1	1-7/16	50012
#11	0.1910	1/4	2-5/8	1	1-7/16	50013
#8	0.1990	1/4	2-5/8	1	1-7/16	50014
#7	0.2010	1/4	2-5/8	1	1-7/16	50015
#2	0.2210	1/4	2-5/8	1	1-7/16	50016
6,0 mm	0.2362	6,0	66,0	28,0	36,0	50017
1/4	0.2500	1/4	3-1/8	1-5/16	1-7/16	50018
.2510	0.2510	5/16	3-1/8	1-5/16	1-7/16	50019
F	0.2570	5/16	3-1/8	1-5/16	1-7/16	50020
I	0.2720	5/16	3-1/8	1-5/16	1-7/16	50021
J	0.2770	5/16	3-1/8	1-5/16	1-7/16	50022
K	0.2810	5/16	3-1/8	1-9/16	1-7/16	50023
5/16	0.3125	5/16	3-1/8	1-9/16	1-7/16	50024
8,0 mm	0.3150	8,0	79,0	41,0	36,0	50025
3/8	0.3750	3/8	3-1/2	1-27/32	1-9/16	50026
V	0.3770	1/2	3-1/2	1-27/32	1-9/16	50027
10,0 mm	0.3937	10,0	89,0	47,0	40,0	50028
7/16	0.4375	1/2	4-1/4	2-3/16	1-9/16	50029
12,0 mm	0.4724	12,0	102,0	55,0	45,0	50030
1/2	0.5000	1/2	4-1/4	2-5/16	1-3/4	50031

TOLERANCES (inch)

D_1= +.0000/–.0005
D_2 = h_6

TOLERANCES (mm)

D_1 = +0,000/–0,013
D_2 = h_6

	Series 135 3D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/32	1/8	1/4	3/8	1/2	5/8	7/8
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	400	RPM	48896	12224	6112	4075	3056	2445	1746
			(320-480)	Fr	0.001	0.0040	0.0080	0.0120	0.0160	0.0200	0.0280
				Feed (IPM)	48.9	48.9	48.9	48.9	48.9	48.9	48.9
		> 200 ≤ 300	350	RPM	42784	10696	5348	3565	2674	2139	1528
			(280-420)	Fr	0.0009	0.0035	0.0070	0.0105	0.0140	0.0175	0.0245
				Feed (IPM)	38.5	37.4	37.4	37.4	37.4	37.4	37.4
		> 300 ≤ 420	160	RPM	19558	4890	2445	1630	1222	978	699
			(128-192)	Fz	0.0008	0.0030	0.0060	0.0090	0.0120	0.0150	0.0210
				Feed (IPM)	15.6	14.7	14.7	14.7	14.7	14.7	14.7
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	300	RPM	36672	9168	4584	3056	2292	1834	1310
			(240-360)	Fz	0.0008	.0030	0.0060	0.0090	0.0120	0.0150	0.0210
				Feed (IPM)	29.3	27.5	27.5	27.5	27.5	27.5	27.5
		> 275 ≤ 375	220	RPM	26893	6723	3362	2241	1681	1345	960
			(176-264)	Fr	0.0006	.0025	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	16.1	16.8	16.8	16.8	16.8	16.8	16.8
		> 375 ≤ 450	120	RPM	14669	3667	1834	1222	917	733	524
			(96-144)	Fr	0.0005	.0018	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	7.3	6.6	6.4	6.7	6.4	6.6	6.5
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	220	RPM	26893	6723	3362	2241	1681	1345	960
			(176-264)	Fr	0.0006	0.0025	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	16.1	16.8	16.8	16.8	16.8	16.8	16.8
		> 250 ≤ 330	150	RPM	18336	4584	2292	1528	1146	917	655
			(120-180)	Fr	0.0005	0.0018	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	9.2	8.0	8.0	8.4	8.0	8.3	8.2
		> 330 ≤ 450	70	RPM	8557	2139	1070	713	535	428	306
			(56-84)	Fr	0.0003	0.0010	0.0020	0.0030	0.0040	0.0050	0.0070
				Feed (IPM)	2.6	2.1	2.1	2.1	2.1	2.1	2.1
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	400	RPM	48896	12224	6112	4075	3056	2445	1746
			(320-480)	Fr	0.0013	0.0050	0.0100	0.0150	0.0200	0.0250	0.0350
				Feed (IPM)	63.6	61.1	61.1	61.1	61.1	61.1	61.1
		> 200 ≤ 330	250	RPM	30560	7640	3820	2547	1910	1528	1091
			(200-300)	Fr	0.0011	0.0045	0.0090	0.0135	0.0180	0.0225	0.0315
				Feed (IPM)	33.6	34.4	34.4	34.4	34.4	34.4	34.4
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	200	RPM	24448	6112	3056	2037	1528	1222	873
			(160-240)	Fr	0.0006	0.0025	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	14.7	15.3	15.3	15.3	15.3	15.3	15.3
		> 250 ≤ 330	150	RPM	18336	4584	2292	1528	1146	917	655
			(120-180)	Fr	0.0005	0.0018	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	9.2	8.0	8.0	8.4	8.0	8.3	8.2

continued on next page

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS

	Series 135 3D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/32	1/8	1/4	3/8	1/2	5/8	7/8
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	90	RPM	11002	2750	1375	917	688	550	393
			(72-108)	Fr	0.0005	0.0018	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	5.5	5.0	4.8	5.0	4.8	5.0	4.9
		> 270 ≤ 370	70	RPM	8557	2139	1070	713	535	428	306
			(56-84)	Fr	0.0004	0.0015	0.0030	0.0045	0.0060	0.0075	0.0105
				Feed (IPM)	3.4	3.2	3.2	3.2	3.2	3.2	3.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	60	RPM	7334	1834	917	611	458	367	262
			(48-72)	Fr	0.0003	0.0010	0.0020	0.0030	0.0040	0.0050	0.0070
				Feed (IPM)	2.2	1.8	1.8	1.8	1.8	1.8	1.8
		> 220 ≤ 330	40	RPM	4890	1222	611	407	306	244	175
			(32-48)	Fr	0.0002	0.0008	0.0015	0.0025	0.0030	0.0040	0.0055
				Feed (IPM)	1.0	0.9	0.9	1.0	0.9	1.0	1.0
		> 330 ≤ 420	30	RPM	3667	917	458	306	229	183	131
			(24-36)	Fr	0.0001	0.0003	0.0010	0.0015	0.0020	0.0025	0.0035
				Feed (IPM)	0.4	0.3	0.5	0.5	0.5	0.5	0.5
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	120	RPM	14669	3667	1834	1222	917	733	524
			(96-144)	Fr	0.0005	0.0018	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	7.3	6.4	6.4	6.7	6.4	6.6	6.5
		> 280 ≤ 350	100	RPM	12224	3056	1528	1019	764	611	437
			(80-120)	Fr	0.0004	0.0015	0.0030	0.0045	0.0060	0.0075	0.0105
				Feed (IPM)	4.9	4.6	4.6	4.6	4.6	4.6	4.6
		> 350 ≤ 440	70	RPM	8557	2139	1070	713	535	428	306
			(56-84)	Fr	0.0003	0.0013	0.0025	0.0040	0.0050	0.0065	0.0090
				Feed (IPM)	2.6	2.7	2.7	2.9	2.7	2.8	2.8
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	700	RPM	85568	21392	10696	7131	5348	4278	3056
			(560-840)	Fr	0.0014	0.0055	0.0110	0.0165	0.0220	0.0275	0.0385
				Feed (IPM)	119.8	117.7	117.7	117.7	117.7	117.7	117.7
		> 80	600	RPM	73344	18336	9168	6112	4584	3667	2619
			(480-720)	Fr	0.0013	0.0050	0.0100	0.0150	0.0200	0.0250	0.0350
				Feed (IPM)	95.3	91.7	91.7	91.7	91.7	91.7	91.7
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	500	RPM	61120	15280	7640	5093	3820	3056	2183
			(400-600)	Fr	0.0005	0.0020	0.0040	0.0060	0.0080	0.0100	0.0140
				Feed (IPM)	30.6	30.6	30.6	30.6	30.6	30.6	30.6
		> 140	400	RPM	48896	12224	6112	4075	3056	2445	1746
			(320-480)	Fr	0.0005	0.0020	0.0040	0.0060	0.0080	0.0100	0.0140
				Feed (IPM)	24.4	24.4	24.4	24.4	24.4	24.4	24.4

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 135M 3D Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	122	RPM	12926	6463	4847	3878	3231	2424	1939
			(98-146)	Fr	0.095	0.195	0.255	0.320	0.385	0.515	0.640
				Feed (mm/min)	1228	1260	1236	1241	1244	1248	1241
		> 200 ≤ 300	107	RPM	11310	5655	4241	3393	2827	2121	1696
			(85-128)	Fr	0.085	0.170	0.225	0.280	0.340	0.450	0.560
				Feed (mm/min)	961	961	954	950	961	954	950
		> 300 ≤ 420	49	RPM	5170	2585	1939	1551	1293	969	776
			(39-59)	Fz	0.070	0.145	0.190	0.240	0.290	0.385	0.480
				Feed (mm/min)	362	375	368	372	375	373	372
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	91	RPM	9694	4847	3635	2908	2424	1818	1454
			(73-110)	Fz	0.070	0.145	0.190	0.240	0.290	0.385	0.480
				Feed (mm/min)	679	703	691	698	703	700	698
		> 275 ≤ 375	67	RPM	7109	3555	2666	2133	1777	1333	1066
			(54-80)	Fr	0.060	0.120	0.160	0.200	0.240	0.320	0.400
				Feed (mm/min)	427	427	427	427	427	427	427
		> 375 ≤ 450	37	RPM	3878	1939	1454	1163	969	727	582
			(29-44)	Fr	0.040	0.085	0.115	0.145	0.170	0.230	0.285
				Feed (mm/min)	155	165	167	169	165	167	166
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	67	RPM	7109	3555	2666	2133	1777	1333	1066
			(54-80)	Fr	0.060	0.120	0.160	0.200	0.240	0.320	0.400
				Feed (mm/min)	427	427	427	427	427	427	427
		> 250 ≤ 330	46	RPM	4847	2424	1818	1454	1212	909	727
			(37-55)	Fr	0.040	0.085	0.115	0.145	0.170	0.230	0.285
				Feed (mm/min)	194	206	209	211	206	209	207
		> 330 ≤ 450	21	RPM	2262	1131	848	679	565	424	339
			(17-26)	Fr	0.025	0.050	0.065	0.080	0.095	0.130	0.160
				Feed (mm/min)	57	57	55	54	54	55	54
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	122	RPM	12926	6463	4847	3878	3231	2424	1939
			(98-146)	Fr	0.120	0.240	0.320	0.400	0.485	0.640	0.800
				Feed (mm/min)	1551	1551	1551	1551	1567	1551	1551
		> 200 ≤ 330	76	RPM	8078	4039	3029	2424	2020	1515	1212
			(61-91)	Fr	0.110	0.215	0.290	0.360	0.435	0.575	0.720
				Feed (mm/min)	889	868	879	872	879	871	872
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	61	RPM	6463	3231	2424	1939	1616	1212	969
			(49-73)	Fr	0.060	0.120	0.160	0.200	0.240	0.320	0.400
				Feed (mm/min)	388	388	388	388	388	388	388
		> 250 ≤ 330	46	RPM	4847	2424	1818	1454	1212	909	727
			(37-55)	Fr	0.050	0.095	0.130	0.160	0.195	0.255	0.320
				Feed (mm/min)	242	230	236	233	236	232	233

continued on next page

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS

	Series 135M 3D Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	16	20
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	27	RPM	2908	1454	1091	872	727	545	436
			(22-33)	Fr	0.035	0.070	0.095	0.120	0.145	0.190	0.240
				Feed (mm/min)	102	102	104	105	105	104	105
		> 270 ≤ 370	21	RPM	2262	1131	848	679	565	424	339
			(17-26)	Fr	0.035	0.070	0.095	0.120	0.145	0.190	0.240
				Feed (mm/min)	79	79	81	81	82	81	81
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	18	RPM	1939	969	727	582	485	364	291
			(15-22)	Fr	0.025	0.050	0.065	0.080	0.095	0.130	0.160
				Feed (mm/min)	48	48	47	47	46	47	47
		> 220 ≤ 330	12	RPM	1293	646	485	388	323	242	194
			(10-15)	Fr	0.020	0.035	0.050	0.065	0.070	0.105	0.125
				Feed (mm/min)	26	23	24	25	23	25	24
		> 330 ≤ 420	9	RPM	969	485	364	291	242	182	145
			(7-11)	Fr	0.010	0.025	0.030	0.040	0.050	0.065	0.080
				Feed (mm/min)	10	12	11	12	12	12	12
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	37	RPM	3878	1939	1454	1163	969	727	582
			(29-44)	Fr	0.040	0.085	0.115	0.145	0.170	0.230	0.285
				Feed (mm/min)	155	165	167	169	165	167	166
		> 280 ≤ 350	30	RPM	3231	1616	1212	969	808	606	485
			(24-37)	Fr	0.035	0.070	0.095	0.120	0.145	0.190	0.240
				Feed (mm/min)	113	113	115	116	117	115	116
		> 350 ≤ 440	21	RPM	2262	1131	848	679	565	424	339
			(17-26)	Fr	0.030	0.060	0.085	0.105	0.120	0.165	0.205
				Feed (mm/min)	68	68	72	71	68	70	70
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	213	RPM	22620	11310	8482	6786	5655	4241	3393
			(171-256)	Fr	0.135	0.265	0.355	0.440	0.530	0.705	0.880
				Feed (mm/min)	3054	2997	3011	2986	2997	2990	2986
		> 80	183	RPM	19388	9694	7271	5816	4847	3635	2908
			(146-219)	Fr	0.120	0.240	0.320	0.400	0.485	0.640	0.800
				Feed (mm/min)	2327	2327	2327	2327	2351	2327	2327
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	152	RPM	16157	8078	6059	4847	4039	3029	2424
			(122-183)	Fr	0.050	0.095	0.130	0.160	0.195	0.255	0.320
				Feed (mm/min)	808	767	788	776	788	773	776
		> 140	122	RPM	12926	6463	4847	3878	3231	2424	1939
			(98-146)	Fr	0.050	0.095	0.130	0.160	0.195	0.255	0.320
				Feed (mm/min)	646	614	630	620	630	618	620

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 135 5D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	360	RPM	11002	7334	5501	3667	2750	2200	1834
			(288-432)	Fr	0.0040	0.0060	0.0080	0.0120	0.0160	0.0200	0.0280
				Feed (IPM)	44.0	44.0	44.0	44.0	44.0	44.0	51.3
		> 200 ≤ 300	310	RPM	9474	6316	4737	3158	2368	1895	1579
			(248-372)	Fr	0.0035	0.0053	0.0070	0.0105	0.0140	0.0175	0.0245
				Feed (IPM)	33.2	33.5	33.2	33.2	33.2	33.2	38.7
		> 300 ≤ 420	150	RPM	4584	3056	2292	1528	1146	917	764
			(120-180)	Fz	0.0030	0.0045	0.0060	0.0090	0.0120	0.0150	0.0210
				Feed (IPM)	13.8	13.8	13.8	13.8	13.8	13.8	16.0
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	270	RPM	8251	5501	4126	2750	2063	1650	1375
			(216-324)	Fz	0.0030	0.0045	0.0060	0.0090	0.0120	0.0150	0.0210
				Feed (IPM)	24.8	24.8	24.8	24.8	24.8	24.8	28.9
		> 270 ≤ 370	200	RPM	6112	4075	3056	2037	1528	1222	1019
			(160-240)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	15.3	15.5	15.3	15.3	15.3	15.3	17.8
		> 375 ≤ 450	110	RPM	3362	2241	1681	1121	840	672	560
			(88-132)	Fr	0.0018	0.0026	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	5.9	5.8	5.9	6.2	5.9	6.1	7.0
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	200	RPM	6112	4075	3056	2037	1528	1222	1019
			(160-240)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	15.3	15.5	15.3	15.3	15.3	15.3	17.8
		> 250 ≤ 330	130	RPM	3973	2649	1986	1324	993	795	662
			(104-156)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	7.0	7.2	7.0	7.3	7.0	7.2	8.3
		> 330 ≤ 450	60	RPM	1834	1222	917	611	458	367	306
			(48-72)	Fr	0.0010	0.0015	0.0020	0.0030	0.0040	0.0050	0.0070
				Feed (IPM)	1.8	1.8	1.8	1.8	1.8	1.8	2.1
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	360	RPM	11002	7334	5501	3667	2750	2200	1834
			(288-432)	Fr	0.0050	0.0075	0.0100	0.0150	0.0200	0.0250	0.0350
				Feed (IPM)	55.0	55.0	55.0	55.0	55.0	55.0	64.2
		> 200 ≤ 330	230	RPM	7029	4686	3514	2343	1757	1406	1171
			(184-276)	Fr	0.0045	0.0068	0.0090	0.0135	0.0180	0.0225	0.0315
				Feed (IPM)	31.6	31.9	31.6	31.6	31.6	31.6	36.9
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	180	RPM	5501	3667	2750	1834	1375	1100	917
			(144-216)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0175
				Feed (IPM)	13.8	13.9	13.8	13.8	13.8	13.8	16.0
		> 250 ≤ 330	130	RPM	3973	2649	1986	1324	993	795	662
			(104-156)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0140
				Feed (IPM)	7.9	7.9	7.9	7.9	7.9	7.9	9.3

continued on next page

HI-PERCARB
HIGH PERFORMANCE CARBIDE DRILLS

	Series 135 5D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	80	RPM	2445	1630	1222	815	611	489	407
			(64-96)	Fr	0.0018	0.0026	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	4.3	4.2	4.3	4.5	4.3	4.4	5.1
		> 270 ≤ 370	60	RPM	1834	1222	917	611	458	367	306
			(48-72)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0105
				Feed (IPM)	2.8	2.8	2.8	2.8	2.8	2.8	3.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	50	RPM	1528	1019	764	509	382	306	255
			(40-60)	Fr	0.0010	0.0015	0.0020	0.0030	0.0040	0.0050	0.0070
				Feed (IPM)	1.5	1.5	1.5	1.5	1.5	1.5	1.8
		> 220 ≤ 330	30	RPM	917	611	458	306	229	183	153
			(24-36)	Fr	0.0008	0.0012	0.0015	0.0025	0.0030	0.0040	0.0055
				Feed (IPM)	0.7	0.7	0.7	0.8	0.7	0.7	0.8
		> 330 ≤ 420	20	RPM	611	407	306	204	153	122	102
			(16-24)	Fr	0.0005	0.0008	0.0010	0.0015	0.0020	0.0025	0.0035
				Feed (IPM)	0.3	0.3	0.3	0.3	0.3	0.3	0.4
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	100	RPM	3056	2037	1528	1019	764	611	509
			(80-120)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0125
				Feed (IPM)	5.3	5.5	5.3	5.6	5.3	5.5	6.4
		> 280 ≤ 350	80	RPM	2445	1630	1222	815	611	489	407
			(64-96)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0105
				Feed (IPM)	3.7	3.7	3.7	3.7	3.7	3.7	4.3
		> 350 ≤ 440	60	RPM	1834	1222	917	611	458	367	306
			(48-72)	Fr	0.0013	0.0019	0.0025	0.0040	0.0050	0.0065	0.0090
				Feed (IPM)	2.3	2.3	2.3	2.4	2.3	2.4	2.8
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	630	RPM	19253	12835	9626	6418	4813	3851	3209
			(504-756)	Fr	0.0055	0.0083	0.0110	0.0165	0.0220	0.0275	0.0385
				Feed (IPM)	105.9	106.5	105.9	105.9	105.9	105.9	123.5
		> 80	540	RPM	16502	11002	8251	5501	4126	3300	2750
			(432-648)	Fr	0.0050	0.0075	0.0100	0.0150	0.0200	0.0250	0.0350
				Feed (IPM)	82.5	82.5	82.5	82.5	82.5	82.5	96.3
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	450	RPM	13752	9168	6876	4584	3438	2750	2292
			(360-540)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0140
				Feed (IPM)	27.5	27.5	27.5	27.5	27.5	27.5	32.1
		> 140	360	RPM	11002	7334	5501	3667	2750	2200	1834
			(288-432)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0140
				Feed (IPM)	22.0	22.0	22.0	22.0	22.0	22.0	25.7

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 140 5D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	440	RPM	13446	8964	6723	4482	3362	2689	2241
			(352-528)	Fr	0.0040	0.0060	0.0080	0.0120	0.0160	0.0200	0.0240
				Feed (IPM)	53.8	53.8	53.8	53.8	53.8	53.8	53.8
		> 200 ≤ 300	380	RPM	11613	7742	5806	3871	2903	2323	1935
			(304-456)	Fr	0.0035	0.0053	0.0070	0.0105	0.0140	0.0175	0.0210
				Feed (IPM)	40.6	41.0	40.6	40.6	40.6	40.6	40.6
		> 300 ≤ 420	180	RPM	5501	3667	2750	1834	1375	1100	917
			(144-216)	Fz	0.0030	0.0045	0.0060	0.0090	0.0120	0.0150	0.0180
				Feed (IPM)	16.5	16.5	16.5	16.5	16.5	16.5	16.5
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	330	RPM	10085	6723	5042	3362	2521	2017	1681
			(264-396)	Fz	0.0030	0.0045	0.0060	0.0090	0.0120	0.0150	0.0180
				Feed (IPM)	30.3	30.3	30.3	30.3	30.3	30.3	30.3
		> 270 ≤ 370	240	RPM	7334	4890	3667	2445	1834	1467	1222
			(192-288)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0150
				Feed (IPM)	18.3	18.6	18.3	18.3	18.3	18.3	18.3
		> 375 ≤ 450	140	RPM	4278	2852	2139	1426	1070	856	713
			(112-168)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0110
				Feed (IPM)	7.7	7.7	7.5	7.8	7.5	7.7	7.8
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	240	RPM	7334	4890	3667	2445	1834	1467	1222
			(192-288)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0150
				Feed (IPM)	18.3	18.6	18.3	18.3	18.3	18.3	18.3
		> 250 ≤ 330	180	RPM	5501	3667	2750	1834	1375	1100	917
			(144-216)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0110
				Feed (IPM)	9.9	9.9	9.6	10.1	9.6	9.9	10.1
		> 330 ≤ 450	90	RPM	2750	1834	1375	917	688	550	458
			(72-108)	Fr	0.0010	0.0015	0.0020	0.0030	0.0040	0.0050	0.0060
				Feed (IPM)	2.8	2.8	2.8	2.8	2.8	2.8	2.8
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	440	RPM	13446	8964	6723	4482	3362	2689	2241
			(352-528)	Fr	0.0050	0.0075	0.0100	0.0150	0.0200	0.0250	0.0300
				Feed (IPM)	67.2	67.2	67.2	67.2	67.2	67.2	67.2
		> 200 ≤ 330	280	RPM	8557	5705	4278	2852	2139	1711	1426
			(224-336)	Fr	0.0045	0.0068	0.0090	0.0135	0.0180	0.0225	0.0270
				Feed (IPM)	38.5	38.8	38.5	38.5	38.5	38.5	38.5
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	220	RPM	6723	4482	3362	2241	1681	1345	1121
			(176-264)	Fr	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0150
				Feed (IPM)	16.8	17.0	16.8	16.8	16.8	16.8	16.8
		> 250 ≤ 330	170	RPM	5195	3463	2598	1732	1299	1039	866
			(136-204)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0120
				Feed (IPM)	10.4	10.4	10.4	10.4	10.4	10.4	10.4

continued on next page

IC Carb
High Performance Internal Coolant Drills

	Series 140 5D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270	150	RPM	4584	3056	2292	1528	1146	917	764
			(120-180)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0110
				Feed (IPM)	8.3	8.3	8.0	8.4	8.0	8.3	8.4
		> 270 ≤ 370	120	RPM	3667	2445	1834	1222	917	733	611
			(96-144)	Fr	0.0012	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	4.4	132.0	5.5	5.5	5.5	5.5	5.5
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	100	RPM	3056	2037	1528	1019	764	611	509
			(80-120)	Fr	0.0010	0.0015	0.0020	0.0030	0.0040	0.0050	0.0060
				Feed (IPM)	3.1	3.1	3.1	3.1	3.1	3.1	3.1
		> 220 ≤ 330	70	RPM	2139	1426	1070	713	535	428	357
			(56-84)	Fr	0.0008	0.0012	0.0015	0.0025	0.0030	0.0040	0.0050
				Feed (IPM)	1.7	1.7	1.6	1.8	1.6	1.7	1.8
		> 330 ≤ 420	50	RPM	1528	1019	764	509	382	306	255
			(40-60)	Fr	0.0005	0.0008	0.0010	0.0015	0.0020	0.0025	0.0030
				Feed (IPM)	0.8	0.8	0.8	0.8	0.8	0.8	0.8
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	200	RPM	6112	4075	3056	2037	1528	1222	1019
			(160-240)	Fr	0.0018	0.0027	0.0035	0.0055	0.0070	0.0090	0.0110
				Feed (IPM)	11.0	11.0	10.7	11.2	10.7	11.0	11.2
		> 280 ≤ 350	160	RPM	4890	3260	2445	1630	1222	978	815
			(128-192)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	7.3	7.5	7.3	7.3	7.3	7.3	7.3
		> 350 ≤ 440	120	RPM	3667	2445	1834	1222	917	733	611
			(96-144)	Fr	0.0013	0.0019	0.0025	0.0040	0.0050	0.0065	0.0080
				Feed (IPM)	4.8	4.6	4.6	4.9	4.6	4.8	4.9
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	770	RPM	23531	15687	11766	7844	5883	4706	3922
			(616-924)	Fr	0.0055	0.0083	0.0110	0.0165	0.0220	0.0275	0.0330
				Feed (IPM)	129.4	130.2	129.4	129.4	129.4	129.4	129.4
		> 80	660	RPM	20170	13446	10085	6723	5042	4034	3362
			(528-792)	Fr	0.0050	0.0075	0.0100	0.0150	0.0200	0.0250	0.0300
				Feed (IPM)	100.8	100.8	100.8	100.8	100.8	100.8	100.8
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	550	RPM	16808	11205	8404	5603	4202	3362	2801
			(440-660)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0120
				Feed (IPM)	33.6	33.6	33.6	33.6	33.6	33.6	33.6
		> 140	440	RPM	13446	8964	6723	4482	3362	2689	2241
			(352-528)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0120
				Feed (IPM)	26.9	26.9	26.9	26.9	26.9	26.9	26.9

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

IC Carb
High Performance Internal Coolant Drills

	Series 140M 5D Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	14	16
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	134	RPM	14206	7103	5327	4262	3552	3044	2664
			(107-161)	Fr	0.145	0.195	0.255	0.320	0.385	0.450	0.515
				Feed (mm/min)	2060	1385	1358	1364	1367	1370	1372
		> 200 ≤ 300	116	RPM	12298	6149	4612	3689	3074	2635	2306
			(93-139)	Fr	0.125	0.170	0.225	0.280	0.340	0.395	0.450
				Feed (mm/min)	1537	1045	1038	1033	1045	1041	1038
		> 300 ≤ 420	55	RPM	5831	2915	2187	1749	1458	1249	1093
			(44-66)	Fz	0.110	0.145	0.190	0.240	0.290	0.335	0.385
				Feed (mm/min)	641	423	415	420	423	419	421
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	101	RPM	10708	5354	4015	3212	2677	2295	2008
			(81-121)	Fz	0.110	0.145	0.190	0.240	0.290	0.335	0.385
				Feed (mm/min)	1178	776	763	771	776	769	773
		> 270 ≤ 370	73	RPM	7739	3870	2902	2322	1935	1658	1451
			(58-88)	Fr	0.090	0.120	0.160	0.200	0.240	0.280	0.320
				Feed (mm/min)	697	464	464	464	464	464	464
		> 370 ≤ 450	43	RPM	4559	2279	1710	1368	1140	977	855
			(34-52)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	296	194	197	198	194	195	197
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	73	RPM	7739	3870	2902	2322	1935	1658	1451
			(58-88)	Fr	0.090	0.120	0.160	0.200	0.240	0.280	0.320
				Feed (mm/min)	697	464	464	464	464	464	464
		> 250 ≤ 330	55	RPM	5831	2915	2187	1749	1458	1249	1093
			(44-66)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	379	248	251	254	248	250	251
		> 330 ≤ 450	27	RPM	2862	1431	1073	859	716	613	537
			(22-32)	Fr	0.035	0.050	0.065	0.080	0.095	0.110	0.130
				Feed (mm/min)	100	72	70	69	68	67	70
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	134	RPM	14206	7103	5327	4262	3552	3044	2664
			(107-161)	Fr	0.180	0.240	0.320	0.400	0.485	0.560	0.640
				Feed (mm/min)	2557	1705	1705	1705	1723	1705	1705
		> 200 ≤ 330	85	RPM	9011	4506	3379	2703	2253	1931	1690
			(68-102)	Fr	0.165	0.215	0.290	0.360	0.435	0.505	0.575
				Feed (mm/min)	1487	969	980	973	980	975	972
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	67	RPM	7103	3552	2664	2131	1776	1522	1332
			(54-80)	Fr	0.090	0.120	0.160	0.200	0.240	0.280	0.320
				Feed (mm/min)	639	426	426	426	426	426	426
		> 250 ≤ 330	50	RPM	5301	2650	1988	1590	1325	1136	994
			(40-60)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	371	252	258	254	258	256	253

continued on next page

IC Carb
High Performance Internal Coolant Drills

	Series 140M 5D Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	14	16
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	46	RPM	4877	2438	1829	1463	1219	1045	914
			(37-55)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	317	207	210	212	207	209	210
		> 270 ≤ 370	37	RPM	3923	1961	1471	1177	981	841	735
			(30-44)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	132	137	140	141	142	143	140
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	30	RPM	3181	1590	1193	954	795	682	596
			(24-36)	Fr	0.035	0.050	0.065	0.080	0.095	0.110	0.130
				Feed (mm/min)	111	80	78	62	76	75	78
		> 220 ≤ 330	21	RPM	2226	1113	835	668	557	477	417
			(17-25)	Fr	0.030	0.035	0.050	0.065	0.070	0.090	0.105
				Feed (mm/min)	67	39	42	43	39	43	44
		> 330 ≤ 420	15	RPM	1590	795	596	477	398	341	298
			(12-18)	Fr	0.020	0.025	0.030	0.040	0.050	0.055	0.065
				Feed (mm/min)	32	20	18	19	20	19	19
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	61	RPM	6467	3234	2425	1940	1617	1386	1213
			(49-73)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	420	275	279	281	275	277	279
		> 280 ≤ 350	49	RPM	5195	2597	1948	1558	1299	1113	974
			(39-59)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	286	182	185	187	188	189	185
		> 350 ≤ 440	37	RPM	3923	1961	1471	1177	981	841	735
			(30-44)	Fr	0.045	0.060	0.085	0.105	0.120	0.145	0.165
				Feed (mm/min)	177	118	125	124	118	122	121
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	235	RPM	24914	12457	9343	7474	6228	5339	4671
			(188-282)	Fr	0.200	0.265	0.355	0.440	0.530	0.620	0.705
				Feed (mm/min)	4983	3301	3317	3289	3301	3310	3293
		> 80	201	RPM	21309	10655	7991	6393	5327	4566	3996
			(161-241)	Fr	0.180	0.240	0.320	0.400	0.485	0.560	0.640
				Feed (mm/min)	3836	2557	2557	2557	2584	2557	2557
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	168	RPM	17811	8905	6679	5343	4453	3817	3340
			(134-202)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	1247	846	868	855	868	859	852
		> 140	134	RPM	14206	7103	5327	4262	3552	3044	2664
			(107-161)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	994	675	693	682	693	685	679

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

IC Carb
High Performance Internal Coolant Drills

	Series 140 8D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	420	RPM	12835	8557	6418	4278	3209	2567	2139
			(336-504)	Fr	0.0035	0.0053	0.0070	0.0105	0.0140	0.0175	0.0210
				Feed (IPM)	44.9	45.4	44.9	44.9	44.9	44.9	44.9
		> 200 ≤ 300	370	RPM	11307	7538	5654	3769	2827	2261	1885
			(296-444)	Fr	0.0030	0.0045	0.0060	0.0090	0.0120	0.0150	0.0180
				Feed (IPM)	33.9	33.9	33.9	33.9	33.9	33.9	33.9
		> 300 ≤ 420	170	RPM	5195	3463	2598	1732	1299	1039	866
			(136-204)	Fz	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0150
				Feed (IPM)	13.0	13.2	13.0	13.0	13.0	13.0	13.0
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	320	RPM	9779	6519	4890	3260	2445	1956	1630
			(256-384)	Fz	0.0025	0.0038	0.0050	0.0075	0.0100	0.0125	0.0150
				Feed (IPM)	24.4	24.8	24.4	24.4	24.4	24.4	24.4
		> 270 ≤ 370	230	RPM	7029	4686	3514	2343	1757	1406	1171
			(184-276)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0125
				Feed (IPM)	70288.0	14.1	14.1	14.1	14.1	14.1	14.6
		> 370 ≤ 450	130	RPM	3973	2649	1986	1324	993	795	662
			(104-156)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	156.0	6.1	6.0	6.0	6.0	6.0	6.0
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	230	RPM	7029	4686	3514	2343	1757	1406	1171
			(184-276)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0125
				Feed (IPM)	240.0	14.1	14.1	14.1	14.1	14.1	14.6
		> 250 ≤ 330	160	RPM	4890	3260	2445	1630	1222	978	815
			(128-192)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	342.0	7.5	7.3	7.3	7.3	7.3	7.3
		> 330 ≤ 450	80	RPM	2445	1630	1222	815	611	489	407
			(64-96)	Fr	0.0008	0.0013	0.0015	0.0025	0.0030	0.0040	0.0045
				Feed (IPM)	2.0	2.1	1.8	2.0	1.8	2.0	1.8
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	420	RPM	12835	8557	6418	4278	3209	2567	2139
			(336-504)	Fr	0.0045	0.0068	0.0090	0.0135	0.0180	0.0225	0.0270
				Feed (IPM)	57.8	58.2	57.8	57.8	57.8	57.8	57.8
		> 200 ≤ 330	270	RPM	8251	5501	4126	2750	2063	1650	1375
			(216-324)	Fr	0.0040	0.0060	0.0080	0.0120	0.0160	0.0200	0.0240
				Feed (IPM)	33.0	33.0	33.0	33.0	33.0	33.0	33.0
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	210	RPM	6418	4278	3209	2139	1604	1284	1070
			(168-252)	Fr	0.0020	0.0030	0.0040	0.0060	0.0080	0.0100	0.0120
				Feed (IPM)	12.8	12.8	12.8	12.8	12.8	12.8	12.8
		> 250 ≤ 330	160	RPM	4890	3260	2445	1630	1222	978	815
			(128-192)	Fr	0.0018	0.0028	0.0035	0.0055	0.0070	0.0090	0.0105
				Feed (IPM)	8.8	9.1	8.6	9.0	8.6	8.8	8.6

continued on next page

	Series 140 8D Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	5/8	3/4
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270	130	RPM	3973	2649	1986	1324	993	795	662
			(104-156)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	6.0	6.1	6.0	6.0	6.0	6.0	6.0
		> 270 ≤ 370	100	RPM	3056	2037	1528	1019	764	611	509
			(80-120)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	4.6	4.7	4.6	4.6	4.6	4.6	4.6
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	80	RPM	2445	1630	1222	815	611	489	407
			(64-96)	Fr	0.0008	0.0013	0.0015	0.0025	0.0030	0.0040	0.0045
				Feed (IPM)	2.0	2.1	1.8	2.0	1.8	2.0	1.8
		> 220 ≤ 330	50	RPM	1528	1019	764	509	382	306	255
			(40-60)	Fr	0.0005	0.0008	0.0010	0.0015	0.0020	0.0025	0.0030
				Feed (IPM)	0.8	0.8	0.8	0.8	0.8	0.8	0.8
		> 330 ≤ 420	35	RPM	1070	713	535	357	267	214	178
			(28-42)	Fr	0.0005	0.0008	0.0010	0.0015	0.0020	0.0025	0.0030
				Feed (IPM)	0.5	0.6	0.5	0.5	0.5	0.5	0.5
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	180	RPM	5501	3667	2750	1834	1375	1100	917
			(144-216)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0075	0.0090
				Feed (IPM)	8.3	8.4	8.3	8.3	8.3	8.3	8.3
		> 280 ≤ 350	140	RPM	4278	2852	2139	1426	1070	856	713
			(112-168)	Fr	0.0013	0.0020	0.0025	0.0040	0.0050	0.0065	0.0080
				Feed (IPM)	5.6	5.7	5.3	5.7	5.3	5.6	5.7
		> 350 ≤ 440	110	RPM	3362	2241	1681	1121	840	672	560
			(88-132)	Fr	0.0013	0.0020	0.0025	0.0040	0.0050	0.0065	0.0080
				Feed (IPM)	4.4	4.5	4.2	4.5	4.2	4.4	4.5
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	730	RPM	22309	14873	11154	7436	5577	4462	3718
			(584-876)	Fr	0.0050	0.0075	0.0100	0.0150	0.0200	0.0250	0.0300
				Feed (IPM)	111.5	111.5	111.5	111.5	111.5	111.5	111.5
		> 80	630	RPM	19253	12835	9626	6418	4813	3851	3209
			(504-756)	Fr	0.0045	0.0068	0.0090	0.0135	0.0180	0.0225	0.0270
				Feed (IPM)	86.6	87.3	86.6	86.6	86.6	86.6	86.6
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	520	RPM	15891	10594	7946	5297	3973	3178	2649
			(416-624)	Fr	0.0018	0.0028	0.0035	0.0055	0.0070	0.0090	0.0105
				Feed (IPM)	28.6	29.7	27.8	29.1	27.8	28.6	27.8
		> 140	420	RPM	12835	8557	6418	4278	3209	2567	2139
			(336-504)	Fr	0.0018	0.0028	0.0035	0.0055	0.0070	0.0090	0.0105
				Feed (IPM)	23.1	24.0	22.5	23.5	22.5	23.1	22.5

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

IC Carb
High Performance Internal Coolant Drills

Series 140M 8D Metric		Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	14	16
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	128	RPM	13570	6785	5089	4071	3393	2908	2544
			(100-170	Fr	0.125	0.170	0.225	0.280	0.340	0.395	0.450
				Feed (mm/min)	1696	1153	1145	1140	1153	1149	1145
		> 200 ≤ 300	113	RPM	11980	5990	4492	3594	2995	2567	31
			(90-136)	Fr	0.110	0.145	0.190	0.240	0.290	0.335	0.385
				Feed (mm/min)	1318	869	854	863	869	860	12
		> 300 ≤ 420	52	RPM	5513	2756	2067	1654	1378	1181	1034
			(42-62)	Fz	0.090	0.120	0.160	0.200	0.240	0.280	0.320
				Feed (mm/min)	496	331	331	331	331	331	331
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	98	RPM	10390	5195	3896	3117	2597	2226	1948
			(78-118)	Fz	0.090	0.120	0.160	0.200	0.240	0.280	0.320
				Feed (mm/min)	935	623	623	2494	623	2494	623
		> 270 ≤ 370	70	RPM	7421	3711	2783	2226	1855	1590	1391
			(56-84)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	519	353	362	356	362	358	355
		> 370 ≤ 450	40	RPM	4241	2120	1590	1272	1060	909	795
			(32-48)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	233	148	151	153	154	154	151
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	70	RPM	7421	3711	2783	2226	1855	1590	1391
			(56-84)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	519	353	362	356	362	358	355
		> 250 ≤ 330	49	RPM	5195	2597	1948	1558	1299	1113	974
			(39-59)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	286	182	185	187	188	189	185
		> 330 ≤ 450	24	RPM	2544	1272	954	763	636	545	477
			(19-29)	Fr	0.030	0.035	0.050	0.065	0.070	0.090	0.105
				Feed (mm/min)	76	45	48	50	45	49	50
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	128	RPM	13570	6785	5089	4071	3393	2908	2544
			(102-154)	Fr	0.165	0.215	0.290	0.360	0.435	0.505	0.575
				Feed (mm/min)	2239	1459	1476	1466	1476	1468	1463
		> 200 ≤ 330	82	RPM	8693	4347	3260	2608	2173	1863	1630
			(66-98)	Fr	0.145	0.195	0.255	0.320	0.385	0.450	0.515
				Feed (mm/min)	1261	848	831	835	2510	838	2518
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	64	RPM	6785	3393	2544	2036	1696	1454	1272
			(51-77)	Fr	0.070	0.095	0.130	0.160	0.195	0.225	0.255
				Feed (mm/min)	475	322	331	326	331	327	324
		> 250 ≤ 330	49	RPM	5195	2597	1948	1558	1299	1113	974
			(39-59)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	338	221	224	226	221	223	224

continued on next page

	Series 140M 8D Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	8	10	12	14	16
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	40	RPM	4241	2120	1590	1272	1060	909	795
			(32-48)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	276	180	183	184	180	182	183
		> 270 ≤ 370	30	RPM	3181	1590	1193	954	795	682	596
			(24-36)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	175	111	113	114	115	116	113
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	24	RPM	2544	1272	954	763	636	545	477
			(19-29)	Fr	0.030	0.035	0.050	0.065	0.070	0.090	0.105
				Feed (mm/min)	76	45	132	9160	45	49	50
		> 220 ≤ 330	15	RPM	1590	795	596	477	398	341	298
			(12-18)	Fr	0.020	0.025	0.030	0.040	0.050	0.055	0.065
				Feed (mm/min)	32	20	210	19	20	19	19
		> 330 ≤ 420	11	RPM	1166	583	437	350	292	250	219
			(9-13)	Fr	0.020	0.025	0.030	0.040	0.050	0.055	0.065
				Feed (mm/min)	23	15	13	14	15	14	14
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	55	RPM	5831	2915	2187	1749	1458	1249	1093
			(44-66)	Fr	0.055	0.070	0.095	0.120	0.145	0.170	0.190
				Feed (mm/min)	321	204	208	210	211	212	208
		> 280 ≤ 350	48	RPM	5089	2544	1908	1527	1272	1090	954
			(38-58)	Fr	0.045	0.060	0.085	0.105	0.120	0.145	0.165
				Feed (mm/min)	229	153	162	160	153	158	157
		> 350 ≤ 440	34	RPM	3605	1802	1352	1081	901	772	676
			(27-41)	Fr	0.035	0.050	0.065	0.080	0.095	0.110	0.130
				Feed (mm/min)	126	90	88	87	86	85	88
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	223	RPM	23642	11821	8866	7093	5910	5066	4433
			(178-268)	Fr	0.180	0.240	0.320	0.400	0.485	0.560	0.640
				Feed (mm/min)	4256	2837	2837	2837	2867	2837	2837
		> 80	192	RPM	20355	10178	7633	6107	5089	4362	3817
			(154-230)	Fr	0.165	0.215	0.290	0.360	0.435	0.505	0.575
				Feed (mm/min)	3359	2188	2214	2198	2214	2203	2195
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	158	RPM	16751	8375	6281	5025	4188	3589	3141
			(126-190)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	1089	712	722	729	712	718	722
		> 140	128	RPM	13570	6785	5089	4071	3393	2908	2544
			(102-154)	Fr	0.065	0.085	0.115	0.145	0.170	0.200	0.230
				Feed (mm/min)	882	577	585	590	577	582	585

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

DI-NAMITE CRYSTALLINE DIAMOND COATING

Series 120 Fractional	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	5/16	3/8	7/16	1/2
CFRP, AFRP (Carbon Fiber, Aramid Fiber)	320	RPM	9779	6519	4890	3912	3260	2794	2445
	(256-384)	Fr	0.0006	0.0008	0.0012	0.0015	0.0018	0.0021	0.0024
		Feed (IPM)	5.9	5.2	5.9	5.9	5.9	5.9	5.9
GFRP (Fiberglass)	240	RPM	7334	4890	3667	2934	2445	2096	1834
	(192-288)	Fr	0.0006	0.0008	0.0012	0.0015	0.0018	0.0021	0.0024
		Feed (IPM)	4.4	3.9	4.4	4.4	4.4	4.4	4.4
CARBON, GRAPHITE	400	RPM	12224	8149	6112	4890	4075	3493	3056
	(320-480)	Fr	0.0008	0.0012	0.0016	0.0020	0.0024	0.0028	0.0032
		Feed (IPM)	9.8	9.8	9.8	9.8	9.8	9.8	9.8

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
adjust speed and / or feed based on resin type and / or fiber structure
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


Series 120 Metric	Vc (m/min)		Diameter (D_1) (mm) 2.5	3	4	6	8	10	12
CFRP, AFRP (Carbon Fiber, Aramid Fiber)	100	RPM	12722	10602	7951	5301	3976	3181	2650
	(80-120)	Fr	0.015	0.018	0.020	0.030	0.038	0.046	0.053
		Feed (mm/min)	191	191	159	159	151	146	140
GFRP (Fiberglass)	75	RPM	9542	7951	5963	3976	2982	2385	1988
	(65-90)	Fr	0.015	0.018	0.020	0.030	0.038	0.046	0.053
		Feed (mm/min)	143	143	119	119	113	110	105
CARBON, GRAPHITE	120	RPM	15266	12722	9542	6361	4771	3817	3181
	(96-144)	Fr	0.020	0.024	0.030	0.041	0.051	0.061	0.071
		Feed (mm/min)	305	305	286	261	243	233	226

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
adjust speed and / or feed based on resin type and / or fiber structure
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


Drilling Operations Coolant Recommendations


- Coolant works to mobilize chips away from the cut zone, reduce the heat created during the cutting process and minimize friction.
- It is important to optimize the coolant pressure and position in order to gain the full benefits coolant offers the cutting process.
- Proper coolant application promotes greater operating parameters, greater material removal rates, improved surface finishes, predictable tool life, reduced power consumption and reduced cycle times.
- Pressure is important, but more importantly is consistency of the pressure and application onto the tool; intermittent cooling of carbide leads to thermal stressing of the material and the formation of "microcracks."
- Proper cleanliness and filtration of coolants is important in order for the coolant to maintain its beneficial properties, and also to avoid a reduction in coolant pressure or the possibility of clogging the coolant channels in coolant through drills.

RECOMMENDED COOLANT PRESSURE
BY DIAMETER – psi




RECOMMENDED COOLANT PRESSURE
BY DIAMETER – bar





LARGE TIP – LOW VELOCITY
NO COVERAGE AT MAXIMUM DEPTH




SMALL TIP – HIGH VELOCITY
COMPLETE COVERAGE

- Reducing the nozzle size helps maximize the cooling benefits of the unique double margin design on the Hi-PerCarb drill by increasing velocity. Aim the nozzles in line with the secondary flute located between the two margins as well as the flute for best results.


Operaciones de taladrado
Refrigerantes recomendados


- El líquido refrigerante actúa movilizando las virutas fuera de la zona de corte, disminuyendo el calor generado durante el proceso de corte y minimizando la fricción.
- Es importante optimizar la presión del refrigerante y la posición para poder obtener todos los beneficios del refrigerante durante el proceso de corte.
- Una aplicación apropiada del refrigerante fomenta mayores parámetros de operación, mayores índices de eliminación de material, acabados de superficie mejorados, una duración de la herramienta más predecible, bajo consumo de energía y un tiempo de ciclo reducido.
- La presión es importante pero lo es más la estabilidad de la presión y la aplicación en la herramienta; la refrigeración intermitente del carburo conlleva un estrés térmico del material y la formación de "microfisuras".
- La limpieza adecuada y la filtración de refrigerantes es importante para que el mismo mantenga sus propiedades beneficiosas, y también para evitar una reducción en la presión o la posibilidad de obstruir los canales del refrigerante del taladro.

PRESIÓN DE REFRIGERANTE
RECOMENDADA POR DIÁMETRO – psi




PRESIÓN DE REFRIGERANTE
RECOMENDADA POR DIÁMETRO – bar





PUNTA GRANDE – BAJA VELOCIDAD
SIN ALCANCE A PROFUNDIDAD MÁXIMA




PUNTA PEQUEÑA – ALTA VELOCIDAD
COMPLETO ALCANCE

- Reducir el tamaño de la boquilla ayuda a maximizar los beneficios de refrigeración del exclusivo diseño de doble margen del taladro Hi-PerCarb aumentando la velocidad. Coloque las boquillas en línea con el segundo filo que se encuentra entre los dos márgenes y también el filo para obtener mejores resultados.


Opérations de forage
Recommandations en matière de refroidissement


- Le réfrigérant sert à éloigner les copeaux de la zone de coupe, à réduire la chaleur dégagée durant la coupe et à minimiser la friction.
- Il est important d'optimiser la pression et la position du réfrigérant pour en retirer les bénéfices maximums durant la coupe.
- L'application adéquate de réfrigérant se traduit par des paramètres opératoires supérieurs, des taux d'élimination supérieurs des matériaux, de plus belles finitions des surfaces, une durée de vie des outils prévisible, moins de consommation d'énergie et des temps de cycle réduits.
- La pression est importante, mais une pression régulière et l'application sur l'outil sont des facteurs encore plus importants ; le refroidissement intermittent du carbure se traduit par des contraintes thermiques pour le matériau et la formation de microfissures.
- La propreté et le filtrage adéquats des réfrigérants sont importants pour qu'ils conservent leur propriétés, mais aussi pour éviter la réduction de pression du réfrigérant ou le risque d'obturation des conduits à réfrigérant dans les perceuses à réfrigérant intégré.

PRESSION DE RÉFRIGÉRANT
RECOMMANDÉE PAR DIAMÈTRE – psi




PRESSION DE RÉFRIGÉRANT
RECOMMANDÉE PAR DIAMÈTRE – bar





POINTE LARGE – BASSE VITESSE
PAS DE COUVERTURE À LA PROFONDEUR MAXIMUM




POINTE FINE – GRANDE VITESSE
COUVERTURE COMPLÈTE

- La réduction de la taille de l'embout permet de maximiser les bienfaits du refroidissement du concept à double listel original de la perceuse Hi-PerCarb en augmentant la vitesse. Pour les meilleurs résultats, orientez les embouts dans l'axe de la goujure secondaire située entre les deux listels, de même que la goujure primaire.







TOLERANCES (inch)

D_1 = +.0000/–.0005

TOLERANCES (mm)

D_1 = +0,0000/–0,0127

101

FRACTIONAL & METRIC SERIES

TECH INFO 214–217


CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#80	0.0135	3/4	3/16	5/32	51080	57076
#79	0.0145	3/4	3/16	5/32	51079	57077
1/64	0.0156	3/4	3/16	5/32	51101	57078
#78	0.0160	3/4	3/16	5/32	51078	57079
#77	0.0180	3/4	3/16	5/32	51077	57080
#76	0.0200	7/8	1/4	13/64	51076	57081
#75	0.0210	7/8	1/4	13/64	51075	57082
#74	0.0225	7/8	1/4	13/64	51074	57083
#73	0.0240	7/8	1/4	13/64	51073	57084
#72	0.0250	1	5/16	1/4	51072	57085
#71	0.0260	1	5/16	1/4	51071	57086
0,7 mm	0.0276	28,0	9,0	7,0	61001	68268
#70	0.0280	1-1/4	1/2	13/32	51070	57087
#69	0.0292	1-1/4	1/2	13/32	51069	57088
#68	0.0310	1-1/4	1/2	13/32	51068	57089
1/32	0.0312	1-1/4	1/2	13/32	51102	57090
0,8 mm	0.0315	30,0	10,0	8,0	61003	68269
#67	0.0320	1-1/4	1/2	13/32	51067	57091
#66	0.0330	1-1/4	1/2	13/32	51066	57092
#65	0.0350	1-3/8	5/8	1/2	51065	57093
0,9 mm	0.0354	32,0	11,0	8,0	61005	68270
#64	0.0360	1-3/8	5/8	1/2	51064	57094
#63	0.0370	1-3/8	5/8	1/2	51063	57095
#62	0.0380	1-3/8	5/8	1/2	51062	57096
#61	0.0390	1-3/8	5/8	1/2	51061	57097
1,0 mm	0.0394	34,0	12,0	9,0	61007	68271
#60	0.0400	1-1/2	3/4	39/64	51060	57098
#59	0.0410	1-1/2	3/4	39/64	51059	57099
#58	0.0420	1-1/2	3/4	39/64	51058	57100
#57	0.0430	1-1/2	3/4	39/64	51057	57101
1,1 mm	0.0433	36,0	14,0	11,0	61052	68294
#56	0.0465	1-1/2	3/4	39/64	51056	57102
3/64	0.0469	1-1/2	3/4	39/64	51103	57103
1,2 mm	0.0472	38,0	16,0	12,0	61053	68295
1,3 mm	0.0512	38,0	16,0	12,0	61054	68296
#55	0.0520	1-1/2	3/4	39/64	51055	57104
#54	0.0550	1-1/2	3/4	39/64	51054	57105
1,4 mm	0.0551	40,0	18,0	14,0	61055	68297
1,5 mm	0.0591	40,0	18,0	14,0	61009	68272

continued on next page

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS







101

FRACTIONAL & METRIC SERIES

TECH INFO 214–217

TOLERANCES (inch)

D_1 = +.0000/–.0005

TOLERANCES (mm)

D_1 = +0,0000/–0,0127

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#53	0.0595	1-1/2	3/4	39/64	51053	57106
*1/16	0.0625	1-1/2	3/4	39/64	51104	57107
1,6 mm	0.0630	43,0	20,0	16,0	61056	68298
#52	0.0635	1-1/2	3/4	39/64	51052	57108
1,7 mm	0.0669	43,0	20,0	17,0	61057	68299
#51	0.0670	1-1/2	3/4	39/64	51051	57109
#50	0.0700	1-3/4	7/8	45/64	51050	57110
1,8 mm	0.0709	46,0	22,0	17,0	61058	68300
#49	0.0730	1-3/4	7/8	45/64	51049	57111
1,9 mm	0.0748	46,0	22,0	17,0	61059	68301
#48	0.0760	1-3/4	7/8	45/64	51048	57112
5/64	0.0781	1-3/4	7/8	45/64	51105	57113
#47	0.0785	1-3/4	7/8	45/64	51047	57114
2,0 mm	0.0787	49,0	24,0	19,0	61011	68273
#46	0.0810	1-3/4	7/8	45/64	51046	57115
#45	0.0820	1-3/4	7/8	45/64	51045	57116
2,1 mm	0.0827	49,0	24,0	19,0	61060	68302
#44	0.0860	2	1	51/64	51044	57117
2,2 mm	0.0866	53,0	27,0	21,0	61061	68303
#43	0.0890	2	1	51/64	51043	57118
2,3 mm	0.0906	53,0	27,0	21,0	61062	68304
#42	0.0935	2	1	51/64	51042	57119
3/32 mm	0.0938	2	1	51/64	51106	57120
2,4 mm	0.0945	57,0	30,0	24,0	61063	68305
#41	0.0960	2	1	51/64	51041	57121
#40	0.0980	2	1	51/64	51040	57122
2,5 mm	0.0984	57,0	30,0	24,0	61013	68274
#39	0.0995	2-1/4	1-1/4	1	51039	57123
#38	0.1015	2-1/4	1-1/4	1	51038	57124
2,6 mm	0.1024	57,0	30,0	24,0	61064	68306
#37	0.1040	2-1/4	1-1/4	1	51037	57125
2,7 mm	0.1063	61,0	33,0	26,0	61065	68307
#36	0.1065	2-1/4	1-1/4	1	51036	57126
7/64	0.1094	2-1/4	1-1/4	1	51107	57127
#35	0.1100	2-1/4	1-1/4	1	51035	57128
2,8 mm	0.1102	61,0	33,0	26,0	61066	68308
#34	0.1110	2-1/4	1-1/4	1	51034	57129
#33	0.1130	2-1/4	1-1/4	1	51033	57130
2,9 mm	0.1142	61,0	33,0	26,0	61067	68309

continued on next page



101
FRACTIONAL & METRIC SERIES


CONTINUED

CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#32	0.1160	2-1/4	1-1/4	1	51032	57131
3,0 mm	0.1181	61,0	33,0	26,0	61015	68275
#31	0.1200	2-1/4	1-1/4	1	51031	57132
3,1 mm	0.1220	65,0	36,0	28,0	61068	68310
*1/8	0.1250	2-1/4	1-1/4	1	51108	57133
3,2 mm	0.1260	65,0	36,0	28,0	61069	68311
#30	0.1285	2-1/4	1-1/4	1	51030	57134
3,3 mm	0.1299	65,0	36,0	28,0	61070	68312
3,4 mm	0.1339	70,0	39,0	31,0	61071	68313
#29	0.1360	2-1/2	1-3/8	1-7/64	51029	57135
3,5 mm	0.1378	70,0	39,0	31,0	61017	68276
#28	0.1405	2-1/2	1-3/8	1-7/64	51028	57136
9/64	0.1406	2-1/2	1-3/8	1-7/64	51109	57137
3,6 mm	0.1417	70,0	39,0	31,0	61072	68314
#27	0.1440	2-1/2	1-3/8	1-7/64	51027	57138
3,7 mm	0.1457	70,0	39,0	31,0	61073	68315
#26	0.1470	2-1/2	1-3/8	1-7/64	51026	57139
#25	0.1495	2-1/2	1-3/8	1-7/64	51025	57140
3,8 mm	0.1496	75,0	43,0	34,0	61074	68316
#24	0.1520	2-1/2	1-3/8	1-7/64	51024	57141
3,9 mm	0.1535	75,0	43,0	34,0	61075	68317
#23	0.1540	2-1/2	1-3/8	1-7/64	51023	57142
5/32	0.1562	2-1/2	1-3/8	1-7/64	51110	57143
#22	0.1570	2-1/2	1-3/8	1-7/64	51022	57144
4,0 mm	0.1575	75,0	43,0	34,0	61019	68277
#21	0.1590	2-1/2	1-3/8	1-7/64	51021	57145
#20	0.1610	2-1/2	1-3/8	1-7/64	51020	57146
4,1 mm	0.1614	75,0	43,0	34,0	61076	68318
4,2 mm	0.1654	75,0	43,0	34,0	61077	68319
#19	0.1660	2-1/2	1-5/8	1-19/64	51019	57147
4,3 mm	0.1693	80,0	47,0	37,0	61078	68320
#18	0.1695	2-3-4	1-5/8	1-19/64	51018	57148
11/64	0.1719	2-3-4	1-5/8	1-19/64	51111	57149
#17	0.1730	2-3-4	1-5/8	1-19/64	51017	57150
4,4 mm	0.1732	80,0	47,0	37,0	61079	68321
#16	0.1770	2-3-4	1-5/8	1-19/64	51016	57151
4,5 mm	0.1772	80,0	47,0	37,0	61021	68278
#15	0.1800	2-3-4	1-5/8	1-19/64	51015	57152
4,6 mm	0.1811	80,0	47,0	37,0	61080	68322
#14	0.1820	2-3-4	1-5/8	1-19/64	51014	57153
4,7 mm	0.1850	80,0	47,0	37,0	61081	68323
#13	0.1850	2-3-4	1-5/8	1-19/64	51013	57154
*3/16	0.1875	2-3-4	1-5/8	1-19/64	51112	57155
4,8 mm	0.1890	86,0	52,0	41,0	61082	68324

continued on next page







101

FRACTIONAL & METRIC SERIES

TECH INFO 214–217

TOLERANCES (inch)

D_1 = +.0000/–.0005

TOLERANCES (mm)

D_1 = +0,0000/–0,0127

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#12	0.1890	2-3-4	1-5/8	1-19/64	51012	57156
#11	0.1910	2-3-4	1-5/8	1-19/64	51011	57157
4,9 mm	0.1929	86,0	52,0	41,0	61083	68325
#10	0.1935	2-3-4	1-5/8	1-19/64	51010	57158
#9	0.1960	3	1-3/4	1-13/32	51009	57159
5,0 mm	0.1969	86,0	52,0	41,0	61023	68279
#8	0.1990	3	1-3/4	1-13/32	51008	57160
5,1 mm	0.2008	86,0	52,0	41,0	61084	68326
#7	0.2010	3	1-3/4	1-13/32	51007	57161
13/64	0.2031	3	1-3/4	1-13/32	51113	57162
#6	0.2040	3	1-3/4	1-13/32	51006	57163
5,2 mm	0.2047	86,0	52,0	41,0	61085	68327
#5	0.2055	3	1-3/4	1-13/32	51005	57164
5,3 mm	0.2087	86,0	52,0	41,0	61086	68328
#4	0.2090	3	1-3/4	1-13/32	51004	57165
5,4 mm	0.2126	93,0	57,0	45,0	61087	68329
#3	0.2130	3	1-3/4	1-13/32	51003	57166
5,5 mm	0.2165	94,5	57,0	1-13/32	61025	68280
7/32	0.2188	3	1-3/4	1-13/32	51114	57167
5,6 mm	0.2205	93,0	57,0	45,0	61088	68330
#2	0.2210	3	1-3/4	1-13/32	51002	57168
5,7 mm	0.2244	93,0	57,0	45,0	61089	68331
#1	0.2280	3	1-3/4	1-13/32	51001	57169
5,8 mm	0.2283	93,0	57,0	45,0	61090	68332
5,9 mm	0.2323	93,0	57,0	45,0	61091	68333
A	0.2340	3-1/4	2	1-39/64	51201	57170
15/64	0.2344	3-1/4	2	1-39/64	51115	57171
6,0 mm	0.2362	93,0	57,0	45,0	61027	68281
B	0.2380	3-1/4	2	1-39/64	51202	57172
6,1 mm	0.2402	101,0	63,0	50,0	61092	68334
C	0.2420	3-1/4	2	1-39/64	51203	57173
6,2 mm	0.2441	101,0	63,0	50,0	61093	68335
D	0.2460	3-1/4	2	1-39/64	51204	57174
6,3 mm	0.2480	101,0	63,0	50,0	61094	68336
1/4	0.2500	3-1/4	2	1-39/64	51205	57176
6,4 mm	0.2520	101,0	63,0	50,0	61095	68337
6,5 mm	0.2559	101,0	63,0	50,0	61029	68282
F	0.2570	3-1/4	2	1-39/64	51206	57177

continued on next page



101
FRACTIONAL & METRIC SERIES


CONTINUED

CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
6,6 mm	0.2598	101,0	63,0	50,0	61096	68338
G	0.2610	3-1/2	2-1/8	1-45/64	51207	57178
6,7 mm	0.2638	101,0	63,0	50,0	61097	68339
17/64	0.2656	3-1/2	2-1/8	1-45/64	51117	57179
H	0.2660	3-1/2	2-1/8	1-45/64	51208	57180
6,8 mm	0.2677	109,0	69,0	55,0	61098	68340
6,9 mm	0.2717	109,0	69,0	55,0	61099	68341
I	0.2720	3-1/2	2-1/8	1-45/64	51209	57181
7,0 mm	0.2756	109,0	69,0	55,0	61031	68283
J	0.2770	3-1/2	2-1/8	1-45/64	51210	57182
7,1 mm	0.2795	109,0	69,0	55,0	61100	68342
K	0.2810	3-1/2	2-1/8	1-45/64	51211	57183
9/32	0.2812	3-1/2	2-1/8	1-45/64	51118	57184
7,2 mm	0.2835	109,0	69,0	55,0	61101	68343
7,3 mm	0.2874	109,0	69,0	55,0	61102	68344
L	0.2900	3-1/2	2-1/8	1-45/64	51212	57185
7,4 mm	0.2913	109,0	69,0	55,0	61103	68345
M	0.2950	3-3/4	2-3/8	1-29/32	51213	57186
7,5 mm	0.2953	109,0	69,0	55,0	61033	68284
19/64	0.2969	3-3/4	2-3/8	1-29/32	51119	57187
7,6 mm	0.2992	117,0	75,0	60,0	61104	68346
N	0.3020	3-3/4	2-3/8	1-29/32	51214	57188
7,7 mm	0.3031	117,0	75,0	60,0	61105	68347
7,8 mm	0.3071	117,0	75,0	60,0	61106	68348
7,9 mm	0.3110	117,0	75,0	60,0	61107	68349
*5/16	0.3125	3-3/4	2-3/8	1-29/32	51120	57189
8,0 mm	0.3150	117,0	75,0	60,0	61035	68285
O	0.3160	3-3/4	2-3/8	1-29/32	51215	57190
8,1 mm	0.3189	117,0	75,0	60,0	61108	68350
8,2 mm	0.3228	117,0	75,0	60,0	61109	68351
P	0.3230	3-3/4	2-3/8	1-29/32	51216	57191
8,3 mm	0.3268	117,0	75,0	60,0	61110	68352
21/64	0.3281	4	2-1/2	2	51121	57192
8,4 mm	0.3307	117,0	75,0	60,0	61111	68353
Q	0.3320	4	2-1/2	2	51217	57193
8,5 mm	0.3346	117,0	75,0	60,0	61037	68286
8,6 mm	0.3386	125,0	81,0	64,0	61112	68354
R	0.3390	4	2-1/2	2	51218	57194
8,7 mm	0.3425	125,0	81,0	64,0	61113	68355
11/32	0.3438	4	2-1/2	2	51122	57195
8,8 mm	0.3465	125,0	81,0	64,0	61114	68356
S	0.3480	4	2-1/2	2	51219	57196
8,9 mm	0.3504	125,0	81,0	64,0	61115	68357
9,0 mm	0.3543	125,0	81,0	64,0	61039	68287

continued on next page







101

FRACTIONAL & METRIC SERIES

TECH INFO 214–217

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

CUTTING DIAMETER D_1	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
T	0.3580	4-1/4	2-3/4	2-13/64	51220	57197
9,1 mm	0.3583	125,0	81,0	64,0	61116	68358
23/64	0.3594	4-1/4	2-3/4	2-13/64	51123	57198
9,2 mm	0.3622	125,0	81,0	64,0	61117	68359
9,3 mm	0.3661	125,0	81,0	64,0	61118	68360
U	0.3680	4-1/4	2-3/4	2-13/64	51221	57199
9,4 mm	0.3701	125,0	81,0	64,0	61119	68361
9,5 mm	0.3740	125,0	81,0	64,0	61041	68288
*3/8	0.3750	4-1/4	2-3/4	2-13/64	51124	57200
V	0.3770	4-1/4	2-3/4	2-13/64	51222	57201
9,6 mm	0.3780	133,0	87,0	69,0	61120	68362
9,7 mm	0.3819	133,0	87,0	69,0	61121	68363
9,8 mm	0.3858	133,0	87,0	69,0	61122	68364
W	0.3860	4-1/2	2-7/8	2-19/64	51223	57202
9,9 mm	0.3898	133,0	87,0	69,0	61123	68365
25/64	0.3906	4-1/2	2-7/8	2-19/64	51125	57203
10,0 mm	0.3937	133,0	87,0	69,0	61043	68289
X	0.3970	4-1/2	2-7/8	2-19/64	51224	57204
10,2 mm	0.4016	133,0	87,0	69,0	61124	68366
Y	0.4040	4-1/2	2-7/8	2-19/64	51225	57205
13/32	0.4062	4-1/2	2-7/8	2-19/64	51126	57206
Z	0.4130	4-1/2	2-7/8	2-19/64	51226	57207
10,5 mm	0.4134	133,0	87,0	69,0	61045	68290
27/64	0.4219	4-1/2	2-7/8	2-19/64	51127	57208
11,0 mm	0.4331	142,0	94,0	75,0	61047	68291
7/16	0.4375	4-1/2	2-7/8	2-19/64	51128	57209
11,5 mm	0.4528	142,0	94,0	75,0	61049	68292
29/64	0.4531	4-3/4	3	2-13/32	51129	57210
15/32	0.4688	4-3/4	3	2-13/32	51130	57211
12,0 mm	0.4724	151,0	101,0	80,0	61051	68293
31/64	0.4844	4-3/4	3	2-13/32	51131	57212
1/2	0.5000	4-3/4	3	2-13/32	51132	57213
*Series 101 Set					61175	57351

TOLERANCES (inch)


D_1 = +.0000/–.0005

TOLERANCES (mm)

D_1 = +0,0000/–0,0127







108M Plus

METRIC SERIES

TECH INFO 216

TOLERANCES h_6 (mm)

≤3 DIAMETER
D_1 = +0,000/–0,010
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,000/–0,012
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,015
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,000/–0,018
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,000/–0,021
D_2 = h_6


mm				EDP NO,	
CUTTING DIAMETER D_1 / D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	UNCOATED	Ti-NAMITE-A (AlTiN)
0,5	20,0	3,0	2,1	62001	68643
0,55	21,0	3,5	2,5	62003	68644
0,6	21,0	3,5	2,5	62005	68645
0,65	22,0	4,0	2,9	62007	68646
0,7	23,0	4,5	3,2	62009	68647
0,75	23,0	4,5	3,2	62011	68648
0,8	24,0	5,0	3,6	62013	68649
0,85	24,0	5,0	3,6	62015	68650
0,9	25,0	5,5	4,0	62017	68651
0,95	25,0	5,5	4,0	62019	68652
1,0	26,0	6,0	4,7	62021	68653
1,05	26,0	6,0	4,7	62023	68654
1,1	28,0	7,0	5,4	62025	68655
1,15	28,0	7,0	5,4	62027	68656
1,2	30,0	8,0	6,0	62029	68657
1,25	30,0	8,0	6,0	62031	68658
1,3	30,0	8,0	6,0	62033	68659
1,35	32,0	9,0	7,0	62035	68660
1,4	32,0	9,0	7,0	62037	68661
1,45	32,0	9,0	7,0	62039	68662
1,5	32,0	9,0	7,0	62041	68663
1,6	34,0	10,0	7,0	62043	68664
1,7	34,0	10,0	7,0	62045	68665
1,8	36,0	11,0	8,0	62047	68666
1,9	36,0	11,0	8,0	62049	68667
2,0	38,0	12,0	9,0	62051	68668
2,1	38,0	12,0	9,0	62053	68669
2,2	40,0	13,0	10,0	62055	68670
2,3	40,0	13,0	10,0	62057	68671
2,4	43,0	14,0	11,0	62059	68672
2,5	43,0	14,0	11,0	62061	68673
2,6	43,0	14,0	11,0	62063	68674
2,7	46,0	16,0	12,0	62065	68675
2,8	46,0	16,0	12,0	62067	68676
2,9	46,0	16,0	12,0	62069	68677
3,0	46,0	16,0	12,0	62071	68678
3,1	49,0	18,0	14,0	62073	68679
3,2	49,0	18,0	14,0	62075	68680

continued on next page

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES







108M Plus

METRIC SERIES

TECH INFO 216

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

mm				EDP NO,	
CUTTING DIAMETER D_1 / D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	UNCOATED	Ti-NAMITE-A (AlTiN)
3,3	49,0	18,0	14,0	62077	68681
3,4	52,0	20,0	15,0	62079	68682
3,5	52,0	20,0	15,0	62081	68683
3,6	52,0	20,0	15,0	62083	68684
3,7	52,0	20,0	15,0	62085	68685
3,8	55,0	22,0	17,0	62087	68686
3,9	55,0	22,0	17,0	62089	68687
4,0	55,0	22,0	17,0	62091	68688
4,1	55,0	22,0	17,0	62093	68689
4,2	55,0	22,0	17,0	62095	68690
4,3	58,0	24,0	18,0	62097	68691
4,4	58,0	24,0	18,0	62099	68692
4,5	58,0	24,0	18,0	62101	68693
4,6	58,0	24,0	18,0	62103	68694
4,7	58,0	24,0	18,0	62105	68695
4,8	62,0	26,0	20,0	62107	68696
4,9	62,0	26,0	20,0	62109	68697
5,0	62,0	26,0	20,0	62111	68698
5,1	62,0	26,0	20,0	62113	68699
5,2	62,0	26,0	20,0	62115	68700
5,3	62,0	26,0	20,0	62117	68701
5,4	66,0	28,0	21,0	62119	68702
5,5	66,0	28,0	21,0	62121	68703
5,6	66,0	28,0	21,0	62123	68704
5,7	66,0	28,0	21,0	62125	68705
5,8	66,0	28,0	21,0	62127	68706
5,9	66,0	28,0	21,0	62129	68707
6,0	66,0	28,0	21,0	62131	68708
6,1	70,0	31,0	23,0	62133	68709
6,2	70,0	31,0	23,0	62135	68710
6,3	70,0	31,0	23,0	62137	68711
6,4	70,0	31,0	23,0	62139	68712
6,5	70,0	31,0	23,0	62141	68713
6,8	70,0	31,0	23,0	62142	68603
7,0	74,0	34,0	25,0	62143	68718
7,5	74,0	34,0	25,0	62145	68723
7,8	79,0	37,0	27,0	62146	68604
8,0	79,0	37,0	27,0	62147	68728

continued on next page

TOLERANCES h_6 (mm)

≤3 DIAMETER
D_1 = +0,000/–0,010
D_2 = h_6

>3–6 DIAMETER
D_1 = +0,000/–0,012
D_2 = h_6

>6–10 DIAMETER
D_1 = +0,000/–0,015
D_2 = h_6

>10–18 DIAMETER
D_1 = +0,000/–0,018
D_2 = h_6

>18–30 DIAMETER
D_1 = +0,000/–0,021
D_2 = h_6



108M Plus


METRIC SERIES

CONTINUED

mm				EDP NO,	
CUTTING DIAMETER D_1 / D_2	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	UNCOATED	Ti-NAMITE-A (AlTiN)
8,5	79,0	37,0	27,0	62149	68733
9,0	84,0	40,0	29,0	62151	68738
9,5	84,0	40,0	29,0	62153	68743
9,8	89,0	43,0	31,0	62154	68606
10,0	89,0	43,0	31,0	62155	68748
10,2	89,0	43,0	31,0	62156	68607
10,5	89,0	43,0	31,0	62066	68753
11,0	95,0	47,0	33,0	62157	68758
11,5	95,0	47,0	33,0	62084	68763
11,8	102,0	51,0	35,0	62158	68608
12,0	102,0	51,0	35,0	62159	68768
12,5	102,0	51,0	35,0	62102	68773
13,0	102,0	51,0	35,0	62112	68778
13,8	107,0	54,0	37,0	62164	68609
14,0	107,0	54,0	37,0	62116	68780
14,5	111,0	56,0	38,0	62166	68611
14,8	111,0	56,0	38,0	62167	68612
15,0	111,0	56,0	38,0	62168	68613
15,8	115,0	58,0	38,0	62170	68614
16,0	115,0	58,0	38,0	62171	68616







106

FRACTIONAL & METRIC SERIES

TECH INFO 218

CAST IRON

HARDENED STEELS

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
1,0 mm	0.0394	26,0	6,0	4,5	66001	66002
#60	0.0400	1-1/2	1/2	13/32	56060	56269
#59	0.0410	1-1/2	1/2	13/32	56059	56268
#58	0.0420	1-1/2	1/2	13/32	56058	56267
#57	0.0430	1-1/2	1/2	13/32	56057	56266
#56	0.0465	1-1/2	1/2	13/32	56056	56265
3/64	0.0469	1-1/2	1/2	13/32	56103	56135
#55	0.0520	1-1/2	1/2	13/32	56055	56264
#54	0.0550	1-1/2	1/2	13/32	56054	56263
1,5 mm	0.0591	32,0	9,0	7,0	66003	66004
#53	0.0595	1-1/2	1/2	13/32	56053	56262
1/16	0.0625	1-1/2	5/8	1/2	56104	56136
#52	0.0635	1-11/16	11/16	35/64	56052	56261
#51	0.0670	1-11/16	11/16	35/64	56051	56260
#50	0.0700	1-11/16	11/16	35/64	56050	56259
#49	0.0730	1-11/16	11/16	35/64	56049	56258
#48	0.0760	1-11/16	11/16	35/64	56048	56257
5/64	0.0781	1-11/16	11/16	35/64	56105	56137
#47	0.0785	1-3/4	3/4	39/64	56047	56256
2,0 mm	0.0787	38,0	12,0	9,0	66005	66006
#46	0.0810	1-3/4	3/4	39/64	56046	56255
#45	0.0820	1-3/4	3/4	39/64	56045	56254
#44	0.0860	1-3/4	3/4	39/64	56044	56253
#43	0.0890	1-3/4	3/4	39/64	56043	56252
#42	0.0935	1-3/4	3/4	39/64	56042	56251
3/32	0.0938	1-3/4	3/4	39/64	56106	56138
#41	0.0960	1-13/16	13/16	21/32	56041	56250
#40	0.0980	1-13/16	13/16	21/32	56040	56249
2,5 mm	0.0984	43,0	14,0	11,0	66007	66008
#39	0.0995	1-13/16	13/16	21/32	56039	56248
#38	0.1015	1-13/16	13/16	21/32	56038	56247
#37	0.1040	1-13/16	13/16	21/32	56037	56246
#36	0.1065	1-13/16	13/16	21/32	56036	56245
7/64	0.1094	1-13/16	13/16	21/32	56107	56139
#35	0.1100	1-7/8	7/8	45/64	56035	56244
#34	0.1110	1-7/8	7/8	45/64	56034	56243
#33	0.1130	1-7/8	7/8	45/64	56033	56242
#32	0.1160	1-7/8	7/8	45/64	56032	56241
3,0 mm	0.1181	46,0	16,0	12,0	66009	66010

continued on next page

TOLERANCES (inch)

D_1 = +.0000/–.0005
D_2 = h6

TOLERANCES (mm)

D_1 = +0,0000/–0,0127
D_2 = h6




CONTINUED

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#31	0.1200	1-7/8	7/8	45/64	56031	56240
1/8	0.1250	1-7/8	7/8	45/64	56108	56140
#30	0.1285	1-15/16	15/16	3/4	56030	56239
#29	0.1360	1-15/16	15/16	3/4	56029	56238
3,5 mm	0.1378	52,0	20,0	15,0	66011	66012
#28	0.1405	1-15/16	15/16	3/4	56028	56237
9/64	0.1406	1-15/16	15/16	3/4	56109	56141
#27	0.1440	2-1/16	1	51/64	56027	56236
#26	0.1470	2-1/16	1	51/64	56026	56235
#25	0.1495	2-1/16	1	51/64	56025	56234
#24	0.1520	2-1/16	1	51/64	56024	56233
#23	0.1540	2-1/16	1	51/64	56023	56232
5/32	0.1562	2-1/16	1	51/64	56110	56142
#22	0.1570	2-1/8	1-1/16	55/64	56022	56231
4,0 mm	0.1575	55,0	22,0	17,0	66013	66014
#21	0.1590	2-1/8	1-1/16	55/64	56021	56230
#20	0.1610	2-1/8	1-1/16	55/64	56020	56229
#19	0.1660	2-1/8	1-1/16	55/64	56019	56228
#18	0.1695	2-1/8	1-1/16	55/64	56018	56227
11/64	0.1719	2-1/8	1-1/16	55/64	56111	56143
#17	0.1730	2-3/16	1-1/8	29/32	56017	56226
#16	0.1770	2-3/16	1-1/8	29/32	56016	56225
4,5 mm	0.1772	58,0	24,0	18,0	66015	66016
#15	0.1800	2-3/16	1-1/8	29/32	56015	56224
#14	0.1820	2-3/16	1-1/8	29/32	56014	56223
#13	0.1850	2-3/16	1-1/8	29/32	56013	56222
3/16	0.1875	2-3/16	1-1/8	29/32	56112	56144
#12	0.1890	2-3/16	1-1/8	29/32	56012	56221
#11	0.1910	2-3/16	1-1/8	29/32	56011	56220
#10	0.1935	2-3/16	1-1/8	29/32	56010	56219
#9	0.1960	2-1/4	1-3/16	61/64	56009	56218
5,0 mm	0.1969	62,0	26,0	20,0	66017	66018
#8	0.1990	2-1/4	1-3/16	61/64	56008	56217
#7	0.2010	2-1/4	1-3/16	61/64	56007	56216
13/64	0.2031	2-1/4	1-3/16	61/64	56113	56145
#6	0.2040	2-3/8	1-1/4	1	56006	56215
#5	0.2055	2-3/8	1-1/4	1	56005	56214
#4	0.2090	2-3/8	1-1/4	1	56004	56213
#3	0.2130	2-3/8	1-1/4	1	56003	56212
5,5 mm	0.2165	66,0	28,0	21,0	66019	66020
7/32	0.2188	2-3/8	1-1/4	1	56114	56146
#2	0.2210	2-7/16	1-5/16	1-3/64	56002	56211
#1	0.2280	2-7/16	1-5/16	1-3/64	56001	56210
15/64	0.2344	2-7/16	1-5/16	1-3/64	56115	56147
6,0 mm	0.2362	66,0	28,0	21,0	66021	66045

continued on next page







106

FRACTIONAL & METRIC SERIES

TECH INFO 218

CAST IRON

HARDENED STEELS

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
1/4	0.2500	2-1/2	1-3/8	1-7/64	56116	56148
6,5 mm	0.2559	70,0	31,0	23,0	66022	66046
17/64	0.2656	2-5/8	1-7/16	1-7/64	56117	56149
7,0 mm	0.2756	74,0	34,0	25,0	66023	66024
9/32	0.2812	2-11/16	1-1/2	1-13/64	56118	56150
7,5 mm	0.2953	74,0	34,0	25,0	66025	66026
19/64	0.2969	2-3/4	1-9/16	1-1/4	56119	56151
5/16	0.3125	2-13/16	1-5/8	1-19/64	56120	56152
8,0 mm	0.3150	79,0	37,0	27,0	66027	66028
21/64	0.3281	2-15/16	1-11/16	1-23/64	56121	56153
8,5 mm	0.3346	79,0	37,0	27,0	66029	66030
11/32	0.3438	3-11/64	1-11/16	1-23/64	56122	56154
9,0 mm	0.3543	84,0	40,0	29,0	66031	66032
23/64	0.3594	3-1/16	1-3/4	1-13/32	56123	56155
9,5 mm	0.3740	84,0	40,0	29,0	66033	66034
3/8	0.3750	3-1/8	1-13/16	1-29/64	56124	56156
25/64	0.3906	3-1/4	1-7/8	1-1/2	56125	56157
10,0 mm	0.3937	89,0	43,0	31,0	66035	66036
13/32	0.4062	3-5/16	1-15/16	1-35/64	56126	56158
10,5 mm	0.4134	95,0	43,0	31,0	66037	66038
27/64	0.4219	3-3/8	2	1-39/64	56127	56159
11,0 mm	0.4331	95,0	47,0	33,0	66039	66040
7/16	0.4375	3-7/16	2-1/16	1-21/32	56128	56160
11,5 mm	0.4528	95,0	47,0	33,0	66041	66042
29/64	0.4531	3-9/16	2-1/8	1-45/64	56129	56161
15/32	0.4688	3-5/8	2-1/8	1-45/64	56130	56162
12,0 mm	0.4724	102,0	51,0	35,0	66043	66044
31/64	0.4844	3-11/16	2-3/16	1-3/4	56131	56163
1/2	0.5000	3-3/4	2-1/4	1-51/64	56132	56164

TOLERANCES (inch)


D_1 = +.0000/–.0005
D_2 = h6

TOLERANCES (mm)

D_1 = +0,0000/–0,0127
D_2 = h6



3xD (mm) | 5xD (inch) | RH



TOLERANCES (inch)

D_1 = +.0000/–.0005
D_2 = h_6

TOLERANCES (mm)

D_1 = +0,0000/–0,0127
D_2 = h_6

103
FRACTIONAL & METRIC SERIES


TECH INFO 219–220

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#36	0.1065	2-1/4	1-1/4	1	53036	58011
7/64	0.1094	2-1/4	1-1/4	1	53107	58012
#35	0.1100	2-1/4	1-1/4	1	53035	58013
#34	0.1110	2-1/4	1-1/4	1	53034	58014
#33	0.1130	2-1/4	1-1/4	1	53033	58015
#32	0.1160	2-1/4	1-1/4	1	53032	58016
3,0 mm	0.1181	46,0	16,0	12,0	63000	68965
#31	0.1200	2-1/4	1-1/4	1	53031	58017
3,1 mm	0.1220	49,0	18,0	14,0	63044	68966
1/8	0.1250	2-1/4	1-1/4	1	53108	58018
3,2 mm	0.1260	49,0	18,0	14,0	63045	68967
#30	0.1285	2-1/4	1-1/4	1	53030	58019
3,3 mm	0.1299	49,0	18,0	14,0	63001	68968
3,4 mm	0.1339	52,0	20,0	15,0	63046	68969
#29	0.1360	2-1/2	1-3/8	1-7/64	53029	58020
3,5 mm	0.1378	52,0	20,0	15,0	63002	68970
#28	0.1405	2-1/2	1-3/8	1-7/64	53028	58021
9/64	0.1406	2-1/2	1-3/8	1-7/64	53109	58022
3,6 mm	0.1417	52,0	20,0	15,0	63047	68971
#27	0.1440	2-1/2	1-3/8	1-7/64	53027	58023
3,7 mm	0.1457	52,0	20,0	15,0	63003	68972
#26	0.1470	2-1/2	1-3/8	1-7/64	53026	58024
#25	0.1495	2-1/2	1-3/8	1-7/64	53025	58025
3,8 mm	0.1496	55,0	22,0	17,0	63048	68973
#24	0.1520	2-1/2	1-3/8	1-7/64	53024	58026
3,9 mm	0.1535	55,0	22,0	17,0	63049	68974
#23	0.1540	2-1/2	1-3/8	1-7/64	53023	58027
5/32	0.1562	2-1/2	1-3/8	1-7/64	53110	58028
#22	0.1570	2-1/2	1-3/8	1-7/64	53022	58029
4,0 mm	0.1575	55,0	22,0	17,0	63004	68975
#21	0.1590	2-1/2	1-3/8	1-7/64	53021	58030
#20	0.1610	2-1/2	1-3/8	1-7/64	53020	58031
4,1 mm	0.1614	55,0	22,0	17,0	63050	68976
4,2 mm	0.1654	55,0	22,0	17,0	63005	68977
#19	0.1660	2-3/4	1-5/8	1-19/64	53019	58032
4,3 mm	0.1693	58,0	24,0	18,0	63051	68978
#18	0.1695	2-3/4	1-5/8	1-19/64	53018	58033
11/64	0.1719	2-3/4	1-5/8	1-19/64	53111	58034

continued on next page



3xD (mm) | 5xD (inch) | RH



103

FRACTIONAL & METRIC SERIES

TECH INFO 219–220

STEELS
CAST IRON
NON-FERROUS

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
#17	0.1730	2-3/4	1-5/8	1-19/64	53017	58035
4,4 mm	0.1732	58,0	24,0	18,0	63052	68979
#16	0.1770	2-3/4	1-5/8	1-19/64	53016	58036
4,5 mm	0.1772	58,0	24,0	18,0	63006	68980
#15	0.1800	2-3/4	1-5/18	1-19/64	53015	58037
4,6 mm	0.1811	58,0	24,0	18,0	63053	68981
#14	0.1820	2-3/4	1-5/8	1-19/64	53014	58038
#13	0.1850	2-3/4	1-5/8	1-19/64	53013	58039
4,7 mm	0.1850	62,0	26,0	18,0	63054	68982
3/16	0.1875	2-3/4	1-5/8	1-19/64	53112	58040
#12	0.1890	2-3/4	1-5/8	1-19/64	53012	58041
4,8 mm	0.1890	62,0	26,0	20,0	63055	68983
#11	0.1910	2-3/4	1-5/8	1-19/64	53011	58042
4,9 mm	0.1929	62,0	26,0	20,0	63056	68984
#10	0.1935	2-3/4	1-5/8	1-19/64	53010	58043
#9	0.1960	3	1-3/4	1-13/32	53009	58044
5,0 mm	0.1969	62,0	26,0	20,0	63007	68985
#8	0.1990	3	1-3/4	1-13/32	53008	58045
5,1 mm	0.2008	62,0	26,0	20,0	63057	68986
#7	0.2010	3	1-3/4	1-13/32	53007	58046
13/64	0.2031	3	1-3/4	1-13/32	53113	58047
#6	0.2040	3	1-3/4	1-13/32	53006	58048
5,2 mm	0.2047	62,0	26,0	20,0	63008	68987
#5	0.2055	3	1-3/4	1-13/32	53005	58049
5,3 mm	0.2087	62,0	26,0	20,0	63058	68988
#4	0.2090	3	1-3/4	1-13/32	53004	58050
5,4 mm	0.2126	66,0	28,0	21,0	63059	68989
#3	0.2130	3	1-3/4	1-13/32	53003	58051
5,5 mm	0.2165	66,0	28,0	21,0	63009	68990
7/32	0.2188	3	1-3/4	1-13/32	53114	58052
5,6 mm	0.2205	66,0	28,0	21,0	63060	68991
#2	0.2210	3	1-3/4	1-13/32	53002	58053
5,7 mm	0.2244	66,0	28,0	21,0	63061	68992
#1	0.2280	3	1-3/4	1-13/32	53001	58054
5,8 mm	0.2283	66,0	28,0	21,0	63062	68993
5,9 mm	0.2323	66,0	28,0	21,0	63063	68994
A	0.2340	3-1/4	2	1-39/64	53201	58055
15/64	0.2344	3-1/4	2	1-39/64	53115	58056

continued on next page

TOLERANCES (inch)

D_1 = +.0000/–.0005
D_2 = h6

TOLERANCES (mm)

D_1 = +0,0000/–0,0127
D_2 = h6



103
FRACTIONAL & METRIC SERIES


CONTINUED

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
6,0 mm	0.2362	66,0	28,0	21,0	63010	68995
B	0.2380	3-1/4	2	1-39/64	53202	58057
6,1 mm	0.2402	70,0	31,0	23,0	63064	68996
C	0.2420	3-1/4	2	1-39/64	53203	58058
6,2 mm	0.2441	70,0	31,0	23,0	63011	68997
D	0.2460	3-1/4	2	1-39/64	53204	58059
6,3 mm	0.2480	70,0	31,0	23,0	63065	68998
1/4	0.2500	3-1/4	2	1-39/64	53116	58061
6,4 mm	0.2520	70,0	31,0	23,0	63066	68999
6,5 mm	0.2559	70,0	31,0	23,0	63012	69000
F	0.2570	3-1/4	2	1-39/64	53206	58062
6,6 mm	0.2598	70,0	31,0	23,0	63067	69001
G	0.2610	3-1/2	2-1/8	1-45/64	53207	58063
6,7 mm	0.2638	70,0	31,0	23,0	63068	69002
17/64	0.2656	3-1/2	2-1/8	1-45/64	53117	58064
H	0.2660	3-1/2	2-1/8	1-45/64	53208	58065
6,8 mm	0.2677	74,0	34,0	25,0	63013	69003
6,9 mm	0.2717	74,0	34,0	25,0	63069	69004
I	0.2720	3-1/2	2-1/8	1-45/64	53209	58066
7,0 mm	0.2756	74,0	34,0	25,0	63014	69005
J	0.2770	3-1/2	2-1/8	1-45/64	53210	58067
7,1 mm	0.2795	74,0	34,0	25,0	63070	69006
K	0.2810	3-1/2	2-1/8	1-45/64	53211	58068
9/32	0.2812	3-1/2	2-1/8	1-45/64	53118	58069
7,2 mm	0.2835	74,0	34,0	25,0	63015	69007
7,3 mm	0.2874	74,0	34,0	25,0	63071	69008
L	0.2900	3-1/2	2-1/8	1-45/64	53212	58070
7,4 mm	0.2913	74,0	34,0	25,0	63072	69009
M	0.2950	3-3/4	2-3/8	1-29/32	53213	58071
7,5 mm	0.2953	74,0	34,0	25,0	63016	69010
19/64	0.2969	3-3/4	2-3/8	1-29/32	53119	58072
7,6 mm	0.2992	79,0	37,0	27,0	63073	69011
N	0.3020	2-3/8	2-3/8	1-29/32	53214	58073
7,7 mm	0.3031	79,0	37,0	27,0	63074	69012
7,8 mm	0.3071	79,0	37,0	27,0	63075	69013
7,9 mm	0.3110	79,0	37,0	27,0	63076	69014
5/16	0.3125	3-3/4	2-3/8	1-29/32	53120	58074
8,0 mm	0.3150	79,0	37,0	27,0	63017	69015
O	0.3160	3-3/4	2-3/8	1-29/32	53215	58075
8,1 mm	0.3189	79,0	37,0	27,0	63077	69016
8,2 mm	0.3228	79,0	37,0	27,0	63018	69017
P	0.3230	3-3/4	2-3/8	1-29/32	53216	58076
8,3 mm	0.3268	79,0	37,0	27,0	63078	69018
21/64	0.3281	4	2-1/2	2	53121	58077

continued on next page



3xD (mm) | 5xD (inch) | RH



103

FRACTIONAL & METRIC SERIES

TECH INFO 219–220

STEELS
CAST IRON
NON-FERROUS

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
8,4 mm	0.3307	79,0	37,0	27,0	63019	69019
Q	0.3320	4	2-1/2	2	53217	58078
8,5 mm	0.3346	79,0	37,0	27,0	63020	69020
8,6 mm	0.3386	84,0	40,0	29,0	63021	69021
R	0.3390	4	2-1/2	2	53218	58079
8,7 mm	0.3425	89,0	40,0	29,0	63079	69022
11/32	0.3438	4	2-1/2	2	53122	58080
8,8 mm	0.3465	89,0	40,0	29,0	63022	69023
S	0.3480	4	2-1/2	2	53219	58081
8,9 mm	0.3504	84,0	40,0	29,0	63080	69024
9,0 mm	0.3543	84,0	40,0	29,0	63023	69025
T	0.3580	4-1/4	2-3/4	2-13/64	53220	58082
9,1 mm	0.3583	84,0	40,0	29,0	63081	69026
23/64	0.3594	4-1/4	2-3/4	2-13/64	53123	58083
9,2 mm	0.3622	84,0	40,0	29,0	63024	69027
9,3 mm	0.3661	84,0	40,0	29,0	63082	69028
U	0.3680	4-1/4	2-3/4	2-13/64	53221	58084
9,4 mm	0.3701	84,0	40,0	29,0	63083	69029
9,5 mm	0.3740	84,0	40,0	29,0	63025	69030
3/8	0.3750	4-1/4	2-3/4	2-13/64	53124	58085
V	0.3770	4-1/4	2-3/4	2-13/64	53222	58086
9,6 mm	0.3780	89,0	43,0	31,0	63084	69031
9,7 mm	0.3819	89,0	43,0	31,0	63085	69032
9,8 mm	0.3858	89,0	43,0	31,0	63086	69033
W	0.3860	4-1/2	2-7/8	2-19/64	53223	58087
9,9 mm	0.3898	89,0	43,0	31,0	63087	69034
25/64	0.3906	4-1/2	2-7/8	2-19/64	53125	58088
10,0 mm	0.3937	89,0	43,0	31,0	63026	69035
X	0.3970	4-1/2	2-7/8	2-19/64	53224	58089
10,1 mm	0.3976	89,0	43,0	31,0	63088	69036
10,2 mm	0.4016	89,0	43,0	31,0	63027	69037
Y	0.4040	4-1/2	2-7/8	2-19/64	53225	58090
13/32	0.4062	4-1/2	2-7/8	2-19/64	53126	58091
10,4 mm	0.4094	89,0	43,0	31,0	63028	69038
Z	0.4130	4-1/2	2-7/8	2-19/64	53226	58092
10,5 mm	0.4134	89,0	43,0	31,0	63029	69039
10,7 mm	0.4213	95,0	47,0	33,0	63030	69040
27/64	0.4219	4-1/2	2-7/8	2-19/64	53127	58093

continued on next page

TOLERANCES (inch)

D_1 = +.0000/–.0005
D_2 = h6

TOLERANCES (mm)

D_1 = +0,0000/–0,0127
D_2 = h6



103
FRACTIONAL & METRIC SERIES

CONTINUED

CUTTING DIAMETER D_1 / D_2	DECIMAL EQUIV.	OVERALL LENGTH L_1	FLUTE LENGTH L_2	CLEARED LENGTH L_3	EDP NO. UNCOATED	EDP NO. Ti-NAMITE-A (AlTiN)
10,8 mm	0.4252	95,0	47,0	33,0	63031	69041
11,0 mm	0.4331	95,0	47,0	33,0	63032	69042
7/16	0.4375	4-1/2	2-7/8	2-19/64	53128	58094
11,5 mm	0.4528	95,0	47,0	33,0	63033	69043
29/64	0.4531	4-3/4	3	2-13/32	53129	58095
15/32	0.4688	4-3/4	3	2-13/32	53130	58096
12,0 mm	0.5039	102,0	51,0	35,0	63034	69044
31/64	0.4844	4-3/4	3	2-13/32	53131	58097
12,5 mm	0.4921	102,0	51,0	35,0	63035	69045
1/2	0.5000	4-3/4	3	2-13/32	53132	58098
12,8 mm	0.5039	102,0	51,0	35,0	63036	69046
13,0 mm	0.5118	102,0	51,0	35,0	63089	69047
33/64	0.5156	4-3/4	3	2-13/32	53135	58099
13,1 mm	0.5157	102,0	51,0	35,0	63037	69048
13,5 mm	0.5315	107,0	54,0	37,0	63090	69049
14,0 mm	0.5512	107,0	54,0	37,0	63038	69050
9/16	0.5625	4-3/4	3	2-13/32	53136	58100
14,3 mm	0.5630	111,0	56,0	38,0	63039	69051
14,5 mm	0.5709	111,0	56,0	38,0	63040	69052
15,0 mm	0.5906	111,0	56,0	38,0	63091	69053
5/8	0.6250	5-3/4	3-1/2	2-51/64	53133	58101
11/16	0.6875	5-3/4	3-1/2	2-51/64	53137	58102
17,5 mm	0.6890	123,0	62,0	40,0	63041	69054
3/4	0.7500	5-3/4	4-1/4	3 13/32	53134	58103
19,5 mm	0.7677	131,0	66,0	42,0	63042	69055
20,0 mm	0.7874	131,0	66,0	42,0	63043	69056

	Series 101 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/64	1/32	1/16	1/8	1/4	3/8	1/2
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	265	RPM	64787	32394	16197	8098	4049	2699	2025
			(212-318)	Fr	0.0002	0.0004	0.0009	0.0017	0.0034	0.0050	0.0070
				Feed (IPM)	13.0	13.0	14.6	13.8	13.8	13.5	14.2
		> 200 ≤ 300	125	RPM	30560	15280	7640	3820	1910	1273	955
			(100-150)	Fr	0.0002	0.0004	0.0008	0.0016	0.0031	0.0045	0.0060
				Feed (IPM)	6.1	6.1	6.1	6.1	5.9	5.7	5.7
		> 300 ≤ 420	85	RPM	20781	10390	5195	2598	1299	866	649
			(68-102)	Fz	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025	0.0035
				Feed (IPM)	2.1	2.1	2.6	2.3	2.3	2.2	2.3
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	230	RPM	56230	28115	14058	7029	3514	2343	1757
			(184-276)	Fz	0.0002	0.0004	0.0008	0.0016	0.0031	0.0045	0.0060
				Feed (IPM)	11.2	11.2	11.2	11.2	10.9	10.5	10.5
		> 275 ≤ 375	145	RPM	35450	17725	8862	4431	2216	1477	1108
			(116-174)	Fr	0.0002	0.0004	0.0008	0.0015	0.0030	0.0045	0.0060
				Feed (IPM)	7.1	7.1	7.1	6.6	6.6	6.6	6.6
		> 375 ≤ 450	60	RPM	14669	7334	3667	1834	917	611	458
			(48-72)	Fr	0.0001	0.0002	0.0004	0.0007	0.0013	0.0020	0.0025
				Feed (IPM)	1.5	1.5	1.5	1.3	1.2	1.2	1.1
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	85	RPM	20781	10390	5195	2598	1299	866	649
			(68-102)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025	0.0035
				Feed (IPM)	2.1	2.1	2.6	2.3	2.3	2.2	2.3
		> 250 ≤ 330	55	RPM	13446	6723	3362	1681	840	560	420
			(44-66)	Fr	0.00005	0.0001	0.0002	0.0004	0.0008	0.0010	0.0015
				Feed (IPM)	0.7	0.7	0.7	0.7	0.7	0.6	0.6
		> 330 ≤ 450	40	RPM	9779	4890	2445	1222	611	407	306
			(32-48)	Fr	0.00005	0.0001	0.0002	0.0004	0.0008	0.0010	0.0015
				Feed (IPM)	0.5	0.5	0.5	0.5	0.5	0.4	0.5
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	280	RPM	68454	34227	17114	8557	4278	2852	2139
			(224-336)	Fr	0.00025	0.0005	0.0011	0.0021	0.0041	0.0060	0.0080
				Feed (IPM)	17.1	17.1	18.8	18.0	17.5	17.1	17.1
		> 200 ≤ 330	250	RPM	61120	30560	15280	7640	3820	2547	1910
			(200-300)	Fr	0.00025	0.0005	0.0011	0.0021	0.0041	0.0060	0.0080
				Feed (IPM)	15.3	15.3	16.8	16.0	15.7	15.3	15.3
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	210	RPM	51341	25670	12835	6418	3209	2139	1604
			(168-252)	Fr	0.00015	0.0003	0.0006	0.0012	0.0024	0.0035	0.0050
				Feed (IPM)	7.7	7.7	7.7	7.7	7.7	7.5	8.0
		> 250 ≤ 330	110	RPM	26893	13446	6723	3362	1681	1121	840
			(88-132)	Fr	0.0001	0.0002	0.0004	0.0007	0.0014	0.0020	0.0030
				Feed (IPM)	2.7	2.7	2.7	2.4	2.4	2.2	2.5

continued on next page

	Series 101 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/64	1/32	1/16	1/8	1/4	3/8	1/2
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	65	RPM	15891	7946	3973	1986	993	662	497
			(52-78)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025	0.0035
				Feed (IPM)	1.6	1.6	2.0	1.8	1.8	1.7	1.7
		> 270 ≤ 370	55	RPM	13446	6723	3362	1681	840	560	420
			(44-66)	Fr	0.0001	0.0002	0.0004	0.0008	0.0015	0.0025	0.0030
				Feed (IPM)	1.3	1.3	1.3	1.3	1.3	1.4	1.3
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	40	RPM	9779	4890	2445	1222	611	407	306
			(32-48)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025	0.0035
				Feed (IPM)	1.0	1.0	1.2	1.1	1.1	1.0	1.1
		> 220 ≤ 330	25	RPM	6112	3056	1528	764	382	255	191
			(20-30)	Fr	0.0001	0.0002	0.0004	0.0008	0.0015	0.0025	0.0030
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
		> 330 ≤ 420	20	RPM	4890	2445	1222	611	306	204	153
			(16-24)	Fr	0.00005	0.0001	0.0002	0.0004	0.0008	0.0010	0.0015
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	85	RPM	20781	10390	5195	2598	1299	866	649
			(68-102)	Fr	0.0002	0.0004	0.0008	0.0016	0.0032	0.0050	0.0065
				Feed (IPM)	4.2	4.2	4.2	4.2	4.2	4.3	4.2
		> 280 ≤ 350	65	RPM	15891	7946	3973	1986	993	662	497
			(52-78)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025	0.0035
				Feed (IPM)	1.6	1.6	2.0	1.8	1.8	1.7	1.7
		> 350 ≤ 440	55	RPM	13446	6723	3362	1681	840	560	420
			(44-66)	Fr	0.0001	0.0002	0.0004	0.0008	0.0015	0.0025	0.0030
				Feed (IPM)	1.3	1.3	1.3	1.3	1.3	1.4	1.3
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	540	RPM	132019	66010	33005	16502	8251	5501	4126
			(432-648)	Fr	0.0003	0.0006	0.0013	0.0025	0.0050	0.0075	0.0100
				Feed (IPM)	39.6	39.6	42.9	41.3	41.3	41.3	41.3
		> 80	455	RPM	111238	55619	27810	13905	6952	4635	3476
			(364-546)	Fr	0.0003	0.0006	0.0013	0.0025	0.0050	0.0075	0.0100
				Feed (IPM)	33.4	33.4	36.2	34.8	34.8	34.8	34.8
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	190	RPM	46451	23226	11613	5806	2903	1935	1452
			(152-228)	Fr	0.00015	0.0003	0.0006	0.0012	0.0024	0.0035	0.0050
				Feed (IPM)	7.0	7.0	7.0	7.0	7.0	6.8	7.3
		> 140	175	RPM	42784	21392	10696	5348	2674	1783	1337
			(140-210)	Fr	0.00015	0.0003	0.0006	0.0012	0.0024	0.0035	0.0050
				Feed (IPM)	6.4	6.4	6.4	6.4	6.4	6.2	6.7
	PLASTICS Polycarbonate, PVC		500	RPM	122240	61120	30560	15280	7640	5093	3820
			(400-600)	Fr	0.0003	0.0006	0.0013	0.0025	0.0050	0.0075	0.0100
				Feed (IPM)	36.7	36.7	39.7	38.2	38.2	38.2	38.2

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 101M, 108M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 1	3	6	8	10	12	16
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	81	RPM	25690	8563	4282	3211	2569	2141	1606
			(65-97)	Fr	0.015	0.040	0.080	0.110	0.135	0.170	0.230
				Feed (mm/min)	385	343	343	353	347	364	369
		> 200 ≤ 300	38	RPM	12118	4039	2020	1515	1212	1010	757
			(30-46)	Fr	0.015	0.035	0.075	0.095	0.120	0.145	0.190
				Feed (mm/min)	182	141	151	144	145	146	144
		> 300 ≤ 420	26	RPM	8240	2747	1373	1030	824	687	515
			(21-31)	Fz	0.005	0.020	0.045	0.055	0.065	0.085	0.115
				Feed (mm/min)	41	55	62	57	54	58	59
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	70	RPM	22297	7432	3716	2787	2230	1858	1394
			(56-84)	Fz	0.015	0.035	0.075	0.095	0.120	0.145	0.190
				Feed (mm/min)	334	260	279	265	268	269	265
		> 275 ≤ 375	44	RPM	14057	4686	2343	1757	1406	1171	879
			(35-53)	Fr	0.010	0.035	0.070	0.095	0.120	0.145	0.190
				Feed (mm/min)	141	164	164	167	169	170	167
		> 375 ≤ 450	18	RPM	5816	1939	969	727	582	485	364
			(15-22)	Fr	0.005	0.015	0.030	0.040	0.055	0.060	0.075
				Feed (mm/min)	29	29	29	29	32	29	27
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	26	RPM	8240	2747	1373	1030	824	687	515
			(21-31)	Fr	0.005	0.020	0.045	0.055	0.065	0.085	0.115
				Feed (mm/min)	41	55	62	57	54	58	59
		> 250 ≤ 330	17	RPM	5332	1777	889	666	533	444	333
			(13-20)	Fr	0.005	0.010	0.020	0.025	0.030	0.035	0.050
				Feed (mm/min)	27	18	18	17	16	16	17
		> 330 ≤ 450	12	RPM	3878	1293	646	485	388	323	242
			(10-15)	Fr	0.005	0.010	0.020	0.025	0.030	0.035	0.050
				Feed (mm/min)	19	13	13	12	12	11	12
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	85	RPM	27144	9048	4524	3393	2714	2262	1696
			(68-102)	Fr	0.015	0.050	0.100	0.130	0.160	0.195	0.255
				Feed (mm/min)	407	452	452	441	434	441	433
		> 200 ≤ 330	76	RPM	24235	8078	4039	3029	2424	2020	1515
			(61-91)	Fr	0.015	0.050	0.100	0.130	0.160	0.195	0.255
				Feed (mm/min)	364	404	404	394	388	394	386
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	64	RPM	20358	6786	3393	2545	2036	1696	1272
			(51-77)	Fr	0.010	0.030	0.060	0.075	0.095	0.120	0.165
				Feed (mm/min)	204	204	204	191	193	204	210
		> 250 ≤ 330	34	RPM	10664	3555	1777	1333	1066	889	666
			(27-40)	Fr	0.050	0.015	0.035	0.045	0.055	0.070	0.105
				Feed (mm/min)	533	53	62	60	59	62	70

continued on next page

	Series 101M, 108M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 1	3	6	8	10	12	16
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	≤ 270	20	RPM	6301	2100	1050	788	630	525	394
			(16-24)	Fr	0.005	0.020	0.045	0.055	0.065	0.085	0.115
				Feed (mm/min)	32	42	47	43	41	45	45
		> 270 ≤ 370	17	RPM	5332	1777	889	666	533	444	333
			(13-20)	Fr	0.005	0.020	0.035	0.050	0.065	0.070	0.105
				Feed (mm/min)	27	36	31	33	35	31	35
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	12	RPM	3878	1293	646	485	388	323	242
			(10-15)	Fr	0.005	0.020	0.045	0.055	0.065	0.085	0.115
				Feed (mm/min)	19	26	29	27	25	27	28
		> 220 ≤ 330	8	RPM	2424	808	404	303	242	202	151
			(6-9)	Fr	0.005	0.020	0.035	0.050	0.065	0.070	0.105
				Feed (mm/min)	12	16	14	15	16	14	16
		> 330 ≤ 420	6	RPM	1939	646	323	242	194	162	121
			(5-7)	Fr	0.010	0.025	0.030	0.040	0.050	0.065	0.080
				Feed (mm/min)	19	16	10	10	10	11	10
S	TITANIUM ALLOYS (DIFFICULT) Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	26	RPM	8240	2747	1373	1030	824	687	515
			(21-31)	Fr	0.015	0.040	0.075	0.105	0.135	0.155	0.205
				Feed (mm/min)	124	110	103	108	111	106	106
		> 280 ≤ 350	20	RPM	6301	2100	1050	788	630	525	394
			(16-24)	Fr	0.005	0.020	0.045	0.055	0.065	0.085	0.115
				Feed (mm/min)	32	42	47	43	41	45	45
		> 350 ≤ 440	17	RPM	5332	1777	889	666	533	444	333
			(13-20)	Fr	0.005	0.020	0.035	0.050	0.065	0.070	0.105
				Feed (mm/min)	27	36	31	33	35	31	35
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	165	RPM	52348	17449	8725	6544	5235	4362	3272
			(132-198)	Fr	0.020	0.060	0.120	0.160	0.200	0.240	0.320
				Feed (mm/min)	1047	1047	1047	1047	1047	1047	1047
		> 80	139	RPM	44108	14703	7351	5514	4411	3676	2757
			(111-166)	Fr	0.020	0.060	0.120	0.160	0.200	0.240	0.320
				Feed (mm/min)	882	882	882	882	882	882	882
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	58	RPM	18419	6140	3070	2302	1842	1535	1151
			(46-69)	Fr	0.010	0.030	0.060	0.075	0.095	0.120	0.165
				Feed (mm/min)	184	184	184	173	175	184	190
		> 140	53	RPM	16965	5655	2827	2121	1696	1414	1060
			(43-64)	Fr	0.010	0.030	0.060	0.075	0.095	0.120	0.165
				Feed (mm/min)	170	170	170	159	161	170	175
	PLASTICS Polycarbonate, PVC		152	RPM	48471	16157	8078	6059	4847	4039	3029
			(122-183)	Fr	0.020	0.060	0.120	0.160	0.200	0.240	0.320
				Feed (mm/min)	969	969	969	969	969	969	969

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 106 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/16	1/8	3/16	1/4	3/8	1/2
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	> 420 ≤ 500	33	RPM	2017	1008	672	504	336	252
			(26-40)	Fz	0.0003	0.0006	0.0008	0.0012	0.0018	0.0024
				Feed (IPM)	0.6	0.6	0.5	0.6	0.6	0.6
		> 500 ≤ 615	33	RPM	2017	1008	672	504	336	252
			(26-40)	Fr	0.0002	0.0004	0.0005	0.0007	0.0010	0.0014
				Feed (IPM)	0.4	0.4	0.3	0.4	0.3	0.4
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 420 ≤ 500	34	RPM	2078	1039	693	520	346	260
			(27-41)	Fr	0.0003	0.0006	0.0008	0.0012	0.0018	0.0023
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6
		> 500 ≤ 615	33	RPM	2017	1008	672	504	336	252
			(26-40)	Fr	0.0002	0.0003	0.0004	0.0006	0.0008	0.0014
				Feed (IPM)	0.4	0.3	0.3	0.3	0.3	0.4
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	252	RPM	15402	7701	5134	3851	2567	1925
			(202-302)	Fr	0.001	0.0020	0.0030	0.0040	0.0060	0.0081
				Feed (IPM)	15.4	15.4	15.4	15.4	15.4	15.6
		> 200 ≤ 330	185	RPM	11307	5654	3769	2827	1885	1413
			(148-222)	Fr	0.001	0.0020	0.0030	0.0040	0.0060	0.0081
				Feed (IPM)	11.3	11.3	11.3	11.3	11.3	11.4

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 106M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 1	3	6	8	10	12
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	> 420 ≤ 500	10	RPM	3199	1066	533	400	320	267
			(8-12)	Fz	0.006	0.017	0.034	0.045	0.057	0.068
				Feed (mm/min)	19	18	18	18	18	18
		> 500 ≤ 615	10	RPM	3199	1066	533	400	320	267
			(8-12)	Fr	0.003	0.009	0.018	0.024	0.030	0.036
				Feed (mm/min)	10	10	10	10	10	10
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	> 420 ≤ 500	10	RPM	3296	1099	549	412	330	275
			(8-12)	Fr	0.003	0.009	0.018	0.024	0.030	0.036
				Feed (mm/min)	10	10	10	10	10	10
		> 500 ≤ 615	10	RPM	3199	1066	533	400	320	267
			(8-12)	Fr	0.002	0.007	0.014	0.019	0.023	0.028
				Feed (mm/min)	6	7	7	8	7	7
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	77	RPM	24429	8143	4072	3054	2443	2036
			(61-92)	Fr	0.016	0.048	0.096	0.128	0.160	0.192
				Feed (mm/min)	391	391	391	391	391	391
		> 200 ≤ 330	56	RPM	17934	5978	2989	2242	1793	1495
			(45-68)	Fr	0.016	0.048	0.096	0.128	0.160	0.192
				Feed (mm/min)	287	287	287	287	287	287

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 103 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	5/8	3/4
P	**CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536**	≤ 200	265	RPM	8098	4049	2699	2025	1620	1350
			(212-318)	Fr	0.0002	0.0004	0.0009	0.0017	0.0034	0.0050
				Feed (IPM)	1.6	1.6	2.4	3.4	5.5	6.7
		> 200 ≤ 300	125	RPM	3820	1910	1273	955	764	637
			(100-150)	Fr	0.0002	0.0004	0.0008	0.0016	0.0031	0.0045
				Feed (IPM)	0.8	0.8	1.0	1.5	2.4	2.9
		> 300 ≤ 420	85	RPM	2598	1299	866	649	520	433
			(68-102)	Fz	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025
				Feed (IPM)	0.3	0.3	0.4	0.6	0.9	1.1
P	**ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100**	≤ 275	230	RPM	7029	3514	2343	1757	1406	1171
			(184-276)	Fz	0.0002	0.0004	0.0008	0.0016	0.0031	0.0045
				Feed (IPM)	1.4	1.4	1.9	2.8	4.4	5.3
		> 275 ≤ 375	145	RPM	4431	2216	1477	1108	886	739
			(116-174)	Fr	0.0002	0.0004	0.0008	0.0015	0.0030	0.0045
				Feed (IPM)	0.9	0.9	1.2	1.7	2.7	3.3
		> 375 ≤ 450	60	RPM	1834	917	611	458	367	306
			(48-72)	Fr	0.0001	0.0002	0.0004	0.0007	0.0013	0.0020
				Feed (IPM)	0.2	0.2	0.2	0.3	0.5	0.6
P	**TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2**	≤ 250	85	RPM	2598	1299	866	649	520	433
			(68-102)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025
				Feed (IPM)	0.3	0.3	0.4	0.6	0.9	1.1
		> 250 ≤ 330	55	RPM	1681	840	560	420	336	280
			(44-66)	Fr	0.00005	0.0001	0.0002	0.0004	0.0008	0.0010
				Feed (IPM)	0.1	0.1	0.1	0.2	0.3	0.3
		> 330 ≤ 450	40	RPM	1222	611	407	306	244	204
			(32-48)	Fr	0.00005	0.0001	0.0002	0.0004	0.0008	0.0010
				Feed (IPM)	0.1	0.1	0.1	0.1	0.2	0.2
K	**CAST IRONS Gray, Malleable, Ductile**	≤ 200	280	RPM	8557	4278	2852	2139	1711	1426
			(224-336)	Fr	0.00025	0.0005	0.0011	0.0021	0.0041	0.0060
				Feed (IPM)	2.1	2.1	3.1	4.5	7.0	8.6
		> 200 ≤ 330	250	RPM	7640	3820	2547	1910	1528	1273
			(200-300)	Fr	0.00025	0.0005	0.0011	0.0021	0.0041	0.0060
				Feed (IPM)	1.9	1.9	2.8	4.0	6.3	7.6
S	**TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V**	≤ 280	85	RPM	2598	1299	866	649	520	433
			(68-102)	Fr	0.0002	0.0004	0.0008	0.0016	0.0032	0.0050
				Feed (IPM)	0.5	0.5	0.7	1.0	1.7	2.2
		> 280 ≤ 350	65	RPM	1986	993	662	497	397	331
			(52-78)	Fr	0.0001	0.0002	0.0005	0.0009	0.0018	0.0025
				Feed (IPM)	0.2	0.2	0.3	0.4	0.7	0.8
		> 350 ≤ 440	55	RPM	1681	840	560	420	336	280
			(44-66)	Fr	0.0001	0.0002	0.0004	0.0008	0.0015	0.0025
				Feed (IPM)	0.2	0.2	0.2	0.3	0.5	0.7
N	**ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075**	≤ 80	540	RPM	16502	8251	5501	4126	3300	2750
			(432-648)	Fr	0.0003	0.0006	0.0013	0.0025	0.0050	0.0075
				Feed (IPM)	5.0	5.0	7.2	10.3	16.5	20.6
		> 80	455	RPM	13905	6952	4635	3476	2781	2317
			(364-546)	Fr	0.0003	0.0006	0.0013	0.0025	0.0050	0.0075
				Feed (IPM)	4.2	4.2	6.0	8.7	13.9	17.4
N	**COPPER ALLOYS Alum Bronze, C110, Muntz Brass**	≤ 140	190	RPM	5806	2903	1935	1452	1161	968
			(152-228)	Fr	0.00015	0.0003	0.0006	0.0012	0.0024	0.0035
				Feed (IPM)	0.9	0.9	1.2	1.7	2.8	3.4
		> 140	175	RPM	5348	2674	1783	1337	1070	891
			(140-210)	Fr	0.00015	0.0003	0.0006	0.0012	0.0024	0.0035
				Feed (IPM)	0.8	0.8	1.1	1.6	2.6	3.1

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


	Series 103M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 3	6	10	12	16	20
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	81	RPM	8563	4282	2569	2141	1606	1284
			(65-97)	Fr	0.053	0.108	0.176	0.216	0.264	0.352
				Feed (IPM)	454	462	452	462	424	452
		> 200 ≤ 300	38	RPM	4039	2020	1212	1010	757	606
			(30-46)	Fr	0.048	0.096	0.160	0.192	0.240	0.320
				Feed (IPM)	194	194	194	194	182	194
		> 300 ≤ 420	26	RPM	2747	1373	824	687	515	412
			(21-31)	Fz	0.031	0.062	0.104	0.125	0.156	0.208
				Feed (IPM)	85	85	86	86	80	86
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	70	RPM	7432	3716	2230	1858	1394	1115
			(56-84)	Fz	0.048	0.096	0.160	0.192	0.240	0.320
				Feed (IPM)	357	357	357	357	334	357
		> 275 ≤ 375	44	RPM	4686	2343	1406	1171	879	703
			(35-53)	Fr	0.048	0.096	0.160	0.192	0.240	0.320
				Feed (IPM)	225	225	225	225	211	225
		> 375 ≤ 450	18	RPM	1939	969	582	485	364	291
			(15-22)	Fr	0.031	0.062	0.104	0.125	0.156	0.208
				Feed (IPM)	60	60	60	61	57	60
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	26	RPM	2747	1373	824	687	515	412
			(21-31)	Fr	0.031	0.062	0.104	0.125	0.156	0.208
				Feed (IPM)	85	85	86	86	80	86
		> 250 ≤ 330	17	RPM	1777	889	533	444	333	267
			(13-20)	Fr	0.017	0.036	0.056	0.074	0.084	0.112
				Feed (IPM)	30	32	30	33	28	30
		> 330 ≤ 450	12	RPM	1293	646	388	323	242	194
			(10-15)	Fr	0.012	0.024	0.040	0.046	0.060	0.080
				Feed (IPM)	16	16	16	15	15	16
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	85	RPM	9048	4524	2714	2262	1696	1357
			(68-102)	Fr	0.060	0.125	0.200	0.247	0.300	0.400
				Feed (IPM)	543	565	543	559	509	543
		> 200 ≤ 330	76	RPM	8078	4039	2424	2020	1515	1212
			(61-91)	Fr	0.060	0.125	0.200	0.247	0.300	0.400
				Feed (IPM)	485	505	485	499	454	485
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	26	RPM	2747	1373	824	687	515	412
			(21-31)	Fr	0.048	0.096	0.160	0.192	0.240	0.320
				Feed (IPM)	132	132	132	132	124	132
		> 280 ≤ 350	20	RPM	2100	1050	630	525	394	315
			(16-24)	Fr	0.029	0.058	0.096	0.113	0.144	0.192
				Feed (IPM)	61	61	60	59	57	60
		> 350 ≤ 440	17	RPM	1777	889	533	444	333	267
			(13-20)	Fr	0.029	0.058	0.096	0.113	0.144	0.192
				Feed (IPM)	52	52	51	50	48	51
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	165	RPM	17449	8725	5235	4362	3272	2617
			(132-198)	Fr	0.077	0.156	0.256	0.312	0.384	0.512
				Feed (IPM)	1344	1361	1340	1361	1256	1340
		> 80	139	RPM	14703	7351	4411	3676	2757	2205
			(111-166)	Fr	0.077	0.156	0.256	0.312	0.384	0.512
				Feed (IPM)	1132	1147	1129	1147	1059	1129
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	58	RPM	6140	3070	1842	1535	1151	921
			(46-69)	Fr	0.038	0.077	0.128	0.156	0.192	0.256
				Feed (IPM)	233	236	236	239	221	236
		> 140	53	RPM	5655	2827	1696	1414	1060	848
			(43-64)	Fr	0.038	0.077	0.128	0.156	0.192	0.256
				Feed (IPM)	215	218	217	221	204	217

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed rates shown by 30 percent when using uncoated drills

reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)







TOLERANCES (inch)

D_1 = +.003/–.000
D_2 = –.0001/–.0005

301
FRACTIONAL SERIES

TECH INFO 225

inch				EDP NO.	
SIZE	BODY DIAMETER D_2	DRILL DIAMETER D_1	APPROX. OVERALL LENGTH L_1	UNCOATED	Ti-NAMITE-A (AlTiN)
00*	1/8	.025	1-1/2	57005	57015
0*	1/8	1/32	1-1/2	57006	57016
1*	1/8	3/64	1-1/2	57007	57017
2*	3/16	5/64	1-7/8	57008	57018
3*	1/4	7/64	2	57009	57019
4*	5/16	1/8	2-1/8	57010	57020
5*	7/16	3/16	2-3/4	57011	57021
6*	1/2	7/32	3	57012	57022
Series 301 Set	–	–	–	57075	–

*Included in Series 301 Set

STEELS
STAINLESS STEELS
CAST IRON
HIGH TEMP ALLOYS
TITANIUM
NON-FERROUS
PLASTICS/COMPOSITES

TOLERANCES (mm)

0,5–2,5 DIAMETER
D_1 = +0,140/–0,000

>2,5–5 DIAMETER
D_1 = +0,000/–0,012

TOLERANCES h9 (mm)

0,5–3 DIAMETER
D_2 = +0,000/–0,025

>3–5 DIAMETER
D_2 = +0,000/–0,030


301M
METRIC SERIES

TECH INFO 227

mm			EDP NO.	
SIZE D_1	BODY DIAMETER D_2	APPROX. OVERALL LENGTH L_1	UNCOATED	Ti-NAMITE-A (AlTiN)
0,5	3,15	20,0	67005	67035
0,8	3,15	20,0	67007	67037
1	3,15	31,5	67009	67039
1,25	3,15	31,5	67011	67041
1,6	4,0	35,5	67013	67043
2	5,0	40,0	67015	67045
2,5	6,3	45,0	67017	67047
3,15	8,0	50,0	67019	67049
4	10,0	56,0	67021	67051
5	12,5	63,0	67023	67053







601
FRACTIONAL SERIES

TECH INFO 229

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES

inch			EDP NO.		
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	OVERALL LENGTH L_1	UNCOATED 60°	UNCOATED 82°	UNCOATED 90°
1/8	1/8	1-1/2	74001	74101	74201
3/16	3/16	2	74004	74104	74204
1/4	1/4	2	74007	74107	74207
3/8*	1/4	2-13/16	74010	74110	74210
1/2*	1/4	2-7/8	74013	74113	74213
5/8*	3/8	3	74016	74116	74216
3/4*	1/2	3	74019	74119	74219
1*	1/2	3-1/4	74022	74122	74222

*Steel Shank / Con mango de acero / Avec queue en acier

TOLERANCES (inch)


1/8–1/4 DIAMETER
D_1 = +.0000/–.0005

3/8–1 DIAMETER
D_1 = +.003/–.000

Included Angle +1°/–1°







TOLERANCES (inch)

1/8–1/4 DIAMETER

D_1 = +.0000/–.0005

3/8–1 DIAMETER

D_1 = +.003/–.000

Included Angle +1°/–1°

603

FRACTIONAL SERIES

TECH INFO 231

inch			EDP NO.		
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	OVERALL LENGTH L_1	UNCOATED 60°	UNCOATED 82°	UNCOATED 90°
1/8	1/8	1-1/2	74025	74125	74225
3/16	3/16	2	74028	74128	74228
1/4	1/4	2	74031	74131	74231
3/8*	1/4	2-13/16	74034	74134	74234
1/2*	1/4	2-7/8	74037	74137	74237
5/8*	3/8	3	74040	74140	74240
3/4*	1/2	3	74043	74143	74243
1*	1/2	3-1/4	74046	74146	74246

*Steel Shank / Con mango de acero / Avec queue en acier

NOTE: D3 dimension varies based on angle. Contact SGS representative or consult Tool Wizard for dimension information.

STEELS

STAINLESS STEELS

CAST IRON


HIGH TEMP ALLOYS


TITANIUM

NON-FERROUS

PLASTICS/COMPOSITES







606
FRACTIONAL SERIES

TECH INFO 233

inch			EDP NO.		
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	OVERALL LENGTH L_1	UNCOATED 60°	UNCOATED 82°	UNCOATED 90°
1/8	1/8	1-1/2	74049	74149	74249
3/16	3/16	2	74052	74152	74252
1/4	1/4	2	74055	74155	74255
3/8*	1/4	2-13/16	74058	74158	74258
1/2*	1/4	2-7/8	74061	74161	74261
5/8*	3/8	3	74064	74164	74264
3/4*	1/2	3	74067	74167	74267
1*	1/2	3-1/4	74070	74170	74270

*Steel Shank / Con mango de acero / Avec queue en acier
NOTE: D3 dimension varies based on angle. Contact SGS representative or consult Tool Wizard for dimension information.

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- HARDENED STEELS

TOLERANCES (inch)

1/8–1/4 DIAMETER
D_1 = +.0000/–.0005

3/8–1 DIAMETER
D_1 = +.003/–.000

Included Angle +1°/–1°

	Series 301 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/32	3/64	5/64	1/8	3/16	7/32
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	275	RPM	33616	22411	13446	8404	5603	4802
			(220-330)	Fr	0.0003	0.0005	0.0007	0.0012	0.0018	0.0021
				Feed (IPM)	10.1	11.2	9.4	10.1	10.1	10.1
		> 200 ≤ 300	150	RPM	18336	12224	7334	4584	3056	2619
			(120-180)	Fr	0.0003	0.0004	0.0007	0.0011	0.0016	0.0019
				Feed (IPM)	5.5	4.9	5.1	5.0	4.9	5.0
		> 300 ≤ 420	105	RPM	12835	8557	5134	3209	2139	1834
			(84-126)	Fz	0.0002	0.0003	0.0005	0.0007	0.0011	0.0013
				Feed (IPM)	2.6	2.6	2.6	2.2	2.4	2.4
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	230	RPM	28115	18743	11246	7029	4686	4016
			(184-276)	Fz	0.0003	0.0004	0.0006	0.0010	0.0015	0.0018
				Feed (IPM)	8.4	7.5	6.7	7.0	7.0	7.2
		> 275 ≤ 375	140	RPM	17114	11409	6845	4278	2852	2445
			(112-168)	Fr	0.0003	0.0004	0.0006	0.0010	0.0015	0.0018
				Feed (IPM)	5.1	4.6	4.1	4.3	4.3	4.4
		> 375 ≤ 450	90	RPM	11002	7334	4401	2750	1834	1572
			(72-108)	Fr	0.0002	0.0003	0.0004	0.0007	0.0010	0.0012
				Feed (IPM)	2.2	2.2	1.8	1.9	1.8	1.9
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	85	RPM	10390	6927	4156	2598	1732	1484
			(68-102)	Fr	0.0002	0.0003	0.0004	0.0007	0.0010	0.0012
				Feed (IPM)	2.1	2.1	1.7	1.8	1.7	1.8
		> 250 ≤ 330	50	RPM	6112	4075	2445	1528	1019	873
			(40-60)	Fr	0.0001	0.0002	0.0002	0.0004	0.0006	0.0007
				Feed (IPM)	0.6	0.8	0.5	0.6	0.6	0.6
		> 330 ≤ 450	40	RPM	4890	3260	1956	1222	815	699
			(32-48)	Fr	0.0001	0.0002	0.0002	0.0004	0.0006	0.0007
				Feed (IPM)	0.5	0.7	0.4	0.5	0.5	0.5
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	250	RPM	30560	20373	12224	7640	5093	4366
			(200-300)	Fr	0.0004	0.0005	0.0009	0.0014	0.0021	0.0025
				Feed (IPM)	12.2	10.2	11.0	10.7	10.7	10.9
		> 200 ≤ 330	185	RPM	22614	15076	9046	5654	3769	3231
			(148-222)	Fr	0.0003	0.0005	0.0009	0.0014	0.0021	0.0024
				Feed (IPM)	6.8	7.5	8.1	7.9	7.9	7.8
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	155	RPM	18947	12631	7579	4737	3158	2707
			(124-186)	Fr	0.0002	0.0003	0.0004	0.0006	0.0009	0.0011
				Feed (IPM)	3.8	3.8	3.0	2.8	2.8	3.0
		> 250 ≤ 330	110	RPM	13446	8964	5379	3362	2241	1921
			(88-132)	Fr	0.0002	0.0003	0.0004	0.0006	0.0009	0.0011
				Feed (IPM)	2.7	2.7	2.2	2.0	2.0	2.1

continued on next page

	Series 301 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/32	3/64	5/64	1/8	3/16	7/32
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	70	RPM	8557	5705	3423	2139	1426	1222
			(56-84)	Fr	0.0002	0.0003	0.0004	0.0006	0.0009	0.0011
				Feed (IPM)	1.7	1.7	1.4	1.3	1.3	1.3
		> 270 ≤ 370	50	RPM	6112	4075	2445	1528	1019	873
			(40-60)	Fr	0.0001	0.0002	0.0003	0.0004	0.0006	0.0007
				Feed (IPM)	0.6	0.8	0.7	0.6	0.6	0.6
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	25	RPM	3056	2037	1222	764	509	437
			(20-30)	Fr	0.0002	0.0003	0.0005	0.0007	0.0011	0.0013
				Feed (IPM)	0.6	0.6	0.6	0.5	0.6	0.6
		> 220 ≤ 330	20	RPM	2445	1630	978	611	407	349
			(16-24)	Fr	0.0001	0.0001	0.0002	0.0003	0.0005	0.0006
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2
		> 330 ≤ 420	15	RPM	1834	1222	733	458	306	262
			(12-18)	Fr	0.0001	0.0001	0.0001	0.0002	0.0003	0.0004
				Feed (IPM)	0.2	0.1	0.1	0.1	0.1	0.1
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	85	RPM	10390	6927	4156	2598	1732	1484
			(68-102)	Fr	0.0003	0.0004	0.0007	0.0011	0.0017	0.0020
				Feed (IPM)	3.1	2.8	2.9	2.9	2.9	3.0
		> 280 ≤ 350	65	RPM	7946	5297	3178	1986	1324	1135
			(52-78)	Fr	0.0001	0.0002	0.0004	0.0006	0.0009	0.0010
				Feed (IPM)	0.8	1.1	1.3	1.2	1.2	1.1
		> 350 ≤ 440	50	RPM	6112	4075	2445	1528	1019	873
			(40-60)	Fr	0.0002	0.0004	0.0008	0.0015	0.0025	0.0030
				Feed (IPM)	1.2	1.6	2.0	2.3	2.5	2.6
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	540	RPM	66010	44006	26404	16502	11002	9430
			(432-648)	Fr	0.0004	0.0007	0.0011	0.0018	0.0027	0.0031
				Feed (IPM)	26.4	30.8	29.0	29.7	29.7	29.2
		> 80	455	RPM	55619	37079	22248	13905	9270	7946
			(364-546)	Fr	0.0004	0.0007	0.0011	0.0018	0.0027	0.0031
				Feed (IPM)	22.2	26.0	24.5	25.0	25.0	24.6
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	230	RPM	28115	18743	11246	7029	4686	4016
			(184-276)	Fr	0.0002	0.0003	0.0005	0.0009	0.0013	0.0015
				Feed (IPM)	5.6	5.6	5.6	6.3	6.1	6.0
		> 140	175	RPM	21392	14261	8557	5348	3565	3056
			(140-210)	Fr	0.0002	0.0003	0.0005	0.0009	0.0013	0.0015
				Feed (IPM)	4.3	4.3	4.3	4.8	4.6	4.6

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 301M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 0.5	1	1.6	2.5	4	5
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	84	RPM	53318	26659	16662	10664	6665	5332
			(67-101)	Fr	0.005	0.011	0.014	0.024	0.038	0.048
				Feed (mm/min)	267	293	233	256	253	256
		> 200 ≤ 300	46	RPM	29082	14541	9088	5816	3635	2908
			(37-55)	Fr	0.005	0.009	0.014	0.022	0.034	0.043
				Feed (mm/min)	145	131	127	128	124	125
		> 300 ≤ 420	32	RPM	20358	10179	6362	4072	2545	2036
			(26-38)	Fz	0.003	0.006	0.010	0.014	0.023	0.030
				Feed (mm/min)	61	61	64	57	59	61
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	70	RPM	44593	22297	13935	8919	5574	4459
			(56-84)	Fz	0.005	0.009	0.012	0.020	0.032	0.041
				Feed (mm/min)	223	201	167	178	178	183
		> 275 ≤ 375	43	RPM	27144	13572	8482	5429	3393	2714
			(34-51)	Fr	0.005	0.009	0.012	0.020	0.032	0.041
				Feed (mm/min)	136	122	102	109	109	111
		> 375 ≤ 450	27	RPM	17449	8725	5453	3490	2181	1745
			(22-33)	Fr	0.003	0.006	0.008	0.014	0.021	0.027
				Feed (mm/min)	52	52	44	49	46	47
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	26	RPM	16480	8240	5150	3296	2060	1648
			(21-31)	Fr	0.003	0.006	0.008	0.014	0.021	0.027
				Feed (mm/min)	49	49	41	46	43	44
		> 250 ≤ 330	15	RPM	9694	4847	3029	1939	1212	969
			(12-18)	Fr	0.002	0.005	0.007	0.010	0.017	0.021
				Feed (mm/min)	19	24	21	19	21	20
		> 330 ≤ 450	12	RPM	7755	3878	2424	1551	969	776
			(10-15)	Fr	0.002	0.004	0.006	0.008	0.013	0.016
				Feed (mm/min)	16	16	15	12	13	12
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	76	RPM	48471	24235	15147	9694	6059	4847
			(61-91)	Fr	0.007	0.011	0.018	0.028	0.045	0.057
				Feed (mm/min)	339	267	273	271	273	276
		> 200 ≤ 330	56	RPM	35868	17934	11209	7174	4484	3587
			(45-68)	Fr	0.007	0.011	0.018	0.028	0.045	0.057
				Feed (mm/min)	251	197	202	201	202	204
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	47	RPM	30052	15026	9391	6010	3756	3005
			(38-57)	Fr	0.003	0.004	0.008	0.012	0.019	0.025
				Feed (mm/min)	90	60	75	72	71	75
		> 250 ≤ 330	34	RPM	21327	10664	6665	4265	2666	2133
			(27-40)	Fr	0.002	0.004	0.008	0.012	0.019	0.023
				Feed (mm/min)	43	43	53	51	51	49

continued on next page

	Series 301M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 0.5	1	1.6	2.5	4	5
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270 ≤ 370	21	RPM	13572	6786	4241	2714	1696	1357
			(17-26)	Fr	0.002	0.004	0.008	0.012	0.019	0.023
				Feed (mm/min)	27	27	34	33	32	31
		> 270 ≤ 370	15	RPM	9694	4847	3029	1939	1212	969
			(12-18)	Fr	0.002	0.004	0.006	0.008	0.013	0.016
				Feed (mm/min)	19	19	18	16	16	16
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	8	RPM	4847	2424	1515	969	606	485
			(6-9)	Fr	0.003	0.006	0.010	0.014	0.023	0.030
				Feed (mm/min)	15	15	15	14	14	15
		> 220 ≤ 330	6	RPM	3878	1939	1212	776	485	388
			(5-7)	Fr	0.002	0.003	0.004	0.006	0.011	0.014
				Feed (mm/min)	8	6	5	5	5	5
		> 330 ≤ 420	5	RPM	2908	1454	909	582	364	291
			(4-5)	Fr	0.002	0.002	0.002	0.004	0.006	0.009
				Feed (mm/min)	6	3	2	2	2	3
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	26	RPM	16480	8240	5150	3296	2060	1648
			(21-31)	Fr	0.005	0.009	0.014	0.022	0.036	0.046
				Feed (mm/min)	82	74	72	73	74	76
		> 280 ≤ 350	20	RPM	12602	6301	3938	2520	1575	1260
			(16-24)	Fr	0.002	0.004	0.008	0.012	0.019	0.023
				Feed (mm/min)	25	25	32	30	30	29
		> 350 ≤ 440	15	RPM	9694	4847	3029	1939	1212	969
			(12-18)	Fr	0.002	0.004	0.004	0.008	0.013	0.016
				Feed (mm/min)	19	19	12	16	16	16
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	165	RPM	104697	52348	32718	20939	13087	10470
			(132-198)	Fr	0.007	0.015	0.023	0.036	0.057	0.071
				Feed (mm/min)	733	785	753	754	746	743
		> 80	139	RPM	88217	44108	27568	17643	11027	8822
			(111-166)	Fr	0.007	0.015	0.023	0.036	0.057	0.071
				Feed (mm/min)	618	662	634	635	629	626
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	70	RPM	44593	22297	13935	8919	5574	4459
			(56-84)	Fr	0.003	0.006	0.010	0.018	0.028	0.034
				Feed (mm/min)	134	134	139	161	156	152
		> 140	53	RPM	33930	16965	10603	6786	4241	3393
			(43-64)	Fr	0.003	0.006	0.010	0.018	0.028	0.034
				Feed (mm/min)	102	102	106	122	119	115

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 601 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	125	RPM	3820	2547	1910	1273	955	637	478
			(100-150)	Fr	0.0005	0.0008	0.0011	0.0016	0.0021	0.0032	0.0042
				Feed (IPM)	1.9	2.0	2.1	2.0	2.0	2.0	2.0
		> 200 ≤ 300	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0005	0.0007	0.0010	0.0014	0.0019	0.0029	0.0038
				Feed (IPM)	0.9	0.9	0.9	0.9	0.9	0.9	0.9
		> 300 ≤ 420	45	RPM	1375	917	688	458	344	229	172
			(36-54)	Fz	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.4	0.5	0.4	0.4	0.4	0.4	0.4
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fz	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	1.5	1.4	1.3	1.4	1.3	1.3	1.3
		> 275 ≤ 375	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.9	0.9	0.8	0.9	0.8	0.8	0.8
		> 375 ≤ 450	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0003	0.0004	0.0006	0.0008	0.0011	0.0017	0.0022
				Feed (IPM)	0.3	0.3	0.3	0.3	0.3	0.3	0.3
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0003	0.0004	0.0006	0.0008	0.0011	0.0017	0.0022
				Feed (IPM)	0.3	0.3	0.3	0.3	0.3	0.3	0.3
		> 250 ≤ 330	25	RPM	764	509	382	255	191	127	96
			(20-30)	Fr	0.0002	0.0002	0.0003	0.0005	0.0006	0.0009	0.0012
				Feed (IPM)	0.2	0.1	0.1	0.1	0.1	0.1	0.1
		> 330 ≤ 450	20	RPM	611	407	306	204	153	102	76
			(16-24)	Fr	0.0002	0.0002	0.0003	0.0005	0.0006	0.0009	0.0012
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	105	RPM	3209	2139	1604	1070	802	535	401
			(84-126)	Fr	0.0006	0.0009	0.0012	0.0018	0.0024	0.0036	0.0048
				Feed (IPM)	1.9	1.9	1.9	1.9	1.9	1.9	1.9
		> 200 ≤ 330	75	RPM	2292	1528	1146	764	573	382	287
			(60-90)	Fr	0.0006	0.0009	0.0012	0.0018	0.0024	0.0036	0.0048
				Feed (IPM)	1.4	1.4	1.4	1.4	1.4	1.4	1.4
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	53	RPM	1620	1080	810	540	405	270	202
			(42-64)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.5	0.5	0.5	0.5	0.5	0.5	0.5
		> 250 ≤ 330	46	RPM	1406	937	703	469	351	234	176
			(37-55)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.3	0.3	0.4	0.3	0.3	0.3	0.3

continued on next page

	Series 601 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	> 270	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0004	0.0005	0.0007	0.0011	0.0014	0.0021	0.0028
				Feed (IPM)	0.3	0.3	0.3	0.3	0.3	0.3	0.3
		> 270 ≤ 370	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0002	0.0002	0.0003	0.0005	0.0006	0.0009	0.0012
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	18	RPM	550	367	275	183	138	92	69
			(14-22)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
		> 220 ≤ 330	14	RPM	428	285	214	143	107	71	53
			(11-17)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
		> 330 ≤ 420	12	RPM	367	244	183	122	92	61	46
			(10-14)	Fr	0.0002	0.0003	0.0004	0.0006	0.0008	0.0012	0.0016
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	36	RPM	1100	733	550	367	275	183	138
			(29-43)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.6	0.5	0.5	0.5	0.5	0.5	0.5
		> 280 ≤ 350	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0004	0.0005	0.0007	0.0011	0.0014	0.0021	0.0028
				Feed (IPM)	0.3	0.3	0.3	0.3	0.3	0.3	0.3
		> 350 ≤ 440	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0002	0.0002	0.0003	0.0005	0.0006	0.0009	0.0012
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	225	RPM	6876	4584	3438	2292	1719	1146	860
			(180-270)	Fr	0.0008	0.0011	0.0015	0.0023	0.0030	0.0045	0.0060
				Feed (IPM)	5.5	5.0	5.2	5.3	5.2	5.2	5.2
		> 80	190	RPM	5806	3871	2903	1935	1452	968	726
			(152-228)	Fr	0.0008	0.0011	0.0015	0.0023	0.0030	0.0045	0.0060
				Feed (IPM)	4.6	4.3	4.4	4.5	4.4	4.4	4.4
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fr	0.0004	0.0006	0.0008	0.0011	0.0015	0.0023	0.0030
				Feed (IPM)	1.2	1.2	1.2	1.1	1.1	1.1	1.1
		> 140	80	RPM	2445	1630	1222	815	611	407	306
			(64-96)	Fr	0.0004	0.0006	0.0008	0.0011	0.0015	0.0023	0.0030
				Feed (IPM)	1.0	1.0	1.0	0.9	0.9	0.9	0.9

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 603 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	125	RPM	3820	2547	1910	1273	955	637	478
			(100-150)	Fr	0.0008	0.0012	0.0016	0.0024	0.0032	0.0047	0.0063
				Feed (IPM)	3.1	3.1	3.1	3.1	3.1	3.0	3.0
		> 200 ≤ 300	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0007	0.0011	0.0014	0.0021	0.0029	0.0043	0.0057
				Feed (IPM)	1.3	1.3	1.3	1.3	1.3	1.3	1.3
		> 300 ≤ 420	45	RPM	1375	917	688	458	344	229	172
			(36-54)	Fz	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.7	0.6	0.6	0.6	0.6	0.6	0.6
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fz	0.0007	0.0010	0.0014	0.0020	0.0027	0.0041	0.0054
				Feed (IPM)	2.0	1.9	2.0	1.9	2.0	2.0	2.0
		> 275 ≤ 375	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0007	0.0010	0.0014	0.0020	0.0027	0.0041	0.0054
				Feed (IPM)	1.3	1.2	1.3	1.2	1.2	1.3	1.2
		> 375 ≤ 450	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0004	0.0006	0.0008	0.0012	0.0017	0.0025	0.0033
				Feed (IPM)	0.4	0.4	0.4	0.4	0.5	0.4	0.4
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0004	0.0006	0.0008	0.0012	0.0017	0.0025	0.0033
				Feed (IPM)	0.4	0.4	0.4	0.4	0.5	0.4	0.4
		> 250 ≤ 330	25	RPM	764	509	382	255	191	127	96
			(20-30)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
		> 330 ≤ 450	20	RPM	611	407	306	204	153	102	76
			(16-24)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.1	0.1	0.2	0.1	0.1	0.1	0.1
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	105	RPM	3209	2139	1604	1070	802	535	401
			(84-126)	Fr	0.0009	0.0014	0.0018	0.0027	0.0036	0.0054	0.0072
				Feed (IPM)	2.9	3.0	2.9	2.9	2.9	2.9	2.9
		> 200 ≤ 330	75	RPM	2292	1528	1146	764	573	382	287
			(60-90)	Fr	0.0009	0.0014	0.0018	0.0027	0.0036	0.0054	0.0072
				Feed (IPM)	2.1	2.1	2.1	2.1	2.1	2.1	2.1
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 250	53	RPM	1620	1080	810	540	405	270	202
			(42-64)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.8	0.8	0.7	0.8	0.7	0.7	0.7
		> 250 ≤ 330	46	RPM	1406	937	703	469	351	234	176
			(37-55)	Fr	0.0003	0.0005	0.0007	0.0010	0.0014	0.0020	0.0027
				Feed (IPM)	0.4	0.5	0.5	0.5	0.5	0.5	0.5

continued on next page

	Series 603 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	≤ 270	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0005	0.0008	0.0011	0.0016	0.0021	0.0032	0.0042
				Feed (IPM)	0.4	0.5	0.5	0.5	0.4	0.5	0.4
		> 270 ≤ 370	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.1	0.1	0.2	0.1	0.1	0.1	0.1
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	18	RPM	550	367	275	183	138	92	69
			(14-22)	Fr	0.0003	0.0005	0.0007	0.0010	0.0014	0.0020	0.0027
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
		> 220 ≤ 330	14	RPM	428	285	214	143	107	71	53
			(11-17)	Fr	0.0003	0.0005	0.0007	0.0010	0.0014	0.0020	0.0027
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
		> 330 ≤ 420	12	RPM	367	244	183	122	92	61	46
			(10-14)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	36	RPM	1100	733	550	367	275	183	138
			(29-43)	Fr	0.0007	0.0010	0.0014	0.0020	0.0027	0.0041	0.0054
				Feed (IPM)	0.8	0.7	0.8	0.7	0.7	0.8	0.7
		> 280 ≤ 350	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0005	0.0008	0.0011	0.0016	0.0021	0.0032	0.0042
				Feed (IPM)	0.4	0.5	0.5	0.5	0.4	0.5	0.4
		> 350 ≤ 440	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0002	0.0003	0.0005	0.0007	0.0009	0.0014	0.0018
				Feed (IPM)	0.1	0.1	0.2	0.1	0.1	0.1	0.1
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	225	RPM	6876	4584	3438	2292	1719	1146	860
			(180-270)	Fr	0.0011	0.0017	0.0023	0.0034	0.0045	0.0068	0.0090
				Feed (IPM)	7.6	7.8	7.9	7.8	7.7	7.8	7.7
		> 80	190	RPM	5806	3871	2903	1935	1452	968	726
			(152-228)	Fr	0.0011	0.0017	0.0023	0.0034	0.0045	0.0068	0.0090
				Feed (IPM)	6.4	6.6	6.7	6.6	6.5	6.6	6.5
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fr	0.0006	0.0008	0.0011	0.0017	0.0023	0.0034	0.0045
				Feed (IPM)	1.7	1.5	1.6	1.6	1.7	1.6	1.6
		> 140	80	RPM	2445	1630	1222	815	611	407	306
			(64-96)	Fr	0.0006	0.0008	0.0011	0.0017	0.0023	0.0034	0.0045
				Feed (IPM)	1.5	1.3	1.3	1.4	1.4	1.4	1.4

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 606 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	125	RPM	3820	2547	1910	1273	955	637	478
			(100-150)	Fr	0.0011	0.0016	0.0021	0.0032	0.0042	0.0063	0.0084
				Feed (IPM)	4.2	4.1	4.0	4.1	4.0	4.0	4.0
		> 200 ≤ 300	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0010	0.0014	0.0019	0.0029	0.0038	0.0057	0.0076
				Feed (IPM)	1.8	1.7	1.7	1.8	1.7	1.7	1.7
		> 300 ≤ 420	45	RPM	1375	917	688	458	344	229	172
			(36-54)	Fz	0.0006	0.0009	0.0012	0.0018	0.0024	0.0036	0.0048
				Feed (IPM)	0.8	0.8	0.8	0.8	0.8	0.8	0.8
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fz	0.0009	0.0014	0.0018	0.0027	0.0036	0.0054	0.0072
				Feed (IPM)	2.6	2.7	2.6	2.6	2.6	2.6	2.6
		> 275 ≤ 375	60	RPM	1834	1222	917	611	458	306	229
			(48-72)	Fr	0.0009	0.0014	0.0018	0.0027	0.0036	0.0054	0.0072
				Feed (IPM)	1.7	1.7	1.7	1.7	1.7	1.7	1.7
		> 375 ≤ 450	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0006	0.0008	0.0011	0.0017	0.0022	0.0033	0.0044
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	35	RPM	1070	713	535	357	267	178	134
			(28-42)	Fr	0.0006	0.0008	0.0011	0.0017	0.0022	0.0033	0.0044
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
		> 250 ≤ 330	25	RPM	764	509	382	255	191	127	96
			(20-30)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.2	0.3	0.2	0.2	0.2	0.2	0.2
		> 330 ≤ 450	20	RPM	611	407	306	204	153	102	76
			(16-24)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	105	RPM	3209	2139	1604	1070	802	535	401
			(84-126)	Fr	0.0012	0.0018	0.0024	0.0036	0.0048	0.0072	0.0096
				Feed (IPM)	3.9	3.9	3.9	3.9	3.9	3.9	3.9
		> 200 ≤ 330	75	RPM	2292	1528	1146	764	573	382	287
			(60-90)	Fr	0.0012	0.0018	0.0024	0.0036	0.0048	0.0072	0.0096
				Feed (IPM)	2.8	2.8	2.8	2.8	2.8	2.8	2.8
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 250	53	RPM	1620	1080	810	540	405	270	202
			(42-64)	Fr	0.0006	0.0009	0.0012	0.0018	0.0024	0.0036	0.0048
				Feed (IPM)	1.0	1.0	1.0	1.0	1.0	1.0	1.0
		> 250 ≤ 330	46	RPM	1406	937	703	469	351	234	176
			(37-55)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.7	0.7	0.6	0.7	0.6	0.6	0.6


continued on next page

	Series 606 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/8	3/16	1/4	3/8	1/2	3/4	1
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	≤ 270	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0007	0.0011	0.0014	0.0021	0.0028	0.0042	0.0056
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
		> 270 ≤ 370	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	18	RPM	550	367	275	183	138	92	69
			(14-22)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.3	0.3	0.2	0.3	0.2	0.2	0.2
		> 220 ≤ 330	14	RPM	428	285	214	143	107	71	53
			(11-17)	Fr	0.0005	0.0007	0.0009	0.0014	0.0018	0.0027	0.0036
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
		> 330 ≤ 420	12	RPM	367	244	183	122	92	61	46
			(10-14)	Fr	0.0004	0.0006	0.0008	0.0012	0.0016	0.0024	0.0032
				Feed (IPM)	0.1	0.1	0.1	0.1	0.1	0.1	0.1
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	36	RPM	1100	733	550	367	275	183	138
			(29-43)	Fr	0.0009	0.0014	0.0018	0.0027	0.0036	0.0054	0.0072
				Feed (IPM)	1.0	1.0	1.0	1.0	1.0	1.0	1.0
		> 280 ≤ 350	28	RPM	856	570	428	285	214	143	107
			(22-34)	Fr	0.0007	0.0011	0.0014	0.0021	0.0028	0.0042	0.0056
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
		> 350 ≤ 440	21	RPM	642	428	321	214	160	107	80
			(17-25)	Fr	0.0003	0.0005	0.0006	0.0009	0.0012	0.0018	0.0024
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	225	RPM	6876	4584	3438	2292	1719	1146	860
			(180-270)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0090	0.0120
				Feed (IPM)	10.3	10.5	10.3	10.3	10.3	10.3	10.3
		> 80	190	RPM	5806	3871	2903	1935	1452	968	726
			(152-228)	Fr	0.0015	0.0023	0.0030	0.0045	0.0060	0.0090	0.0120
				Feed (IPM)	8.7	8.9	8.7	8.7	8.7	8.7	8.7
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	95	RPM	2903	1935	1452	968	726	484	363
			(76-114)	Fr	0.0008	0.0011	0.0015	0.0023	0.0030	0.0045	0.0060
				Feed (IPM)	2.3	2.1	2.2	2.2	2.2	2.2	2.2
		> 140	80	RPM	2445	1630	1222	815	611	407	306
			(64-96)	Fr	0.0008	0.0011	0.0015	0.0023	0.0030	0.0045	0.0060
				Feed (IPM)	2.0	1.8	1.8	1.9	1.8	1.8	1.8

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)







TOLERANCES (mm)

1–6 DIAMETER
D_1 = +0,008/–0,000

>6–10 DIAMETER
D_1 = +0,011/–0,00

201M
METRIC SERIES


TECH INFO 240

mm					EDP NO.
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	MAXIMUM REAM LENGTH L_2	OVERALL LENGTH L_1	NO. OF FLUTES	UNCOATED
1,0	1,0	6,0	32,0	4	81001
1,5	1,5	9,5	38,0	4	81003
2,0	2,0	12,7	44,0	4	81005
2,5	2,5	12,7	50,0	4	81007
3,0	3,0	16,0	57,0	4	81009
3,5	3,5	19, 0	63,0	4	81011
4,0	4,0	19,0	63,0	4	81013
4,5	4,5	22,0	70,0	4	81015
5,0	5,0	25,0	75,0	4	81017
5,5	5,5	25,0	75,0	4	81019
6,0	6,0	25,0	75,0	4	81021
7,0	7,0	28,0	82,0	6	81023
8,0	8,0	28,0	82,0	6	81025
9,0	9,0	31,0	89,0	6	81027
10,0	10,0	31,0	89,0	6	81029

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- HARDENED STEELS







200
FRACTIONAL SERIES

TECH INFO 238

TOLERANCES (inch)

D_1 = +.0002/–.0000


D_2 = +.0002/–.0000

- STEELS
- STAINLESS STEELS
- CAST IRON
- HIGH TEMP ALLOYS
- TITANIUM
- NON-FERROUS
- PLASTICS/COMPOSITES
- HARDENED STEELS

inch					EDP NO.
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	MAXIMUM REAM LENGTH L_2	OVERALL LENGTH L_1	NO. OF FLUTES	UNCOATED
3/64	3/64	3/4	1-1/2	4	70003
1/16	1/16	3/4	1-1/2	4	70004
5/64	5/64	1	2	4	70005
3/32	3/32	1-1/4	2-1/4	4	70006
7/64	7/64	1-1/4	2-1/4	4	70007
1/8	1/8	1-1/4	2-1/4	4	70008
9/64	9/64	1-1/2	2-1/2	4	70009
5/32	5/32	1-1/2	2-1/2	4	70010
11/64	11/64	1-3/4	2-3/4	4	70011
3/16	3/16	1-3/4	2-3/4	4	70012
13/64	13/64	2	3	4	70013
7/32	7/32	2	3	4	70014
15/64	15/64	2	3	4	70015
1/4	1/4	2	3	4	70016
17/64	17/64	2-1/4	3-1/4	6	70017
9/32	9/32	2-1/4	3-1/4	6	70018
19/64	19/64	2-1/4	3-1/4	6	70019
5/16	5/16	2-1/4	3-1/4	6	70020
21/64	21/64	2-3/8	3-1/2	6	70021
11/32	11/32	2-3/8	3-1/2	6	70022
23/64	23/64	2-3/8	3-1/2	6	70023
3/8	3/8	2-3/8	3-1/2	6	70024
25/64	25/64	2-7/8	4	6	70025
13/32	13/32	2-7/8	4	6	70026
27/64	27/64	2-7/8	4	6	70027
7/16	7/16	2-7/8	4	6	70028
29/64	29/64	2-7/8	4	6	70029
15/32	15/32	2-7/8	4	6	70030
31/64	31/64	2-7/8	4	6	70031
1/2	1/2	2-7/8	4	6	70032







TOLERANCES (inch)

D_1 = +.0002/–.0000
D_2 = +.0002/–.0000

200
FRACTIONAL SERIES

TECH INFO 238

inch				
CUTTING DIAMETER D_1	SHANK DIAMETER D_2	MAXIMUM REAM LENGTH L_2	OVERALL LENGTH L_1	NO. OF FLUTES
.0470 – .0625	1/16	3/4	1-1/2	4
.0626 – .0781	5/64	1	2	4
.0782 – .0938	3/32	1-1/4	2-1/4	4
.0939 – .1094	7/64	1-1/4	2-1/4	4
.1095 – .1250	1/8	1-1/4	2-1/4	4
.1251 – .1406	9/64	1-1/2	2-1/2	4
.1407 – .1563	5/32	1-1/2	2-1/2	4
.1564 – .1719	11/64	1-3/4	2-3/4	4
.1720 – .1875	3/16	1-3/4	2-3/4	4
.1876 – .2031	13/64	2	3	4
.2032 – .2188	7/32	2	3	4
.2189 – .2344	15/64	2	3	4
.2345 – .2500	1/4	2	3	4
.2501 – .2656	17/64	2-1/4	3-1/4	6
.2657 – .2813	9/32	2-1/4	3-1/4	6
.2814 – .2969	19/64	2-1/4	3-1/4	6
.2970 – .3125	5/16	2-1/4	3-1/4	6
.3126 – .3281	21/64	2-3/8	3-1/2	6
.3282 – .3438	11/32	2-3/8	3-1/2	6
.3439 – .3594	23/64	2-3/8	3-1/2	6
.3595 – .3750	3/8	2-3/8	3-1/2	6
.3751 – .3906	25/64	2-7/8	4	6
.3907 – .4063	13/32	2-7/8	4	6
.4064 – .4219	27/64	2-7/8	4	6
.4220 – .4375	7/16	2-7/8	4	6
.4376 – .4531	29/64	2-7/8	4	6
.4532 – .4688	15/32	2-7/8	4	6
.4689 – .4844	31/64	2-7/8	4	6
.4845 – .5000	1/2	2-7/8	4	6

	Series 200 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/16	1/8	3/16	1/4	1/3	3/8	1/2
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	150	RPM	9168	4584	3056	2292	1834	1528	1146
			(120-180)	Fr	0.0018	0.0035	0.0053	0.0071	0.0088	0.0106	0.0141
				Feed (IPM)	16.5	16.0	16.2	16.3	16.1	16.2	16.2
		> 200 ≤ 300	75	RPM	4584	2292	1528	1146	917	764	573
			(60-90)	Fr	0.0016	0.0031	0.0047	0.0062	0.0078	0.0093	0.0124
				Feed (IPM)	7.3	7.1	7.2	7.1	7.2	7.1	7.1
		> 300 ≤ 420	55	RPM	3362	1681	1121	840	672	560	420
			(44-66)	Fz	0.0009	0.0019	0.0028	0.0037	0.0046	0.0056	0.0074
				Feed (IPM)	3.0	3.2	3.1	3.1	3.1	3.1	3.1
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 275	115	RPM	7029	3514	2343	1757	1406	1171	879
			(92-138)	Fz	0.0015	0.0030	0.0045	0.0060	0.0075	0.0090	0.0120
				Feed (IPM)	10.5	10.5	10.5	10.5	10.5	10.5	10.5
		> 275 ≤ 375	70	RPM	4278	2139	1426	1070	856	713	535
			(56-84)	Fr	0.0015	0.0030	0.0045	0.0060	0.0075	0.0090	0.0120
				Feed (IPM)	6.4	6.4	6.4	6.4	6.4	6.4	6.4
		> 375 ≤ 450	45	RPM	2750	1375	917	688	550	458	344
			(36-54)	Fr	0.0009	0.0019	0.0028	0.0037	0.0046	0.0056	0.0074
				Feed (IPM)	2.5	2.6	2.6	2.5	2.5	2.6	2.5
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	40	RPM	2445	1222	815	611	489	407	306
			(32-48)	Fr	0.0010	0.0020	0.0029	0.0039	0.0049	0.0059	0.0078
				Feed (IPM)	2.4	2.4	2.4	2.4	2.4	2.4	2.4
		> 250 ≤ 330	25	RPM	1528	764	509	382	306	255	191
			(20-30)	Fr	0.0006	0.0013	0.0019	0.0025	0.0031	0.0038	0.0050
				Feed (IPM)	0.9	1.0	1.0	1.0	0.9	1.0	1.0
		> 330 ≤ 450	20	RPM	1222	611	407	306	244	204	153
			(16-24)	Fr	0.0004	0.0008	0.0012	0.0016	0.0019	0.0023	0.0031
				Feed (IPM)	0.5	0.5	0.5	0.5	0.5	0.5	0.5
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	125	RPM	7640	3820	2547	1910	1528	1273	955
			(100-150)	Fr	0.0020	0.0040	0.0060	0.0081	0.0101	0.0121	0.0161
				Feed (IPM)	15.3	15.3	15.3	15.5	15.4	15.4	15.4
		> 200 ≤ 330	95	RPM	5806	2903	1935	1452	1161	968	726
			(76-114)	Fr	0.0020	0.0040	0.0060	0.0081	0.0101	0.0121	0.0161
				Feed (IPM)	11.6	11.6	11.6	11.8	11.7	11.7	11.7
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	≤ 250	75	RPM	4584	2292	1528	1146	917	764	573
			(60-90)	Fr	0.0010	0.0020	0.0029	0.0039	0.0049	0.0059	0.0078
				Feed (IPM)	4.6	4.6	4.4	4.5	4.5	4.5	4.5
		> 250 ≤ 330	55	RPM	3362	1681	1121	840	672	560	420
			(44-66)	Fr	0.0008	0.0015	0.0023	0.0030	0.0038	0.0045	0.0060
				Feed (IPM)	2.7	2.5	2.6	2.5	2.6	2.5	2.5

continued on next page

	Series 200 Fractional	Hardness BRINELL	Vc (SFM)		Diameter (D_1) (inch) 1/16	1/8	3/16	1/4	1/3	3/8	1/2
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	≤ 270	35	RPM	2139	1070	713	535	428	357	267
			(28-42)	Fr	0.0010	0.0020	0.0029	0.0039	0.0049	0.0059	0.0078
				Feed (IPM)	2.1	2.1	2.1	2.1	2.1	2.1	2.1
		> 270 ≤ 370	25	RPM	1528	764	509	382	306	255	191
			(20-30)	Fr	0.0006	0.0013	0.0019	0.0025	0.0031	0.0038	0.0050
				Feed (IPM)	0.9	1.0	1.0	1.0	0.9	1.0	1.0
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	20	RPM	1222	611	407	306	244	204	153
			(16-24)	Fr	0.0008	0.0015	0.0023	0.0030	0.0038	0.0045	0.0060
				Feed (IPM)	1.0	0.9	0.9	0.9	0.9	0.9	0.9
		> 220 ≤ 330	15	RPM	917	458	306	229	183	153	115
			(12-18)	Fr	0.0006	0.0013	0.0019	0.0025	0.0031	0.0038	0.0050
				Feed (IPM)	0.6	0.6	0.6	0.6	0.6	0.6	0.6
		> 330 ≤ 420	10	RPM	611	306	204	153	122	102	76
			(8-12)	Fr	0.0004	0.0007	0.0011	0.0015	0.0018	0.0022	0.0029
				Feed (IPM)	0.2	0.2	0.2	0.2	0.2	0.2	0.2
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	45	RPM	2750	1375	917	688	550	458	344
			(36-54)	Fr	0.0015	0.0030	0.0045	0.0060	0.0075	0.0090	0.0120
				Feed (IPM)	4.1	4.1	4.1	4.1	4.1	4.1	4.1
		> 280 ≤ 350	35	RPM	2139	1070	713	535	428	357	267
			(28-42)	Fr	0.0010	0.0020	0.0029	0.0039	0.0049	0.0059	0.0078
				Feed (IPM)	2.1	2.1	2.1	2.1	2.1	2.1	2.1
		> 350 ≤ 440	25	RPM	1528	764	509	382	306	255	191
			(20-30)	Fr	0.0006	0.0013	0.0019	0.0025	0.0031	0.0038	0.0050
				Feed (IPM)	0.9	1.0	1.0	1.0	0.9	1.0	1.0
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	270	RPM	16502	8251	5501	4126	3300	2750	2063
			(216-324)	Fr	0.0025	0.0050	0.0075	0.0100	0.0125	0.0150	0.0200
				Feed (IPM)	41.3	41.3	41.3	41.3	41.3	41.3	41.3
		> 80	230	RPM	14058	7029	4686	3514	2812	2343	1757
			(184-276)	Fr	0.0025	0.0050	0.0075	0.0100	0.0125	0.0150	0.0200
				Feed (IPM)	35.1	35.1	35.1	35.1	35.1	35.1	35.1
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	115	RPM	7029	3514	2343	1757	1406	1171	879
			(92-138)	Fr	0.0013	0.0026	0.0038	0.0051	0.0064	0.0077	0.0102
				Feed (IPM)	9.1	9.1	8.9	9.0	9.0	9.0	9.0
		> 140	95	RPM	5806	2903	1935	1452	1161	968	726
			(76-114)	Fr	0.0013	0.0026	0.0038	0.0051	0.0064	0.0077	0.0102
				Feed (IPM)	7.5	7.5	7.4	7.4	7.4	7.5	7.4

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
increase speed and feed rates shown by 30 percent when using coated reamers
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

	Series 201M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 1	2	3	4	6	8	10
P	CARBON STEELS 1018, 1040, 1080, 1090, 10L50, 1140, 1212, 12L15, 1525, 1536	≤ 200	46	RPM	14541	7271	4847	3635	2424	1818	1454
			(37-55)	Fr	0.028	0.056	0.085	0.113	0.169	0.226	0.282
				Feed (mm/min)	407	407	412	411	410	411	410
		> 200 ≤ 300	23	RPM	7271	3635	2424	1818	1212	909	727
			(18-27)	Fr	0.025	0.050	0.074	0.099	0.149	0.198	0.248
				Feed (mm/min)	182	182	179	180	181	180	180
		> 300 ≤ 420	17	RPM	5332	2666	1777	1333	889	666	533
			(13-20)	Fz	0.015	0.030	0.044	0.059	0.089	0.118	0.148
				Feed (mm/min)	80	80	78	79	79	79	79
P	ALLOY STEELS 4140, 4150, 4320, 5120, 5150, 8630, 86L20, 50100	≤ 270	35	RPM	11148	5574	3716	2787	1858	1394	1115
			(28-42)	Fz	0.024	0.048	0.072	0.096	0.144	0.192	0.240
				Feed (mm/min)	268	268	268	268	268	268	268
		> 275 ≤ 375	21	RPM	6786	3393	2262	1696	1131	848	679
			(17-26)	Fr	0.024	0.048	0.072	0.096	0.144	0.192	0.240
				Feed (mm/min)	163	163	163	163	163	163	163
		> 375 ≤ 450	14	RPM	4362	2181	1454	1091	727	545	436
			(11-16)	Fr	0.015	0.030	0.044	0.059	0.089	0.118	0.148
				Feed (mm/min)	65	65	64	64	65	64	65
P	TOOL STEELS A2, D2, H13, L2, M2, P20, S7, T15, W2	≤ 250	12	RPM	3878	1939	1293	969	646	485	388
			(10-15)	Fr	0.016	0.031	0.047	0.062	0.094	0.125	0.156
				Feed (mm/min)	62	60	61	60	61	61	60
		> 250 ≤ 330	8	RPM	2424	1212	808	606	404	303	242
			(6-9)	Fr	0.010	0.020	0.030	0.040	0.060	0.080	0.100
				Feed (mm/min)	24	24	24	24	24	24	24
		> 330 ≤ 450	6	RPM	1939	969	646	485	323	242	194
			(5-7)	Fr	0.006	0.012	0.019	0.025	0.037	0.050	0.062
				Feed (mm/min)	12	12	12	12	12	12	12
K	CAST IRONS Gray, Malleable, Ductile	≤ 200	38	RPM	12118	6059	4039	3029	2020	1515	1212
			(30-46)	Fr	0.032	0.064	0.097	0.129	0.193	0.258	0.322
				Feed (mm/min)	388	388	392	391	390	391	390
		> 200 ≤ 330	29	RPM	9209	4605	3070	2302	1535	1151	921
			(23-35)	Fr	0.032	0.064	0.097	0.129	0.193	0.258	0.322
				Feed (mm/min)	295	295	298	297	296	297	297
M	STAINLESS STEELS (FREE MACHINING) 303, 416, 420F, 430F 440F	< 250	23	RPM	7271	3635	2424	1818	1212	909	727
			(18-27)	Fr	0.015	0.030	0.044	0.059	0.089	0.118	0.148
				Feed (mm/min)	109	109	107	107	108	107	108
		> 250 ≤ 330	17	RPM	5332	2666	1777	1333	889	666	533
			(13-20)	Fr	0.012	0.024	0.036	0.048	0.072	0.096	0.120
				Feed (mm/min)	64	64	64	64	64	64	64

continued on next page

	Series 201M Metric	Hardness BRINELL	Vc (m/min)		Diameter (D_1) (mm) 1	2	3	4	6	8	10
M	STAINLESS STEELS (DIFFICULT) 304, 316, 321, 13-8 PH, 15-5PH, 17-4 PH, Custom 450	≤ 270	11	RPM	3393	1696	1131	848	565	424	339
			(9-13)	Fr	0.015	0.030	0.044	0.059	0.089	0.118	0.148
				Feed (mm/min)	51	51	50	50	50	50	50
		> 270 ≤ 370	8	RPM	2424	1212	808	606	404	303	242
			(6-9)	Fr	0.010	0.020	0.030	0.040	0.060	0.080	0.100
				Feed (mm/min)	24	24	24	24	24	24	24
S	SUPER ALLOYS (NICKEL, COBALT, IRON BASE) Inconel 601, 617, 625, Incoly 800, Monel 400, Rene, Waspaloy	≤ 220	6	RPM	1939	969	646	485	323	242	194
			(5-7)	Fr	0.012	0.024	0.036	0.048	0.072	0.096	0.120
				Feed (mm/min)	23	23	23	23	23	23	23
		> 220 ≤ 330	5	RPM	1454	727	485	364	242	182	145
			(4-5)	Fr	0.010	0.020	0.030	0.040	0.060	0.080	0.100
				Feed (mm/min)	15	15	15	15	15	15	15
		> 330 ≤ 420	3	RPM	969	485	323	242	162	121	97
			(2-4)	Fr	0.006	0.012	0.019	0.025	0.037	0.050	0.062
				Feed (mm/min)	6	6	6	6	6	6	6
S	TITANIUM ALLOYS Pure Ttanium, Ti6Al4V, Ti6Al2Sn4Zr2Mo, Ti4Al4Mo2Sn0.5Si, Ti-6Al4V	≤ 280	14	RPM	4362	2181	1454	1091	727	545	436
			(11-16)	Fr	0.024	0.048	0.072	0.096	0.144	0.192	0.240
				Feed (mm/min)	105	105	105	105	105	105	105
		> 280 ≤ 350	11	RPM	3393	1696	1131	848	565	424	339
			(9-13)	Fr	0.015	0.030	0.044	0.059	0.089	0.118	0.148
				Feed (mm/min)	51	51	50	50	50	50	50
		> 350 ≤ 440	8	RPM	2424	1212	808	606	404	303	242
			(6-9)	Fr	0.010	0.020	0.030	0.040	0.060	0.080	0.100
				Feed (mm/min)	24	24	24	24	24	24	24
N	ALUMINUM ALLOYS 2017, 2024, 356, 6061, 7075	≤ 80	82	RPM	26174	13087	8725	6544	4362	3272	2617
			(66-99)	Fr	0.040	0.080	0.120	0.160	0.240	0.320	0.400
				Feed (mm/min)	1047	1047	1047	1047	1047	1047	1047
		> 80	70	RPM	22297	11148	7432	5574	3716	2787	2230
			(56-84)	Fr	0.040	0.080	0.120	0.160	0.240	0.320	0.400
				Feed (mm/min)	892	892	892	892	892	892	892
N	COPPER ALLOYS Alum Bronze, C110, Muntz Brass	≤ 140	35	RPM	11148	5574	3716	2787	1858	1394	1115
			(28-42)	Fr	0.020	0.041	0.061	0.082	0.122	0.163	0.204
				Feed (mm/min)	223	229	227	229	227	227	227
		> 140	29	RPM	9209	4605	3070	2302	1535	1151	921
			(23-35)	Fr	0.020	0.041	0.061	0.082	0.122	0.163	0.204
				Feed (mm/min)	184	189	187	189	187	188	188

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
increase speed and feed rates shown by 30 percent when using coated reamers
reduce speed and feed for materials harder than listed
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)

ROUTERS



Routing

HIGH PERFORMANCE ROUTERS	SERIES	PAGE
Carbon Composite Routers	20-CCR, 20M-CCR	246
Coarse Cut Carbon Composite Routers	31-CCR, 31M-CCR	247
Compression Routers	25, 25-M	248

GENERAL PURPOSE ROUTERS	SERIES	PAGE
Up Cut Routers	21, 21M	249
Down Cut Routers	22, 22M	250

TECHNICAL INFORMATION

Speed & Feed Recommendations		251

Ranurado

RANURADORES DE ALTO RENDIMIENTO	SERIE	PÁGINA
Ranuradores de compuesto de carbono	20-CCR, 20M-CCR	246
Ranuradores de compuesto de carbono de corte áspero	31-CCR, 31M-CCR	247
Ranuradores de compresión	25, 25-M	248
RANURADORES DE USO GENERAL	**SERIE**	**PÁGINA**
Ranuradores de corte ascendente	21, 21M	249
Ranuradores de corte descendente	22, 22M	250
INFORMACIÓN TÉCNICA		
Velocidades y avances recomendados		251

Détourage

FRAISES A DETOURER HAUTE PERFORMANCE	SERIES	PAGE
Fraises à détourer pour composite carbone	20-CCR, 20M-CCR	246
Fraises à détourer pour composite carbone coupe grossière	31-CCR, 31M-CCR	247
Fraises à détourer compression	25, 25-M	248
FRAISES À DÉTOURER UNIVERSELLES	**SERIES**	**PAGE**
Fraises à détourer up cut	21, 21M	249
Fraises à détourer down cut	22, 22M	250
INFORMATIONS TECHNIQUES		
Recommandations de vitesse et avance		251

Router Icon Legend
Leyenda del icono de los ranuradores
Légende des icônes de détourage

END CONFIGURATIONS
CONFIGURACIONES DE LA PUNTA
CONFIGURATIONS TERMINALES



Square
Plana
Carrée

SHANK TYPE
TIPO DE VÁSTAGO
TYPE DE TIGE



Straight
Recto
Droite

RAKE ANGLE
ÁNGULO DE ATAQUE
ANGLE DE PENTE



Positive
Positivo
Positif



Neutral
Neutro
Neutre



Negative
Negativo
Négatif



Variable
Variable
Variable

HELIX ANGLES
ÁNGULOS HELICOIDALES
ANGLES DE L'HÉLICE



Right Spiral
Espiral sentido derecho
Spirale droite



Left Spiral
Espiral sentido izquierdo
Spirale gauche

ADDITIONAL GEOMETRY
CARACTERÍSTICAS GEOMÉTRICAS ADICIONALES
GÉOMÉTRIE SUPPLÉMENTAIRE



Left Cut Direction
Fresado sentido izquierda
Coupe vers la gauche



Right Cut Direction
Fresado sentido derecha
Coupe vers la droite



Chip Breaker
Rompevirutas
Brise-copeaux


COATINGS
REVESTIMIENTOS
REVÊTEMENTS




Uncoated



Di-NAMITE
(Diamond)







20-CCR
FRACTIONAL SERIES

TECH INFO 251

PLASTICS/COMPOSITES

inch						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	END STYLE	UNCOATED	Di-NAMITE (Diamond)
1/4	1	2-1/2	1/4	8	No End Cutting	72930	73013
1/4	1	2-1/2	1/4	8	End Cutting	72947	73012
5/16	1	2-1/2	5/16	10	No End Cutting	72948	73026
5/16	1	2-1/2	5/16	10	End Cutting	72949	73014
3/8	1-1/8	2-1/2	3/8	12	No End Cutting	72950	73028
3/8	1-1/8	2-1/2	3/8	12	End Cutting	72951	73027
1/2	1-1/2	3-1/2	1/2	12	No End Cutting	72952	73041
1/2	1-1/2	3-1/2	1/2	12	End Cutting	72953	73029

TOLERANCES (inch)
D_1 = +.000/–.005
D_2 = h_6

20M-CCR
METRIC SERIES


TECH INFO 252

mm						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	END STYLE	UNCOATED	Di-NAMITE (Diamond)
6,0	25,0	63,0	6,0	8	No End Cutting	82966	83027
6,0	25,0	63,0	6,0	8	End Cutting	82967	83026
8,0	25,0	63,0	8,0	10	No End Cutting	82968	83029
8,0	25,0	63,0	8,0	10	End Cutting	82969	83028
10,0	28,0	63,0	10,0	12	No End Cutting	82970	83042
10,0	28,0	63,0	10,0	12	End Cutting	82971	83041
12,0	38,0	89,0	12,0	12	No End Cutting	82972	83044
12,0	38,0	89,0	12,0	12	End Cutting	82973	83043

TOLERANCES (mm)
D_1 = +0,00/–0,13
D_2 = h_6







TOLERANCES (inch)

D_1 = +.000/–.005

D_2 = h_6

31-CCR
FRACTIONAL SERIES

TECH INFO 251

PLASTICS/COMPOSITES

inch						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	END STYLE	UNCOATED	Di-NAMITE (Diamond)
1/4	1	2-1/2	1/4	5	End Cutting	72954	72955
1/4	1	2-1/2	1/4	5	No End Cutting	72956	72957
5/16	1	2-1/2	5/16	7	End Cutting	72958	72959
5/16	1	2-1/2	5/16	7	No End Cutting	72960	72961
3/8	1-1/8	2-1/2	3/8	8	End Cutting	72962	72963
3/8	1-1/8	2-1/2	3/8	8	No End Cutting	72964	72965
1/2	1-1/2	3-1/2	1/2	10	End Cutting	72966	72967
1/2	1-1/2	3-1/2	1/2	10	No End Cutting	72968	72969

TOLERANCES (mm)

D_1 = +0,00/–0,13

D_2 = h_6


31M-CCR
METRIC SERIES

TECH INFO 252

mm						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	NO. OF FLUTES	END STYLE	UNCOATED	Di-NAMITE (Diamond)
6,0	18,0	63,0	6,0	5	End Cutting	82974	82982
6,0	18,0	63,0	6,0	5	No End Cutting	82975	82983
8,0	25,0	63,0	8,0	7	End Cutting	82976	82984
8,0	25,0	63,0	8,0	7	No End Cutting	82977	82985
10,0	30,0	63,0	10,0	8	End Cutting	82978	82986
10,0	30,0	63,0	10,0	8	No End Cutting	82979	82987
12,0	38,0	89,0	12,0	10	End Cutting	82980	82988
12,0	38,0	89,0	12,0	10	No End Cutting	82981	82989







25
FRACTIONAL SERIES

TECH INFO 253

PLASTICS/COMPOSITES

inch						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	L_3	NO. OF FLUTES	UNCOATED	Di-NAMITE (Diamond)
1/4	1	2-1/2	1/4	11/64	4	72970	72971
5/16	1	2-1/2	5/16	7/32	4	72972	72973
3/8	1-1/8	2-1/2	3/8	17/64	6	72974	72975
1/2	1-1/2	3-1/2	1/2	23/64	8	72976	72977

TOLERANCES (inch)

D_1 = +.000/–.003
D_2 = h_6

25M
METRIC SERIES

TECH INFO 254

mm						EDP NO.	
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	L_3	NO. OF FLUTES	UNCOATED	Di-NAMITE (Diamond)
6,0	25,0	63,0	6,0	4,10	4	82990	82991
8,0	25,0	63,0	8,0	5,58	4	82992	82993
10,0	28,0	63,0	10,0	7,05	6	82994	82995
12,0	38,0	89,0	12,0	8,60	8	82996	82997

TOLERANCES (mm)

D_1 = +0,00/–0,08
D_2 = h_6






TOLERANCES (inch)

D_1 = +.000/–.003

D_2 = h_6



21
FRACTIONAL SERIES

TECH INFO 255

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
1/8	1/2	2	1/4	90001
5/32	5/8	2-1/2	1/4	90005
3/16	3/4	2-1/2	1/4	90009
1/4	3/4	2-1/2	1/4	90013
1/4	1	2-1/2	1/4	90017
5/16	1	2-1/2	5/16	90021
5/16	1	3	1/2	90025
3/8	1	2-1/2	3/8	90029
3/8	1-1/4	3	1/2	90033
1/2	1-1/4	3	1/2	90037
1/2	1-1/2	3-1/2	1/2	90041
1/2	2	4	1/2	90045
5/8	2	4-1/2	5/8	90049
3/4	2	4-1/2	3/4	90053

NON-FERROUS

PLASTICS/COMPOSITES

TOLERANCES (mm)

D_1 = +0,00/–0,08

D_2 = h_6


21M
METRIC SERIES

TECH INFO 256

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
3,0	13,0	50,0	6,0	90101
4,0	16,0	63,0	6,0	90107
5,0	19,0	63,0	6,0	90109
6,0	25,0	63,0	6,0	90113
8,0	25,0	63,0	8,0	90121
10,0	31,0	75,0	10,0	90129
12,0	31,0	75,0	12,0	90137







22
FRACTIONAL SERIES

TECH INFO 255

TOLERANCES (inch)

D_1 = +.000/–.003
D_2 = h_6

NON-FERROUS
PLASTICS/COMPOSITES

inch				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
1/8	1/2	2	1/4	91001
5/32	5/8	2-1/2	1/4	91005
3/16	3/4	2-1/2	1/4	91009
1/4	3/4	2-1/2	1/4	91013
1/4	1	2-1/2	1/4	91017
5/16	1	2-1/2	5/16	91021
5/16	1	3	1/2	91025
3/8	1	2-1/2	3/8	91029
3/8	1-1/4	3	1/2	91033
1/2	1-1/4	3	1/2	91037
1/2	1-1/2	3-1/2	1/2	91041
1/2	2	4	1/2	91045
5/8	2	4-1/2	5/8	91049
3/4	2	4-1/2	3/4	91053

22M
METRIC SERIES


TECH INFO 256

TOLERANCES (mm)

D_1 = +0,00/–0,08
D_2 = h_6

mm				EDP NO.
CUTTING DIAMETER D_1	LENGTH OF CUT L_2	OVERALL LENGTH L_1	SHANK DIAMETER D_2	UNCOATED
3,0	13,0	50,0	6,0	91101
4,0	16,0	63,0	6,0	91107
5,0	19,0	63,0	6,0	91109
6,0	25,0	63,0	6,0	91113
8,0	25,0	63,0	8,0	91121
10,0	31,0	75,0	10,0	91129
12,0	31,0	75,0	12,0	91137


CCR CARBON-FIBER COMPOSITE ROUTERS



Series 20, 31 Fractional		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	5/16	3/8	1/2
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Slot	1	≤ 1	400	RPM	6112	4890	4075	3056
				(320-480)	Fz	0.0060	0.0075	0.0090	0.0120
					Feed (IPM)	36.7	36.7	36.7	36.7
	Profile	≤ 0.5	≤ 1.5	500	RPM	7640	6112	5093	3820
				(400-600)	Fz	0.0060	0.0075	0.0090	0.0120
					Feed (IPM)	45.8	45.8	45.8	45.8
	HSM	≤ 0.5	≤ 2	825	RPM	12606	10085	8404	6303
				(660-990)	Fz	0.0138	0.0173	0.0207	0.0276
					Feed (IPM)	174.0	174.0	174.0	174.0
GFRP (FIBERGLASS)	Slot	1	≤ 1	320	RPM	4890	3912	3260	2445
				(256-384)	Fz	0.0060	0.0075	0.0090	0.0120
					Feed (IPM)	29.3	29.3	29.3	29.3
	Profile	≤ 0.5	≤ 1.5	400	RPM	6112	4890	4075	3056
				(320-480)	Fz	0.0060	0.0075	0.0090	0.0120
					Feed (IPM)	36.7	36.7	36.7	36.7
	HSM	≤ 0.05	≤ 2	660	RPM	10085	8068	6723	5042
				(528-792)	Fz	0.0138	0.0172	0.0207	0.0276
					Feed (IPM)	139.0	139.0	139.0	139.0
CARBON, GRAPHITE	Slot	1	≤ 1	480	RPM	7334	5868	4890	3667
				(384-576)	Fz	0.0075	0.0094	0.0112	0.0150
					Feed (IPM)	55.0	55.0	55.0	55.0
	Profile	≤ 0.5	≤ 1.5	600	RPM	9168	7334	6112	4584
				(480-720)	Fz	0.0075	0.0094	0.0112	0.0150
					Feed (IPM)	68.7	68.7	68.7	68.7
	HSM	≤ 0.05	≤ 2	990	RPM	15127	12102	10085	7564
				(792-1188)	Fz	0.0172	0.0215	0.0258	0.0344
					Feed (IPM)	260.0	260.0	260.0	260.0
PLASTICS	Slot	1	≤ 1	800	RPM	12224	9779	8149	6112
				(640-690)	Fz	0.0075	0.0094	0.0113	0.0150
					Feed (IPM)	91.7	91.7	91.7	91.7
	Profile	≤ 0.5	≤ 1.5	1000	RPM	15280	12224	10187	7640
				(800-1200)	Fz	0.0075	0.0094	0.0113	0.0150
					Feed (IPM)	114.6	114.6	114.6	114.6
	HSM	≤ 0.05	≤ 2	1650	RPM	25212	20170	16808	12606
				(1320-1980)	Fz	0.0069	0.0086	0.0104	0.0138
					Feed (IPM)	174.0	174.0	174.0	174.0

rpm = sfm x 3.82 / D_1
ipm = (inch / revolution) x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur

finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)




Series 20, 31 Metric		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Slot	1	≤ 1	120	RPM	6361	4771	3817	3181
				(96-164)	Fz	0.152	0.203	0.254	0.305
					Feed (mm/min)	970	970	970	970
	Profile	≤ 0.5	≤ 1.5	150	RPM	7951	5963	4771	3976
				(120-180)	Fz	0.153	0.203	0.254	0.305
					Feed (mm/min)	1213	1213	1213	1213
	HSM	≤ 0.05	≤ 2	250	RPM	13252	9939	7951	6626
				(200-300)	Fz	0.350	0.467	0.583	0.700
					Feed (mm/min)	4638	4638	4638	4638
GFRP (FIBERGLASS)	Slot	1	≤ 1	100	RPM	5301	3976	3181	2650
				(80-120)	Fz	0.152	0.203	0.254	0.305
					Feed (mm/min)	808	808	808	808
	Profile	≤ 0.5	≤ 1.5	120	RPM	6361	4771	3817	3181
				(96-164)	Fz	0.152	0.203	0.254	0.305
					Feed (mm/min)	970	970	970	970
	HSM	≤ 0.05	≤ 2	200	RPM	10602	7951	6361	5301
				(160-240)	Fz	0.350	0.467	0.583	0.700
					Feed (mm/min)	3711	3711	3711	3711
CARBON, GRAPHITE	Slot	1	≤ 1	145	RPM	7686	5765	4612	3843
				(116-174)	Fz	0.190	0.253	0.317	0.380
					Feed (mm/min)	1460	1460	1460	1460
	Profile	≤ 0.5	≤ 1.5	185	RPM	9807	7355	5884	4903
				(148-222)	Fz	0.190	0.253	0.317	0.380
					Feed (mm/min)	1863	1863	1863	1863
	HSM	≤ 0.05	≤ 2	300	RPM	15903	11927	9542	7951
				(240-360)	Fz	0.437	0.583	0.729	0.875
					Feed (mm/min)	6957	6957	6957	6957
PLASTICS	Slot	1	≤ 1	245	RPM	12987	9740	7792	6494
				(196-294)	Fz	0.075	0.100	0.125	0.150
					Feed (mm/min)	974	974	974	974
	Profile	≤ 0.5	≤ 1.5	305	RPM	16168	12126	9701	8084
				(244-366)	Fz	0.075	0.100	0.125	0.150
					Feed (mm/min)	1213	1213	1213	1213
	HSM	≤ 0.05	≤ 2	505	RPM	26769	20077	16062	13385
				(404-606)	Fz	0.175	0.233	0.292	0.350
					Feed (mm/min)	4685	4685	4685	4685

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / revolution) x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur

finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)


DYNAMITE CRYSTALLINE DIAMOND COATING



Series 25 Fractional		Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/4	5/16	3/8	1/2	3/4
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Profile	≤ 0.5	≤ 1.5	500	RPM	7640	6112	5093	3820	2547
				(400-600)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	48.9	61.1	91.7	122.2	97.8
	HSM	≤ 0.05	≤ 2	825	RPM	12606	10085	8404	6303	4202
				(660-990)	Fz	0.0037	0.0057	0.0069	0.0092	0.0110
					Feed (IPM)	186.6	229.9	347.9	463.9	369.8
GFRP (FIBERGLASS)	Profile	≤ 0.5	≤ 1.5	400	RPM	6112	4890	4075	3056	2037
				(320-480)	Fz	0.0016	0.0025	0.0030	0.0040	0.0048
					Feed (IPM)	39.1	48.9	73.3	97.8	78.2
	HSM	≤ 0.05	≤ 2	660	RPM	10085	8068	6723	5042	3362
				(528-792)	Fz	0.0037	0.0057	0.0069	0.0092	0.0110
					Feed (IPM)	149.3	183.9	278.3	371.1	295.8
CARBON, GRAPHITE	Profile	≤ 0.5	≤ 1.5	600	RPM	9168	7334	6112	4584	3056
				(480-720)	Fz	0.0020	0.0031	0.0038	0.0050	0.0050
					Feed (IPM)	73.3	90.9	139.4	183.4	122.2
	HSM	≤ 0.05	≤ 2	990	RPM	15127	12102	10085	7564	5042
				(792-1188)	Fz	0.0046	0.0072	0.0086	0.0115	0.0138
					Feed (IPM)	278.3	348.5	520.4	695.9	556.7
PLASTICS	Profile	≤ 0.5	≤ 1.5	1000	RPM	15280	12224	10187	7640	5093
				(800-1200)	Fz	0.0020	0.0031	0.0038	0.0050	0.0060
					Feed (IPM)	122.2	151.6	232.3	305.6	244.5
	HSM	≤ 0.05	≤ 2	1650	RPM	25212	20170	16808	12606	8404
				(1320-1980)	Fz	0.0046	0.0072	0.0086	0.0115	0.0138
					Feed (IPM)	463.9	580.9	867.3	1159.8	927.8
MACHINABLE CERAMICS MACHINABLE GLASS	Profile	≤ 0.5	≤ 1.5	50	RPM	764	611	509	382	255
				(40-60)	Fz	0.0008	0.0013	0.0015	0.0020	0.0024
					Feed (IPM)	2.4	3.2	4.6	6.1	4.9
	HSM	≤ 0.05	≤ 2	85	RPM	1299	1039	866	649	433
				(68-102)	Fz	0.0018	0.0029	0.0034	0.0046	0.0550
					Feed (IPM)	9.4	12.1	17.7	23.9	190.5

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 4 x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur


finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



Series 25 Metric		Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 6	8	10	12	16
CFRP, AFRP (CARBON FIBER, ARAMID FIBER)	Profile	≤ 0.5	≤ 1.5	150	RPM	7951	5963	4771	3976	2982
				(96-164)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	1272	1550	2147	3181	2862
	HSM	≤ 0.05	≤ 2	250	RPM	13252	9939	7951	6626	4970
				(200-300)	Fz	0.095	0.145	0.175	0.235	0.280
					Feed (mm/min)	5036	5765	8349	12457	11132
GFRP (FIBERGLASS)	Profile	≤ 0.5	≤ 1.5	120	RPM	6361	4771	3817	3181	2385
				(96-164)	Fz	0.040	0.065	0.075	0.100	0.120
					Feed (mm/min)	1018	1240	1717	2544	2290
	HSM	≤ 0.05	≤ 2	200	RPM	10602	7951	6361	5301	3976
				(160-240)	Fz	0.095	0.145	0.175	0.235	0.280
					Feed (mm/min)	4029	4612	6679	9966	8905
CARBON, GRAPHITE	Profile	≤ 0.5	≤ 1.5	185	RPM	9807	7355	5884	4903	3677
				(148-222)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	1961	2354	3354	4903	4413
	HSM	≤ 0.05	≤ 2	300	RPM	15903	11927	9542	7951	5963
				(240-360)	Fz	0.115	0.185	0.220	0.290	0.350
					Feed (mm/min)	7315	8826	12595	18447	16698
PLASTICS	Profile	≤ 0.5	≤ 1.5	305	RPM	16168	12126	9701	8084	6063
				(244-366)	Fz	0.050	0.080	0.095	0.125	0.150
					Feed (mm/min)	3234	3880	5529	8084	7275
	HSM	≤ 0.05	≤ 2	505	RPM	26769	20077	16062	13385	10038
				(404-606)	Fz	0.115	0.185	0.220	0.290	0.350
					Feed (mm/min)	12314	14857	21201	31052	28108
MACHINABLE CERAMICS MACHINABLE GLASS	Profile	≤ 0.5	≤ 1.5	15	RPM	795	596	477	398	298
				(12-18)	Fz	0.020	0.035	0.045	0.050	0.060
					Feed (mm/min)	64	83	129	159	143
	HSM	≤ 0.05	≤ 2	25	RPM	1325	994	795	663	497
				(20-30)	Fz	0.045	0.075	0.085	0.115	0.140
					Feed (mm/min)	239	298	406	610	557


rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 4 x rpm
HSM (high speed machining)
adjust parameters based on resin type and fiber structure
reduce speed when overheating causes melting or damage to resin
reduce feed if delamination or fraying occur

finish cuts typically required reduced feed and cutting depths
rates shown are for use without coolant; rates may be increased with coolant
dust collection is vital when machining dry
diamond coating will increase tool life in graphite and composite materials
refer to the SGS Tool Wizard for complete technical information (www.sgstool.com)



Series 21, 22 Fractional			Ae x D_1	Ap x D_1	Vc (SFM)		Diameter (D_1) (inch) 1/8	1/4	3/8	1/2	3/4
HARDWOODS	Slot		1	≤ 1	1550	RPM	47368	23684	15789	11842	7895
					(1240-1860)	Fz	0.0008	0.0015	0.0025	0.0030	0.0045
						Feed (IPM)	76	71	79	71	71
	Profile		≤ 0.5	≤ 1.5	1550	RPM	47368	23684	15789	11842	7895
					(1240-1860)	Fz	0.0008	0.0015	0.0025	0.0030	0.0045
						Feed (IPM)	76	71	79	71	71
SOFTWOODS	Slot		1	≤ 1	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0010	0.0020	0.0030	0.0035	0.0055
						Feed (IPM)	119	119	119	104	109
	Profile		≤ 0.5	≤ 1.5	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0010	0.0020	0.0030	0.0035	0.0055
						Feed (IPM)	119	119	119	104	109
PLYWOODS	Slot		1	≤ 1	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0013	0.0025	0.0040	0.0050	0.0075
						Feed (IPM)	155	149	159	149	149
	Profile		≤ 0.5	≤ 1.5	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0013	0.0025	0.0040	0.0050	0.0075
						Feed (IPM)	155	149	159	149	149
N ALUMINUM ALLOYS	Slot		1	≤ 1	1150	RPM	35144	17572	11715	8786	5857
					(920-1380)	Fz	0.0006	0.0015	0.0020	0.0025	0.0040
						Feed (IPM)	42	53	47	44	47
	Profile		≤ 0.5	≤ 1.5	1150	RPM	35144	17572	11715	8786	5857
					(920-1380)	Fz	0.0006	0.0015	0.0020	0.0025	0.0040
						Feed (IPM)	42	53	47	44	47
PLASTICS	Slot		1	≤ 1	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0008	0.0017	0.0025	0.0035	0.0050
						Feed (IPM)	95	101	99	104	99
	Profile		≤ 0.5	≤ 1.5	1950	RPM	59592	29796	19864	14898	9932
					(1560-2340)	Fz	0.0008	0.0017	0.0025	0.0035	0.0050
						Feed (IPM)	95	101	99	104	99

rpm = sfm x 3.82 / D_1
ipm = (inch / flute) x 2 x rpm



Series 21M, 22M Metric			Ae x D_1	Ap x D_1	Vc (m/min)		Diameter (D_1) (mm) 3	6	10	12	20
	HARDWOODS	Slot	1	≤ 1	470	RPM	49828	24914	14948	12457	7474
					(376-564)	Fz	0.020	0.040	0.065	0.075	0.115
						Feed (mm/min)	1993	1993	1943	1869	1719
		Profile	≤ 0.5	≤ 1.5	470	RPM	49828	24914	8155	4241	1509
					(376-564)	Fz	0.020	0.040	0.065	0.075	0.115
						Feed (mm/min)	1993	1993	1060	636	347
	SOFTWOODS	Slot	1	≤ 1	600	RPM	63610	31805	19083	15903	9542
					(480-720)	Fz	0.025	0.050	0.075	0.090	0.140
						Feed (mm/min)	3181	3181	2862	2862	2672
		Profile	≤ 0.5	≤ 1.5	600	RPM	63610	31805	19083	15903	303467
					(480-720)	Fz	0.025	0.050	0.075	0.090	0.140
						Feed (mm/min)	3181	3181	2862	2862	84971
	PLYWOODS	Slot	1	≤ 1	600	RPM	63610	31805	19083	15903	9542
					(480-720)	Fz	0.030	0.065	0.100	0.125	0.190
						Feed (mm/min)	3817	4135	3817	3976	3626
		Profile	≤ 0.5	≤ 1.5	600	RPM	63610	31805	19083	15903	303467
					(480-720)	Fz	0.030	0.065	0.100	0.125	0.190
						Feed (mm/min)	3817	4135	3817	3976	115318
N	ALUMINUM ALLOYS	Slot	1	≤ 1	350	RPM	37106	18553	11132	9276	5566
					(289-420)	Fz	0.015	0.040	0.050	0.065	0.100
						Feed (mm/min)	1113	1484	1113	1206	1113
		Profile	≤ 0.5	≤ 1.5	350	RPM	37106	18553	11132	9276	177023
					(289-420)	Fz	0.015	0.040	0.050	0.065	0.100
						Feed (mm/min)	1113	1484	1113	1206	35405
	PLASTICS	Slot	1	≤ 1	600	RPM	63610	31805	19083	15903	9542
					(480-720)	Fz	0.020	0.040	0.065	0.090	0.125
						Feed (mm/min)	2544	2544	2481	2862	2385
		Profile	≤ 0.5	≤ 1.5	600	RPM	63610	31805	19083	15903	9542
					(480-720)	Fz	0.020	0.040	0.065	0.090	0.125
						Feed (mm/min)	2544	2544	2481	2862	2385

rpm = (1000 x m/min) / (3.14 x D_1)
mm / min = (mm / flute) x 2 x rpm

EDP Number Index

EDP NO.	PAGE
30000	99
30001	99
30002	99
30003	99
30004	99
30005	99
30006	99
30007	99
30008	99
30009	99
30010	99
30011	99
30012	99
30013	99
30014	99
30015	99
30016	100
30017	100
30018	100
30019	100
30020	100
30021	100
30022	100
30023	100
30024	100
30025	100
30026	100
30027	100
30028	100
30029	99
30030	100
30030	138
30031	104
30032	104
30033	104
30034	104
30035	104
30036	104
30037	104
30038	104
30039	104
30040	104
30041	104
30042	104
30043	104
30044	104
30045	104
30046	104
30047	104
30048	104
30049	104
30050	104
30051	105
30052	105
30053	105
30054	105
30055	105
30056	105
30057	105
30058	105
30059	105
30060	105
30061	105
30062	105
30063	105
30064	105
30065	105
30066	105
30067	105
30068	105
30069	104
30070	105
30070	138
30101	99
30102	104
30103	99
30104	104
30105	99
30106	104
30107	99
30108	104
30109	99
30110	104
30111	99
30112	104
30113	99
30114	104
30115	99
30116	104
30117	99
30118	104
30119	99
30120	104
30121	99
30122	104
30123	99
30124	104
30125	99
30126	104
30127	99
30128	104
30129	99
30130	104
30131	99
30132	104
30133	99
30134	104
30135	99
30136	104
30137	99
30138	104
30139	99
30140	104
30141	99
30142	105
30143	99
30144	105
30145	99
30146	105
30147	99
30148	105
30149	99
30150	105
30151	100
30152	105
30153	100
30154	105
30155	100
30156	105
30157	100
30158	105
30159	100
30160	105
30161	100
30162	105
30163	100
30164	105
30165	100
30166	105
30167	100
30168	105
30169	100
30170	105
30171	100
30172	105
30173	100
30174	105
30175	100
30176	105
30177	99
30179	99
30180	100
30181	100
30182	100
30183	100
30184	105
30185	105
30186	105
30187	105
30188	105
30189	100
30189	138
30190	105
30190	138
30191	99
30192	99
30193	99
30194	99
30195	99
30196	99
30197	99
30198	99
30199	99
30301	114
30302	120
30303	114
30304	120
30305	114
30306	120
30307	114
30308	120
30309	114
30310	120
30311	114
30312	120
30313	114
30314	120
30315	114
30316	120
30317	114
30318	120
30319	114
30320	120
30321	114
30322	120
30323	114
30324	120
30325	114
30326	120
30327	114
30328	120
30329	114
30330	120
30331	114
30332	120
30333	114
30334	120
30335	114
30336	120
30337	114
30338	120
30339	114
30340	120
30341	115
30342	121
30343	115
30344	121
30345	115
30346	121
30347	115
30348	121
30349	115
30350	121
30351	115
30352	121
30353	115
30354	121
30355	115
30356	121
30357	115
30358	121
30359	115
30360	121
30361	115
30362	121
30363	115
30364	121
30365	115
30366	121
30367	115
30368	121
30369	115
30370	121
30371	115
30372	121
30373	115
30374	121
30375	115
30376	121
30377	114
30378	120
30379	99
30380	100
30381	100
30382	100
30383	100
30384	105
30385	105
30386	105
30387	105
30388	105
30389	115
30389	138
30390	121
30390	138
30397	114
30398	114
30399	114
30400	114
30435	114
30436	114
30437	114
30438	114
30439	114
30440	114
30441	114
30442	114
30443	114
30444	114
30445	114
30446	114
30447	114
30448	114
30449	114
30450	114
30451	115
30452	115
30453	115
30454	115
30455	115
30456	115
30457	115
30458	115
30459	115
30460	115
30461	115
30462	115
30463	115
30464	115
30465	115
30466	115
30467	115
30468	115
30469	114
30470	115
30470	138
30471	120
30472	120
30473	120
30474	120
30475	120
30476	120
30477	120
30478	120
30479	120
30480	120
30481	120
30482	120
30483	120
30484	120
30485	120
30486	120
30487	120
30488	120
30489	120
30490	120
30491	121
30492	121
30493	121
30494	121
30495	121
30496	121
30497	121
30498	121
30499	121
30500	121
30501	128
30502	130
30503	128
30504	130
30505	128
30506	130
30507	128
30508	130
30509	128
30510	130
30511	128
30512	130
30513	128
30514	130
30515	128
30516	130
30517	128
30518	130
30519	128
30520	130
30521	128
30522	130
30523	128
30524	130
30525	128
30526	130
30527	128
30528	130
30529	128
30530	130
30531	128
30532	130
30533	128
30534	130
30535	128
30536	130
30537	128
30538	130
30539	128
30540	130
30541	128
30542	130
30543	128
30544	130
30545	128
30546	130
30547	128
30548	130
30549	128
30550	130
30551	128
30552	130
30553	128
30554	130
30555	128
30556	130
30557	128
30558	130
30559	128
30560	130
30561	128
30562	130
30563	128
30564	130
30565	128
30566	130
30567	128
30568	130
30569	128
30570	130
30571	128
30572	130
30573	128
30574	130
30575	128
30576	130
30577	128
30578	130
30589	138
30590	130
30590	138
30591	121
30592	121
30593	121
30594	121
30595	121
30596	121
30597	121
30598	121
30599	120
30600	121
30600	138
30602	130
30604	130
30606	130
30608	130
30610	130
30612	130
30771	128
30772	128
30773	128
30774	128
30775	128
30776	128
30777	128
30778	128
30779	128
30780	128
30781	128
30782	128
30783	128
30784	128
30785	128
30786	128
30787	128
30788	128
30789	128
30790	128
30791	128
30792	128
30793	128
30794	128
30795	128
30796	128
30797	128
30798	128

EDP Number Index

EDP NO.	PAGE
30799	128
30800	128
30801	128
30802	128
30803	128
30804	128
30805	128
30806	128
30807	128
30808	128
30809	128
30810	138
30811	128
30812	128
30813	128
30814	128
30815	128
30816	128
30817	128
30818	128
30819	128
30820	128
30821	128
30822	128
30823	128
30824	128
30825	128
30826	128
30827	128
30828	128
30829	128
30830	128
30831	128
30832	128
30833	128
30834	128
30835	128
30836	128
30837	128
30838	128
30839	128
30840	128
30841	128
30842	128
30843	128
30844	128
30845	128
30846	128
30847	128
30848	128
30849	128
30850	138
30851	130
30852	130
30853	130
30854	130
30855	130
30856	130
30857	130
30858	130
30859	130
30860	130
30861	130
30862	130
30863	130
30864	130
30865	130
30866	130
30867	130
30868	130
30869	130
30870	130
30871	130
30872	130
30873	130
30874	130
30875	130
30876	130
30877	130
30878	130
30879	130
30880	130
30881	130
30882	130
30883	130
30884	130
30885	130
30886	130
30887	130
30888	130
30889	130
30900	130
30900	138
30902	130
30904	130
30906	130
30908	130
30910	130
30912	130
30914	130
30916	130
30918	130
30920	130
30921	130
30922	130
30923	130
30924	130
30925	130
30926	130
30927	130
30928	130
30929	130
30930	130
30931	130
30932	130
30933	130
30934	130
30935	130
30936	130
30937	130
30938	130
30939	130
30940	130
30941	130
30942	130
30943	130
30944	130
30944	138
31130	130
31131	130
31132	130
31133	130
31134	130
31135	130
31136	130
31137	130
31138	130
31139	130
31140	130
31141	130
31142	130
31143	130
31144	130
31145	130
31146	130
31147	130
31148	130
31149	130
31150	130
31151	130
31152	130
31153	130
31154	130
31155	130
31156	130
31157	130
31158	130
31159	130
31160	130
31161	130
31162	130
31163	130
31164	130
31165	130
31166	130
31167	130
31168	130
31169	130
31169	138
31170	102
31171	102
31172	102
31173	102
31174	102
31175	102
31176	102
31177	102
31178	102
31179	102
31180	102
31181	102
31182	102
31183	102
31184	102
31185	102
31186	102
31187	102
31188	102
31189	102
31190	138
31217	107
31217	138
31218	107
31219	107
31220	107
31221	107
31222	107
31223	107
31224	107
31225	107
31226	107
31227	107
31228	107
31229	107
31230	107
31231	107
31232	107
31233	107
31234	107
31235	107
31236	107
31237	107
31238	98
31239	98
31240	98
31241	98
31242	98
31243	98
31244	98
31245	98
31246	98
31247	98
31248	98
31249	98
31250	98
31251	98
31252	98
31253	98
31254	98
31255	98
31256	98
31257	98
31258	98
31259	98
31260	98
31261	98
31262	98
31263	98
31303	113
31304	113
31305	113
31306	113
31307	113
31308	113
31309	113
31310	113
31311	113
31312	113
31313	113
31314	113
31315	113
31316	118
31317	118
31318	118
31319	118
31320	118
31321	118
31322	118
31323	118
31324	118
31325	118
31326	118
31327	118
31328	118
31329	118
31330	118
31331	118
31332	118
31333	118
31334	118
31335	118
31336	118
31336	138
31337	124
31338	124
31339	124
31340	124
31341	124
31342	124
31343	124
31344	124
31345	124
31346	124
31347	124
31348	124
31349	124
31350	124
31351	124
31352	124
31353	124
31354	124
31355	124
31356	124
31357	124
31357	138
31358	113
31359	113
31360	113
31361	113
31362	113
31363	113
31364	113
31365	113
31366	113
31367	113
31368	113
31369	113
31370	113
31401	102
31402	107
31403	102
31404	107
31405	102
31406	107
31407	102
31408	107
31409	102
31410	107
31411	102
31412	107
31413	102
31414	107
31415	102
31416	107
31417	102
31418	107
31419	102
31420	107
31421	102
31422	107
31423	102
31424	107
31425	102
31426	107
31427	102
31428	107
31429	102
31430	107
31431	102
31432	107
31433	102
31434	107
31435	102
31436	107
31437	102
31438	107
31439	102
31440	107
31441	102
31442	107
31443	102
31444	107
31445	102
31446	107
31447	102
31448	107
31449	102
31450	107
31451	102
31452	107
31453	102
31454	107
31455	102
31456	107
31457	102
31458	107
31459	102
31460	107
31461	102
31462	107
31463	102
31464	107
31465	102
31466	107
31467	102
31468	107
31469	102
31470	107
31471	102
31472	107
31473	102
31474	107
31475	102
31476	107
31477	102
31478	107
31479	102
31480	107
31481	138
31482	107
31482	138
31489	138
31490	107
31490	138
31501	118
31502	124
31503	118
31504	124
31505	118
31506	124
31507	118
31508	124
31509	118
31510	124
31511	118
31512	124
31513	118
31514	124
31515	118
31516	124
31517	118
31518	124
31519	118
31520	124
31521	118
31522	124
31523	118
31524	124
31525	118
31526	124
31527	118
31528	124
31529	118
31530	124
31531	118
31532	124
31533	118
31534	124
31535	118
31536	124
31537	118
31538	124
31539	118
31540	124
31541	118
31542	124
31543	118
31544	124
31545	118
31546	124
31547	118
31548	124
31549	118
31550	124
31551	118
31552	124
31553	118
31554	124
31555	118
31556	124
31557	118
31558	124
31559	118
31560	124
31561	118
31562	124
31563	118
31564	124
31565	118
31566	124
31567	118
31568	124

EDP Number Index

EDP NO.	PAGE
31569	118
31570	124
31571	118
31572	124
31573	118
31574	124
31575	118
31576	124
31577	118
31578	124
31579	118
31580	124
31581	118
31581	138
31582	124
31582	138
31589	118
31589	138
31590	124
31590	138
31601	98
31603	98
31605	98
31607	98
31609	98
31611	98
31613	98
31615	98
31617	98
31619	98
31621	98
31623	98
31625	98
31650	98
31651	98
31652	98
31653	98
31654	98
31655	98
31656	98
31657	98
31658	98
31659	98
31660	98
31661	98
31662	98
31701	113
31703	113
31705	113
31707	113
31709	113
31711	113
31713	113
31715	113
31717	113
31719	113
31721	113
31723	113
31725	113
31727	99
31728	99
31729	99
31730	99
31731	99
31732	100
31733	100
31734	100
31735	100
31736	100
31737	99
31738	99
31739	99
31740	99
31741	99
31742	100
31743	100
31744	100
31745	100
31746	100
31747	99
31748	99
31749	99
31750	113
31751	113
31752	113
31753	113
31754	113
31755	113
31756	113
31757	113
31758	113
31759	113
31760	113
31761	113
31762	113
31763	99
31764	99
31765	100
31766	100
31767	100
31768	100
31769	100
31770	104
31771	104
31772	104
31773	104
31774	105
31775	105
31776	105
31777	105
31778	105
31779	105
31780	104
31781	104
31782	104
31783	104
31784	105
31785	105
31786	105
31787	105
31788	105
31789	105
31790	104
31791	104
31792	104
31793	104
31794	105
31795	105
31796	105
31797	105
31798	105
31799	105
31800	114
31802	114
31804	115
31806	115
31808	115
31810	114
31812	114
31814	115
31816	115
31817	115
31818	115
31819	115
31820	114
31821	114
31822	115
31823	115
31824	115
31825	114
31826	114
31827	115
31830	120
31831	120
31832	120
31833	120
31834	121
31835	121
31836	121
31837	121
31838	121
31839	121
31840	120
31841	120
31842	120
31843	120
31844	121
31845	121
31846	121
31847	121
31848	121
31849	121
31850	114
31851	114
31852	114
31853	114
31854	115
31855	115
31856	115
31857	115
31858	115
31859	115
31860	99
31861	99
31862	99
31863	99
31864	99
31865	100
31866	100
31867	100
31868	100
31869	100
31870	99
31871	99
31872	99
31873	99
31874	99
31875	100
31876	100
31877	100
31878	100
31879	100
31880	99
31881	99
31882	99
31883	99
31884	99
31885	100
31886	100
31887	100
31888	100
31889	100
31890	120
31891	120
31892	120
31893	120
31894	121
31895	121
31896	121
31897	121
31898	121
31899	121
31900	104
31902	104
31904	104
31906	105
31908	105
31910	105
31912	105
31914	105
31916	105
31917	105
31918	104
31919	104
31920	104
31921	105
31922	105
31923	105
31924	105
31925	105
31926	105
31927	105
31928	104
31929	104
31930	104
31931	105
31932	105
31933	105
31934	105
31935	105
31936	105
31937	105
31938	114
31939	114
31940	114
31941	115
31942	115
31943	115
31944	115
31945	115
31946	115
31947	115
31948	114
31949	114
31950	114
31951	115
31952	115
31953	115
31954	115
31955	115
31956	115
31957	115
31958	114
31959	114
31960	114
31961	115
31962	115
31963	115
31964	115
31965	115
31966	115
31967	115
31968	120
31969	120
31970	120
31971	121
31972	121
31973	121
31974	121
31975	121
31976	121
31977	121
31978	120
31979	120
31980	120
31981	121
31982	121
31983	121
31984	121
31985	121
31986	121
31987	121
31988	120
31989	120
31990	120
31991	121
31992	121
31993	121
31994	121
31995	121
31996	121
31997	121
32033	44
32034	44
32035	44
32036	44
32037	44
32038	44
32039	44
32040	44
32041	44
32042	44
32043	44
32044	44
32045	44
32046	44
32047	44
32048	44
32049	44
32053	44
32054	44
32055	44
32056	44
32057	44
32058	44
32059	44
32060	44
32061	44
32062	44
32063	44
32064	44
32065	44
32066	44
32067	44
32068	44
32069	44
32200	123
32201	123
32202	123
32203	123
32204	123
32205	123
32206	123
32207	123
32210	123
32211	123
32212	123
32213	123
32214	123
32215	123
32216	123
32217	123
32260	117
32261	117
32262	117
32263	117
32264	117
32265	117
32266	117
32267	117
32270	117
32271	117
32272	117
32273	117
32274	117
32275	117
32276	117
32277	117
32280	117
32281	117
32282	117
32283	117
32284	117
32285	117
32286	117
32287	117
32290	123
32291	123
32292	123
32293	123
32294	123
32295	123
32296	123
32297	123
32301	136
32302	136
32303	136
32304	136
32305	136
32306	136
32307	136
32308	136
32309	136
32310	136
32311	136
32312	136
32313	136
32314	136
32315	136
32316	136
32317	136
32318	136
32319	136
32320	136
32321	136
32322	136
32323	136
32324	136
32325	136
32326	136
32327	136
32328	136
32329	136
32330	136
32333	136
32334	136
32335	136
32336	136
32337	136
32339	136
32340	136
32341	136
32342	136
32345	136
32346	136
32347	136
32348	136
32349	136
32350	136
32351	136
32352	136
32353	136
32354	136
32355	136
32356	136
32357	136
32358	136
32359	136
32360	136
32361	136
32362	136
32363	136
32364	136
32370	136
32371	136
32372	136
32373	136
32374	136
32375	136
32376	136
32377	136
32378	136

EDP Number Index

EDP NO.	PAGE
32379	136
32380	136
32381	136
32382	136
32383	136
32384	136
32385	136
32386	136
32387	136
32388	136
32388	136
32389	136
32402	137
32403	137
32404	137
32405	137
32406	137
32407	137
32408	137
32409	137
32410	137
32411	137
32412	137
32413	137
32414	137
32415	137
32416	137
32417	137
32418	137
32419	137
32420	137
32421	137
32422	137
32423	137
32424	137
32425	137
32426	137
32427	137
32428	137
32429	137
32430	137
32431	137
32434	137
32435	137
32436	137
32437	137
32438	137
32439	137
32440	137
32441	137
32442	137
32443	137
32445	137
32446	137
32447	137
32448	137
32449	137
32450	137
32451	137
32452	137
32453	137
32454	137
32455	137
32456	137
32457	137
32458	137
32459	137
32460	137
32461	137
32462	137
32463	137
32464	137
32470	137
32471	137
32472	137
32473	137
32474	137
32475	137
32476	137
32477	137
32478	137
32479	137
32480	137
32481	137
32482	137
32483	137
32484	137
32485	137
32486	137
32487	137
32488	137
32489	137
32569	32
32570	33
32571	33
32572	33
32573	32
32574	32
32575	33
32576	33
32577	33
32578	33
32579	33
32580	33
32581	33
32582	33
32583	33
32584	33
32585	33
32586	33
32587	33
32588	33
32589	33
32590	33
32591	32
32592	32
32593	32
32594	33
32595	33
32596	33
32597	33
32598	33
32599	33
32600	33
32601	33
32602	33
32603	33
32604	33
32605	33
32606	32
32607	32
32608	32
32609	32
32610	32
32611	32
32612	32
32613	32
32614	32
32615	32
32616	32
32619	32
32620	32
32621	32
32625	32
32626	32
32627	32
32628	32
32632	33
32633	33
32655	30
32656	30
32657	30
32658	30
32659	30
32660	30
32661	30
32662	30
32663	30
32664	30
32665	30
32666	30
32667	30
32668	30
32669	30
32670	30
32671	30
32672	30
32673	30
32674	30
32675	30
32676	30
32677	30
32678	30
32679	30
32680	30
32681	30
32682	30
32683	30
32685	33
32686	33
32687	33
32688	33
32689	33
32700	52
32701	52
32702	52
32703	52
32704	52
32705	52
32706	52
32707	52
32708	52
32709	52
32710	52
32711	52
32712	52
32713	52
32714	52
32715	52
32716	52
32717	52
32718	52
32719	52
32720	52
32725	52
32726	52
32727	52
32728	52
32729	52
32730	52
32731	52
32732	52
32733	52
32734	52
32735	52
32736	52
32737	52
32738	52
32739	52
32740	52
32741	52
32742	52
32743	52
32744	52
32745	52
32751	48
32752	48
32753	48
32754	48
32755	48
32756	48
32757	48
32758	48
32759	48
32760	48
32761	46
32762	48
32763	48
32764	48
32765	48
32766	46
32767	48
32768	48
32769	48
32770	48
32771	48
32772	48
32773	48
32774	48
32775	48
32776	48
32777	48
32778	48
32779	49
32780	49
32781	49
32782	49
32783	49
32784	49
32785	49
32786	49
32787	49
32788	49
32789	49
32790	49
32791	49
32792	49
32793	49
32794	49
32795	49
32796	49
32797	49
32798	49
32799	49
32800	49
32801	49
32802	49
32803	49
32804	49
32805	49
32806	49
32807	49
32808	49
32809	49
32810	49
32815	48
32816	48
32817	48
32818	48
32819	48
32820	48
32821	48
32822	48
32823	48
32824	48
32825	46
32826	48
32827	48
32828	48
32829	48
32830	46
32831	48
32832	48
32833	48
32834	48
32835	48
32836	48
32837	48
32838	48
32839	48
32840	48
32841	48
32842	48
32843	49
32844	49
32845	49
32846	49
32847	49
32848	49
32849	49
32850	49
32851	49
32852	49
32853	49
32854	49
32855	49
32856	49
32857	49
32858	49
32859	49
32860	49
32861	49
32862	49
32863	49
32864	49
32865	49
32866	49
32867	49
32868	49
32869	49
32870	49
32871	49
32872	49
32873	49
32874	49
33101	99
33102	104
33103	99
33104	104
33105	99
33106	104
33107	99
33108	105
33109	100
33110	105
33111	100
33112	105
33113	100
33114	105
33115	100
33116	105
33117	100
33118	105
33121	99
33122	104
33123	99
33124	104
33125	99
33126	105
33127	99
33128	105
33129	100
33130	105
33131	100
33132	105
33133	100
33134	105
33135	100
33136	105
33137	100
33138	105
33141	99
33142	104
33143	99
33144	104
33301	114
33302	120
33303	114
33304	120
33305	114
33306	120
33307	115
33308	121
33309	115
33310	121
33311	115
33312	121
33313	115
33314	121
33315	115
33316	121
33317	115
33318	121
33321	114
33322	120
33323	114
33324	120
33325	115
33326	121
33327	115
33328	121
33329	115
33330	121
33331	115
33332	121
33333	115
33334	121
33335	115
33336	121
33337	115
33338	121
33341	114
33342	120
33343	114
33344	120
33345	42
33346	42
33347	42
33348	42
33349	42
33350	42
33351	42
33352	42
33353	42
33354	42
34300	53
34301	53
34302	53
34303	53
34304	53
34305	53
34306	53
34307	53
34308	53
34309	53
34501	44
34502	44
34503	44
34504	44
34505	44
34506	44
34507	44
34508	44
34509	44
34510	44
34511	44
34512	44
34513	44
34514	44
34515	44
34516	44
34517	44

EDP Number Index

EDP NO.	PAGE
34518	44
34519	44
34520	44
34521	44
34522	44
34523	44
34524	44
34525	44
34526	44
34527	44
34528	44
34529	44
34530	44
34531	44
34532	44
34533	44
34534	44
34620	54
34621	54
34622	54
34623	54
34624	54
34625	54
34626	54
34627	54
34628	54
34630	55
34631	55
34632	55
34633	55
34634	55
34635	55
34636	55
34637	55
34638	55
34640	56
34641	56
34642	56
34643	56
34644	56
34645	56
34646	56
34647	56
34650	57
34651	57
34652	57
34653	57
34654	57
34655	57
34656	57
34657	57
34660	54
34661	54
34662	54
34663	54
34664	54
34665	54
34666	54
34667	54
34668	54
34669	55
34670	55
34671	55
34672	55
34673	55
34674	55
34675	55
34676	55
34677	55
34678	56
34679	56
34680	56
34681	56
34682	56
34683	56
34684	56
34685	56
34686	57
34687	57
34688	57
34689	57
34690	57
34691	57
34692	57
34693	57
34701	50
34702	50
34703	50
34704	50
34705	50
34706	50
34707	50
34708	50
34709	50
34710	50
34711	50
34712	50
34713	50
34714	50
34715	50
34716	50
34717	50
34718	50
34719	50
34720	50
34721	50
34722	50
34723	50
34724	50
34725	50
34726	50
34727	50
34728	50
34729	50
34730	50
34731	50
34732	50
34733	50
34734	50
34735	50
34736	50
34737	50
34738	50
34739	50
34740	50
34741	50
34742	50
34743	50
34744	50
34745	50
34746	50
34747	50
34748	50
34749	50
34750	50
34751	50
34752	50
34753	50
34754	50
34771	46
34772	46
34773	46
34774	46
34775	46
34776	46
34777	46
34778	46
34779	46
34780	46
34781	46
34782	46
34783	46
34784	46
34785	46
34786	46
34787	46
34789	46
34790	46
34791	46
34793	46
34794	46
34795	46
34796	46
34797	46
34798	46
34799	46
34800	46
34801	46
34802	46
34803	46
34804	46
34805	46
34806	46
34807	46
34808	46
34809	46
34811	46
34812	46
34813	46
34815	46
34816	46
34817	46
34818	46
35100	34
35101	34
35102	34
35103	34
35104	34
35105	34
35106	35
35107	35
35108	35
35109	35
35110	35
35111	35
35112	36
35113	36
35114	36
35115	36
35116	36
35117	36
35118	36
35119	36
35120	36
35121	36
35122	36
35123	36
35124	36
35125	36
35126	36
35127	37
35128	37
35129	37
35130	37
35131	37
35132	37
35133	37
35134	37
35135	37
35136	37
35137	37
35138	37
35139	37
35140	37
35141	37
35273	127
35275	127
35277	127
35278	127
35279	127
35280	127
35281	127
35282	127
35283	127
35285	127
35287	127
35289	127
35291	127
35293	127
35295	127
35297	127
35300	127
35301	127
35302	127
35303	127
35304	127
35305	127
35306	127
35307	127
35308	127
35309	127
35310	127
35311	127
35312	127
35313	127
35314	127
35315	127
35473	112
35475	112
35477	112
35478	112
35479	112
35480	112
35481	112
35482	112
35483	112
35485	112
35487	112
35489	112
35491	112
35493	112
35495	112
35497	112
35500	112
35501	112
35502	112
35503	112
35504	112
35505	112
35506	112
35507	112
35508	112
35509	112
35510	112
35511	112
35512	112
35513	112
35514	112
35515	112
36106	132
36107	132
36108	132
36109	132
36110	132
36111	132
36112	132
36113	132
36114	132
36116	132
36117	132
36118	132
36120	132
36121	132
36124	132
36125	132
36126	132
36128	132
36129	132
36130	132
36140	41
36141	41
36142	41
36143	41
36206	133
36207	133
36208	133
36209	133
36210	133
36211	133
36212	133
36213	133
36214	133
36216	133
36217	133
36218	133
36220	133
36221	133
36222	132
36222	133
36224	133
36225	133
36226	133
36228	133
36229	133
36230	133
36344	21
36345	21
36346	21
36347	21
36348	21
36349	21
36350	21
36351	21
36352	21
36353	21
36354	21
36355	21
36356	21
36357	21
36358	21
36359	21
36361	21
36370	14
36371	14
36372	14
36373	14
36374	14
36375	14
36376	14
36378	15
36380	15
36381	15
36383	15
36384	15
36385	15
36386	15
36387	15
36388	15
36389	15
36390	15
36391	15
36392	15
36393	15
36404	19
36406	19
36408	19
36410	19
36416	19
36418	19
36420	19
36422	19
36424	19
36426	19
36428	19
36430	19
36432	19
36436	19
36440	19
36442	19
36444	19
36450	17
36452	17
36456	17
36460	17
36462	17
36466	17
36470	17
36472	17
36474	17
36480	18
36482	18
36486	18
36500	18
36502	18
36504	18
36505	23
36506	23
36507	23
36508	23
36509	23
36511	23
36513	23
36515	23
36517	23
36519	23
36520	23
36530	19
36531	19
36532	19
36533	19
36534	19
36535	19
36536	19
36537	19
36538	19
36539	21
36540	21
36541	21
36542	21
36543	21
36544	21
36545	21
36546	21
36547	21
36555	24
36556	24
36557	24
36558	24
36559	24
36560	24
36561	24
36570	24
36571	24
36572	24
36573	24
36574	24
36575	24
36576	24
36577	24
36578	24
36590	21
36591	21
36592	21
36596	19
36597	19
36598	19
36599	14
36600	14
36601	14
36602	15
36603	15
36604	15

EDP Number Index

EDP NO.	PAGE
36605	15
36610	15
36611	15
36612	15
36613	15
36614	15
36615	15
36616	24
36617	24
36618	24
36620	38
36621	38
36622	38
36623	38
36624	38
36625	38
36626	38
36627	39
36628	39
36629	39
36630	39
36631	39
36632	39
36633	39
36634	39
36635	39
36636	39
36637	39
36638	39
36639	39
36640	39
36641	39
36701	14
36702	14
36704	15
36706	15
36707	15
36709	15
36710	15
36711	15
36712	15
36713	15
36714	15
36715	15
36716	15
36717	15
36718	15
36719	15
36722	14
36723	14
36724	14
36725	14
36727	14
36729	15
36731	15
36733	15
36736	14
36738	14
36740	15
36742	15
36744	15
36780	25
36781	25
36782	25
36783	25
36784	25
36785	25
36786	25
36787	25
36788	25
36789	25
36790	25
36791	25
36792	25
36793	25
36804	15
36805	15
36806	15
36807	15
36808	15
36809	15
36810	15
36811	15
36812	15
36813	15
36814	15
36815	15
36816	15
36817	15
36818	15
36819	15
36820	15
36821	15
36822	15
36823	15
36824	15
36825	15
36826	19
36827	19
36828	19
36829	19
36830	19
36846	21
36847	21
36848	21
36849	21
36850	21
36851	14
36852	14
36853	14
36854	14
36855	14
36856	14
36857	14
36858	15
36859	15
36860	15
36861	15
36862	15
36863	15
36864	14
36865	14
36866	15
36867	15
36868	15
36869	15
36870	15
36871	15
36872	14
36873	14
38001	109
38002	109
38003	109
38004	109
38009	109
38010	109
38011	109
38012	109
38013	109
38014	109
38019	109
38020	109
38021	109
38022	109
38023	109
38024	109
38025	109
38026	109
38031	109
38032	109
38033	109
38034	109
38035	109
38036	109
38037	109
38038	109
38045	109
38046	109
38047	109
38048	109
38049	109
38050	109
38051	109
38052	109
38059	109
38060	109
38061	109
38062	109
38063	109
38064	109
38065	109
38066	109
38067	109
38068	109
38073	109
38074	109
38075	109
38076	109
38077	109
38078	109
38079	109
38080	109
38081	109
38082	109
38083	109
38084	109
38087	109
38088	109
38089	109
38090	109
38091	110
38092	110
38093	110
38094	110
38095	110
38096	110
38097	110
38098	110
38099	110
38100	110
38101	110
38102	110
38103	110
38104	110
38105	110
38106	110
38107	110
38108	110
38109	110
38110	110
38111	110
38112	110
38113	110
38114	110
38115	109
38116	109
38117	109
38118	109
38119	109
38120	109
38121	109
38122	109
38123	109
38124	109
38125	109
38126	109
38127	109
38128	109
38129	109
38130	109
38131	109
38132	109
38133	109
38134	109
38135	109
38136	109
38137	109
38138	109
38139	109
38140	109
38141	109
38142	109
38143	109
38144	109
38145	110
38146	110
38147	110
38148	110
38149	110
38150	110
38151	110
38152	110
38153	110
38154	110
38155	110
38156	110
38157	109
38158	109
38159	109
38160	109
38161	109
38162	109
38163	109
38164	109
38165	109
38166	109
38167	109
38168	109
38169	109
38170	109
38171	109
38172	109
38173	109
38174	109
38175	109
38176	109
38177	109
38178	109
38179	109
38180	109
38181	109
38182	109
38183	109
38184	109
38185	109
38186	109
38187	110
38188	110
38189	110
38190	110
38191	110
38192	110
38193	110
38194	110
38195	110
38196	110
38197	110
38198	110
38201	126
38202	126
38203	126
38204	126
38209	126
38210	126
38211	126
38212	126
38213	126
38214	126
38219	126
38220	126
38221	126
38222	126
38223	126
38224	126
38225	126
38226	126
38231	126
38232	126
38233	126
38234	126
38235	126
38236	126
38237	126
38238	126
38245	126
38246	126
38247	126
38248	126
38249	126
38250	126
38251	126
38252	126
38259	126
38260	126
38261	126
38262	126
38263	126
38264	126
38265	126
38266	126
38267	126
38268	126
38273	126
38274	126
38275	126
38276	126
38277	126
38278	126
38279	126
38280	126
38281	126
38282	126
38283	126
38284	126
38287	126
38288	126
38289	126
38290	126
38291	126
38292	126
38293	126
38294	126
38295	126
38296	126
38297	126
38298	126
38299	126
38300	126
38301	126
38302	126
38303	126
38304	126
38305	126
38306	126
38307	126
38308	126
38309	126
38310	126
38311	126
38312	126
38313	126
38314	126
38315	126
38316	126
38317	126
38318	126
38319	126
38320	126
38321	126
38322	126
38323	126
38324	126
38325	126
38326	126
38327	126
38328	126
38329	126
38330	126
38331	126
38332	126
38333	126
38334	126
38335	126
38336	126
38337	126
38338	126
38339	126
38340	126
38341	126
38342	126
38343	126
38344	126
38345	126
38346	126
38347	126
38348	126
38349	126
38350	126
38351	126
38352	126
38353	126
38354	126
38355	126
38356	126
38357	126
38358	126
38359	126
38360	126
38361	126
38362	126
38363	126
38364	126
38365	126
38366	126
38367	126
38368	126
38369	126
38370	126
38371	126
38372	126
38373	126
38374	126
38375	126
38376	126
38377	126
38378	126
38379	126
38380	126
38381	126
38382	126
38383	126
38384	126
38385	126
38386	126
38387	126
38388	126
38389	126
38390	126
38391	126
38392	126
38393	126
38394	126

EDP Number Index

EDP NO.	PAGE
38395	126
38396	126
38397	126
38398	126
38490	18
38492	18
38496	18
39001	99
39002	104
39003	99
39004	104
39005	99
39006	104
39007	99
39008	104
39009	99
39010	104
39011	99
39012	104
39013	99
39014	104
39015	99
39016	104
39017	99
39018	104
39019	99
39020	104
39021	99
39022	104
39023	99
39024	104
39025	99
39026	104
39027	99
39028	104
39029	99
39030	104
39031	99
39032	104
39033	99
39034	104
39035	99
39036	104
39037	99
39038	104
39039	99
39040	104
39041	99
39042	105
39043	99
39044	105
39045	99
39046	105
39047	99
39048	105
39049	99
39050	105
39051	100
39052	105
39053	100
39054	105
39055	100
39056	105
39057	100
39058	105
39059	100
39060	105
39061	100
39062	105
39063	100
39064	105
39065	100
39066	105
39067	100
39068	105
39069	100
39070	105
39071	100
39072	105
39073	100
39074	105
39075	100
39076	105
39077	99
39078	104
39089	100
39089	138
39090	105
39090	138
39101	99
39102	104
39103	99
39104	104
39105	99
39106	104
39107	99
39108	104
39109	138
39109	99
39110	104
39111	99
39112	104
39113	99
39114	104
39115	99
39116	104
39117	99
39118	104
39119	99
39120	104
39121	99
39122	104
39123	99
39124	104
39125	99
39126	104
39127	99
39128	104
39129	99
39130	104
39131	99
39132	104
39133	99
39134	104
39135	99
39136	104
39137	99
39138	104
39139	99
39140	104
39141	99
39142	105
39143	99
39144	105
39145	99
39146	105
39147	99
39148	105
39149	99
39150	105
39151	100
39152	105
39153	100
39154	105
39155	100
39156	105
39157	100
39158	105
39159	100
39160	105
39161	100
39162	105
39163	100
39164	105
39165	100
39166	105
39167	100
39168	105
39169	100
39170	105
39171	100
39172	105
39173	100
39174	105
39175	100
39176	105
39177	99
39178	104
39189	100
39189	138
39190	105
39208	134
39208	135
39209	134
39209	135
39210	134
39210	135
39211	134
39211	135
39212	134
39212	135
39213	134
39213	135
39214	134
39214	135
39215	134
39215	135
39216	134
39216	135
39217	134
39217	135
39218	134
39218	135
39219	134
39219	135
39220	134
39220	135
39221	134
39221	135
39222	134
39222	135
39223	134
39223	135
39224	134
39224	135
39225	134
39225	135
39226	134
39226	135
39227	134
39227	135
39228	134
39228	135
39229	134
39229	135
39230	134
39230	135
39231	134
39231	135
39235	134
39235	135
39240	134
39240	135
39247	134
39247	135
39250	134
39250	135
39255	134
39255	135
39260	134
39260	135
39301	114
39302	120
39303	114
39304	120
39305	114
39306	120
39307	114
39308	120
39309	114
39310	120
39311	114
39312	120
39313	114
39314	120
39315	114
39316	120
39317	114
39318	120
39319	114
39320	120
39321	114
39322	120
39323	114
39324	120
39325	114
39326	120
39327	114
39328	120
39329	114
39330	120
39331	114
39332	120
39333	114
39334	120
39335	114
39336	120
39337	114
39338	120
39339	114
39340	120
39341	115
39342	121
39343	115
39344	121
39345	115
39346	121
39347	115
39348	121
39349	115
39350	121
39351	115
39352	121
39353	115
39354	121
39355	115
39356	121
39357	115
39358	121
39359	115
39360	121
39361	115
39362	121
39363	115
39364	121
39365	115
39366	121
39367	115
39368	121
39369	115
39370	121
39371	115
39372	121
39373	115
39374	121
39375	115
39376	121
39377	114
39378	120
39389	115
39389	138
39390	121
39390	138
39501	114
39502	120
39503	114
39504	120
39505	114
39506	120
39507	114
39508	120
39509	114
39510	120
39511	114
39512	120
39513	114
39514	120
39515	114
39516	120
39517	114
39518	120
39519	114
39520	120
39521	114
39522	120
39523	114
39524	120
39525	114
39526	120
39527	114
39528	120
39529	114
39530	120
39531	114
39532	120
39533	114
39534	120
39535	114
39536	120
39537	114
39538	120
39539	114
39540	120
39541	115
39542	121
39543	115
39544	121
39545	115
39546	121
39547	115
39548	121
39549	115
39550	121
39551	115
39552	121
39553	115
39554	121
39555	115
39556	121
39557	115
39558	121
39559	115
39560	121
39561	115
39562	121
39563	115
39564	121
39565	115
39566	121
39567	115
39568	121
39569	115
39570	121
39571	115
39572	121
39573	115
39574	121
39575	115
39576	121
39577	114
39578	120
39589	115
39589	138
39590	121
39590	138
39601	102
39602	107
39603	102
39604	107
39605	102
39606	107
39607	102
39608	107
39609	102
39610	107
39611	102
39612	107
39613	102
39614	107
39615	102
39616	107
39617	102
39618	107
39619	102
39620	107
39621	102
39622	107
39623	102
39624	107
39625	102
39626	107
39627	102
39628	107
39629	102
39630	107
39631	102
39632	107
39633	102
39634	107
39635	102
39636	107
39637	102
39638	107
39639	102
39640	107
39641	138
39642	107
39642	138
39651	118
39652	124
39653	118
39654	124
39655	118
39656	124
39657	118
39658	124
39659	118
39660	124
39661	118
39662	124
39663	118
39664	124
39665	118
39666	124
39667	118
39668	124
39669	118
39671	118
39672	124
39673	118
39674	124
39675	118

EDP Number Index

EDP NO.	PAGE
39676	124
39677	118
39678	124
39679	118
39680	124
39681	118
39682	124
39683	118
39684	124
39685	118
39686	124
39687	118
39688	124
39689	118
39690	124
39691	118
39691	138
39692	124
39692	138
39701	128
39703	128
39705	128
39707	128
39709	128
39711	128
39713	128
39715	128
39717	128
39719	128
39721	128
39723	128
39725	128
39727	128
39729	128
39731	128
39733	128
39735	128
39737	128
39739	128
39741	128
39743	128
39745	128
39747	128
39749	128
39751	128
39753	128
39755	128
39757	128
39759	128
39760	124
39761	128
39763	128
39765	128
39767	128
39769	128
39771	128
39773	128
39775	128
39777	128
39789	138
40000	111
40001	111
40003	111
40004	111
40005	111
40007	111
40009	111
40010	111
40011	111
40012	111
40015	111
40016	111
40017	111
40019	111
40020	111
40021	111
40023	111
40024	111
40025	111
40028	111
40030	111
40031	111
40032	111
40035	111
40037	111
40038	111
40039	111
40105	101
40106	106
40109	101
40110	106
40113	101
40114	106
40117	101
40118	106
40121	101
40122	106
40125	101
40126	106
40129	101
40130	106
40133	101
40134	106
40137	101
40138	106
40141	101
40142	106
40145	101
40146	106
40149	101
40150	106
40153	101
40154	106
40157	101
40158	106
40161	101
40162	106
40165	98
40166	106
40169	101
40170	106
40173	101
40174	106
40177	101
40178	106
40181	101
40182	106
40185	101
40186	106
40305	116
40306	122
40309	116
40310	122
40313	116
40314	122
40317	116
40318	122
40321	116
40322	122
40325	116
40326	122
40329	116
40330	122
40333	116
40334	122
40337	116
40338	122
40341	116
40342	122
40345	116
40346	122
40349	116
40350	122
40353	116
40354	122
40357	116
40358	122
40361	116
40362	122
40365	116
40366	122
40369	116
40370	122
40373	116
40374	122
40377	116
40378	122
40381	116
40382	122
40385	116
40386	122
40505	129
40506	131
40509	129
40510	131
40513	129
40514	131
40517	129
40518	131
40521	129
40522	131
40525	129
40526	131
40529	129
40530	131
40533	129
40534	131
40537	129
40538	131
40541	129
40542	131
40545	129
40546	131
40549	129
40550	131
40553	129
40554	131
40557	129
40558	131
40561	129
40562	131
40565	129
40566	131
40569	129
40570	131
40573	129
40574	131
40577	129
40578	131
40581	129
40582	131
40585	129
40586	131
41405	103
41406	108
41409	103
41410	108
41413	103
41414	108
41417	103
41418	108
41421	103
41422	108
41425	103
41426	108
41429	103
41430	108
41433	103
41434	108
41437	103
41438	108
41441	103
41442	108
41445	103
41446	108
41449	103
41450	108
41453	103
41454	108
41457	103
41458	108
41461	103
41462	108
41465	103
41466	108
41505	119
41506	125
41509	119
41510	125
41513	119
41514	125
41517	119
41518	125
41521	119
41522	125
41525	119
41526	125
41529	119
41530	125
41533	119
41534	125
41537	119
41538	125
41541	119
41542	125
41545	119
41546	125
41549	119
41550	125
41553	119
41554	125
41557	119
41558	125
41561	119
41562	125
41565	119
41566	125
41605	98
41609	98
41613	98
41617	98
41621	98
41625	98
41629	98
41633	98
41637	98
41641	98
41645	98
41649	98
41653	98
41657	98
41661	98
41665	101
41705	113
41709	113
41713	113
41717	113
41721	113
41725	113
41729	113
41733	113
41737	113
41741	113
41745	113
41749	113
41753	113
41757	113
41761	113
41765	113
42606	31
42607	31
42608	31
42609	31
42610	31
42611	31
42612	31
42613	31
42614	31
42615	31
42616	31
42617	31
42618	31
42619	31
42620	31
42621	31
42622	31
42623	31
42624	31
42625	31
42718	16
42722	16
43101	101
43102	106
43103	101
43104	106
43105	101
43106	106
43107	101
43108	106
43115	101
43116	106
43125	101
43126	106
43135	101
43136	106
43145	101
43146	106
43155	101
43156	106
43165	101
43166	106
43175	101
43176	106
43185	101
43186	106
43195	101
43196	106
43301	116
43302	122
43303	116
43304	122
43305	116
43306	122
43307	116
43308	122
43315	116
43316	122
43325	116
43326	122
43335	116
43336	122
43345	116
43346	122
43355	116
43356	122
43365	116
43366	122
43375	116
43376	122
43385	116
43386	122
43395	116
43396	122
43445	42
43446	42
43447	42
43448	42
43449	42
43450	42
43451	42
43452	42
43453	42
43501	129
43502	131
43503	129
43504	131
43505	129
43506	131
43507	129
43508	131
43515	129
43516	131
43525	129
43526	131
43535	129
43536	131
43545	129
43546	131
43555	129
43556	131
43565	129
43566	131
43575	129
43576	131
43585	129
43586	131
43595	129
43596	131
43900	123
43901	123
43902	123
43903	123
43904	123
43905	123
43906	123
43907	123
43908	123
43909	123
43910	117
43911	117
43912	117
43913	117
43914	117
43915	117
43916	117
43917	117
43918	117
43919	117
43920	117
43921	117
43922	117
43923	117
43924	117
43925	117
43926	117
43927	117
43928	117
43929	117
43930	117
43931	117
43932	117
43933	117
43934	117
43935	117
43936	117
43937	117
43938	117
43939	117
43950	117
43951	117
43952	117
43953	117

EDP Number Index

EDP NO.	PAGE
43954	117
43955	117
43956	117
43957	117
43958	117
43959	117
44300	53
44301	53
44302	53
44303	53
44304	53
44305	53
44306	53
44307	53
44308	53
44309	53
44505	45
44506	45
44509	45
44510	45
44513	45
44514	45
44517	45
44518	45
44521	45
44522	45
44525	45
44526	45
44529	45
44530	45
44533	45
44534	45
44537	45
44538	45
44541	45
44542	45
44545	45
44546	45
44550	54
44551	54
44552	54
44553	54
44554	54
44555	54
44556	54
44557	54
44558	54
44559	54
44560	54
44561	56
44562	56
44563	56
44564	56
44565	56
44566	56
44570	55
44571	55
44572	55
44573	55
44574	55
44575	55
44576	55
44577	55
44578	55
44579	55
44580	55
44581	57
44582	57
44583	57
44584	57
44585	57
44586	57
44587	54
44588	54
44589	54
44590	54
44591	54
44592	54
44593	54
44594	54
44595	54
44596	54
44597	54
44598	55
44599	55
44600	55
44601	55
44602	55
44603	55
44604	55
44605	55
44606	55
44607	55
44608	55
44609	56
44610	56
44611	56
44612	56
44613	56
44614	56
44615	57
44616	57
44617	57
44618	57
44619	57
44620	57
44701	51
44702	51
44703	51
44705	51
44708	51
44711	51
44714	51
44715	51
44716	51
44717	51
44719	51
44722	51
44725	51
44728	51
44769	47
44770	47
44771	47
44772	47
44773	47
44774	47
44775	47
44776	47
44777	47
44778	47
44779	47
44780	47
44781	47
44782	47
44783	47
44784	47
44785	47
44786	47
44787	47
44788	47
44789	47
44790	47
44791	47
44792	47
44793	47
44794	47
44795	47
44796	47
44797	47
44798	47
44799	47
44800	47
44801	47
44802	47
44803	47
44804	47
44805	47
44806	47
44807	47
44808	47
45100	34
45101	34
45102	34
45103	34
45104	34
45105	34
45106	35
45107	35
45108	35
45109	35
45110	35
45111	35
45112	36
45113	36
45114	36
45115	36
45116	36
45117	36
45118	36
45119	36
45120	36
45121	36
45122	36
45123	36
45124	36
45125	36
45126	36
45127	37
45128	37
45129	37
45130	37
45131	37
45132	37
45133	37
45134	37
45135	37
45136	37
45137	37
45138	37
45139	37
45140	37
45141	37
45277	127
45279	127
45281	127
45283	127
45285	127
45287	127
45289	127
45291	127
45293	127
45295	127
45297	127
45299	127
45477	112
45478	112
45479	112
45480	112
45481	112
45482	112
45483	112
45484	112
45485	112
45486	112
45487	112
45488	112
45489	112
45490	112
45491	112
45492	112
45493	112
45494	112
45495	112
45496	112
45497	112
45498	112
45499	112
45500	112
46106	132
46107	132
46108	132
46109	132
46110	132
46111	132
46112	132
46113	132
46114	132
46116	132
46117	132
46118	132
46120	132
46121	132
46122	132
46128	132
46129	132
46130	132
46131	132
46132	132
46133	132
46140	41
46141	41
46142	41
46143	41
46206	133
46207	133
46208	133
46209	133
46210	133
46211	133
46212	133
46213	133
46214	133
46216	133
46217	133
46218	133
46220	133
46221	133
46222	133
46228	133
46229	133
46230	133
46231	133
46232	133
46233	133
46343	22
46344	22
46345	22
46346	22
46347	22
46348	22
46349	22
46350	22
46351	22
46354	22
46355	22
46356	22
46357	20
46358	20
46359	20
46360	20
46362	20
46364	20
46366	20
46368	20
46370	20
46372	20
46374	20
46376	20
46450	24
46451	24
46452	24
46453	24
46454	24
46455	24
46456	24
46457	24
46458	24
46459	24
46460	24
46461	24
46462	24
46463	24
46464	24
46465	24
46466	24
46467	24
46468	24
46469	24
46470	24
46471	24
46472	24
46473	24
46474	24
46475	24
46476	24
46477	24
46478	24
46479	24
46480	24
46481	24
46494	16
46495	16
46497	16
46498	16
46506	20
46507	20
46508	20
46509	20
46510	20
46518	22
46519	22
46520	22
46521	22
46522	22
46560	25
46561	25
46562	25
46563	25
46564	25
46565	25
46566	25
46567	25
46568	25
46620	38
46621	38
46622	38
46623	38
46624	38
46625	38
46626	38
46627	39
46629	39
46632	39
46636	39
46638	39
46640	39
46641	39
46643	39
46645	39
46647	39
46649	39
46651	39
46654	39
46656	39
46658	39
46737	17
46821	17
46822	17
46823	17
46824	17
46825	17
46826	17
46827	17
46828	17
46829	17
46830	17
46831	17
46832	17
46833	17
46834	17
46835	17
46836	17
46838	17
46839	17
46840	17
46841	17
46849	16
46850	16
46851	16
46852	16
46853	16
46854	16
46855	16
46856	16
46857	16
46858	16
46859	16
46860	16
46861	16
46862	16
46863	16
46864	16
46865	16
46866	16
46880	16
46881	16
46882	16
46884	16
46886	16
46887	16
46889	16
46890	16
46891	16
46893	16
46894	16
46895	16
46896	16
46898	16
46899	16
46900	16
46903	16
46904	16
46905	16
46909	16
46910	16
46911	16
46912	16
46913	16
46914	16
46915	16
46916	16
46917	16
46918	16
46919	16
46920	16
46921	16
46922	16
46923	16
46924	16
46925	16
46926	16
46927	16

EDP Number Index

EDP NO.	PAGE
48500	101
48501	101
48502	101
48503	101
48504	101
48505	101
48506	101
48507	101
48508	101
48509	101
48510	101
48511	101
48512	101
48513	101
48514	101
48515	101
48516	101
48517	101
48518	101
48519	101
48520	101
48522	101
48523	101
48524	101
48525	101
48526	101
48527	101
48528	101
48529	101
48530	101
48531	101
48532	101
48533	101
48534	101
48535	101
48536	101
48537	101
48538	101
48539	101
48540	101
48541	101
48542	101
48543	101
48544	101
48545	101
48546	101
48547	101
48548	101
48549	101
48550	101
48551	101
48552	101
48553	101
48554	101
48555	101
48556	101
48557	101
48558	101
48559	101
48560	101
48561	101
48562	101
48563	101
48564	106
48565	106
48566	106
48567	106
48568	106
48569	106
48570	106
48571	106
48572	106
48573	106
48574	106
48575	106
48576	106
48577	106
48578	106
48579	106
48580	106
48581	106
48582	106
48583	106
48584	106
48586	106
48587	106
48588	106
48589	106
48590	106
48591	106
48592	106
48593	106
48594	106
48595	106
48596	106
48597	106
48598	106
48599	106
48600	106
48601	106
48602	106
48603	106
48604	106
48605	106
48606	106
48607	106
48608	106
48609	106
48610	106
48611	106
48612	106
48613	106
48614	106
48615	106
48616	106
48617	106
48618	106
48619	106
48620	106
48621	106
48622	106
48623	106
48624	106
48625	106
48626	106
48627	106
48628	116
48629	116
48630	116
48631	116
48632	116
48633	116
48634	116
48635	116
48636	116
48637	116
48638	116
48639	116
48640	116
48641	116
48642	116
48643	116
48644	116
48645	116
48646	116
48647	116
48648	116
48650	116
48651	116
48652	116
48653	116
48654	116
48655	116
48656	116
48657	116
48658	116
48659	116
48660	116
48661	116
48662	116
48663	116
48664	116
48665	116
48666	116
48667	116
48668	116
48669	116
48670	116
48671	116
48672	116
48673	116
48674	116
48675	116
48676	116
48677	116
48678	116
48679	116
48680	116
48681	116
48682	116
48683	116
48684	116
48685	116
48686	116
48687	116
48688	116
48689	116
48690	116
48691	116
48692	122
48693	122
48694	122
48695	122
48696	122
48697	122
48698	122
48699	122
48700	122
48701	122
48702	122
48703	122
48704	122
48705	122
48706	122
48707	122
48708	122
48709	122
48710	122
48711	122
48712	122
48714	122
48715	122
48716	122
48717	122
48718	122
48719	122
48720	122
48721	122
48722	122
48723	122
48724	122
48725	122
48726	122
48727	122
48728	122
48729	122
48730	122
48731	122
48732	122
48733	122
48734	122
48735	122
48736	122
48737	122
48738	122
48739	122
48740	122
48741	122
48742	122
48743	122
48744	122
48745	122
48746	122
48747	122
48748	122
48749	122
48750	122
48751	122
48752	122
48753	122
48754	122
48755	122
48756	129
48757	129
48758	129
48759	129
48760	129
48761	129
48762	129
48763	129
48764	129
48765	129
48766	129
48767	129
48768	129
48769	129
48770	129
48771	129
48772	129
48773	129
48774	129
48775	129
48776	129
48778	129
48779	129
48780	129
48781	129
48782	129
48783	129
48784	129
48785	129
48786	129
48787	129
48788	129
48789	129
48790	129
48791	129
48792	129
48793	129
48794	129
48795	129
48796	129
48797	129
48798	129
48799	129
48800	129
48801	129
48802	129
48803	129
48804	129
48805	129
48806	129
48807	129
48808	129
48809	129
48810	129
48811	129
48812	129
48813	129
48814	129
48815	129
48816	129
48817	129
48818	129
48819	129
48820	131
48821	131
48822	131
48823	131
48824	131
48825	131
48826	131
48827	131
48828	131
48829	131
48830	131
48831	131
48832	131
48833	131
48834	131
48835	131
48836	131
48837	131
48838	131
48839	131
48840	131
48842	131
48843	131
48844	131
48845	131
48846	131
48847	131
48848	131
48849	131
48850	131
48851	131
48852	131
48853	131
48854	131
48855	131
48856	131
48857	131
48858	131
48859	131
48860	131
48861	131
48862	131
48863	131
48864	131
48865	131
48866	131
48867	131
48868	131
48869	131
48870	131
48871	131
48872	131
48873	131
48874	131
48875	131
48876	131
48877	131
48878	131
48879	131
48880	131
48881	131
48882	131
48883	131
48884	103
48885	103
48886	103
48887	103
48888	103
48889	103
48890	103
48891	103
48892	103
48893	103
48894	103
48895	103
48896	103
48897	103
48898	103
48899	103
48905	103
48906	103
48907	103
48908	103
48909	103
48910	103
48911	103
48912	103
48913	103
48914	103
48915	103
48916	103
48917	103
48918	103
48919	103
48920	103
48926	103
48927	103
48928	103
48929	103
48930	103
48931	103
48932	103
48933	103
48934	103
48935	103
48936	103
48937	103
48938	103
48939	103
48940	103
48941	103
48947	108
48948	108
48949	108
48950	108
48951	108
48952	108
48953	108
48954	108
48955	108
48956	108
48957	108
48958	108
48959	108
48960	108
48961	108
48962	108
48968	108
48969	108
48970	108
48971	108
48972	108
48973	108
48974	108
48975	108
48976	108
48977	108
48978	108
48979	108
48980	108
48981	108
48982	108
48983	108
48989	108
48990	108
48991	108
48992	108

EDP Number Index

EDP NO.	PAGE
48993	108
48994	108
48995	108
48996	108
48997	108
48998	108
48999	108
49000	108
49001	108
49002	108
49003	108
49004	108
49010	119
49011	119
49012	119
49013	119
49014	119
49015	119
49016	119
49017	119
49018	119
49019	119
49020	119
49021	119
49022	119
49023	119
49024	119
49025	119
49031	119
49032	119
49033	119
49034	119
49035	119
49036	119
49037	119
49038	119
49039	119
49040	119
49041	119
49042	119
49043	119
49044	119
49045	119
49046	119
49052	119
49053	119
49054	119
49055	119
49056	119
49057	119
49058	119
49059	119
49060	119
49061	119
49062	119
49063	119
49064	119
49065	119
49066	119
49067	119
49073	125
49074	125
49075	125
49076	125
49077	125
49078	125
49079	125
49080	125
49081	125
49082	125
49083	125
49084	125
49085	125
49086	125
49087	125
49088	125
49094	125
49095	125
49096	125
49097	125
49098	125
49099	125
49100	125
49101	125
49102	125
49103	125
49104	125
49105	125
49106	125
49107	125
49108	125
49109	125
49115	125
49116	125
49117	125
49118	125
49119	125
49120	125
49121	125
49122	125
49123	125
49124	125
49125	125
49126	125
49127	125
49128	125
49129	125
49130	125
49136	98
49137	98
49138	98
49139	98
49140	98
49141	98
49142	98
49143	98
49144	98
49145	98
49146	98
49147	98
49148	98
49149	98
49150	98
49151	98
49157	98
49158	98
49159	98
49160	98
49161	98
49162	98
49163	98
49164	98
49165	98
49166	98
49167	98
49168	98
49169	98
49170	98
49171	98
49172	98
49178	98
49179	98
49180	98
49181	98
49182	98
49183	98
49184	98
49185	98
49186	98
49187	98
49188	98
49189	98
49190	98
49191	98
49192	98
49193	98
49262	113
49263	113
49264	113
49265	113
49266	113
49267	113
49268	113
49269	113
49270	113
49271	113
49272	113
49273	113
49274	113
49275	113
49276	113
49277	113
49283	113
49284	113
49285	113
49286	113
49287	113
49288	113
49289	113
49290	113
49291	113
49292	113
49293	113
49294	113
49295	113
49296	113
49297	113
49298	113
49304	113
49305	113
49306	113
49307	113
49308	113
49309	113
49310	113
49311	113
49312	113
49313	113
49314	113
49315	113
49316	113
49317	113
49318	113
49319	113
49388	101
49389	101
49390	101
49391	101
49392	101
49393	101
49394	101
49395	101
49396	101
49397	101
49398	101
49399	101
49400	101
49401	101
49402	101
49403	101
49404	101
49405	101
49406	101
49407	101
49408	101
49409	101
49410	101
49411	101
49412	101
49413	101
49414	101
49415	101
49416	101
49417	101
49418	101
49419	101
49420	101
49421	101
49422	101
49423	101
49424	101
49425	101
49426	101
49427	116
49428	116
49429	116
49430	116
49431	116
49432	116
49433	116
49434	116
49435	116
49436	116
49437	116
49438	116
49439	116
49440	116
49441	116
49442	116
49443	116
49444	116
49445	116
49446	116
49447	116
49448	116
49449	116
49450	116
49451	116
49452	116
49453	116
49454	116
49455	116
49456	116
49457	116
49458	116
49459	116
49460	116
49461	116
49462	116
49463	116
49464	116
49465	116
49466	129
49467	129
49468	129
49469	129
49470	129
49471	129
49472	129
49473	129
49474	129
49475	129
49476	129
49477	129
49478	129
49479	129
49480	129
49481	129
49482	129
49483	129
49484	129
49485	129
49486	129
49487	129
49488	129
49489	129
49490	129
49491	129
49492	129
49493	129
49494	129
49495	129
49496	129
49497	129
49498	129
49499	129
49500	129
49501	129
49502	129
49503	129
49504	129
49505	106
49506	106
49507	106
49508	106
49509	106
49510	106
49511	106
49512	106
49513	106
49514	106
49515	106
49516	106
49517	106
49518	106
49519	106
49520	106
49521	106
49522	106
49523	106
49524	106
49525	106
49526	106
49527	106
49528	106
49529	106
49530	106
49531	106
49532	106
49533	106
49534	106
49535	106
49536	106
49537	106
49538	106
49539	106
49540	106
49541	106
49542	106
49543	106
49544	122
49545	122
49546	122
49547	122
49548	122
49549	122
49550	122
49551	122
49552	122
49553	122
49554	122
49555	122
49556	122
49557	122
49558	122
49559	122
49560	122
49561	122
49562	122
49563	122
49564	122
49565	122
49566	122
49567	122
49568	122
49569	122
49570	122
49571	122
49572	122
49573	122
49574	122
49575	122
49576	122
49577	122
49578	122
49579	122
49580	122
49581	122
49582	122
49583	131
49584	131
49585	131
49586	131
49587	131
49588	131
49589	131
49590	131
49591	131
49592	131
49593	131
49594	131
49595	131
49596	131
49597	131
49598	131
49599	131
49600	131
49601	131
49602	131
49603	131
49604	131
49605	131
49606	131
49607	131
49608	131
49609	131
49610	131
49611	131
49612	131
49613	131
49614	131
49615	131
49616	131
49617	131
49618	131
49619	131
49620	131
49621	131
49622	123
49623	123
49624	123
49625	123
49626	123
49627	123
49628	123
49629	123
49630	123
49631	123
49632	123
49633	123
49634	123
49635	123
49636	123
49637	123
49638	123
49639	123
49640	123
49641	123
49642	123
49643	123
49644	123
49645	123

EDP Number Index

EDP NO.	PAGE
49646	123
49647	123
49648	123
49649	123
49650	123
49651	123
49663	45
49664	45
49665	45
49666	45
49667	45
49668	45
49669	45
49670	45
49671	45
49672	45
49673	45
49674	45
49675	45
49676	45
49677	45
49678	45
49679	45
49680	45
49681	45
49682	45
49683	45
49684	45
49829	127
49830	127
49831	127
49832	127
49833	127
49834	127
49835	127
49836	127
49837	127
49838	127
49839	127
49840	127
50000	178
50001	178
50002	178
50003	178
50004	178
50005	178
50006	178
50007	178
50008	178
50009	178
50010	178
50011	178
50012	178
50013	178
50014	178
50015	178
50016	178
50017	178
50018	178
50019	178
50020	178
50021	178
50022	178
50023	178
50024	178
50025	178
50026	178
50027	178
50028	178
50029	178
50030	178
50031	178
51001	200
51002	200
51003	200
51004	200
51005	200
51006	200
51007	200
51008	200
51009	200
51010	200
51011	200
51012	200
51013	199
51014	199
51015	199
51016	199
51017	199
51018	199
51019	199
51020	199
51021	199
51022	199
51023	199
51024	199
51025	199
51026	199
51027	199
51028	199
51029	199
51030	199
51031	199
51032	199
51033	198
51034	198
51035	198
51036	198
51037	198
51038	198
51039	198
51040	198
51041	198
51042	198
51043	198
51044	198
51045	198
51046	198
51047	198
51048	198
51049	198
51050	198
51051	198
51052	198
51053	198
51104	198
51105	198
51106	198
51107	198
51108	199
51109	199
51110	199
51111	199
51112	199
51113	200
51114	200
51115	200
51117	201
51118	201
51119	201
51120	201
51121	201
51122	201
51123	202
51124	202
51125	202
51126	202
51127	202
51128	202
51129	202
51130	202
51131	202
51132	202
51201	200
51202	200
51203	200
51204	200
51205	200
51206	200
51207	201
51208	201
51209	201
51210	201
51211	201
51212	201
51213	201
51214	201
51215	201
51216	201
51217	201
51218	201
51219	201
51220	202
51221	202
51222	202
51223	202
51224	202
51225	202
51226	202
51269	163
51270	163
51271	163
51272	163
51273	163
51274	163
51275	163
51276	163
51277	163
51278	163
51279	163
51330	163
51331	163
51332	163
51333	163
51334	163
51335	163
51336	164
51337	164
51338	164
51339	164
51340	164
51341	164
51342	164
51343	165
51344	165
51345	165
51346	165
51347	165
51348	165
51349	165
51350	165
51351	165
51352	166
51353	166
51354	166
51355	166
51356	166
51357	166
51358	166
51359	166
51360	167
51361	167
51362	167
51363	167
51364	167
51365	167
51366	167
51367	167
51368	167
51369	167
51370	167
51371	167
51372	167
51373	167
51374	167
51375	167
51506	168
51507	168
51508	168
51509	168
51510	168
51511	168
51512	168
51513	168
51514	168
51515	168
51516	168
51517	168
51518	168
51519	168
51520	168
51521	168
51522	168
51523	168
51524	169
51525	169
51526	169
51527	169
51528	169
51529	169
51530	169
51531	169
51532	169
51533	169
51534	169
51535	169
51536	169
51537	169
51538	169
51539	169
51540	169
51541	169
51542	169
51543	169
51544	169
51545	169
51580	168
51581	168
51582	168
51583	168
51584	168
51585	168
51586	168
51587	168
51588	168
51589	168
51590	168
51591	168
51592	169
51593	169
51594	169
51595	169
51596	169
51601	164
51602	165
51603	165
51604	165
51606	165
51607	165
51608	165
51609	165
51610	165
51611	165
51612	165
51613	165
51614	165
51615	165
51616	166
51617	166
51618	166
51619	166
51620	166
51621	166
51622	166
51752	163
51753	163
51754	163
51755	163
51756	163
51757	163
51758	163
51759	163
51760	163
51761	163
51762	163
51763	163
51764	163
51765	163
51766	164
51767	164
51768	164
51769	164
51770	164
51771	164
51772	164
51773	164
51774	164
51775	164
51776	164
51777	164
51778	164
51779	164
51780	164
51781	164
51782	164
51783	167
51784	167
51785	167
51786	167
51787	167
51788	167
51789	167
51790	167
51791	167
51792	167
51801	174
51802	174
51803	174
51804	174
51805	174
51806	174
51807	174
51808	174
51809	175
51810	175
51811	175
51812	175
51813	175
51814	175
51815	175
51816	175
51817	176
51818	176
51819	176
51820	176
51821	176
51822	176
51823	176
51824	176
51825	177
51826	177
51827	177
51828	177
51829	177
51830	177
51831	177
51832	177
51833	177
51834	177
51835	177
51836	177
51901	170
51902	170
51903	170
51904	170
51905	170
51906	170
51907	170
51908	170
51910	170
51912	171
51913	171
51914	171
51915	171
51916	171
51918	171
51919	171
51920	171
51921	172
51922	172
51923	172
51924	172
51925	172
51926	172
51927	172
51928	172
51929	173
51930	173
51932	173
51933	173
51934	173
51935	173
51937	173
51938	173
51939	173
51940	173
51941	173
51942	173
53001	210
53002	210
53003	210
53004	210
53005	210
53006	210
53007	210
53008	210
53009	210
53010	210
53011	210
53012	210
53013	210
53014	210
53015	210
53016	210
53017	210
53018	209
53019	209
53020	209
53021	209
53022	209
53023	209
53024	209
53025	209
53026	209
53027	209
53028	209
53029	209
53030	209
53031	209
53032	209
53033	209
53034	209

EDP Number Index

EDP NO.	PAGE
53035	209
53036	209
53107	209
53108	209
53109	209
53110	209
53111	209
53112	210
53113	210
53114	210
53115	210
53116	211
53117	211
53118	211
53119	211
53120	211
53121	211
53122	212
53123	212
53124	212
53125	212
53126	212
53127	212
53128	213
53129	213
53130	213
53131	213
53132	213
53133	213
53134	213
53135	213
53136	213
53137	213
53201	210
53202	211
53203	211
53204	211
53206	211
53207	211
53208	211
53209	211
53210	211
53211	211
53212	211
53213	211
53214	211
53215	211
53216	211
53217	212
53218	212
53219	212
53220	212
53221	212
53222	212
53223	212
53224	212
53225	212
53226	212
56001	207
56002	207
56003	207
56004	207
56005	207
56006	207
56007	207
56008	207
56009	207
56010	207
56011	207
56012	207
56013	207
56014	207
56015	207
56016	207
56017	207
56018	207
56019	207
56020	207
56021	207
56022	207
56023	207
56024	207
56025	207
56026	207
56027	207
56028	207
56029	207
56030	207
56031	207
56032	206
56033	206
56034	206
56035	206
56036	206
56037	206
56038	206
56039	206
56040	206
56041	206
56042	206
56043	206
56044	206
56045	206
56046	206
56047	206
56048	206
56049	206
56050	206
56051	206
56052	206
56053	206
56054	206
56055	206
56056	206
56057	206
56058	206
56059	206
56060	206
56103	206
56104	206
56105	206
56106	206
56107	206
56108	207
56109	207
56110	207
56111	207
56112	207
56113	207
56114	207
56115	207
56116	208
56117	208
56118	208
56119	208
56120	208
56121	208
56122	208
56123	208
56124	208
56125	208
56126	208
56127	208
56128	208
56129	208
56130	208
56131	208
56132	208
56135	206
56136	206
56137	206
56138	206
56139	206
56140	207
56141	207
56142	207
56143	207
56144	207
56145	207
56146	207
56147	207
56148	208
56149	208
56150	208
56151	208
56152	208
56153	208
56154	208
56155	208
56156	208
56157	208
56158	208
56159	208
56160	208
56161	208
56162	208
56163	208
56164	208
56210	207
56211	207
56212	207
56213	207
56214	207
56215	207
56216	207
56217	207
56218	207
56219	207
56220	207
56221	207
56222	207
56223	207
56224	207
56225	207
56226	207
56227	207
56228	207
56229	207
56230	207
56231	207
56232	207
56233	207
56234	207
56235	207
56236	207
56237	207
56238	207
56239	207
56240	207
56241	206
56242	206
56243	206
56244	206
56245	206
56246	206
56247	206
56248	206
56249	206
56250	206
56251	206
56252	206
56253	206
56254	206
56255	206
56256	206
56257	206
56258	206
56259	206
56260	206
56261	206
56262	206
56263	206
56264	206
56265	206
56266	206
56267	206
56268	206
56269	206
57005	221
57006	221
57007	221
57008	221
57009	221
57010	221
57011	221
57012	221
57015	221
57016	221
57017	221
57018	221
57019	221
57020	221
57021	221
57022	221
57075	221
57076	197
57077	197
57078	197
57079	197
57080	197
57081	197
57082	197
57083	197
57084	197
57085	197
57086	197
57087	197
57088	197
57089	197
57090	197
57091	197
57092	197
57093	197
57094	197
57095	197
57096	197
57097	197
57098	197
57099	197
57100	197
57101	197
57102	197
57103	197
57104	197
57105	197
57106	198
57107	198
57108	198
57109	198
57110	198
57111	198
57112	198
57113	198
57114	198
57115	198
57116	198
57117	198
57118	198
57119	198
57120	198
57121	198
57122	198
57123	198
57124	198
57125	198
57126	198
57127	198
57128	198
57129	198
57130	198
57131	199
57132	199
57133	199
57134	199
57135	199
57136	199
57137	199
57138	199
57139	199
57140	199
57141	199
57142	199
57143	199
57144	199
57145	199
57146	199
57147	199
57148	199
57149	199
57150	199
57151	199
57152	199
57153	199
57154	199
57155	199
57156	200
57157	200
57158	200
57159	200
57160	200
57161	200
57162	200
57163	200
57164	200
57165	200
57166	200
57167	200
57168	200
57169	200
57170	200
57171	200
57172	200
57173	200
57174	200
57176	200
57177	200
57178	201
57179	201
57180	201
57181	201
57182	201
57183	201
57184	201
57185	201
57186	201
57187	201
57188	201
57189	201
57190	201
57191	201
57192	201
57193	201
57194	201
57195	201
57196	201
57197	202
57198	202
57199	202
57200	202
57201	202
57202	202
57203	202
57204	202
57205	202
57206	202
57207	202
57208	202
57209	202
57210	202
57211	202
57212	202
57213	202
57351	202
58011	209
58012	209
58013	209
58014	209
58015	209
58016	209
58017	209
58018	209
58019	209
58020	209
58021	209
58022	209
58023	209
58024	209
58025	209
58026	209
58027	209
58028	209
58029	209
58030	209
58031	209
58032	209
58033	209
58034	209
58035	210
58036	210
58037	210
58038	210
58039	210
58040	210
58041	210
58042	210
58043	210
58044	210
58045	210
58046	210
58047	210
58048	210
58049	210
58050	210
58051	210
58052	210
58053	210
58054	210
58055	210
58056	210
58057	211
58058	211
58059	211
58061	211
58062	211
58063	211
58064	211
58065	211
58066	211
58067	211
58068	211
58069	211
58070	211
58071	211
58072	211
58073	211
58074	211
58075	211
58076	211
58077	211
58078	212
58079	212
58080	212

EDP Number Index

EDP NO.	PAGE
58081	212
58082	212
58083	212
58084	212
58085	212
58086	212
58087	212
58088	212
58089	212
58090	212
58091	212
58092	212
58093	212
58094	213
58095	213
58096	213
58097	213
58098	213
58099	213
58100	213
58101	213
58102	213
58103	213
61011	198
61013	198
61015	199
61017	199
61019	199
61021	199
61023	200
61025	200
61027	200
61029	200
61031	201
61033	201
61035	201
61037	201
61039	201
61041	202
61043	202
61045	202
61047	202
61049	202
61051	202
61056	198
61057	198
61058	198
61059	198
61060	198
61061	198
61062	198
61063	198
61064	198
61065	198
61066	198
61067	198
61068	199
61069	199
61070	199
61071	199
61072	199
61073	199
61074	199
61075	199
61076	199
61077	199
61078	199
61079	199
61080	199
61081	199
61082	199
61083	200
61084	200
61085	200
61086	200
61087	200
61088	200
61089	200
61090	200
61091	200
61092	200
61093	200
61094	200
61095	200
61096	201
61097	201
61098	201
61099	201
61100	201
61101	201
61102	201
61103	201
61104	201
61105	201
61106	201
61107	201
61108	201
61109	201
61110	201
61111	201
61112	201
61113	201
61114	201
61115	201
61116	202
61117	202
61118	202
61119	202
61120	202
61121	202
61122	202
61123	202
61124	202
61175	202
62001	203
62003	203
62005	203
62007	203
62009	203
62011	203
62013	203
62015	203
62017	203
62019	203
62021	203
62023	203
62025	203
62027	203
62029	203
62031	203
62033	203
62035	203
62037	203
62039	203
62041	203
62043	203
62045	203
62047	203
62049	203
62051	203
62053	203
62055	203
62057	203
62059	203
62061	203
62063	203
62065	203
62066	205
62067	203
62069	203
62071	203
62073	203
62075	203
62077	204
62079	204
62081	204
62083	204
62084	205
62085	204
62087	204
62089	204
62091	204
62093	204
62095	204
62097	204
62099	204
62101	204
62102	205
62103	204
62105	204
62107	204
62109	204
62111	204
62112	205
62113	204
62115	204
62116	205
62117	204
62119	204
62121	204
62123	204
62125	204
62127	204
62129	204
62131	204
62133	204
62135	204
62137	204
62139	204
62141	204
62142	204
62143	204
62145	204
62146	204
62147	204
62149	205
62151	205
62153	205
62154	205
62155	205
62156	205
62157	205
62158	205
62159	205
62164	205
62166	205
62167	205
62168	205
62170	205
62171	205
63000	209
63001	209
63002	209
63003	209
63004	209
63005	209
63006	210
63007	210
63008	210
63009	210
63010	211
63011	211
63012	211
63013	211
63014	211
63015	211
63016	211
63017	211
63018	211
63019	212
63020	212
63021	212
63022	212
63023	212
63024	212
63025	212
63026	212
63027	212
63028	212
63029	212
63030	212
63031	213
63032	213
63033	213
63034	213
63035	213
63036	213
63037	213
63038	213
63039	213
63040	213
63041	213
63042	213
63043	213
63044	209
63045	209
63046	209
63047	209
63048	209
63049	209
63050	209
63051	209
63052	210
63053	210
63054	210
63055	210
63056	210
63057	210
63058	210
63059	210
63060	210
63061	210
63062	210
63063	210
63064	211
63065	211
63066	211
63067	211
63068	211
63069	211
63070	211
63071	211
63072	211
63073	211
63074	211
63075	211
63076	211
63077	211
63078	211
63079	212
63080	212
63081	212
63082	212
63083	212
63084	212
63085	212
63086	212
63087	212
63088	212
63089	213
63090	213
63091	213
63155	163
63156	163
63157	163
63158	163
63159	163
63160	163
63161	163
63162	163
63163	163
63164	164
63165	164
63166	164
63167	164
63168	164
63169	164
63170	164
63171	164
63172	164
63173	164
63174	165
63175	165
63176	165
63177	165
63178	165
63179	165
63180	165
63181	165
63182	165
63183	165
63184	166
63185	166
63186	166
63187	166
63188	166
63189	166
63190	166
63191	166
63192	166
63193	166
63194	167
63195	167
63196	167
63197	167
63198	167
63199	167
63200	167
63201	167
63202	167
63203	167
63204	167
63205	167
63206	167
63207	167
63208	167
63209	167
63210	167
63211	167
63212	167
63213	165
63575	174
63576	174
63577	174
63578	174
63579	174
63580	174
63581	174
63582	174
63583	174
63584	174
63585	174
63586	174
63587	174
63588	174
63589	174
63590	174
63591	174
63592	174
63593	174
63594	174
63595	174
63596	174
63597	174
63598	174
63599	175
63600	175
63601	175
63602	175
63603	175
63604	175
63605	175
63606	175
63607	175
63608	175
63609	175
63610	175
63611	175
63612	175
63613	175
63614	175
63615	175
63616	175
63617	175
63618	175
63619	175
63620	175
63621	175
63622	175
63623	175
63624	175
63625	175
63626	175
63627	175
63628	175
63629	176
63630	176
63631	176
63632	176
63633	176
63634	176
63635	176
63636	176
63637	176
63638	176
63639	176
63640	176
63641	176
63642	176
63643	176
63644	176
63645	176
63646	176
63647	176
63648	176
63649	176
63650	176
63651	176
63652	176
63653	177
63654	177
63655	177
63656	177
63657	177
63658	177
63659	177
63660	177
63661	177
63662	177
63663	177
63664	177
63665	177
63666	177
63667	177
63668	177
63669	177
63670	177
63671	177
63672	177
63673	177
63674	177
63675	177

EDP Number Index

EDP NO.	PAGE
63676	177
63677	177
63741	163
63742	163
63743	163
63744	163
63745	164
63746	164
63747	164
63748	164
63749	164
63750	164
63751	164
63752	164
63753	164
63754	165
63755	165
63756	165
63757	165
63758	165
63759	165
63760	165
63761	165
63762	165
63763	165
63764	165
63765	165
63766	165
63767	165
63768	165
63769	165
63770	165
63771	166
63772	166
63773	166
63774	166
63775	166
63776	166
63777	166
63778	166
63779	166
63780	166
63781	166
63782	166
63783	166
63784	166
63785	166
63786	166
63787	166
63788	166
63789	166
63790	167
63791	167
63792	167
63793	167
63794	167
63900	170
63901	170
63902	170
63903	170
63904	170
63905	170
63906	170
63907	170
63908	170
63909	170
63910	170
63911	170
63912	170
63913	170
63914	170
63915	170
63916	170
63917	170
63918	170
63919	170
63920	170
63921	170
63922	170
63923	171
63924	171
63925	171
63926	171
63927	171
63928,0	171
63929	171
63930	171
63931	171
63932	171
63933	171
63934	171
63935	171
63936	171
63937	171
63938	171
63939	171
63940	171
63941	171
63942	171
63943	171
63944	171
63945	171
63946	171
63947	171
63948	171
63949	171
63950	171
63951	172
63952	172
63953	172
63954	172
63955	172
63956	172
63957	172
63958	172
63959	172
63960	172
63961	172
63962	172
63963	172
63964	172
63965	172
63966	172
63967	172
63968	172
63969	172
63970	172
63971	172
63972	172
63973	172
63974	172
63975	173
63976	173
63977	173
63978	173
63979	173
63980	173
63981	173
63982	173
63983	173
63984	173
63985	173
63986	173
63987	173
63988	173
63989	173
63990	173
63991	173
63992	173
63993	173
63994	173
63995	173
63996	173
63997	173
63998	171
63999	171
64000	173
64001	173
66001	206
66002	206
66003	206
66004	206
66005	206
66006	206
66007	206
66008	206
66009	206
66010	206
66011	207
66012	207
66013	207
66014	207
66015	207
66016	207
66017	207
66018	207
66019	207
66020	207
66021	207
66022	208
66023	208
66024	208
66025	208
66026	208
66027	208
66028	208
66029	208
66030	208
66031	208
66032	208
66033	208
66034	208
66035	208
66036	208
66037	208
66038	208
66039	208
66040	208
66041	208
66042	208
66043	208
66044	208
66045	207
66046	208
67005	221
67007	221
67009	221
67011	221
67013	221
67015	221
67017	221
67019	221
67021	221
67023	221
67035	221
67037	221
67039	221
67041	221
67043	221
67045	221
67047	221
67049	221
67051	221
67053	221
68268	197
68269	197
68270	197
68271	197
68272	197
68273	198
68274	198
68275	199
68276	199
68277	199
68278	199
68279	200
68280	200
68281	200
68282	200
68283	201
68284	201
68285	201
68286	201
68287	201
68288	202
68289	202
68290	202
68291	202
68292	202
68293	202
68294	197
68295	197
68296	197
68297	197
68298	198
68299	198
68300	198
68301	198
68302	198
68303	198
68304	198
68305	198
68306	198
68307	198
68308	198
68309	198
68310	199
68311	199
68312	199
68313	199
68314	199
68315	199
68316	199
68317	199
68318	199
68319	199
68320	199
68321	199
68322	199
68323	199
68324	199
68325	200
68326	200
68327	200
68328	200
68329	200
68330	200
68331	200
68332	200
68333	200
68334	200
68335	200
68336	200
68337	200
68338	201
68339	201
68340	201
68341	201
68342	201
68343	201
68344	201
68345	201
68346	201
68347	201
68348	201
68349	201
68350	201
68351	201
68352	201
68353	201
68354	201
68355	201
68356	201
68357	201
68358	202
68359	202
68360	202
68361	202
68362	202
68363	202
68364	202
68365	202
68366	202
68603	204
68604	204
68606	205
68607	205
68608	205
68609	205
68611	205
68612	205
68613	205
68614	205
68616	205
68643	203
68644	203
68645	203
68646	203
68647	203
68648	203
68649	203
68650	203
68651	203
68652	203
68653	203
68654	203
68655	203
68656	203
68657	203
68658	203
68659	203
68660	203
68661	203
68662	203
68663	203
68664	203
68665	203
68666	203
68667	203
68668	203
68669	203
68670	203
68671	203
68672	203
68673	203
68674	203
68675	203
68676	203
68677	203
68678	203
68679	203
68680	203
68681	204
68682	204
68683	204
68684	204
68685	204
68686	204
68687	204
68688	204
68689	204
68690	204
68691	204
68692	204
68693	204
68694	204
68695	204
68696	204
68697	204
68698	204
68699	204
68700	204
68701	204
68702	204
68703	204
68704	204
68705	204
68706	204
68707	204
68708	204
68709	204
68710	204
68711	204
68712	204
68713	204
68718	204
68723	204
68728	204
68733	205
68738	205
68743	205
68748	205
68753	205
68758	205
68763	205
68768	205
68773	205
68778	205
68780	205
68965	209
68966	209
68967	209
68968	209
68969	209
68970	209
68971	209
68972	209
68973	209
68974	209
68975	209
68976	209
68977	209
68978	209
68979	210
68980	210
68981	210
68982	210
68983	210
68984	210
68985	210
68986	210
68987	210
68988	210
68989	210
68990	210
68991	210
68992	210
68993	210
68994	210
68995	211
68996	211
68997	211
68998	211
68999	211
69000	211
69001	211
69002	211
69003	211
69004	211
69005	211
69006	211
69007	211

EDP Number Index

EDP NO.	PAGE
69008	211
69009	211
69010	211
69011	211
69012	211
69013	211
69014	211
69015	211
69016	211
69017	211
69018	211
69019	212
69020	212
69021	212
69022	212
69023	212
69024	212
69025	212
69026	212
69027	212
69028	212
69029	212
69030	212
69031	212
69032	212
69033	212
69034	212
69035	212
69036	212
69037	212
69038	212
69039	212
69040	212
69041	213
69042	213
69043	213
69044	213
69045	213
69046	213
69047	213
69048	213
69049	213
69050	213
69051	213
69052	213
69053	213
69054	213
69055	213
69056	213
70003	236
70004	236
70005	236
70006	236
70007	236
70008	236
70009	236
70010	236
70011	236
70012	236
70013	236
70014	236
70015	236
70016	236
70017	236
70018	236
70019	236
70020	236
70021	236
70022	236
70023	236
70024	236
70025	236
70026	236
70027	236
70028	236
70029	236
70030	236
70031	236
70032	236
70441	28
70442	28
70444	28
70445	28
70447	28
70448	28
70450	28
70451	28
70453	28
70454	28
70456	28
70457	28
70459	28
70460	28
70462	28
70463	28
70465	28
70466	28
70468	28
70469	28
70470	26
70471	26
70472	26
70473	26
70474	26
70475	26
70476	26
70477	26
70478	26
70479	26
70480	26
70481	26
70482	26
70483	26
70484	26
70485	26
70486	26
70487	26
70488	26
70489	26
70527	29
70529	29
70531	29
70533	29
70535	29
70537	29
70539	29
70540	29
70542	29
70544	29
70546	29
70548	29
70550	29
70551	27
70552	27
70553	27
70554	27
70555	27
70556	27
70557	27
70558	27
70559	27
70560	27
70561	27
70562	27
70563	27
72930	246
72947	246
72948	246
72949	246
72950	246
72951	246
72952	246
72953	246
72954	247
72955	247
72956	247
72957	247
72958	247
72959	247
72960	247
72961	247
72962	247
72963	247
72964	247
72965	247
72966	247
72967	247
72968	247
72969	247
72970	248
72971	248
72972	248
72973	248
72974	248
72975	248
72976	248
72977	248
72978	58
72979	58
72980	58
72981	58
72982	58
72983	58
72984	58
72985	58
73012	246
73013	246
73014	246
73026	246
73027	246
73028	246
73029	246
73041	246
74001	222
74004	222
74007	222
74010	222
74013	222
74016	222
74019	222
74022	222
74025	223
74028	223
74031	223
74034	223
74037	223
74040	223
74043	223
74046	223
74049	224
74052	224
74055	224
74058	224
74061	224
74064	224
74067	224
74070	224
74101	222
74104	222
74107	222
74110	222
74113	222
74116	222
74119	222
74122	222
74125	223
74128	223
74131	223
74134	223
74137	223
74140	223
74143	223
74146	223
74149	224
74152	224
74155	224
74158	224
74161	224
74164	224
74167	224
74170	224
74201	222
74204	222
74207	222
74210	222
74213	222
74216	222
74219	222
74222	222
74225	223
74228	223
74231	223
74234	223
74237	223
74240	223
74243	223
74246	223
74249	224
74252	224
74255	224
74258	224
74261	224
74264	224
74267	224
74270	224
81001	235
81003	235
81005	235
81007	235
81009	235
81011	235
81013	235
81015	235
81017	235
81019	235
81021	235
81023	235
81025	235
81027	235
81029	235
82966	246
82967	246
82968	246
82969	246
82970	246
82971	246
82972	246
82973	246
82974	247
82975	247
82976	247
82977	247
82978	247
82979	247
82980	247
82981	247
82982	247
82983	247
82984	247
82985	247
82986	247
82987	247
82988	247
82989	247
82990	248
82991	248
82992	248
82993	248
82994	248
82995	248
82996	248
82997	248
83026	246
83027	246
83028	246
83029	246
83041	246
83042	246
83043	246
83044	246
83056	59
83057	59
83058	59
83059	59
83060	59
83061	59
83062	59
83063	59
83064	59
83065	59
90001	249
90005	249
90009	249
90013	249
90017	249
90021	249
90025	249
90029	249
90033	249
90037	249
90041	249
90045	249
90049	249
90053	249
90101	249
90107	249
90109	249
90113	249
90121	249
90129	249
90137	249
91001	250
91005	250
91009	250
91013	250
91017	250
91021	250
91025	250
91029	250
91033	250
91037	250
91041	250
91045	250
91049	250
91053	250
91101	250
91107	250
91109	250
91113	250
91121	250
91129	250
91137	250
91235	43
91236	43
91237	43
91238	43
91239	43
91240	43
91241	43
91242	43
91243	43
91244	43
91245	43
91246	43
91247	43
91248	43
91250	43
91251	43
91252	43
91253	43
91254	43
91255	43
91256	43
91257	43
91258	43
91259	43
91260	43
91261	43
91262	43
91263	43
91266	114
91268	99
91269	104
91270	114
91272	99
91273	104
91274	114
91276	99
91277	104
91278	114
91280	99
91281	104
91282	114
91284	99
91285	104
91286	115
91288	99
91289	105
91290	115
91292	100
91293	105
91349	40
91350	40
91351	40
91352	40
91353	40
91354	40
91355	40
91356	40
91357	40
91358	40
91359	40
91360	40
91361	40
93272	40
93273	40
93274	40
93275	40
93276	40
93277	40
93278	40
93279	40
93280	40
93281	40
93282	40

ISO H6 SPECIFICATIONS

DIAMETER	+	–	DIAMETER	+	–
≥ 1/8 - 3/16	0.00000	–0.00032	≤ 3	0,000	0,006
> 3/16 - 7/16	0.00000	–0.00035	> 3 - 6	0,000	0,008
> 7/16 - 5/8	0.00000	–0.00043	> 6 - 10	0,000	0,009
> 5/8 - 1	0.00000	–0.00051	> 10 - 18	0,000	0,011
> 1 - 1-1/4	0.00000	–0.00063	> 18 - 25	0,000	0,013

MACHINING FORMULAS

INCH FORMULAS

sfm = rpm x .262 x cutting diameter

rpm = sfm x 3.82 / cutting diameter

feed (inches per tooth) = ipm / (number of teeth x rpm)

feed (inches / minute) = inches per tooth x number of teeth x rpm

feed (inches / minute) = ipr x rpm

feed (inches / revolution) = ipm / rpm

cusp height* = (tool diameter / 2) – $\sqrt{(\text{tool diameter}^2 - \text{pitch}^2) / 4}$

pitch = $\sqrt{4 \times (\text{cusp height} \times \text{tool diameter}) - 4 \times (\text{cusp height}^2)}$

mrr – milling – (in^3/min) = width of cut x depth of cut x ipm

cutting time – drilling – (minutes) = length / ipm

METRIC FORMULAS

m/min = (3.14 x cutting diameter x rpm) / 1000

rpm = (1000 x m / min) / (3.14 x cutting diameter)

feed (mm per tooth) = millimeters per minute / (number of teeth x rpm)

feed (mm/minute) = feed per tooth x number of teeth x rpm

feed (mm/minute) = mmr x rpm

feed (mm per revolution) = mmr / rpm

cusp height* = (tool diameter / 2) –$\sqrt{(\text{tool diameter}^2 - \text{pitch}^2) / 4}$

pitch = $\sqrt{4 \times (\text{cusp height} \times \text{tool diameter}) - 4 \times (\text{cusp height}^2)}$

mrr – milling – (cm^3/min) = (width of cut x depth of cut x mm/min) / 1000

cutting time – drilling – (minutes) = length / mm/min

sfm	surface feet per minute
rpm	revolutions per minute
ipm	feed rate in inches per minutes
ipr	inches per revolution
mmr	millimeters per revolution
mm/min	feed rate in millimeters per minute
mrr	material removal rate
*	on flat surface

GENERAL FORMULAS

coolant pressure: 1 Bar = 14.5 Pounds per Square Inch (PSI)

calculation of coolant pressure: Pounds Per Square Inch (PSI) = (Horsepower of Pump x 1.460) / Gallons per Minute (GPM)

1 Liter = 0.254 Gallons

inch = millimeters / 25.4 millimeters = inch x 25.4

inch tap drill sizes = major diameter – ((1.299 x % of thread) / threads per inch)

metric tap drill sizes = major diameter – (1.082 x pitch x % of thread)

inch thread forming drill size: maximum diameter = basic major diameter – (3/8 x number of threads per inch)

inch thread forming drill size: minimum diameter = basic major diameter – (1/2 x number of threads per inch)

metric thread forming drill size: maximum diameter = basic major diameter – (.375 x pitch)

metric thread forming drill size: minimum diameter = basic major diameter – (.500 x pitch)

Decimal Equivalents

Fraction • Number • Letter • Metric Sizes

INCH	METRIC	DECIMAL EQUIVALENT
–	0,10	0.0039
–	0,20	0.0079
–	0,25	0.0098
–	0,30	0.0118
#80	0,34	0.0135
–	0,35	0.0138
#79	0,37	0.0145
1/64	0,40	0.0156
#78	0,41	0.0160
–	0,45	0.0177
#77	0,46	0.0180
–	0,50	0.0197
#76	0,51	0.0200
#75	0,53	0.0210
–	0,55	0.0217
#74	0,57	0.0225
–	0,60	0.0236
#73	0,61	0.0240
#72	0,64	0.0250
–	0,65	0.0256
#71	0,66	0.0260
–	0,70	0.0276
#70	0,71	0.0280
#69	0,74	0.0292
–	0,75	0.0295
#68	0,79	0.0310
1/32	0,79	0.0313
–	0,80	0.0315
#67	0,81	0.0320
#66	0,84	0.0330
–	0,85	0.0335
#65	0,89	0.0350
–	0,90	0.0354
#64	0,91	0.0360
#63	0,94	0.0370
–	0,95	0.0374
#62	0,97	0.0380
#61	0,99	0.0390
–	1,00	0.0394
#60	1,02	0.0400
#59	1,04	0.0410
–	1,05	0.0413
#58	1,07	0.0420
#57	1,09	0.0430
–	1,10	0.0433
–	1,15	0.0453
#56	1,18	0.0465
3/64	1,19	0.0469
–	1,20	0.0472
–	1,25	0.0492
–	1,30	0.0512
#55	1,32	0.0520
–	1,35	0.0531
#54	1,40	0.0550
#53	1,51	0.0595
–	1,55	0.0610
1/16	1,59	0.0625

INCH	METRIC	DECIMAL EQUIVALENT
–	1,60	0.0630
#52	1,61	0.0635
–	1,65	0.0650
#51	1,70	0.0669
–	1,75	0.0689
#50	1,78	0.0700
–	1,80	0.0709
#49	1,85	0.0728
–	1,90	0.0748
#48	1,93	0.0760
–	1,95	0.0768
5/64	1,98	0.0781
#47	1,99	0.0785
–	2,00	0.0787
–	2,05	0.0807
#46	2,06	0.0810
#45	2,08	0.0820
–	2,10	0.0827
–	2,15	0.0846
#44	2,18	0.0860
–	2,20	0.0866
–	2,25	0.0886
#43	2,26	0.0890
–	2,30	0.0906
–	2,35	0.0925
#42	2,37	0.0935
3/32	2,38	0.0938
–	2,40	0.0945
#41	2,44	0.0960
–	2,45	0.0965
#40	2,50	0.0984
#39	2,53	0.0995
#38	2,58	0.1015
–	2,60	0.1024
#37	2,64	0.1040
–	2,70	0.1063
#36	2,71	0.1065
–	2,75	0.1083
7/64	2,78	0.1094
#35	2,79	0.1100
–	2,80	0.1102
#34	2,82	0.1110
#33	2,87	0.1130
–	2,90	0.1142
#32	2,95	0.1160
–	3,00	0.1181
#31	3,05	0.1200
–	3,10	0.1220
1/8	3,18	0.1250
–	3,20	0.1260
–	3,25	0.1280
#30	3,26	0.1285
–	3,30	0.1299
–	3,40	0.1339
#29	3,45	0.1360
–	3,50	0.1378
#28	3,57	0.1405

INCH	METRIC	DECIMAL EQUIVALENT
9/64	3,57	0.1406
–	3,60	0.1417
#27	3,66	0.1440
–	3,70	0.1457
#26	3,73	0.1470
–	3,75	0.1476
#25	3,80	0.1495
–	3,80	0.1496
#24	3,86	0.1520
–	3,90	0.1535
#23	3,91	0.1540
5/32	3,97	0.1562
#22	3,99	0.1570
–	4,00	0.1575
#21	4,04	0.1590
#20	4,09	0.1610
–	4,10	0.1614
–	4,20	0.1654
#19	4,22	0.1660
–	4,25	0.1673
–	4,30	0.1693
#18	4,31	0.1695
11/64	4,37	0.1719
#17	4,39	0.1730
–	4,40	0.1732
#16	4,50	0.1770
–	4,50	0.1772
#15	4,57	0.1800
–	4,60	0.1811
#14	4,62	0.1820
#13	4,70	0.1850
–	4,75	0.1870
3/16	4,76	0.1875
#12	4,80	0.1890
#11	4,85	0.1910
–	4,90	0.1929
#10	4,91	0.1935
#9	4,98	0.1960
–	5,00	0.1969
#8	5,05	0.1990
–	5,10	0.2008
#7	5,11	0.2010
13/64	5,16	0.2031
#6	5,18	0.2040
–	5,20	0.2047
#5	5,22	0.2055
–	5,25	0.2067
–	5,3	0.2087
#4	5,31	0.2090
–	5,40	0.2126
#3	5,41	0.2130
–	5,50	0.2165
7/32	5,56	0.2188
–	5,60	0.2205
#2	5,61	0.2210
–	5,70	0.2244
–	5,75	0.2264

INCH	METRIC	DECIMAL EQUIVALENT
#1	5,79	0.2280
–	5,80	0.2283
–	5,90	0.2323
A	5,94	0.2340
15/64	5,95	0.2344
–	6,00	0.2362
B	6,05	0.2380
–	6,10	0.2402
C	6,15	0.2420
–	6,20	0.2441
D	6,25	0.2461
–	6,30	0.2480
E	6,35	0.2500
1/4	6,35	0.2500
–	6,40	0.2520
–	6,50	0.2559
F	6,53	0.2570
–	6,60	0.2598
G	6,63	0.2610
–	6,70	0.2638
17/64	6,75	0.2656
H	6,76	0.2660
–	6,80	0.2677
–	6,90	0.2717
I	6,91	0.2720
–	7,00	0.2756
J	7,04	0.2770
–	7,10	0.2795
K	7,14	0.2810
9/32	7,14	0.2812
–	7,20	0.2835
–	7,25	0.2854
–	7,30	0.2874
L	7,37	0.2900
–	7,40	0.2913
M	7,49	0.2950
–	7,50	0.2953
19/64	7,54	0.2969
–	7,60	0.2992
N	7,67	0.3020
–	7,70	0.3031
–	7,75	0.3051
–	7,80	0.3071
–	7,90	0.3110
5/16	7,94	0.3125
–	8,00	0.3150
O	8,03	0.3160
–	8,10	0.3189
–	8,20	0.3228
P	8,20	0.3230
–	8,25	0.3248
–	8,30	0.3268
21/64	8,33	0.3281
–	8,40	0.3307
Q	8,43	0.3320
–	8,50	0.3346
–	8,60	0.3386

INCH	METRIC	DECIMAL EQUIVALENT
R	8,61	0.3390
–	8,70	0.3425
11/32	8,73	0.3438
–	8,75	0.3445
–	8,80	0.3465
S	8,84	0.3480
–	8,90	0.3504
–	9,00	0.3543
T	9,09	0.3580
–	9,10	0.3583
23/64	9,13	0.3594
–	9,20	0.3622
–	9,25	0.3642
–	9,30	0.3661
U	9,35	0.3680
–	9,40	0.3701
–	9,50	0.3740
3/8	9,53	0.3750
V	9,56	0.3770
–	9,60	0.3780
–	9,70	0.3819
–	9,75	0.3839
W	9,80	0.3858
–	9,90	0.3898
25/64	9,92	0.3906
–	10,00	0.3937
X	10,08	0.3970
–	10,10	0.3976
–	10,20	0.4016
Y	10,26	0.4040
–	10,30	0.4055
13/32	10,32	0.4062
–	10,40	0.4094
Z	10,49	0.4130
–	10,50	0.4134
–	10,60	0.4173
–	10,70	0.4213
27/64	10,72	0.4219
–	10,80	0.4252
–	10,90	0.4291
–	11,00	0.4331
–	11,10	0.4370
7/16	11,11	0.4375
–	11,20	0.4409
–	11,30	0.4449
–	11,40	0.4488
–	11,50	0.4528
29/64	11,51	0.4531
–	11,60	0.4567
–	11,70	0.4606
–	11,80	0.4646
–	11,90	0.4685
15/32	11,91	0.4688
–	12,00	0.4724
31/64	12,30	0.4844
–	12,50	0.4921
1/2	12,70	0.5000

INCH	METRIC	DECIMAL EQUIVALENT
–	13,00	0.5118
33/64	13,10	0.5156
17/32	13,49	0.5312
–	13,50	0.5315
35/64	13,89	0.5469
–	14,00	0.5512
9/16	14,29	0.5625
–	14,50	0.5709
37/64	14,68	0.5781
–	15,00	0.5906
19/32	15,08	0.5938
39/64	15,48	0.6094
–	15,50	0.6102
5/8	15,88	0.6250
–	16,00	0.6299
41/64	16,27	0.6406
–	16,50	0.6496
21/32	16,67	0.6562
–	17,00	0.6693
43/64	17,07	0.6719
11/16	17,46	0.6875
–	17,50	0.6890
45/64	17,86	0.7031
–	18,00	0.7087
23/32	18,26	0.7188
–	18,50	0.7283
47/64	18,65	0.7344
–	19,00	0.7480
3/4	19,05	0.7500
49/64	19,45	0.7656
–	19,50	0.7677
25/32	19,84	0.7812
–	20,00	0.7874
51/64	20,24	0.7969
–	20,50	0.8071
13/16	20,64	0.8125
–	21,00	0.8268
53/64	21,03	0.8281
27/32	21,43	0.8438
–	21,50	0.8465
55/64	21,84	0.8594
–	22,00	0.8661
7/8	22,23	0.8750
–	22,50	0.8858
57/64	22,62	0.8906
–	23,00	0.9055
29/32	23,02	0.9062
59/64	23,42	0.9219
–	23,50	0.9252
15/16	23,81	0.9375
–	24,00	0.9449
61/64	24,21	0.9531
–	24,50	0.9646
31/32	24,61	0.9688
–	25,00	0.9843
63/64	25,00	0.9844
1	25,40	1.0000

Hardness Conversion Chart

ROCKWELL HARDNESS (HRb)	ROCKWELL HARDNESS (HRc)	BRINELL HARDNESS (HB)	VICKERS HARDNESS (HV)	TENSILE STRENGTH (N/mm2)	PSI (1000lb/in2)
67	–	121	122	401	58
70	–	126	127	432	63
73	–	132	132	448	65
75	–	136	137	455	66
77	–	140	143	463	67
80	–	147	150	479	69
82	–	153	156	494	72
84	–	159	163	525	76
86	–	165	171	540	78
89	–	177	178	556	81
91	–	186	188	602	88
93	–	197	196	632	92
96	–	216	212	664	97
97	–	223	218	695	101
98	21	230	234	756	110
–	22	236	241	772	112
–	23	242	247	787	114
–	24	248	255	818	118
–	25	254	261	849	123
–	27	266	269	865	125
–	28	272	275	895	130
–	29	278	284	911	132
–	30	284	292	942	136
–	31	293	300	973	141
–	32	302	308	988	143
–	33	310	318	1019	147
–	34	319	327	1050	152
–	35	328	337	1096	159
–	37	345	349	1127	163
–	38	353	359	1158	168
–	39	362	370	1189	172
–	40	370	381	1235	179
–	41	381	395	1266	183
–	42	391	408	1312	190
–	44	411	422	1359	197
–	45	422	437	1420	206
–	46	433	452	1467	212
–	48	455	470	1513	219
–	50	479	497	1559	226
–	51	485	517	1621	235
–	52	497	532	1668	241
–	54	–	573	1729	250
–	56	–	609	1807	262
–	57	–	630	1884	273
–	59	–	670	1961	284
–	60	–	698	2039	295
–	61	–	725	–	–
–	62	–	740	–	–
–	63	–	780	–	–
–	64	–	812	–	–
–	65	–	847	–	–
–	66	–	885	–	–
–	67	–	926	–	–
–	68	–	971	–	–

Conversions from each scale are approximate

Performance by Design

Solutions Around The Globe
SGS Tool Company is a privately-held, ISO-certified leader of round solid carbide cutting tool technology for the aerospace, metalworking, and automotive industries with manufacturing sites in the United States and United Kingdom. Our global network of Sales Representatives, Industrial Distributors, and Agents blanket the world selling into more than 60 countries.

Leaders in Solid Carbide Tool Technology
Brand names such as Z-Carb, S-Carb, V-Carb, Hi-PerCarb, Multi-Carb have become synonymous with high performance tooling in the machining and metalworking industry.

We're proud to have pioneered some of the world's most advanced cutting technology right here in our Northeast Ohio manufacturing campus. SGS high performance end mills, drills and routers are increasing productivity and reducing cost around the world.

Exceeding Customer Expectations
In addition to our substantial R&D facilities, we offer a portfolio of products and services that have an unparalleled track record in manufacture, supply and value at the spindle.

- Incredible batch-to-batch consistency
- Metallurgical lab dedicated to testing and rigorous quality control
- ISO-certified quality procedures
- Patented geometries that extend tool life, reduce chatter, cut cycle times, and improve part quality—even at extreme parameters
- Specialists in extreme and demanding product applications
- Experienced Field Sales Engineers who work to optimize a tool for your particular application
- Dedicated multi-lingual customer service representatives

SGS Products are distributed by:

UNITED STATES OF AMERICA
SGS TOOL COMPANY
World Headquarters
P.O. Box 187
55 South Main Street
Munroe Falls, Ohio 44262 U.S.A.
phone: (330) 688-6667
customer service -
US and Canada: (330) 686-5700
fax - US & Canada: (800) 447-4017
international fax: (330) 686-2146
e-mail: webmaster@sgstool.com

UNITED KINGDOM
SGS CARBIDE TOOL (UK) LTD.
10 Ashville Way
Wokingham, Berkshire
RG41 2PL England
phone: (44) 1189-795-200
fax: (44) 1189-795-295
e-mail: sales@sgstool.co.uk

FRANCE
SGS FRANCE
Business Parc SILIC
20 Rue Saarinen
Case Postale 10248
94568 RUNGIS CEDEX
France
phone: +33 (0) 1 49 79 76 90
fax: +33 (0) 1 49 79 76 94
e-mail: sgsfrance@sgstool.fr

sgstool.com

GERMANY
SGS TOOL GmbH
Hitdorfer Strasse 10C
Langenfeld D40764
phone: (49) 2173-9100-91
fax: (49) 2173-9100-99
e-mail: info@sgs-tool.de

CANADA
SGS TOOL CANADA
171 Northport Road, Unit #3
Port Perry, ON L9L 1B2
phone: 905/982-0888
fax: 905/982-0488
e-mail: sgstool@powergate.ca

EASTERN EUROPE
SINTCOM
phone: (359) 283-64421
fax: (359) 286-52493
e-mail: sintcom@cablebg.net

RUSSIA
HALTEC
phone: (7) 842-231-0738
fax: (7) 842-231-0601
e-mail: info@haltec.ru
web: www.haltec.ru

CHINA
SGS TOOL DIVISION
phone: (86) 21-50589822
fax: (86) 21-50817160
e-mail: china@sgstool.com
web: www.sgstool.com/china

EDP 00008 Rev 0914
© SGS Tool Company