

Toplac

Premium high durability marine gloss enamel

Toplac's silicone alkyd formula is extremely smooth-flowing, producing a very high gloss. Superior UV filters combine with this to produce a surface which will retain its colour and gloss up to three times longer than conventional gloss paints.



Pack size: 2.5 Lt / 750 ml / 375 ml

Product Code: YKA184-Mediterranean White, YKA187-Ivory, YFK684-Atlantic Grey, YFK991-Mauritius Blue, YKS299-Rochelle Red, YKS936-Lauderdale Blue, YKT541-Donegal Green, YKY999-Jet Black, YKB000-Snow White, YKB993-Oxford Blue, YKJ292-Bounty, YKS101-Yellow, YKU898-Bondi Blue, YKZ501-Rustic Red.

KEY FEATURES AND BENEFITS

- Premium gloss marine enamel for all substrates above the waterline.
- Silky smooth flow-out characteristics, making it exceptionally easy to apply by brush, roller or pad.
- Unique chemical structure enables Toplac to outperform traditional finishes giving a long lasting high definition gloss and a deep lustrous finish.
- Enhanced UV stability reduces harmful effects of sunlight.
- Available in a range of bright colours, and crisp white.

Testimonial:

"I recently painted my 38' sailboat with Toplac paint and I am very satisfied with the results...the coverage was so good...Application was by roller and brush and the job was done with the boat in the water...I find that other boat owners are unaware that a job like this is within their capabilities." David Spiwak, Bloomberg, USA

SYSTEMS AND COMPATIBILITY

Use over suitable prepared and undercoated surfaces or existing paint schemes.
Not suitable for permanently immersed surfaces.

TOPLAC PRODUCT DATA

PRODUCT CODE & COLOUR	YKA184-Mediterranean White, YKA187-Ivory, YFK684-Atlantic Grey, YFK991-Mauritius Blue, YKS299-Rochelle Red, YKS936-Lauderdale Blue, YKT541-Donegal Green, YKY999-Jet Black, YKB000-Snow White, YKB993-Oxford Blue, YKJ292-Bounty, YKS101-Yellow, YKU898-Bondi Blue, YKZ501-Rustic Red.
FINISH	Gloss
THINNER	YTA800 Thinner No.1 / YTA063 Thinner No.10
NUMBER OF COATS	1 - 2
APPLICATION METHOD	Conventional Spray / Brush / Roller
PACK SIZES	2.5 Lt / 750 ml / 375 ml
TYPICAL SHELF LIFE	2 years

Refer to Toplac product data sheet for more information, including drying times.

SURFACE PREPARATIONS AND SYSTEMS

Previously painted surface in good condition: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade paper. **Poor surface condition:** Remove all previous coatings and prime the substrate.

PRIMING: Substrate preparation is covered separately on the primer datasheet.

GRP: Wash down with Super Cleaner, rinse with fresh water and allow to dry. Use Prekote undercoat, or if applying by spray use polyurethane Basecoat.

STEEL: Prime with Interprotect or Yacht Primer.

BARE WOOD: Prime with Yacht Primer or UCP.

ALUMINIUM: Prime with Etch Primer followed by Yacht Primer or Interprotect.

METHOD: Sand the undercoat smooth with 320-400 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.

For full scheme specifications please refer to your local International Representative.

DRYING TIMES:

	DRYING			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	6hrs	3hrs	2hrs	1hr

OVERCOATING TIMES

Overcoated by

	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Toplac	24hrs	4days	16hrs	3days	8hrs	2days	6hrs	1day

RELATED PRODUCTS

PRODUCT CODE	DESCRIPTION
YTA800	Thinner No.1
YTA063	Thinner No.10
YMA620	Super Cleaner

International Coatings Ltd., 24-30 Canute Road, Southampton.
Tel: 023 8022 6722 Fax: 023 8033 5975

 and International® are registered trademarks of International Coatings Ltd.
Akzo Nobel Logo is a registered trademark of Akzo Nobel NV.
Teflon is a registered trademark of DuPont.

Disclaimer

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

August 2006

